CCC-C-444
APRIL 8, 1958
SUPERSEDING
Fed. Spec. CCC–J–191
January 5, 1932

FEDERAL SPECIFICATION

CLOTH, COTTON, JEAN, (BLEACHED)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers the requirements for one type of bleached cotton jean cloth primarily intended for use in the manufacture of clothing and equipage.

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

CCC–T–191—Textile Test Methods.

PPP–P–51 — Packaging, Packing and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks and Synthetics).

Federal Standards:

Fed. Std. No. 4—Glossary of Fabric Imperfections.

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards, required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material.

3.1.1 *Cotton.*—The cotton shall be of a suitable length of staple and grade to meet the requirements of this specification.

3.1.2 *Yarn.*—The cotton used in the manufacture of the yarn shall be thoroughly cleaned, well carded, drawn and evenly spun.

3.2 Physical requirements.—The finished fabric shall conform to the requirements shown in table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE I.—*Physical requirements*

Weight per square yard		Yarns per inch, minimum		Breaking strength (grab method), minimum		Weave
Min.	Max.	Warp	Filling	Warp	Filling	
Ounces	*Ounces*			*Pounds*	*Pounds*	$\frac{2}{1}$ twill
4.7	5.0	98	60	85	48	

3.2.1 *Width.*—The width shall be as specified and shall be the minimum acceptable width inclusive of selvages (see 6.2).

3.3 Finish.—The cloth shall be closely singed, desized, and bleached. Residual size, finishing, or nonfibrous material shall not exceed 2 percent when tested as specified in 4.3.

3.4 Shrinkage.—The cloth shall be preshrunk and shall not shrink more than 1 percent in either the direction of the warp or filling when tested as specified in 4.3. The preshrinking process used shall not be identified on the cloth, the ticket, or on the package.

3.5 Length. — Unless otherwise specified, the cloth shall be in one continuous piece of not less than 50 yards.

3.6 Tickets. — Each piece shall have a ticket attached to the selvage at the inner end of the cloth with not finer than 5-ply cotton string doubled to not less than 8 inches long. The ticket shall be made of cardboard not less than 0.020 inch in thickness and the color shall be white or light in intensity to permit easy reading of printed or penciled markings. The finish on the cardboard shall be suitable for pencil markings. The ticket shall have a reinforced eyelet for attaching the tying cord and shall be legibly printed with water-insoluble ink with the following information, except when otherwise specified by civilian government agencies:

Nomenclature
Width_____
Stock number
Contractor's name
Contract number and date
Contractor's piece number
Specification number and date
Name of contracting office
Gross yards
Net yards

In addition, the ticket shall have sufficient blank space for the inspector's stamp.

3.7 Workmanship.—The cloth shall conform to the quality and grade of product established by this specification, and the occurrence of defects shall not exceed the levels set by the applicable acceptable quality levels.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Nonmilitary. — Nonmilitary agencies may use sampling, inspection, and test procedures outlined in 4.2 when desirable. When procedures outlined under 4.2 are not deemed suitable, the procedures specified under nonmilitary paragraphs shall be followed.

4.1.1 *Sampling.*

4.1.1.1 *Inspection lot.* — Unless otherwise specified in the invitation for bids, all cloth submitted at one time shall be considered a lot for purposes of inspection and tests.

4.1.1.2 *Sampling for inspection.*—A random sample of cloth shall be taken from each lot in accordance with table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE II.—*Sampling for Inspection*

Number of yards in lot	No. of rolls or bolts in the inspection sample	No. of yards in the inspection sample [1]	Acceptance number-total (defective)	Rejection number-total (defective)	Acceptance number-major (defective)	Rejection number-major (defective)
300 and under	2	35	5	6	1	2
301 to 500	3	50	6	7	2	3
501 to 800	5	75	9	10	3	4
801 to 1,300	7	110	12	13	4	5
1,301 to 3,200	10	150	17	18	5	6
3,201 to 8,000	15	225	24	25	8	9
8,001 to 22,000	20	300	32	33	10	11
22,001 to 110,000	30	450	43	44	14	15
110,001 to 550,000	40	750	68	69	20	21
550,001 and over	60	1500	124	125	35	36

[1] Yards in the inspection sample shall be divided equally among sample rolls of cloth and that number of yards shall be unrolled from each sample roll.

4.1.1.3 *Sampling for tests.*—Random samples for tests shall be taken from each inspection lot in accordance with table III.

TABLE III.—*Sampling for tests*

Number of rolls or bolts in lot	Number of rolls or bolts in sample[1]	Acceptance number (defective)	Rejection number (defective)
8 and under	2	0	1
9 to 15	3	0	1
16 to 40	4	0	1
41 and over	5	0	1

[1] One unit of product (test sample) at least 1½ yards long and the full width of the cloth shall be taken from each sample roll.

4.1.2 *Preproduction sample inspection.*—When a preproduction sample is required it shall be inspected and tested as specified in 4.3.

4.1.3 *Yard-by-yard inspection.*—Each of the samples selected in accordance with table II shall be visually inspected and defects classified in accordance with 4.2.2.1.1.1. The maximum number of defects acceptable shall be as specified in table II.

4.1.4 *Over-all inspection and inspection for length.*—Over-all inspection and inspection for length shall be as specified in 4.2.2.1.1.2 and 4.2.2.1.1.3, respectively. Sample size and the maximum number of defects acceptable shall be as specified in table IV.

4.1.5 *Tests.*—Samples selected for tests in accordance with table III shall be tested in accordance with the applicable methods of Federal Specification CCC–T–191 as listed in table V of this specification. The physical values specified in section 3 of this specification apply to the average of the determina-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

tions made on a unit of product for test purposes as specified in the applicable test methods. The unit of product shall be 1½ continuous yards full width of finished cloth.

4.1.6 *Compliance criteria.*

4.1.6.1 *Inspection.*—Any piece in the sample for inspection failing to conform to the requirements for which the inspection was made shall be considered defective. If the number of defective pieces in the sample exceeds the acceptance number for that sample specified in table II or IV as applicable, the entire lot from which the sample was taken shall be considered to have failed to meet the requirements of this specification.

4.1.6.2 *Tests.*—Any piece in the sample for tests failing to conform to the requirements for which tests were made shall be considered defective. If the number of defective pieces in the sample exceeds the acceptance number for that sample, the entire lot from which the sample was taken shall be considered to have failed to meet the requirements of this specification.

4.2 Military.

4.2.1 *General.*—The quality assurance provisions contained in this section are applicable to inspection performed by and/or for the Government. Quality assurance provisions for components or materials described herein shall be in accordance with this specification and with subsidiary specifications referenced herein to the extent applicable, except that this specification shall govern in the event of conflict.

4.2.2 *Inspection for acceptance.* — Inspection shall be in accordance with the provisions of Military Standard MIL–STD–105 and Appendix, except where otherwise indicated.

4.2.2.1 *Inspection of the end item.*

4.2.2.1.1 *Examination of the end item.*— The cloth shall be examined to determine conformance with the requirements of this specification. Defects found during this examination shall be classified in accordance with the list in 4.2.2.1.1.1.

4.2.2.1.1.1 *Yard-by-yard examination.* — The required yardage of each piece shall be inspected and visual defects classified as listed below. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be 1 linear yard. The acceptable quality levels (AQL's) for this examination shall be 1.5 major and 6.5 total (major and minor combined) defects per 100 units (yards). The sample size shall be based upon inspection level II, table III of Military Standard MIL–STD–105. The sample size shall be expressed in units of 1 yard each. The number of pieces from which the sample is to be selected shall be in accordance with table IV of this specification. An approximately equal number of yards shall be examined in each piece of the sample.

Glossary No. of Fed. Std. No. 4	Defect	Classification	
		Major	Minor
90, 91, 92	Hole, cut, tear or break—in body of cloth.	X	
78	Smash.	X	
79, 89	Abrasion marks, bruise, tender or weak spot.	X	
11, 33	Broken or missing yarns—Two or more contiguous, 2 inches or more missing.	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

Glossary No. of Fed. Std. No. 4	Defect	Classification	
		Major	Minor
	Two contiguous, less than 2 inches in length, or single, 2 inches or more in length.		X
8, 9	Fine or light filling bar or light place, clearly noticeable.	X	
12, 35	Crack or hitchback—Opening between yarns at widest point more than three yarns diameters.	X	
13, 34	Floats, skips—Multiple, ½ inch or more in combined warp and filling directions.	X	
	Multiple, less than ½ inch in combined warp and filling directions, or single 2 inches or more in length.		X
10	Mispick—Clearly noticeable fillingwise disruption in sequence of weave not resulting in skips.		X
1, 26	Coarse or heavy yarn—more than twice the thickness of the normal yarn.		X
2	Heavy filling bar—clearly noticeable.		X
3, 5, 7, 27, 29, 77	Jerked-in filling, slubs, slugs or slough-off, gouts, knots, more than three times the thickness of the normal yarn.		X
6, 28	Kinks—multiple, clearly noticeable.		X
37, 38	Tight, or slack end—Multiple.	X	
	Single.		X
39	Slack warp—resulting in baggy, ridgy or wavy cloth.	X	
49, 50	Slack or tight selvage—resulting in pronounced slackness or waviness in cloth.		X
51	Scalloped selvage—width of cloth inside defect less than specified.		X
54	Loopy or corded selvage—more than twice the normal thickness of the selvage.		X
59, 61	Crease, wrinkle mark—hard, embedded.		X
58	Sanforizing mark—clearly noticeable in body of cloth.		X
74, 75, 76	Spot, stain or streak—clearly noticeable.		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

4.2.2.1.1.2 *Overall examination.*—Each defect list shall be counted not more than once in each piece examined. The unit of product for this examination shall be one piece. The sample size (number of pieces selected as sample) for this examination and the acceptance number (number of defects acceptable) shall be as shown in table IV. The examination shall be conducted for the defects listed below:

Defects

(*a*) Width less than specified.
(*b*) Selvage curled, doubled, folded, or rolled extending continuously or intermittently throughout the piece.
(*c*) Uneven weaving throughout the piece, clearly noticeable.
(*d*) Finish not equal to standard sample.
(*e*) Not fully bleached.
(*f*) Objectionable odor.
(*g*) Overall uncleanness.

TABLE IV.

Lot size in yards	Sample size in pieces	Acceptable number
Up to 1,300[1]	3	0
1,301 to 3,200	5	0
3,201 to 8,000	7	0
8,001 to 22,000	10	0
22,001 to 110,000	15	1
110,001 to 550,000	25	1
550,001 and up	50	2

[1] If a lot contains fewer than three pieces, each piece in the lot shall be examined.

4.2.2.1.1.3 *Examination for length.*

4.2.2.1.1.3.1 *Individual pieces.*—The piece shall be examined for gross length. Any gross length found to be less than the minimum specified, or more than 2 yards below the gross length marked on the ticket, shall be considered a defect with respect to length. The unit of product for this examination shall be one piece. The number of pieces selected as the sample (sample size) for this examination and the acceptance number shall be as specified in table IV.

4.2.2.1.1.3.2 *Total yardage in sample.*—The lot shall be unacceptable if the total of the actual gross lengths of the pieces in the sample is less than the total of the gross lengths marked on the tickets.

4.3 Testing of the end item.—The methods of testing specified in Federal Specification CCC–T–191, wherever applicable, and as listed in table V shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test method. The unit of product shall be 3½ continuous yards, full width of the finished fabric. For each characteristic, the acceptable quality level shall be 4.0 test failures per hundred units, and the inspection level shall be level L–1, table VII, of Appendix to Military Standard MIL–STD–105.

TABLE V.—*Test methods*

Characteristic	Requirement reference	Test method
Weave	Table I	Visual
Yarns per inch	Table I	5050
Weight, oz./sq. yard	Table I	5041
Breaking strength	Table I	5100
Shrinkage in laundering	3.4	5550
Nonfibrous material[1]	3.3	2611

[1] The nonfibrous material content shall be computed according to the following formula:

$$\text{Nonfibrous material content, percent} = \frac{O-S}{O} \times 100$$

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 *Levels A and B.*—The cloth shall be packaged in accordance with the applicable requirements for class 3 fabrics of Federal Specification PPP–P–51.

5.1.2 *Level C.*—The cloth shall be packaged in accordance with manufacturer's normal practice.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

5.2 Packing.

5.2.1 *Levels A and B.*—The cloth shall be packed in accordance with the applicable requirements of Federal Specification PPP–P–51.

5.2.2 *Level C.* — The cloth, packaged as specified in 5.1.2, shall be packed in a manner acceptable to common carriers for safe transportation to point of destination specified in shipping instructions at the lowest transportation rate for such supplies.

5.3 Marking.

5.3.1 *Military agencies.*—Shipments shall be marked in accordance with the requirements of Federal Specification PPP–P–51.

5.3.2 *Civilian agencies.*—Shipments shall be marked in accordance with the requirements of Federal Standard Fed. Std. No. 123.

5.4 Federal Standard 102 shall be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment.

6. NOTES

6.1 Intended use.—The cloth, cotton, jean covered by this specification is intended for use in the manufacture of clothing and equipage items.

6.2 Ordering data. — Procurement documents should specify the following:

(*a*) Title, number and date of this specification.

(*b*) Width of cloth required (see 3.2.1).

(*c*) Both the level of packaging and the level of packing required. (See 5.1, 5.2 and 6.3.)

6.3 In the preparation of contracts or orders, it must be noted that various options, choices and alternatives, as indicated in Federal Specification PPP–P–51, may be exercised in the preparation for delivery of this commodity.

6.4 Transportation description. — The transportation description applicable to this item is:

Cotton piece goods, in the original piece, not otherwise indexed by name.

Carload minimum weight, any quantity.

Motor volume minimum weight, any quantity.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—M Q
Navy—S MC
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.