CCC-C-444b
June 6, 1963
SUPERSEDING
Fed. Spec. CCC-C-444a
September 23, 1960

FEDERAL SPECIFICATION

CLOTH, COTTON, JEAN, (BLEACHED)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers one type of bleached cotton jean cloth.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein.

Federal Specifications:

CCC-T-191—Textile Test Methods.

PPP-P-51—Packaging, Packing, and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks, and Synthetics).

Federal Standards:

Fed. Std. No. 4—Glossary of Fabric Imperfections.

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Standard:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained, free of charge, from the Federal Trade Commission, Washington 25, D. C.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE I.- Physical requirements

Weight per square yard (minimum)	Yarns per inch (minimum)		Breaking strength (minimum)		Weave
	Warp	Filling	Warp	Filling	
Ounces			Pounds	Pounds	
4.7	98	60	85	48	2/1 twill

3. REQUIREMENTS

3.1 Material.

3.1.1 *Yarn.* The cotton used in the manufacture of the yarn shall be cleaned, carded, drawn, and spun.

3.2 Physical requirements. The finished cloth shall conform to the requirements shown in table I when tested as specified in 4.4.

3.2.1 *Width.* The width shall be as specified (see 6.2) and shall be the minimum acceptable width inclusive of selvages.

3.3 Finish. The cloth shall be singed, desized, and bleached. The total sizing, finishing, and nonfibrous material shall not exceed 2.0 percent when tested as specified in 4.4.

3.4 Shrinkage. The cloth shall be preshrunk and shall not shrink more than 1.0 percent in either the direction of the warp or filling when tested as specified in 4.4. The preshrinking process used shall not be identified on the cloth, the ticket, or on the package.

3.5 Length. Unless otherwise specified (see 6.2), the cloth shall be in one continuous length of not less than 50 yards and shall be put up in bolts or flat folded pieces as specified in PPP-P-51.

3.6 Fiber identification. Each piece shall be labeled, ticketed or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.7 Workmanship. The cloth shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the point level specified.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Examination of the end item. Examination of the end item shall be in accordance with the provisions of MIL-STD-105 and 4.2.1 through 4.2.3.

4.2.1 *Yard-by-yard examination.* The required yardage of each piece shall be examined on the face side and all defects as defined in Federal Standard No. 4 which are

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points at listed in 4.2.2.1, except that spots, stains, and streaks shall be counted regardless of cause, (i.e., not restricted to rust, oil, or grease), and only those slubs and knots which exceed the maximum acceptable limits shown for each shall be scored (see 4.2.1.2). Defects on the selvage shall not be scored unless the body of the cloth is affected. No yard shall be penalized more than four points. For purpose of this examination, a yard shall begin at the last scored defect. The sample unit for this examination shall be one linear yard. The sample size shall be 750 linear yards, regardless of lot size. The sample yardage shall be examined from 25 pieces taken from 25 containers. An approximately equal number of yards shall be examined from each piece of the sample. The lot shall be unacceptable if the points per hundred square yards exceed 35.00 points. Point computation shall be as follows:

$$\frac{\text{Total points scored in sample size} \times 3600}{\text{Sample size (yards)} \times \text{Contracted width of material (inches)}} = \text{Points per 100 square yards}$$

4.2.1.1 *Demerit points.* Demerit points shall be assigned as follows:

For defects up to 3 inches in any dimension	—one point.
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	—two points.
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	—three points.
For defects exceeding 9 inches in any dimension	—four points.

Note: The following defects, when present, shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth.

Objectionable odor.

Width less than specified.

Not singed.

Excessive neppiness.

4.2.1.2 *Limits of slubs and knots.* Only slubs and knots which exceed the limits shown on figure 1 shall be scored:

4.2.2 *Examination for length.*

4.2.2.1 *Individual pieces.* During the yard-by-yard examination, each piece in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards below the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more pieces in the sample are defective in respect to length.

4.2.2.2 *Total yardage in sample.* The lot shall be unacceptable if the total of the actual lengths of pieces in the sample is less than the total of lengths marked on the tickets.

4.2.3 *Examination for identification of preshrinkage process and noncompliance with Textile Fiber Products Identification Act.* During the yard-by-yard examination, each piece in the sample shall be examined for these defects. The lot shall be unacceptable if two or more pieces in the sample contain identification of the preshrinkage process by name or trademark on the cloth or ticket or are not labeled, ticketed, or invoiced in accordance with the Textile Fiber Products Identification Act.

4.3 Examination of preparation for delivery requirements. An examination shall be made to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the num-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

ber of shipping containers in the end item inspection lot. The inspection level shall be L-4 and the AQL shall be 4.0 defects per 100 units.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components, such as: incomplete closure of case liners, container flaps; loose strapping, inadequate stapling. Bulging or distortion of containers.
Weight	Gross weight exceeds requirements.

4.4 Testing of the end item. The method of testing specified in CCC-T-191, wherever applicable and as listed in table II shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 3-1/2 continuous yards full width of the cloth. The lot shall be unacceptable if one or more units fail to meet any requirement specified. The sample size shall be as follows:

Lot size (yards)	Sample size (units)
800 or less	2
801 to 22,000	3
22,001 and over	5

5. PREPARATION FOR DELIVERY

(Fed. Std. No. 102 shall be referred to for definitions and application of the various levels of packaging and packing protection for civil agency procurements.)

5.1 Packaging. Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 *Levels A, B, and C.* The cloth, put up as specified in 3.5, shall be packaged in accordance with the applicable requirements for class 3 fabrics of PPP-P-51.

5.2 Packing. Packing shall be Level A, B, or C, as specified (see 6.2).

5.2.1 *Levels A, B, and C.* The cloth shall be packed in accordance with the applicable requirements of PPP-P-51.

TABLE II.- Test methods

Characteristic	Requirement reference	Test method
Weight	Table I	5041
Weave	Table I	Visual 1/
Yarns per inch	Table I	5050
Breaking strength	Table I	5100
Nonfibrous material	3.3	2611
Shrinkage	3.4	5550 2/

1/ One determination shall be made from each sample unit and the results reported as "pass" or "fail".

2/ The three specimens required for the shrinkage test shall be selected from the cloth (sample unit) as follows: One specimen from each side of the cloth to within 3 inches of selvage and one specimen from the center of the cloth. No two specimens shall contain the same filling yarns. Each elongation value shall be prefixed with a minus sign and both inclosed in parenthesis.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, shipments shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, shipments shall be marked in accordance with PPP-P-51.

6. NOTES

6.1 Intended use. The cloth, cotton, jean covered by this specification is intended for use in the manufacture of clothing and equipage items.

6.2 Ordering data. Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) Width of cloth required (3.2.1).
(*c*) When length of piece is other than specified (3.5).
(*d*) Selection of applicable levels of packaging and packing (5.1 and 5.2).

6.2.1 In the preparation of contracts or orders, it must be noted that various options, choices, and alternatives, as indicated in PPP-P-51, may be exercised in the preparation for delivery of this commodity.

6.3 Transportation description. Transportation descriptions and minimum weights applicable to this commodity are:

Rail:
Cotton piece goods, in the original piece.
Carload minimum weight—any quantity.

Motor:
Cotton piece goods, not otherwise indexed, in the original piece.
Motor volume minimum weight—any quantity.


6.4 Level B. Level B packaging and packing should be used by ordering agencies only when shipment is known to be made to a holding supply depot or warehouse from which partial shipments will be made to ultimate consumers.

Notice. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.


MILITARY INTERESTS:
Army—GL
Navy—S
Air Force—ASD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

Slub



Slub (Loose, Thick)



Lump or Knot (Fuzz)




Figure 1. (Limits of acceptability).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.