MIL-I-14511C
22 June 1987
SUPERSEDING
MIL-I-14511B(AT)
31 March 1980

MILITARY SPECIFICATION

INSULATION SHEET, CELLULAR, PLASTIC: THERMAL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers unicellular, elastomeric, expanded plastic thermal insulating material (see 6.1).

1.2 Part numbering format. The items covered by this specification shall be assigned part numbers in accordance with the following part numbering format (see 3.7 and 6.2).

M 14511 - 1 X

- X — Size (see 1.2.1.4).
- 1 — Sheet form (see 1.2.1.3).
- 14511 — Specification number (see 1.2.1.2).
- M — Prefix M (see 1.2.1.1).

1.2.1.1 Prefix M. Prefix M specifies that the item shall be defined by inch-pound (US) units.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Tank-Automotive Command, ATTN: AMSTA-GDS, Warren, MI 48397-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document, or by letter.

AMSC N/A FSC 5640

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

1.2.1.2 Specification number. Specification number shall not include the revision letter or activity symbol.

1.2.1.3 Sheet form. The sheet form shall be designated with Arabic numeral 1.

1.2.1.4 Size. The specific size shall be designated by using alpha code as shown in the following example:

A = 4 feet (ft) by 4 ft by 1 inch.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS
FEDERAL

MMM-A-1617	- Adhesive, Rubber Base, General Purpose.

MILITARY

MIL-E-52835	- Enamel, Modified Alkyd, Camouflage, Lusterless.

STANDARDS
FEDERAL

FED-STD-601	- Rubber; Sampling and Testing.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-45662	- Calibration Systems Requirements.

(Copies of specifications and standards required by the contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 202640-18T03:22Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D395	- Rubber Property - Compression Set, Test Methods for.
ASTM D412	- Tension Testing of Vulcanized Rubber - Die A.
ASTM D3574	- Flexible Cellular Materials - Slab, Bonded, and Molded Urethane Foams, Methods of Testing.

(Application for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA, 19103.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. Unless otherwise specified (see 6.2), the contractor shall furnish sample sheets which shall be subjected to first article inspection (see 4.4). First article inspection samples, properly marked with identifying information shall be representative of the unit to be furnished to the Government. All subsequent materials delivered to the Government shall conform to these samples in all of their pertinent physical and performance attributes.

3.2 Materials. Materials shall be as specified herein and in referenced specifications, standards and drawings. Material shall be free of defects which adversely affect performance or appearance of the finished product (see 4.8.1).

3.2.1 Recycled, virgin and reclaimed materials. There are no requirements for the exclusive use of virgin materials; however, all materials shall be new and unused. The use of recycled or reclaimed (recovered) materials is acceptable provided that all other requirements of this specification are met and that the suppliers' employees are not exposed to undue hazards from the recovered materials (see 6.3).

3.3 Construction. Construction of insulation shall consist of a multitude of individual cells of uniform size, a large majority of which are sealed off one from the other; homogeneous throughout; free of large voids, foreign inclusions, contaminations, or seams; and shall be free from any materials that accelerates aging and deterioration, or contributes to the formation of toxic gases in harmful concentrations. (see 4.8.1)

Source: https://assist.dla.mil -- Downloaded: 20261O-18T03:22Z
Check the source to verify that this is the current version before use.

3.4 Physical properties.

3.4.1 Compression set. The resilience capability of the insulation material shall be 35 to 50 percent (%) (see 4.8.3.2).

3.4.2 Volume change on heat aging. The volume change on heat aging insulation material shall be not more than 8% (see 4.8.3.3).

3.4.3 "K" factor. The coefficient of insulation material heat transfer shall be no more than 0.30 British thermal units (BTU) per hour, per square foot, per degree Fahrenheit (°F), per inch of thickness (see 4.8.3.4).

3.4.4 Density. The density of insulation material shall be not more than 7.5 pounds per cubic foot (see 4.8.3.5).

3.4.5 Tensile strength. The tensile strength of the insulation material shall be not less than 50 pounds per square inch (psi) (see 4.8.3.6).

3.4.6 Elongation. The elongation of the insulation material shall be not less than 200% (see 4.8.3.7).

3.4.7 Water absorption. The water absorption of the insulation material shall be not more than 4% by weight (see 4.8.3.8).

3.4.8 Flame resistance. The insulation material shall be self-extinguishing (see 4.8.3.9).

3.4.9 Brittleness. The insulation material shall withstand a 180 degree bend in 15 seconds at a temperature of minus 65 $\pm$ 5 °F without cracking (see 4.8.3.10).

3.4.10 Dimensional change. The change in the linear or transverse dimensions shall be not more than 1.5% (see 4.8.3.11).

3.4.11 Coherency with adhesive at cemented joint. The tensile strength of the cemented joint shall be not less than 50 psi (see 4.8.3.12).

3.5 Dimensions and tolerances. Dimensions and tolerances shall be as specified by the contracting activity (see 4.8.2 and 6.2).

3.6 Color. Unless otherwise specified (see 6.2), the color of the insulating material shall be Forest Green as specified in MIL-E-52835 (see 4.8.2).

3.7 Identification marking. Identification marking shall be in accordance with the item part numbering format specified in 1.2 (see 4.8.2).

3.8 Workmanship. Workmanship shall be of a quality which will assure a product free of large voids, foreign inclusions, contaminations, or seams (see 4.8.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order (see 6.2), the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform or witness any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply wih all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Inspection equipment. Unless otherwise specified in the contract (see 6.2), the contractor is responsible for the provision and maintenance of all inspection equipment necessary to assure that supplies and services conform to contract requirements. Inspection equipment must be capable of repetitive measurements to an accuracy of 10 % of the measurement tolerance. Calibration of inspection equipment shall be in accordance with MIL-STD-45662.

4.2 Classification of inspections:

a. First article inspection (see 4.4).
b. Quality conformance inspections (see 4.5).
    1. Examination (see 4.5.2).
    2. Tests (see 4.5.3).
c. Control tests (see 4.6).

4.3 Inspection conditions. Unless otherwise specified (see 6.2), all inspections shall be conducted under the following conditions:

a. Air temperature 73 $\pm$ 18°F
b. Barometric pressure $28.5 \begin{smallmatrix} +2 \\ -3 \end{smallmatrix}$ inches mercury (Hg)
c. Relative humidity 50 $\pm$ 30 percent

4.4 First article inspection. Unless otherwise specified (see 6.2), first article inspection shall be performed. The Government shall specify the number of sample sheets that shall be subjected to first article inspection (see 6.2). First article samples shall be inspected as specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

in table I. Approval of the first article sample by the Government shall not relieve the contractor of his obligation to supply parts that are fully representative of those inspected as a first article sample. Any changes or deviation of the production units from the first article sample shall be subject to the approval of the contracting officer.

TABLE I. Classification of inspections.

Title	Requirement	Inspection	First article	Quality conformance		
				Examination	Tests	Control
Materials and construction	3.2 and 3.3	4.8.1	X			X
Defects	3.5, 3.6, 3.7 and 3.8	4.8.2	X	X		
Compression set	3.4.1	4.8.3.2	X		X	
Volume change on heat aging	3.4.2	4.8.3.3	X			X
"K" factor	3.4.3	4.8.3.4	X			X
Density	3.4.4	4.8.3.5	X			X
Tensile strength	3.4.5	4.8.3.6	X		X	
Elongation	3.4.6	4.8.3.7	X			X
Water absorption	3.4.7	4.8.3.8	X			X
Flame resistance	3.4.8	4.8.3.9	X		X	
Brittleness	3.4.9	4.8.3.10	X		X	
Dimensional change	3.4.10	4.8.3.11	X			X
Coherency with adhesive at cemented joint	3.4.11	4.8.3.12	X		X	

4.4.1 First article inspection failure. Any deficiency found during, or as a result of the first article test, shall be evidence that all items already produced prior to completion of the first article test are similarly deficient unless contrary evidence satisfactory to the contracting officer is furnished by the contractor. Such deficiencies on all items shall be corrected by the contractor. The Government shall not accept products until first article testing is completed to the satisfaction of the Government.

4.5 Quality conformance inspections.

4.5.1 Sampling.

4.5.1.1 Lot formation. An inspection lot shall consist of all the insulation materials of one type and part number, from an identifiable production period, from one manufacturer, submitted at one time for acceptance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

4.5.1.2 Sampling for examination. Samples for quality conformance examination shall be selected in accordance with general inspection level II of MIL-STD-105.

4.5.1.3 Sampling for acceptance tests. Samples for acceptance tests shall be selected in accordance with level S-3 of MIL-STD-105.

4.5.2 Examination.

4.5.2.1 Acceptable quality level. Each sample selected in accordance with 4.5.1.2 shall be examined to determine conformance to the following acceptable quality levels (AQL).

Classification	AQL
Major	1.0
Minor	2.5

4.5.2.2 Classification of defects. For examination purposes, defects shall be classified as listed in table II.

TABLE II. Classification of defects.

Category	Defect	Method of examination
Critical	None	
Major	AQL 1.0% Defective	
101	Dimensions and tolerances not as specified (see 3.5).	SIE 1/
102	Identification marking improper (see 3.7).	Visual
103	Faulty workmanship affecting performance (see 3.8).	Visual
Minor	AQL 2.5% Defective	
201	Improper color (see 3.6).	Visual
202	Faulty workmanship affecting appearance (see 3.7).	Visual

1/ SIE = Standard Inspection Equipment.

4.5.3 Test. Test samples selected in accordance with 4.5.1.3 shall be subjected to the quality conformance tests specified in table I and shall conform to an AQL of 6.5.

4.6 Control tests. Unless otherwise specified (see 6.2), control tests shall be conducted on one sample from every 200 sheets consecutively produced, except that not more than one test shall be performed in a 6-month period, nor less than one test in a 3-month period. Sample shall be subjected to the tests specified in table I.

Source: https://assist.dla.mil -- Downloaded: 202640-18T03:22Z
Check the source to verify that this is the current version before use.

4.7 Failure. Failure of control tests sample to pass any of the tests specified in table I shall be cause for the Government to refuse to permit additional testing until the faults revealed have been corrected.

4.8 Methods of inspection.

4.8.1 Materials and construction. Conformance to 3.2 and 3.3, shall be determined by inspection of contractor records providing proof or certification that design, construction, processing, and materials conform to requirements. Applicable records shall include drawings, specifications, design data, receiving inspection records, processing and quality control standards, vendor catalogs and certifications, industry standards, test reports, and rating data.

4.8.2 Defects. Conformance to 3.5, 3.6, 3.7 and 3.8 shall be determined by examination for the defects listed in table II. Examination shall be visual, tactile, or by measurement with standard inspection equipment.

4.8.3 Physical properties.

4.8.3.1 Test samples. The physical property test samples shall be conditioned in an oven at 158 $\pm$ 2°F for seven days, cooled to testing temperatures of 73 $\pm$ 2°F and allowed to rest for a period of 16 to 48 hours.

4.8.3.2 Compression set. To determine conformance to 3.4.1, the test samples shall be tested in accordance with method B of ASTM D395.

4.8.3.3 Volume change on heat aging. To determine conformance to 3.4.2, a minimum of six samples each 4 x 4 x 1 inch, or thickness as manufactured shall be tested in accordance with method 7221 of FED-STD-601.

4.8.3.4 "K" factor. To determine conformance to 3.4.3, a minimum of two test samples each 4 x 4 x 1/2 inch shall be used. The test sample shall be placed between the upper vessel and base of a Cenco Fitch thermal conductivity apparatus, or equivalent. With the use of thermocouples, and a galvanometer, the temperature difference shall be measured. From the rate at which heat is conducted through the material, and the area, thickness, and temperature differences of the faces of specimens of material, their thermal conductivity shall be calculated at minus 65°F and plus 165°F using the following formula:

$$K = \frac{46.34 \times I^2 \times D}{T}$$

Where: K = Thermal conductivity in BTU per hour, per square foot, per °F, per inch of thickness.
I = Current in amperes in main heater.
D = Thickness of specimen in inches.
T = Temperature difference, in 0°F, between the hot and cold plates.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

4.8.3.5 Density. To determine conformance to 3.4.4, three test samples each 4 x 4 inch shall be used. No specific thickness is required. The volume shall be obtained by measurement and expressed in cubic inches. The weight of the specimen shall be obtained by weighing on an analytical balance or scale, and expressed in grams. Calculation of density shall then be made using the following formula:

$$\text{Density} = \frac{W}{V} \times 3.810 = \text{lb./cu.ft.}$$

Where: W = weight of the specimen in grams.
V = volume of the sample in cubic inches.

4.8.3.6 Tensile strength. To determine conformance to 3.4.5, a minimum of four test samples (4 x 4 inches) shall be tested in accordance with ASTM D412 or D3574. Conditions for testing shall be 73 ± 2°F and 50 ± 2% relative humidity. Two specimens shall be taken from the center of the sheet of insulation material and two from one side of the sheet, keeping the skin surface intact. The average tensile strength of the four specimens shall be recorded.

4.8.3.7 Elongation. To determine conformance to 3.4.6, the elongation shall be measured and recorded during tensile strength testing (see 4.8.3.6).

4.8.3.8 Water absorption. To determine conformance to 3.4.7, three specimens (4 x 4 inches) shall be tested in accordance with method 12411 of FED-STD-601. The percentage by volume of water absorbed due to immersion of the specimen shall be calculated as follows:

Water absorption, percentage by volume =

$$\frac{W_2 - W_1 \times 100}{W_1} = \textit{Percent weight increase}$$

Where: W_1 = Weight of specimen (grams) before immersion.

W_2 = Weight of specimen (grams) after immersion.

The average of three specimens tested shall be determined and expressed to the nearest one-tenth percent.

4.8.3.9 Flame resistance. To determine conformance to 3.4.8, three test samples 1/4 x 1/2 x 6 inches, shall be tested. Each specimen shall be clamped at one end in a position such that the long dimension forms a 45 degree angle with the horizontal and the width is in a vertical position. A candle flame shall be applied to the lower, or free, end of the specimen for 15 seconds. The candle shall then be removed. If the flame ceases within five seconds, the material shall be considered self-extinguishing.

4.8.3.10 Brittleness. To determine conformance to 3.4.9, four test samples 1/4 x 1/4 x 3 inches shall be subjected to the test. A low-temperature cabinet, as specified in method 5311 of FED-STD-601, shall be used; except that provision shall be made for clamping specimens between two

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

horizontal glass rods approximately 5/16 inch in diameter, allowing no less than 2/3 of the length of the specimens to extend vertically above the two glass rods. The glass rods, with the specimens clamped between them, shall be supported horizontally between two test stands by means of clamps. Brittleness test values shall be determined as follows: Specimens shall be placed in the chamber at room temperature. The temperature in the chamber shall be gradually lowered to 0 ± 5°F. The specimens shall be conditioned at this temperature for 15 minutes. Test specimens shall then be bent 180 degrees within 5 seconds, by means of a hooked glass rod, over one of the clamping glass rods. The approximate percentage of recovery shall be recorded. The temperature in the chamber shall be gradually lowered and the procedure repeated each 5°F. When the temperature is reached at which the first specimen breaks, the next specimen shall be bent to 180 degrees within 15 seconds at a rate of approximately 12 degrees each second. This procedure shall be repeated until all of the specimens break at the slower rate. The average temperature at which the last three specimens break shall be considered as the brittle temperature. For acceptance tests, the 5 and 15 second procedure shall be performed at minus 65 ± 5°F only.

4.8.3.11 Dimensional change. To determine conformance to 3.4.10, two test samples 12 inches square shall be subjected to the test. No specific thickness is required. Shrinkage shall be determined by the change in the linear dimension of the insulation material after exposure to a temperature of 158 ± 5°F for 24 hours. Two parallel lines not less than 1.2 inch from each edge shall be marked on the specimens and the distance between these lines used to measure the change. The test specimens shall be exposed to the test temperature in a horizontal position on heavy kraft paper. Specimens shall not be restricted or deformed. The specimens shall be reconditioned for a minimum of 4 hours at room temperature prior to re-measurement.

The percentage of change shall be calculated as follows:

$$\text{Percentage change} = \frac{A_1 - A_2 \times 100}{A_1}$$

Where: A_1 = original measurement value.

A_2 = final measurement value.

4.8.3.12 Coherency with adhesive at cemented joint. To determine conformance to 3.4.11, a minimum of four test samples 4x4 inches shall be required. The samples shall be cut in half, perpendicular to the longitudinal axis. The two halves shall then be cemented together at the cut surfaces, using adhesive conforming to type II of MMM-A-1617, and allowed to set for no less than 24 hours. The tensile strength of the bonded specimens shall then be determined in the same manner specified in 4.8.3.6. Information shall be recorded as to whether the break occurs at the bonded joint or beyond the joint. The average tensile strength of the four specimens shall be recorded.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation, packaging, packing, and marking. Preservation, packaging, packing, and marking for the desired level shall be in accordance with the applicable packaging standard or packaging data sheet specified by the contracting authority (see 6.2).

6. NOTES

6.1 Intended use. The material covered by this specification is intended for application to metallic personnel compartment panels of military vehicles, as a thermal barrier for temperatures ranging from 165°F to minus 65°F.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. Part number (see 1.2).
c. If first article is not required (see 3.1).
d. Dimensions and tolerances (see 3.5).
e. If color of the insulation material is other than as specified (see 3.6).
f. If responsibility for inspection shall be other than as specified (see 4.1).
g. If responsibility for inspection equipment shall be other than as specified (see 4.1.2).
h. If inspection conditions shall be other than as specified (see 4.3).
i. If first article inspection is not required (see 4.4).
j. Number of parts to be submitted for first article inspection (see 4.4).
k. If control testing is not required (see 4.6).
l. Selection of applicable level and packaging standard or packaging data sheet (see 5.1).

6.3 Recovered materials. 'Recovered materials' means materials that have been collected or recovered from solid waste (see 6.3.1) to become a source of new materials, as distinguished from virgin raw materials.

6.3.1 Solid waste. For definition of 'solid waste', refer to section 23.402 of the Federal Acquisition Regulations.

6.4 Subject term (key word) listing.

Cellular insulation sheet
Plastic insulation sheet
Thermal insulation sheet

6.5 Changes from previous issue. Asterisks (or vertical lines) are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

Custodians:
Army - AT
Air Force - 99

Review activities:
Army - MI, AR, MR
Air Force - 84

User activities:
Army - AV, ME

Preparing activity:
Army - AT

(Project 5640-0121)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Tank-Automotive Command
ATTN: AMSTA-GDS
Warren, MI 48397-5000

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426

PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:22Z
Check the source to verify that this is the current version before use.