INCH-POUND

MIL-DTL-11484/406
30 August 2017

DETAIL SPECIFICATION SHEET

LAPEL BUTTON, DEFENSE CONTRACT MANAGEMENT AGENCY

This specification is approved for use by all
Departments and Agencies of the Department of Defense

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-11484.



MATERIAL: (-1 AND -2) Red Brass 85/15 (UNS Alloy No.C-230)

FINISH:
BASE: Epoxy resin 24K Gold Plated Mirror-like Polished and shall match The Institute of Heraldry (TIOH) Metal Finish Chip Number 6.
DEVICE: Epoxy resin24K Gold Plated, Mirror- like Polish and shall match TIOH Metal Finish Chip Number 6.

DIMENSIONS:
BASE DIAMETER: 3/4 inch (REF)
DEVICE:
HEIGHT: 27/32 inch (REF)
WIDTH: 15/16 inch (REF)
THICKNESS BASE (End of the ray): 0.065 ± 0.010 inch
THICKNESS DEVICE (End of the wing): 0.040 ± 0.010 inch
THICKNESS OVERALL (End of the wing/ray): 0.098 ± 0.010 inch

ATTACHING DEVICE:
1. Attaching device will be a prong with pick and wing type clutch fused or soldered on the vertical center line 1/4 inch from the top of the lapel button.

AMSC N/A FSC 8455

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T18:09Z
Check the source to verify that this is the current version before use.

2. Attaching device will be a prong with pick and wing type clutch fused or soldered on the vertical center line 1/4 inch from the top of the lapel button.

EPOXY:

1. Epoxy resin shall be applied to the Badge Qualification as indicated above, and shall match TIOH Hard Enamel Color Chip Numbers listed below.

TIOH HARD ENAMEL COLOR CHIPS	
COLOR	**CHIP NUMBER**
White	#28
Blue	#33
Red	#1
Blue	#20

2. BASE: The background of the base shall be filled with Blue Epoxy #33. The stars shall be filled with White Epoxy #28. All epoxy will be floating epoxy.

3. DEVICE: The stripes on the shield shall be alternating White Epoxy #28 and Red Epoxy #1; beginning with white and ending with white. The lapel button shield has 7 stripes. The top of the shield shall be Blue Epoxy #20. All epoxy will be floating epoxy.

NOTES:

1. The term (REF) refers to the measurements taken from the Government furnished hub or die.

2. The device will be secured to the base by two solid brass rivets and shall be dapped to insure a snug fit.

3. The lapel button will be spherically dapped to radius of 10 inches + 1/4 inch - 0 when measured on the reverse.

4. Hard cloisonné enamel may be used in lieu of epoxy. If hard cloisonné enamel is used, the required base material shall be Gilding Metal 95/5 (UNS Alloy C-210).

Custodian:
Army - IH

Preparing activity:
Army - IH

Review activity:
DLA - CT

(Project No. 8455-2017-291)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T18:09Z
Check the source to verify that this is the current version before use.