MILITARY SPECIFICATION

ADHESIVE SYSTEM, EPOXY-ELASTOMERIC, FOR GLASS TO METAL

This interim amendment is issued for use by US Army Armament Research and Development Command, with Military Specification MIL-A-48611A, dated 30 March 1981

Page 12

Add the following new paragraph:

"6.7 Debonding procedure. Satisfactory debonding of glass to metal bonds, formed with epoxy based adhesives conforming to the requirements as contained herein, can be accomplished through the use of the solvent N-Methyl-2-Pyrrolidone. A quantity of solvent, sufficient to completely submerse the assembly to be debonded, should be brought to an elevated temperature in excess of 90°C but less than 150°C. (The higher the solvent temperature the faster will be the debonding effect). The volatility of the solvent at elevated temperatures will necessitate a hooded area such as in 6.5 above plus the use of condensing retort for the confining and condensing of gaseous solvent. A debonding effect should be obtained in one hour or less for a $2cm^2$ assembly and in three hours or less for an $8cm^2$ assembly depending on actual solvent temperature. The time of submersion may have to be extended to completely remove the primer coating (if applicable). Further debonding information, debonding process detail or solvent availability or use, is obtainable from the address indicated in 6.4."

Custodian:

Army - AR

Preparing activity:

Army - AR

(Project Number 8040-A112)

FSC 8040

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:34Z
Check the source to verify that this is the current version before use.