MIL-C-3154A (OS)
16 September 1971
SUPERSEDING
MIL-C-3154
20 March 1950

MILITARY SPECIFICATION

CLOTH, COATED, COTTON (CREPED, PHENOLIC RESIN TREATED)

This specification has been approved by the Naval Ordnance Systems Command, Department of the Navy.

1. SCOPE

1.1 Creped resin-treated fabric furnished under this specification shall be of one grade.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

PPP-P-1136	Packaging and Packing of Coated (Plastic: Rubber) and Laminated Fabrics

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material. The material shall consist of cotton sheeting (40"—3.75—48×40 grey goods) coated with a thermosetting phenolic resin and subjected to the creping process.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:13Z
Check the source to verify that this is the current version before use.

3.2 Creping. The creping process shall take place after resin treatment and shall be such as to increase the number of ends and picks per inch not less than 15 percent of the original construction of the untreated fabric.

3.3 Resin content.

3.3.1 Rolls. The resin content of each individual roll of the creped resin-treated fabric shall be 43 ± 2 percent.

3.3.2 Test specimens. The resin content of each individual test specimen of the creped resin-treated fabric shall be 43 ± 5 percent.

3.4 Volatile content. The volatile content of each lot of the creped resin-treated fabric, at the time of manufacture, shall be 6 to 7 percent as averaged from all individual test specimens.

3.5 Color. The color of the creped resin-treated fabric shall be as specified. (See 6.2.)

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Size of lot. Unless otherwise specified, a lot shall consist of no more than one roll of the creped resin-treated fabric.

4.3 Sampling. A sufficient number of test specimens, 12 by 18 inches, considered necessary by the Government inspector to be respresentative of the lot, shall be cut at regular intervals from both sides of each roll of creped resin-treated fabric for inspection and tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:13Z
Check the source to verify that this is the current version before use.

4.4 Inspection. All of the finished creped resin-treated fabric shall be subjected to visual examination for any defects which are considered to be detrimental to the durability or use of the material.

4.5 Tests.

4.5.1 Creping. The degree of creping shall be determined by the difference in construction of the creped resin-treated fabric and the untreated fabric (number of ends and picks per inch). The percentage increase shall be based upon the original construction.

4.5.2 Resin content.

4.5.2.1 Rolls. The resin content of each roll of the creped resin-treated fabric shall be determined by the difference in weight between the treated fabric and the untreated roll. The percentage shall be based upon the weight of the treated fabric.

4.5.2.2 Test specimens. The resin content of the test specimens, selected as specified in 4.3, shall be determined by the difference in weight between the treated specimens and untreated specimens of the same dimensions. The percentage shall be based upon the weight of the treated fabric.

4.6 Volatile content. Specimens 5 by 9 inches, cut from each of the specimens used in determining the resin content, shall be placed in an oven at 320° Fahrenheit and allowed to dry for 10 minutes. The average of the differences in weight of the specimens before and after drying shall be considered as the volatile content.

5. PREPARATION FOR DELIVERY

5.1 Packaging and packing. The packaging and packing of the subject commodity for shipment and storage shall be level A or C as specified (see 6.2) and in accordance with PPP-P-1136.

5.2 Marking. The marking of the subject commodity for shipment and storage shall be in accordance with PPP-P-1136.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:13Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. Creped resin-treated fabric is intended for use in the fabrication of ogives for certain types of fuze.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification

(b) Color required (see 3.5)

(c) Level of packaging and packing required (see 5.1).

Custodian:
Navy - OS

Preparing activity:
Navy - OS
(Project no. 8305-N196)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:13Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

MIL-C-3154A (OS), Cloth, Coated, Cotton (Creped, Phenolic Resin Treated)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:13Z
Check the source to verify that this is the current version before use.