INTERIM AMENDMENT

VIALS, LEVEL

This Interim Amendment is issued for use by the Department of The Army, Munitions Command (Frankford Arsenal), with Military Specification MIL-V-3144B dated 6 February 1967.

Paragraph 2.1: Add the following drawing: "D7680606 - Abrasion Tester, Optical Coating."

Table II, Characteristic 103: Change: "Markings water soluble" to "Graduations and markings".

Paragraph 4.4.5: Delete and substitute the following:

"4.4.5 Graduation and markings.

4.4.5.1 Water solubility.- Subsequent to the test of 4.4.4, and the vials having attained thermal stability at room temperature (60° to 90°F), the vials shall be immersed for a period of 24 hours in a solution of water and common table salt (sodium chloride). The mixture shall contain 6 ounces of salt per gallon of water. Upon removal the vials shall be wiped with a dry cloth and visually examined for compliance with the requirement of 3.4.4.1.

4.4.5.2 Abrasion resistance.- Five (5) level vials shall be randomly selected from the first fifty (50) produced for abrasion resistance testing. Three (3) from each subsequent lot of one hundred fifty (150) shall be randomly selected and subjected to this test. Utilizing abrasion Tester, Optical Coating, Drawing D7680606, each level vial shall receive twenty (20) strokes across all graduation markings with the abrasive tip under a spring load of 1.5 pounds. The abrasion tester shall be tipped with 600 grit silicon carbide paper. Subsequent to the twenty (20) strokes, the markings shall be examined with the unaided eye and the level vial graduations shall still be legible to conform with 3.4.4.1."

Custodian:

Army - MU

Preparing activity:

Army - MU

Project No. 1290 - A221

FSC 1290

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:11Z
Check the source to verify that this is the current version before use.