MILITARY SPECIFICATION

INTERIM AMENDMENT

VIALS, LEVEL

This Interim Amendment is issued for use by the Department of the Army, Munitions Command (Frankford Arsenal), with Military Specification MIL-V-3144B dated 6 February 1967.

* Paragraph 2.1: Add the following drawing: "D11730813 - Tester, Abrasion".

* Paragraph 4.2, 4.2.1, 4.2.1.1 and 4.2.1.3: Delete and substitute the following:

"4.2 First Article (Initial Production) Approval.- The requirement for first article approval and the responsibility (Government or contractor) for first article testing shall be as specified in the contract. The sample for first article approval tests shall consist of three (3) level vials manufactured in the same manner using the same materials, equipment, processes, and procedures as used in regular production. All parts and materials, including packaging and packing, shall be obtained from the same source of supply as used in regular production.

4.2.1 Government Testing.- When the Government is responsible for conducting first article approval tests, the contractor, prior to submitting the sample to the Government, shall inspect the sample to insure that it conforms to all the requirements of the contract and submit a record of this inspection with the sample, including certificates of conformance for materials.

4.2.2 Contractor Testing.- When the contractor is responsible for conducting first article approval tests, the sample shall be inspected by the contractor for all the requirements of the contract. The sample and a record of this inspection, including certificates of conformance for materials, shall be submitted to the Government for approval. The Government reserves the right to witness the contractor's inspection."

Table II, Characteristic 103: Change: "Marking water soluble" to "Graduations and markings".

Paragraph 4.4.5: Delete and substitute the following:

"4.4.5 Graduation and markings.

4.4.5.1 Water solubility.- Subsequent to the test of 4.4.4, and the vials having attained thermal stability at room temperature (60° to

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:52
Check the source to verify that this is the current version before use.

90°F), the vials shall be immersed for a period of 24 hours in a solution of water and common table salt (sodium chloride). The mixture shall contain 6 ounces of salt per gallon of water. Upon removal the vials shall be wiped with a dry cloth and visually examined for compliance with the requirement of 3.4.4.1.

* 4.4.5.2 Abrasion resistance.- Five (5) level vials shall be randomly selected from the first fifty (50) produced for abrasion resistance testing. Three (3) from each subsequent lot of one hundred fifty (150) shall be randomly selected and subjected to this test. Utilizing Abrasion Tester, Drawing D11730813, each level vial shall receive twenty (20) strokes across all graduation markings with the abrasive tip under a spring load of 1.5 pounds. The abrasion tester shall be tipped with 600 grit silicon carbide paper. Subsequent to the twenty (20) strokes, the markings shall be examined with the unaided eye and the level vial graduations shall still be legible to conform with 3.4.4.1."

*The margins of this amendment are marked with an asterisk to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:

Army - MU

Preparing activity:

Army - MU

Project No. 1290-A234

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:11Z
Check the source to verify that this is the current version before use.