INCH-POUND

A-A-52069
April 23, 1990

COMMERCIAL ITEM DESCRIPTION

FIBER ROPE ASSEMBLY, SINGLE LEG

The General Services Administration has authorized the use of this commercial item description in preference to MIL-F-14052.

1. SALIENT CHARACTERISTICS

1.1 Description. The fiber rope assembly shall be fabricated from a twisted (laid), three strand manila, 3-1/2 inch circumference rope with a minimum initial breaking strength of 10,800 pounds. The assembly shall consist of one continuous length of manila rope with eye spliced loops on each end. The splices shall be made with 4-full and 1-1/2 tucks. The length of the assembly shall be 20 feet ± 3 inches as determined by measuring from the farthest extremity of each eye spliced loop. The inner perimeter of each eye spliced loop shall be 43 ± 1-1/2 inches. The rope shall be natural in color and treated with copper-8-quinolinolate to retard mildew. The minimum length of rope per pound shall be 2.78 feet.

1.2 Marking. The rope assembly shall be marked with a corrosion resistant tag securely fastened to one of the eye spliced loops and shall contain the following information:

Fiber Rope Assembly, Single Leg
20 foot, 3-strand manila
Name of manufacturer
Stock number

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: Commander, U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-ESC, Natick, MA 01760-5014.

AMSC/NA FSC 4020

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

2. QUALITY ASSURANCE

2.1 Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics and requirements of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

2.2 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

2.3 End item visual examination. Each lot of fiber rope assemblies shall be inspected in accordance with MIL-STD-105, inspection level II. The assemblies shall be examined for consumer type defects, as follows:

Defects in design, construction, or workmanship; any cut, kink, broken or loose ends, bulged strands; not of continuous length; contains knots, splices, or otherwise secured to make a continuous length; tucks of splices not made against lay of rope; end strands of splices not tapered or trimmed; loose tucks, bulged splices or uneven splicing; any spot or stain clearly noticeable; served end not secured, served, loose ends not tucked in lay of rope; marking omitted or not as specified.

The lot size shall be expressed in units of completed fiber rope assemblies, and the sample unit shall be one completed fiber rope assembly. The inspection level shall be II, and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 6.5.

2.4 End item dimensional examination. The finished fiber rope assembly shall be examined for conformance to the dimensions specified in 1.1. Measurements shall be made as follows:

Characteristic	Measurement method
Length and inner perimeter of eye splice	All measurements shall be made with a metal ruler or tape on the rope which has been spread out on a flat surface in a relaxed state.
Circumference of rope	With the rope held under slight tension, pass a fiber snugly around the rope, cut it where it overlaps and measure the circumference. Perform this procedure in three random areas and average the results.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

to any special markings 5.2 Marking. In addition

Any dimension not within the specified tolerance shall be classified as a defect. The lot shall be expressed in units of completed fiber rope assemblies, and the sample unit shall be one completed fiber rope assembly. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

2.5 Breaking strength test. The rope shall be tested for breaking strength in accordance with ASTM D 4268. The lot size shall be expressed in units of completed fiber rope assemblies, and the sample unit shall be one completed fiber rope assembly. The sample size shall be in accordance with table I. The lot shall be rejected if one or more sample units fail to meet the breaking strength requirement.

TABLE I. Sample size

Lot size (completed fiber rope assemblies)	Sample size (sample units)
15 and under	2
16 up to and including 40	3
41 up to and including 110	5
Exceeding 110	7

3. PACKAGING

3.1 Packaging. Each individually coiled rope assembly shall be secured with a minimum of four equally spaced ties of cord on rope passing through the coil center to the outside, and knotted on the circumference of the coil.

3.2 Packing. Six rope assemblies, packaged as specified, shall be stacked in a snug-fitting fiberboard shipping container conforming to class domestic, grade 275, style optional of PPP-B-636. The dimensions of each container shall be palletizable in accordance with MIL-STD-147. The weight of each shipping container shall not exceed 65 pounds. Shipping containers shall be closed in accordance with the appendix of PPP-B-636.

3.3 Palletization. When specified (see 4.2), rope assemblies packed as specified, shall be palletized in accordance with load type Ia of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C and D or film bonding means F and G. Pallet pattern shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

3.4 Marking. Marking shall be in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

4. NOTES

4.1 Intended use. The fiber rope assembly is intended for use in cargo and material handling operations by military personnel.

4.2 Ordering data. Acquisition documents must specify the following:

a. Title, number, and date of this document
b. When palletization is required (see 3.3)

4.3 Sources of documents.

4.3.1 Source for Government documents. Copies of military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

4.3.2 Source of nongovernment document. Copies of ASTM D 4268, Testing Fiber Ropes, is available from:

American Society for Testing and Materials
1916 Race Street
Philadelphia, PA 19103-1187

MILITARY INTERESTS:

Custodians

Army - GL
Air Force - 99

Review activities

Army - ME
Air Force - 82
DLA - IS

User activity

Navy - SH

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

PREPARING ACTIVITY:

Army - GL

Project 4020-0316

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.