INCH-POUND
A-A-52071A
May 1, 2019
SUPERSEDING
A-A-52071
April 25, 1990

COMMERCIAL ITEM DESCRIPTION

TAPE, TEXTILE, COTTON, GENERAL PURPOSE

The General Services Administration has authorized the use of this Commercial Item Description (CID) for all federal agencies.

1. SCOPE. This Commercial Item Description covers the requirements for general purpose cotton textile tape used as binding on fabrication of various clothing and other textile items.

2. CLASSIFICATION. The tape shall be available in the following types and classes, as specified.

2.1 Types.

Type I - Stay bindings, herringbone twill weave
Type II - Bindings, plain weave

2.2 Classes.

Class 1 - Unbleached
Class 2 - Bleached
Class 3 - Dyed

3. SALIENT CHARACTERISTICS.

3.1 Description. The tape shall be manufactured from 100 percent cotton yarns and shall meet the requirements specified in Table I and Table II. The width shall be as specified in the contract or purchase order (see 3.5).

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Attn: DLA Troop Support, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil/.

AMSC N/A FSC 8315

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

3.2 Weave.

3.2.1 Type I. The weave of the Type I tape shall be two up and two down single or multiple herringbone twill with one or more reversals of the twill across the width of the tape. The tape shall be constructed so that it shall have a finished edge. The curvature of the finished tape shall show no more lateral curvature than 1/4-inch within a yard.

3.2.2 Type II. The weave of the Type II tape shall be plain. The tape shall be constructed so that it shall have a finished edge.

3.3 Color.

3.3.1 Color - Class 3 only. The color and appearance of the finished tape shall be as specified in the contract, and shall match the standard sample when tested as specified in 3.6.

3.3.2 Colorfastness. The colored tapes shall meet the colorfastness requirements as specified in Table I when tested in accordance with test methods cited in Table I. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyed tape shall be "Free" of labile sulfur when tested as specified in 3.7.

Table I. Colorfastness requirements (Class 3 only).

Characteristic	Requirement	Test method
Colorfastness:		
Dry Cleaning one (1) cycle, (color change and staining) 1/ (min.)	3-4	AATCC 132
Laundering one (1) cycle (color change and staining) 1/ (min.)	3-4	AATCC 61, Test 2A
Light (40 AFU or 170 kJ/(m^2nm) @ 420 nm 2/ (color change) 3/ (min.)	3-4	AATCC 16.3, Option 3
Perspiration (acid & alkaline) (color change and staining) 1/ (min.)	3-4	AATCC 15

1/ AATCC Evaluation Procedure 1, Gray Scale for Color Change and AATCC Evaluation Procedure 2, Gray Scale for Staining
2/ AFU: AATCC Fading Units
3/ AATCC Evaluation Procedure 1, Gray Scale for Color Change

3.4 Dimensional stability. Classes 1, 2 and 3 tape shall not shrink more than 4.0 percent in the warp direction when tested in accordance with AATCC 135 (3), (III),(Aiii).

3.5 Physical characteristics and requirements. The finished Type I and Type II tape shall conform to the physical characteristics specified in Table II when tested in accordance with test methods cited in Table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

TABLE II. Physical characteristics and test methods

Type	Width 1/, 2/ (inches)	Warp strength (lbs min.) 3/	Filling yarns (picks per inch) (min.) 4/, 5/
I	3/16	22	58
I	1/4	25	38
I	3/8	30	38
I	1/2	42	38
I	5/8	50	38
I	3/4	65	38
I	7/8	80	38
I	1	85	38
I	1-1/8	95	38
I	1-1/4	115	38
I	1-1/2	130	38
II	3/16	14	28
II	1/4	18	28
II	3/8	24	28
II	1/2	35	28

1/ Tolerance for all types shall be (±1/32) inch; except for Type I widths 1-1/8 through 1-1/2-inches, the tolerance shall be (+ 1/16, -1/32) inch.
2/ Using a calibrated steel ruler.
3/ Using ASTM D5035
4/ If woven on a shuttleless loom, then the minimum picks required shall be doubled resulting in two picks per shed.
5/ Using ASTM D3775

3.6 Visual shade matching. The color and appearance of the finished tape shall match the standard sample when viewed using the AATCC Evaluation Procedure 9, Option A with sources simulating artificial daylight D75 illuminant with a color temperature of 7500K (± 200) illumination of 100 (± 20) foot candles, and shall be a good match to the standard sample under incandescent A illuminant with a color temperature of 2856K (± 200).

3.7 Presence of labile sulfur test. In the determination of presence of labile sulfur in textile materials with lead acetate, two 1.50 (± 0.01) gram samples from each material submitted for evaluation shall be tested. Each of the two (2) samples shall be cut into very small pieces and placed into separate test tubes. The samples shall be submersed in a stannous chloride solution that contains 100 grams of stannous chloride crystals ACS in 100 milliliters of hydrochloric acid

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

ACS (35 percent concentration) and 50 milliliters of distilled water. A filter paper wet out with a 5.0 percent lead acetate solution shall be placed over the top of the test tube. The lead acetate solution contains 5.0 grams of lead acetate CP reagent grade and enough distilled water to make up a 100 milliliter solution; if the solution is not clear add a few drops (one at a time) of glacial acetic acid until the solution is clear. The test tube containing the textile sample, stannous chloride and wet filter paper shall be heated over a low flame until the solution is boiling. The solution should not be heated for more than 15 seconds. A brown to black stain on the filter paper should be evaluated as follows:

Free - The filter paper shows no discoloration or staining of any kind.
Slight - The filter paper shows a light tan to light brown discoloration stain.
Moderate - The filter paper shows a dark brown discoloration stain.
Severe - The filter paper shows a black color stain.

3.8 Length and put-up. For Government procurement only, unless otherwise specified (see 7.4), the tape shall be wound on standard commercial spools containing 720 (± 10) yards for ¼ through 1 inch widths and 500 (± 10) yards for 1-1/8-inch through 1-1/2-inch widths.

3.9 Labels. Each spool shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act.

3.10 Workmanship. The finished tape shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the contractor's own quality assurance standards and the quality assurance standards defined by the technical data in the bid package.

4. REGULATORY REQUIREMENTS. Unless otherwise specified the offer/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The finished tape provided shall meet the salient characteristics of this CID, conform to the producer's specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptability. This finished tape must have been sold to the commercial market or the Government.

5.3 End item inspection procedures. Sampling for inspection shall be conducted in accordance with ANSI/ASQ Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.2).

5.4 Visual examination. The finished tape shall be examined for the defects listed below as defined in ASTM D3990:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

Floats and skips that are over 1-inch.
Hitch-back crack; light or heavy places resulting from opening between adjoining picks.
Kinks – more than three (3) kinks in any 9-linear inches.
Knots – more than one (1) knot in any 9-linear inches.
Uneven width or width not as specified within a tolerance.
Any area of poor dye penetration, streak or shade bar that is 9-inches or less. Defective shade areas that are greater than 9-inches constitute a failure.
Objectionable odor.
Any embedded foreign matter or uncleanness.
Edges rolled folded, creases, scalloped or corded, baggy, ridgy or wavy tape.
Label missing, incorrect, or illegible. Required information missing from label
Not packaged in accordance with the contract or purchase order.

5.5 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order (see 7.4).

6. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or purchase order (see 7.4).

7. NOTES.

7.1 Sources of Government documents.

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 Rules and Regulations under the Textile Fiber Products Identification Act is available online at https://www.ftc.gov.

7.2 Sources for Non-Government documents.

7.2.1 AATCC test methods are available online at https://www.aatcc.org.

7.2.2 ANSI/ASQ Z1.4 – Sampling Procedures is available online at https://www. asq.org.

7.2.3 ASTM Standards are available online at https://www.astm.org.

7.3 Intended use. This tape is intended to be used as binding tape for clothing and other textile items.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

7.4 Ordering data. The contract or purchase order should specify the following:

a. Title, number, and date of this Commercial Item Description
b. Type, class and color required (see 2.1)
c. Width required (see 3.5)
d. Length put-up required (see 3.8)
e. Labeling information (see 3.9)
f. Product conformance provisions (see 5.)
g. Packaging requirement (see 6.)

7.5 Subject terms.

Filling yarns
Herringbone
Warp strength

MILITARY INTERESTS:

Custodians:
Army - GL
Navy - NU
Air Force - 11

Review Activities:
Army - MD
Navy - MC

CIVIL COORDINATING AGENCY ACTIVITY

GSA-FAS

Preparing Activity:

DLA - CT

(Project 8315 -2019-004)

Note: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIT Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.