INCH-POUND

A-A-52073
June 28, 1990

COMMERCIAL ITEM DESCRIPTION

PAPER, WRAPPING, LAMINATED AND CREPED

The General Services Administration has authorized the use of this commercial item description in preference to MIL-P-130.

1. CLASSIFICATION

1.1 Classification. This commercial item description covers 36 (± 1/8) inch width wrapping paper furnished in lengths of 100 or 200 yards (see 5.2) in the following types:

Type I - Heavy duty
Type II - Medium duty
Type III - Light duty

2. SALIENT CHARACTERISTICS

2.1 Description. The wrapping paper shall be made from paper and nonbituminous laminating or treating materials. The wrapping paper shall be creped one-way or two-way. The finished material shall meet the requirements listed in table I.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: Commander, U.S. Army Natick Research, Development, and Engineering Center, Natick, MA STRNC-ES 01760-5014.

AMSC/NA FSC 8135

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

TABLE I. Physical properties

Characteristic	Requirement			Tappi Test Method
	Type I	Type II	Type III	
Basic weight (24 x 36-500) creped, minimum, in pounds	150	125	100	T 410
Tearing resistance, weakest direction, minimum, in grams	250	200	150	T 414
Tensile strength, one-way creped only, in weakest direction, minimum, in pounds per inch	30	25	20	T 404
Bursting strength, two-way creped only, minimum, in p.s.i.	40	35	30	T 403
Acid content, maximum, in percent	0.02	0.02	0.02	T 428
Minimum stretch (percent)				
one-way	20	20	20	T 404
two-way	15	15	15	

3. QUALITY ASSURANCE

3.1 Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics and requirements of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

3.2 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

3.3 End item visual examination. Each lot of paper shall be examined for consumer type defects, defined as follows:

Foreign matter, dirt, sand, grit, or oil spots; holes, cuts, tears, punctures, chafed spots, wrinkles, or folds; edges ragged, crushed, uneven, or unclean; width not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

The lot size shall be expressed in units of rolls of paper. The sample unit shall be two linear yards full width selected from each of three randomly selected rolls from the lot, and both sides shall be examined. Defects of each type shall be scored only once within each two yard speciman of the sample unit. The inspection level shall be S-3, and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0.

3.4 Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

4. PACKAGING

4.1 Packaging. Wrapping paper shall be furnished in rolls of the length specified.

4.2 Packing. Each roll shall be wrapped with 40-pound minimum basis weight kraft paper in such a way that the paper shall encircle the roll twice and fold over and protect the ends of the roll. Seams and headers shall be sealed with adhesive or tape.

4.3 Palletization. When specified (see 5.2), rolls packed as specified, shall be palletized on a 4-way entry pallet in accordance with load type XIII of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C and D.

4.4 Marking. In addition to any special markings required by the contract or purchase order, rolls and palletized unit loads shall be marked in accordance with MIL-STD-129.

5. NOTES

5.1 Intended use. The paper is intended for use as a protective cover or wrapper, and not as a substitute for waterproof barrier material.

5.2 Ordering data. Acquisition documents must specify the following:

a. Title, number, and date of this document.
b. Length of roll required (see 1.1).
c. Type required (see 1.1).
d. When palletization is required (see 4.3).

5.3 Sources of documents.

5.3.1 Sources of nongovernment association documents.

TAPPI T 403 - Bursting Strength of Paper
T 404 - Tensile Breaking Strength and Elongation of Paper and Paperboard (Using Pendulum Type Tester)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.

T 410 - Grammage of Paper and Paperboard (Weight per Unit Area)
T 414 - Internal Tearing Resistance of Paper
T 428 - Hot Water Extractable Acidity or Alkalinity of Paper

All are available from:

Technical Association of the Pulp and Paper Industry (TAPPI) Standards
Technology Park/Atlanta, P.O. Box 105113
Atlanta, GA 30348
(404) 446-1400

5.3.2 Source of government documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

MILITARY INTERESTS:

Custodians

Army - GL
Navy - SA
Air Force - 69

Review Activities

Army - MD
Navy - MC, OS
Air Force - 84, 99

User Activities

Army - AT
Navy - SH, YD

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

Preparing activity:

Army - GL

Project 8135-0616

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:05Z
Check the source to verify that this is the current version before use.