MIL-C-58104A
20 May 1983
Superseding
MIL-C-58104(AV)
12 September 1980

MILITARY SPECIFICATION

COVER, PROTECTIVE, FOR PARTS AND EQUIPMENT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers requirements for protective covers to be used to provide environmental protection for end item equipment or major components during shipment and storage.

1.2 Classification. Protective covers manufactured to this specification shall be of the following types, as specified (see 6.2).

Type I - Watervaporproof
Type II - Moderately Watervaporproof
Type III - Waterproof

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

TT-I-1795	Ink, Marking, Stencil, Opaque, (Porous and Non-Porous Surfaces)
PPP-B-601	Box, Wood-Cleated, Plywood
PPP-B-636	Box, Shipping, Fiberboard
PPP-B-640	Box, Fiberboard, Corrugated, Triplewall

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Aviation Research and Development Command, ATTN: DRDAV-ERS, 4300 Goodfellow Boulevard, St. Louis, MO 63120. Use the self-addressed Standardization Improvement Form (DD Form 1426) appearing at the end of this document.

FSC 8145

NO DELIVERABLE DATA REQUIRED BY THIS DOCUMENT .

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-D-3464	Preservation - Packing, Methods of
MIL-P-116	Desiccants, Activated, Bagged, Packaging Use and Static Dehumidification
MIL-T-5624	Turbine Fuel, Aviation, Grades JP-4 and JP-5
MIL-H-6083	Hydraulic Fluid, Petroleum Base, for Preservation and Operation
MIL-L-23699	Lubricating Oil, Aircraft Turbine Engine, Synthetic Base
MIL-I-26860	Indicator, Humidity, Plug, Color Change
MIL-V-27166	Valve, Pressure Equalizing Gaseous Products
MIL-P-58102	Plastic Sheet and Laminates, Flexible, for Environmental Protective Storage and Shipping Systems

STANDARDS

FEDERAL

FED-STD-101	Preservation, Packaging and Packing Material, Test Procedures
FED-STD-191	Textile Test Methods
FED-STD-406	Plastic, Methods of Testing

MILITARY

MIL-STD-105	Sampling Procedures and Tables for Inspection Attributes
MIL-STD-129	Marking for Shipment and Storage
MIL-STD-831	Test Reports, Preparation of
MIL-STD-1188	Commercial Packaging of Supplies and Equipment

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other Publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

D471	Change in Properties of Elastomeric Vulcanizates Resulting from Immersion in Liquids
D882	Tensile Properties of Thin Plastic Sheeting
D1203	Loss of Plasticizer from Plastics (Activated Carbon Method)
D3137	Hydrolytic Stability of Elastomeric Vulcanizates
G23	Operating Light-Exposure Apparatus (Carbon Arc Type) With and Without Water for Exposure of Nonmetallic Materials

3. REQUIREMENTS.

3.1 First Article Inspection. This specification makes provision for First Article Inspection, as specifed (see 6.2).

3.2 Material.

3.2.1 Type I. Type I protective covers shall be made of material conforming to MIL-P-58102, Type I, class, grade, and color as specified (see 6.2).

3.2.2 Type II. Type II protective covers shall be made of material conforming to MIL-P-58102, Type II, class grade, and color as specified (see 6.2).

3.2.3 Type III. Type III protective covers shall be made of material conforming to MIL-P-58102, Type III, class, grade, and color as specified (see 6.2).

3.3 Design. The cover shall be designed to conform to the configuration of the equipment specified (see 6.2).

3.3.1 Patterns. The patterns for the protective covers shall be taken directly from the equipment. Access to the equipment shall be as stipulated in the contract (see 6.2).

3.3.2 Fit. Protective covers shall be generally form-fitting without obstructing the passage of air currents and shall be sufficiently loose at extremities to relieve any strain on the closure and to ease the installation process, as required.

3.4 Construction.

3.4.1 One-piece. The protective cover shall be one-piece or two-piece, as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

3.4.2 Joints. Joints shall be uniform and free from wrinkles, bubbles, areas of non-adhesion and other imperfections.

3.4.3 Towing. The installed cover shall not prevent wheeled equipment from being towed, though the storage environment need not be kept intact during the procedure.

3.4.4 Sleeves. Sleeves shall be incorporated for the following purposes. The sleeves shall be no less than six (15.2 cm) nor more than eight inches (20.3 cm) long and of the diameter specified.

3.4.4.1 Hoisting. One 9-inch (22.9 cm) sleeve for each hoisting point as specified (see 6.2).

3.4.4.2 Dehumidification. Two to four 3½-inch (8.9 cm) sleeves, as specified (see 6.2), for dehumidification hookup. These sleeves shall be located as specified (see 6.2).

3.4.4.3 Tiedown. A number of 6-inch (15.2 cm) sleeves, as specified (see 6.2) to provide access for tiedown.

3.4.4.4 Antennas. When specified (see 6.2), a 3½-inch (8.9 cm) sleeve to allow antennas to protrude.

3.4.4.5 Cavities. The cover shall incorporate sleeve- or pocket-construction, in lieu of draping, at major projections.

3.4.4.6 Sleeve Clamps. Nonmetallic clamps shall be provided for each sleeve and sized to fit the appropriate connection. One spare set of clamps shall be included with each repair kit.

3.4.5 Access to fuel filler. When specified (see 6.2), the protective cover shall incorporate 25-inch (63.5 cm) fuel filler slots designed with a closure identical to the main cover closure.

3.4.6 Draining. The protective cover shall have provision for draining water, fuel or oil from any low points. This may be accomplished through the cover closure, if practicable, or by means of a 2- to 3-inch (5.1 to 7.6 cm) sleeve.

3.4.7 Access door. When specified (see 6.2), the protective cover shall have a 3-sided opening to serve as an access door. The opening shall be approximately 2 feet (.6 m) wide and 5 feet (1.5 m) high and be located at the equipment entry hatch or door.

3.4.8 Record receptable. The cover shall incorporate a record receptable pouch with a flap and a suitable sealing device. The interior dimensions of the pouch shall be as specified (see 6.2).

3.4.9 Desiccant pouch. When specified (see 6.2), the cover shall incorporate a desiccant pouch. The disiccant pouch(es) size shall be calculated IAW MIL-P-116 to accommodate a specified number of 16-unit desiccant

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

bags conforming to MIL-D-3464. The pouch shall be perforated with 1/2-inch (1.3 cm) (approx.) holes, spaced 1-inch (2.5 cm) (approx.) apart. The pouch shall be closed with a suitable sealing device.

3.4.9.1 Humidity indicators. When specified (see 6.2), the cover shall be equipped with humidity indicator(s) conforming to the requirements of MIL-I-26860 to provide an indication of humidity within the cover. The indicator(s) shall be installed in a manner to provide easy removal and replacement, and shall be located as far as practical from the desiccant pouch.

3.4.10 Closure. Each cover shall incorporate a manually operated closure for the rapid installation/removal and sealing of the cover. More than one closure shall be permitted. There shall be no gaps in the closure and all joints shall have smooth surfaces. The performance of the closure shall require no tape, lubricants (i.e., silicone spray) or sealant. The lip of the closure shall be installed in the down position to prevent accumulation of water. Closure time shall be as specified (see 6.2). In addition, the closure shall meet the requirements of Table I when tested as specified in 4.5.1.

3.4.10.1 Support Straps. The closure shall be supported along its course by sets of straps made of reinforced cover material anchored to the cover on either side of the closure and designed to be snap-closed over the closure with quick disconnects. The straps shall be fitted in a manner to relieve stress on the closure during the closing operation. The straps shall be a minimum of 1 inch (2.5 cm) in width. They shall be spaced 24 inches (.6 m) apart along the closure, except on curves where they shall be spaced 18 inches apart. In the area of sharp radius curves there shall be a set of straps at each end of the radius.

3.4.10.2 Draw straps. If required, draw straps shall be installed on the cover to hold loose fitting material close to the item (see 6.2). The straps shall be an integral part of the cover to prevent accidental loss of the strap assembly.

3.4.11 Match-marking. The cover shall be match-marked, as required, to assure correct installation.

3.4.12 Reinforcements. The cover shall be reinforced with a second ply of material at all sharp corners and angles.

3.4.13 Pressure relief valves. When specified, the covers shall be equipped with pressure relief valve(s) conforming to the requirements of MIL-V-27166, Type III, Class I. Valve(s) shall be installed in a manner to provide for easy removal and installation. The flow rates and no-leak pressures shall be as specified by the procuring activity (see 6.2).

3.5 Closure tool. When specified (see 6.2), each cover shall be accompanied by a closure tool designed to operate smoothly without forcing or binding. The closure tool shall be housed in a pocket made as an integral part of the cover, and designed to preclude damage to the cover during shipment or storage. This tool shall be used during the closure operation test of 4.5.1.1.8.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

3.6 Installation instructions. Each cover shall be accompanied by one durable set of instructions placed in a record pocket, made as an integral part of the cover. Instructions shall include a step-by-step procedure for closing, opening, installing, and removing the cover from the equipment. The instructions shall include the procedure for folding and securing the cover in the stowage bag (3.8), when applicable.

3.7 Patching kit. Each cover shall be accompanied by a patching kit consisting of a sheet of identical material, taken from the same production, made in the same process and in the same color, as the covers offered for acceptance. The sheet shall measure not less than twelve (12) inches (30.5 cm) wide and ten (10) feet (3 m) long. This patching material shall be provided with adhesive and a set of instructions for patching. The adhesive shall be as specified in MIL-P-58102 for the material used in the covers. The adhesive shall be packed IAW AFR 71-4 and CFR-49. The kits shall be housed in a pocket which shall be an integral part of the cover assembly. Installed patches shall have the bond strength indicated in Table I, MIL-P-58102, when tested in accordance with 4.5.4.

3.8 Stowage bag. When specified (see 6.2), each cover shall be accompanied by a stowage bag made of the identical material, taken from the same production, made by the same process and of the came color as the covers offered for acceptance. The bag shall incorporate the identical closure provisions as the cover. The bag closure shall be taken from the same production, made by the same process and of the same color as the closure incorporated in the cover offered for acceptance. The stowage bag shall slip easily over the cover and close without any difficulty when demonstrated in accordance with 4.5.4.

3.8.1 Girth straps. When specified (see 6.2), the storage bag shall incorporate a minimum of two straps girthing the bag, designed with loops for fork-lift access and fixed to the bag in such a manner that the gross weight of the bag is not unduly focused at any one point on the strap. When tested in accordance with 4.5.5, the straps shall exhibit no fork-lift interference and no unbalanced loading or concentrated stress.

3.9 Assembly. Covers, together with closure tools, as applicable, patching kits, stowage bags, as applicable, and installation instructions, shall be considered unit assemblies for identification, drawing, and packaging purposes. As offered for acceptance, prior to packaging, closure tools, as applicable, installation instructions and patching kits shall be enclosed in their respective pockets and the cover enclosed, as applicable, in the stowage bag.

3.10 Markings. Each cover and stowage bag, when applicable, shall be marked as follows, in durable letters in a color contrasting with the color of the cover and bag. The markings shall be legible and waterproof.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

3.10.1 Identification markings. On the forward, right, upper half of the cover and on one end of the stowage bag, as applicable, in one-inch (2.5 cm) lettering:

SHIPPING AND STORAGE COVER
APPLICABLE TO: (Complete)
NSN: (Complete)
PART NO. (Complete)
MFR CODE: (Complete)
CONTRACT NO: (Complete)
(Manufacturer's Name and Trademark)
(US Army), US Air Force or other, as specified (see 6.2).

3.10.2 Functional markings.

a. On the cover only, as applicable:

(1) Adjacent to dehumidification machine inspection ports, in one-inch (2.5 cm) lettering:

DH INSPECTION PORT

(2) Adjacent to drains, in one-inch (2.5 cm) lettering:

DRAIN

(3) Adjacent to repair kit, in one-inch (2.5 cm) lettering:

REPAIR KIT

(4) Adjacent to installation instructions, in one-inch (2.5 cm) lettering:

INSTALLATION INSTRUCTIONS

(5) Adjacent to closure tool, as applicable, in one-inch (2.5 cm) lettering:

CLOSURE TOOL

(6) If adhesive is flammable, mark adjacent to patching kit in one-inch (2.5 cm) lettering:

FLAMMABLE MATERIAL INSIDE

b. On the stowage bag only, as applicable, in one-inch (2.5 cm) lettering:

SHIPPING AND STORAGE COVER, (name of equipment)
STORE IN AIRCRAFT CABIN WHEN COVER IS INSTALLED
ON AIRCRAFT (aircraft covers only)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

TABLE I

PHYSICAL PROPERTIES OF CLOSURE

Properties	Requirements	Test Para
Water Vapor Transmission Rate; Gms/Ft^2/24 Hrs Max.	Not applicable to Type III for Type II, .08; for Type I, .02.	4.5.1.1.1
Waterproofness	Not applicable to Types I and II. For Type III, no dye penetration.	4.5.1.1.2
Bond Strength % of original breaking strength of cover material or closure webbing, whichever is less	80 Min.	4.5.1.1.3
Breaking Strength as received (original) after hydrolytic aging % change from original	120 pounds (54.5 kg) -20 Max.	4.5.1.1.4
Elongation: % As received (original) After hydrolytic aging % change from original	Type III, 500 Min.; Types I and II, 50 Min. ±25	4.5.1.1.5
Flexibility As received After cold temperature conditioning	Easily hand-folded, flexed, twisted and bent.	4.5.1.1.6
Resistance to blocking	No blocking, delamination or rupture.	4.5.1.1.7
Operation As received After cold temperature conditioning	No binding, jamming, misalignment or other malfunction.	4.5.1.1.8
Resistance to parting force As receivee After high temperature conditioning	80#/inch (36.3 kg/2.5 cm) 80#/inch (36.3 kg/2.5 cm)	4.5.1.1.9

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

Properties	Requirements	Test Para
Resistance to fluids After 24 hr immersion at 158°F (70°C)		4.5.1.1.10
MIL-T-5624 MIL-L-23699 MIL-H-6083	No swelling, delamination, embrittlement, or other visible defects.	
Corrosivity	No corrosion	4.5.1.1.11
Volatility Weight loss shall not exceed	1%	4.5.1.1.12
Resistance to Abrasion Avg loss in grams per 2000 Wear Cycles	.07	4.5.1.1.13
Flame Resistance	The closure shall show a time of flame of not more than ten seconds.	4.5.1.1.14
Resistance to light	No embrittlement, cracking or delamination.	4.5.1.1.15
Pressure retention	No leakage after 30 min.	4.5.1.1.16

[1]Appreciable means a change that is immediately noticeable in comparing the tested specimen with the original.

3.11 Workmanship. The covers and stowage bags shall be uniformly made and free from dirt, oil, foreign matter, rough or sharp edges, tears, cuts, holes, and cracks.

4. QUALITY ASSURANCE PROVISIONS.

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the supplier is responsible for the performance of all inspection requirements as specified herein. The supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of examination and tests shall be kept complete and available to the Government. The Government reserves the right to perform

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

any of the inspections set forth in the specification when such inspections are deemed necessary to assure that suppliers and services conform to prescribed requirements.

4.2 Classification of tests. The test requirements specified herein are classified as follows:

a. First Article Tests

b. Quality Conformance Inspection

4.3 First Article inspection tests. First Article inspection tests shall be performed on one completed cover, one completed stowage bag, as applicable, one completed patching kit and one completed closure tool, as applicable, manufactured from the same material under the same manufacturing process used for production and shall consist of all tests specified in 4.5 and 4.6.

4.3.1 First Article inspection report. After the supplier or manufacturer completes the final First Article inspection, he shall prepare a First Article inspection report in accordance with MIL-STD-831, including a statement of compliance or noncompliance and furnish three copies of the report to the procuring activity.

4.4 Quality conformance inspection. Acceptance tests shall be as specified in 4.6. A random sample shall be selected from each lot offered for acceptance in accordance with MIL-STD-105 at inspection level S-4. The Acceptance Quality Level (AQL) shall be 1.0% for Major defects and 10.0% for Minor defects.

4.4.1 Lot. All covers and components, produced by one manufacturer and by the same manufacturing process from the same material for delivery at one time shall be considered a lot for purposes of inspection and test.

4.4.1.2 Inspection of components and materials. In accordance with 3.1, the supplier shall be responsible for ensuring that the materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced specifications, and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.5 First Article inspection tests. First Article inspection tests shall consist of the closure tests of 4.5.1, the fit and function of 4.5.2, the patch test of 4.5.3 and the stowage bag demonstration of 4.5.4.

4.5.1 Closure tests. Physical tests shall be performed for the applicable characteristics specified in Table I for each lot presented for acceptance. Unless otherwise indicated, the sample unit shall be a six-foot (1.8 m) sample of the closure, bonded to an eight-foot (2.3 m) piece of cover material, part of the same material used in the production of the lot of covers offered for acceptance.

4.5.1.1 Test methods.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

4.5.1.1.1 Water Vapor Transmission Rate (WVTR). The WVTR shall be determined in the "as received" condition in accordance with Federal Test Method Standard 101, Method 3030, Procedure B, in an environment of 100±2°F (38±1°C) and 95±2 percent relative humidity. The pouch shall be formed from an eight-inch (20.3 cm) piece of closure plus cover material, sealed on three sides with a continuous seal using the same methods and equipment used for fabricating the cover, and in such a manner that the inside dimensions of the pouch are 5 5/16±1/16 inches (13.5±.8 cm) wide by 6±1/8 inches (15.6±.3 cm) deep. The six-inch (15.2 cm) dimensions shall be measured from the locking part of the closure.

4.5.1.1.2 Waterproofness. Waterproofness shall be determined in the "as received" condition. The test specimen shall be identical to 4.5.1.1.1. A quantity of shredded absorbent paper sufficient to fill the pouch shall be placed inside the pouch and the pouch placed in a water solution containing one percent Aerosol O.T. and methyl violet for ten minutes. The pouch shall then be removed, wiped dry, and the shredded paper examined for dye stains.

4.5.1.1.3 Bond strength. The bonding strength of the closure with the cover material shall be tested in accordance with ASTM Test Method D882. The test specimen shall consist of two 1-inch (2.5 cm) strips of closure webbing bonded with a 1-inch (2.5 cm) overlay to a 1-inch (2.5 cm) strip of cover material. The tests shall be run not sooner than 24 hours after bonding.

4.5.1.1.4 Breaking strength. The breaking strength test shall be performed on a strip of the webbing taken from the closure. The breaking strength shall be determined in accordance with Federal Test Method Standard 191, procedure 5100. The tests shall be run on eight different samples; four in the "as received" condition, and four after hydrolytic aging (4.5.1.1.4.1).

4.5.1.1.4.1 Hydrolytic aging. The Breaking Strength test shall be applied in conjunction with ASTM Test Method D3137 on four samples of 4.5.1.1.4 to determine hydrolytic stability of the closure material.

4.5.1.1.5 Elongation. The elongation test shall be conducted in accordance with Procedure A of ASTM Test Method D882 on eight different specimens of closure webbing, four in the "as received" condition and four after hydrolytic aging (4.5.1.1.4.1).

4.5.1.1.6 Flexibility. A twelve-inch (.3 m) section of the 4.5.1 closure sample shall be manually manipulated, after conditioning for 24 hours at minus 20°F (-29°C). This test shall be conducted in conjunction with the operating test of 4.5.1.1.8.

4.5.1.1.7 Resistance to blocking. The blocking resistance of the closure material shall be determined in accordance with Federal Test Method Standard 101, Method 3003, Procedure A. The test sample shall be a square section of the closure webbing as large as the size of the webbing shall permit, not to exceed 1.5 inches (3.8 cm).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

4.5.1.1.8 Operation. The six-foot (1.8 m) sample of 4.5.1 shall be manually operated 20 times. An operation shall consist of one complete opening followed by one complete closing. The closure shall be flexed so as to develop at least four curves along its length with an approximate radius of 12 inches (.3 m) and an arc of 90 degrees. The test shall be run in conjunction with the Flexibility test (4.5.1.1.6), once after each conditioning period. The closure tool specified in 3.5 shall be used in this test. The performance of the closure tool shall be evaluated separately.

4.5.1.1.9 Resistance to parting. The ability of the closure to resist separation shall be determined in accordance with Federal Test Method Standard 406, Method 1013, with force applied at an angle of 180° to the two mating surfaces. The specimen shall be conditioned beforehand for 24 hours at 140°F (60°C).

4.5.1.1.10 Resistance to fluids. The resistance to fluids shall be determined in accordance with ASTM Test Method D471. The specimen size shall be 1 x 2 inches (2.5 x 5.1 cm) taken from the closure webbing. The exposure to MIL-L-23699 shall be for 72 hours at 160°F (71°C).

4.5.1.1.11 Corrosiveness. Corrosiveness of the closure material shall be determined in accordance with Federal Test Method Standard No. 101, Method 3005. The sample shall be cut from the webbing of the closure segment to approximately the specified dimensions as closely as possible. The test surface shall be aluminum.

4.5.1.1.12 Volatility. The volatility of the closure material shall be determined in accordance with ASTM Test Method D1203, Method A.

4.5.1.1.13 Resistance to abrasion. The resistance to abrasion of the closure material shall be determined in accordance with Federal Test Method Standard No. 406, Method 1091. The wheels shall be H-18. The wheel load shall be 500 grams and the number of revolutions shall be 2000.

4.5.1.1.14 Flame resistance. The flame resistance of the closure material shall be determined in accordance with Federal Test Method Standard 406, Method 2022.

4.5.1.1.15 Resistance to light. Resistance to light shall be determined in accordance with ASTM Test Method G23. Three test specimens shall be used.

4.5.1.1.16 Pressure retention test. The container shall be inflated to a pressure of 1" (2.5 cm) of water less than the pressure required to separate the closure device. (The pressure required to separate the closure device shall be determined by trial). After inflation, the container shall stand a minimum of 30 minutes to allow the internal pressure and temperature to stabilize. The pressure should then be recorded and the test begun and timed for the prescribed length of time. Any blister or bubbles or loss of more than 5% pressure over a period of 30 minutes shall be a cause for rejection. Evidence of leakage shall be detected by means of a connected pressure indicator graduated in inches of water. Compensation for known changes in temperature as recorded shall be allowed in the test procedure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

4.5.2 Fit and Function. A fit and function test shall be carried out on the live equipment in accordance with specific instructions in the contract (see 6.2).

4.5.3 Patching kit test. Using the patching instructions and the material in the patching kit, two 12-inch (.3 m) tears shall be patched and tested in accordance with MIL-P-58102. The tears shall be made in sample material taken from the same production, made in the same process and of the same color, as the covers offered for acceptance.

4.5.4 Stowage demonstration. Using installation instructions, the environmental protective cover shall be secured in the stowage bag.

4.5.5 Stowage bag fork-lift test. Stowage bags having straps (3.8.1) shall be lifted clear of the ground by fork-lift, using the loops affixed to the bag, and observed for ease of fork-lift access and for individual strap stress.

4.6 Quality conformance inspection. Each cover offered for acceptance shall be inspected in accordance with 4.4 for the defects in Table II. The closure operating test shall consist of one complete opening and one complete closing performed once over the full length of the closure. The operating test shall be performed with the closure tool specified in 3.5.

TABLE II

DEFECTS	MAJOR	MINOR
Type: Not as specified.	X	
Material: Not as specified.	X	
Color: Not as specified.		X
Workmanship: Not uniformly made; dirt, oil, foreign matter present, rough or sharp edges, tears, cuts, holes or cracks	X	
Construction: Not in conformance with approved First Article as to sleeves, drains, closure and dimensions.	X	
Joints: Not uniform; wrinkles, bubbles, areas of non-adhesive or other imperfections.	X	
Patching kit: Omitted; not as specified; adhesive omitted; instructions omitted.		X
Stowage bag, when applicable: Omitted; not constructed as specified; workmanship not as specified.		X
Closure: Not operable as specified.	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

TABLE II

DEFECTS	MAJOR	MINOR
Pouches: Not provided for stowage bag (as applicable), patching kit, closure tool or installation instructions; not constructed in accordance with First Article.	X	
Closure tool, when applicable: Omitted; not constructed in accordance with approved First Article.		X
Installation Instructions: Omitted; do not include folding for packaging; incomplete.		X
Functional markings: Not as specified; not clear and legible; incorrectly located.		X
Identification markings: Not as specified; omitted from cover and/or stowage bag, when applicable; incorrectly located.		X
Packaging: Not as specified; containers not in accordance with applicable specification.	X	
Marking for shipment: Not as specified.		X
Match-marking: Not as determined in First Article; omitted; incorrectly located.	X	

5. PACKAGING

5.1 Packaging. Each cover shall be packaged level A, B, or Commercial, as specified (see 6.2).

5.1.1 Level A. Each cover or cover/stowage bag assembly shall be placed in a snug-fitting, wood-cleated, plywood box conforming to PPP-B-601, Grade A type overseas.

5.1.2 Level B. Each cover or cover/stowage bag assembly not exceeding 100 pounds shall be placed in a snug-fitting fiberboard box conforming to V3C of PPP-B-636. Each cover or cover/stowage bag assembly exceeding 100 pounds shall be placed in a fiberboard box conforming to PPP-B-640, Class 2.

5.1.3 Commercial. Each cover or cover/stowage bag assembly shall be packaged in accordance with MIL-STD-1188 in a snug-fitting shipping container.

5.2 Packing. Not required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

5.3 Marking. In addition to any special requirements of the contract or order, marking shall be in accordance with MIL-STD-129 or MIL-STD-1188, as applicable (see 6.2).

6. NOTES

6.1 Intended use. Covers made in accordance with this specification are tailored to the configuration of specified equipment. Bidders are generally given access to the equipment for the purpose of taking patterns. The concept is an individual environmental enclosure which dependably and wholly protects major items such as aircraft, tanks and locomotives, in an easily installed/removed envelope which allows the equipment to be readied for service without involved depreservation. Type III covers are suitable where only a weather shelter is required. Type II covers are appropriate in connection with dynamic dehumidification. Type I covers are intended as an alternate rendering of MIL-P-116 Method II preservation for components and sub-assemblies, and are also appropriate as shelters utilizing dehumidification machines. End item covers should be furnished with their own individual stowage bags for use when the covers are set aside at the unit.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number and date of this specification.

b. Type of cover required (see 1.2).

c. When First Article test sample is required (see 3.1).

d. Class, grade and color of material (see 3.2).

e. Equipment for which cover is to be designed (see 3.3).

f. Arrangements for contractor access to equipment (see 3.3.1) or GFP, and First Article fit and function (see 4.5.2).

g. Specify one-piece or two-piece (see 3.4.1).

h. Number and location of hoisting points, if required (see 3.4.4.1).

i. Number and location of dehumidification sleeves (see 3.4.4.2).

j. Number and location of tiedown sleeves (see 3.4.4.3).

k. Whether an antenna sleeve is required (see 3.4.4.4).

l. Whether an access to the fuel filter is required (see 3.4.5).

m. Whether an access door is required (see 3.4.7).

n. Record receptacle as specified (see 3.4.8).

o. Whether a desiccant pouch is required (see 3.4.9).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

p. Units of desiccant, if required (see 3.4.9).

q. Number of humidity indicators, if required (see 3.4.9.1).

r. Closure time required (see 3.4.10).

s. Draw straps required (see 3.4.10.2).

t. Number of pressure relief valves, flow rates and no-leak pressures, if required (see 3.4.13).

u. If a closure tool is required (see 3.5).

v. If a stowage bag is required (see 3.8).

w. Whether girth straps are required on stowage bags (see 3.8.1).

x. Customer identification required (see 3.10.1).

y. Level of packaging (see 5.1).

z. Marking required (see 5.3).

6.3 DISPOSIBILITY

One or more of the following methods shown in order of their preference shall be used to accomplish disposal of the MIL-C-58104, cover protective; reuse, daily recycling, incineration, pyrolysis, composting, sanitary landfill, or sea disposal.

Custodian:

Army - AV
Air Force - 69

Preparing activity:

Army - AV

Review activities:

Army - SM
-AT
Air Force - 99

Project No. 8145-0019

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

NSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in ubmitting comments and suggestions for improvements. All users of military standardization documents are invited to provide uggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and nailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was oo rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the roblems Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an cknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being onsidered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of pecification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization o waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

)EPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

)FFICIAL BUSINESS
'ENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
'FIRST CLASS PERMIT NO 12062 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

US Army Aviation Research and
Development Command
ATTN: DRDAV-ERS
4300 Goodfellow Boulevard
St. Louis, MO 63120

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*. _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation.

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:01Z
Check the source to verify that this is the current version before use.