INCH-POUND

MIL-W-70948 (AR)
04 December 1991

MILITARY SPECIFICATION

WARHEAD SECTION, GM, PRACTICE XM276 LOADING, ASSEMBLING AND PACKING

This Specification is approved for use by the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the loading, assembling and packing for one type of warhead section designated as Warhead Section GM Practice XM276 with live FLSC and dummy inert bombs: P/Ns 12598664, 69C7448, or SK 476. (see 6.1)

2. APPLICABLE DOCUMENTS

2.1 Government documents

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation. (see 6.2)

SPECIFICATIONS

MILITARY

MIL-A-48078 - Ammunition, Standard Quality Provisions, General Specifications for

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U.S. Army ARDEC, ATTN: SMCAR-BAC-S, Picatinny Arsenal, New Jersey 07806-5000 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 1336

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. Army Armament, Research, Development And Engineering Center (ARDEC)

Product and Packaging Drawings

9266382 - Roll Moment Fixture
9266426 - Pitch and Yaw Moment of Inertia Fixture
12913864 - Warhead Section, GM, Practice XM276 with Live FLSC and Inert Loaded Bombs, Dummy
12913897 - Pkg and Mkg for Warhead Section, GM, Practice (XM276) with Live FLSC and Inert Loaded Bombs, Dummy

(Copies of drawings required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

PUBLICATIONS

CODE OF FEDERAL REGULATIONS

Title 49 - Transportation, Parts 0-190

(The Code of Federal Regulations is available from the superintendent of Document, U.S. Government Printing Office, Washington, D.C., 20402. Orders should specify, "49 CFR 0-190 (latest revision)".)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

2.2 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. The issues of the documents which are DoD adopted are those listed in the issues of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation. (see 6.2)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D1621-73 - Test for Compressive Strength of Rigid Cellular Plastics
ASTM D1622-63 - Test for Apparent Density of Rigid Cellular Plastics

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1137.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Material. Materials shall be in accordance with the applicable drawings and specifications.

3.2 Components and assemblies. The components and assemblies shall comply with all requirements specified on Drawing 12913864, all associated drawings, and with all requirements specified in applicable specifications.

3.3 Stability of bag and filler assembly. The foaming filler in the bag assembly shall expand and achieve a uniformly firm set within the specified time after removal from cold temperature storage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

3.4 Workmanship. All parts and assemblies shall be fabricated, loaded and assembled in a thorough, workmanlike manner. They shall be free of burrs, sharp edges, cracks, dirt, grease, rust, and other foreign matter. The cleaning method used shall not be injurious to any part nor shall the parts be contaminated by the cleaning agents. Exterior surface coatings shall be continuous; however, a few light scratches not exposing base material may be permitted. All required marking and stamping shall be neat and sharply defined.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of section 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system of quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Quality conformance inspection (see 4.4)

4.3 Quality conformance inspection.

4.3.1 Inspection lot formation. Inspection lots shall comply with lot formation provisions of MIL-A-48078 and the following criteria:

a. Metal parts assemblies of one lot interfix number from one manufacturer.

b. Warhead fuzes of one lot interfix number from one manufacturer.

4.3.2 Examination and test. Except as noted, the examinations and tests listed in the following subparagraphs shall be performed 100% on inspection lots (see 4.3.1) of the components or assemblies designated in the applicable paragraph headings.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE		SHEET		DRAWING NUMBER
4.3.2.1	Bag and Filler Assy		1 OF 1		8880943
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Filler missing		100%	3.2	Visual/
102	Stability of bag and filler assy		1/	3.3	Visual/4.4.1
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES: 1/ See Paragraph 4.3.3.1.

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9287511
4.3.2.2	Bag, Polyethylene				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Cut or tear		100%	3.2	Visual
102	Length		100%	3.2	Gage
103	Width		100%	3.2	Gage
104	Holes missing		100%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9287515
4.3.2.3	Bag and Bag Filler Assy				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Flap facing wrong direction		100%	3.2	Visual
102	Open end of bag and filler assy facing toward open end of polyethylene bag		100%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9287485
4.3.2.4	Block, Wood				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length		100%	3.2	Gage
102	Width		100%	3.2	Gage
103	Height		100%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.5	Warhead Section, During Loading, GM Practice XM276 With Live FLSC and Loaded Dummy Bombs	1 OF 1	12913864
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Containment block pad missing or improperly installed		100%	3.2	Visual
102	Wood block missing		100%	3.2	Visual
103	Distance to bombs and wood blocks		100%	3.2	Visual
104	Polyethylene sheet improperly installed, torn or missing		100%	3.2	Visual
105	Incorrect number of bag and bag filler assemblies		100%	3.2	Visual
106	Bag and bag filler assy flap facing forward		100%	3.2	Visual
107	Wedge missing or improperly assembled		100%	3.2	Visual
108	Skin missing or improperly assembled		100%	3.2	Visual
109	Spacer missing or improperly assembled		100%	3.2	Visual
110	Insulation tape missing, damaged or improperly installed on aft ring assembly		100%	3.2	Visual
111	O-ring missing, damaged, or improperly installed on aft ring assembly		100%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.6	Warhead Section GM, Practice XM276 With Live FLSC and Loaded Dummy Bombs After Assembly of Aft Ring Assembly	1 OF 1	12913864
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Distance from aft skin to aft ring assy, max		100%	3.2	Gage
102	Screw holding aft ring assy loose or missing		100%	3.2	Gage
103	Center tube bolt o-ring improperly assembled or missing		100%	3.2	Visual
104	Center tube moves when subjected to minimum torque		100%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

REMARKS:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.7	Warhead Section GM, Practice XM276 With Live FLSC and Loaded Dummy Bombs, During & After Assy of Fuze, Port Covers & Boosters	1 OF 1	12913864
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL					
1	Fuze Armed		100%	3.2	Visual
MAJOR					
101	Fuze gasket missing or improperly assembled		100%	3.2	Visual
102	Lock washer missing from fuze cap screw		100%	3.2	Visual
103	Fuze cap screw moves when subjected to minimum torque		100%	3.2	Visual
104	Lead seal missing or improperly assembled to fuze cap screw		100%	3.2	Visual
105	Insulation missing from port cover		100%	3.2	Visual
106	Setback plug missing or improperly assembled (2 places)		100%	3.2	Visual
107	Setscrew missing or improperly assembled (2 places)		100%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.8	Warhead Section During Loading, GM Live FLSC and Loaded Dummy Bombs	1 OF 2	12913864
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Adhesive missing from slit in skin, around port cover		100%	3.2	Visual
102	Nose assy. loose or improperly assembled		100%	3.2	Visual/Manual
103	Gap between nose assy and forward skin, max		100%	3.2	Gage
104	Tee bolt binds or too loose in cavitie		100%	3.2	Manual
105	Aft section seal missing, damaged or improperly assmebled		100%	3.2	Visual
106	Weight		100%	3.2	Test
107	Longitudinal center of gravity		100%	3.2	Test 4.4.3
108	Runout		100%	3.2	Gage
109	Pitch and yaw moment of inertia		100%	3.2	Test 4.3.3, 4.4.4
110	Roll moment of inertia		100%	3.2	Test 4.3.3, 4.4.5
111	Interface of aft ring assy improper		100%	3.2	Gage
112	Connector pins in cable assy damaged		100%	3.2	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.8	Warhead Section During Loading, GM XM276 With Live FLSC & Loaded Dummy Bombs	2 OF 2	12913864
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
MAJOR					
113	Protector cap missing or improperly assembled to electrical recepticle connector		100%	3.2	Visual/Manual
114	Any component removed during inspection and testing improperly reassembled or damaged		100%	3.2	Visual
115	Forward facing step at nose cone assy, max.		100%	3.2	Gage
116	Aft facing step at nose cone assy, max.		100%	3.2	Gage
117	Marking missing, incomplete or illegible		100%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.9	Pkg and Mkg for Warhead Section GM, Practice XM276 With Live FLSC & Loaded Dummy Bombs, Prior to Assy of Cover Assy	1 OF 1	12913897
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Swing bolt not in place in aft support assembly		100%	3.2	Visual
102	Swing bolt nut moves when minimum torque is applied		100%	3.2	Gage
103	Safety pin missing or improperly assembled to strap assembly		100%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.10	Pkg and Mkg for Warhead Section GM, Practice XM276 With Live FLSC & Loaded Dummy Bombs	1 OF 1	12913897
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Cover assembly improperly assembled		100%	3.2	Visual
102	T-bolt missing or improperly assembled		100%	3.2	Visual
103	T-bolt moves when minimum torque is applied		100%	3.2	Gage
104	Lead seal missing or improperly assembled		100%	3.2	Visual
105	Marking missing, incomplete or illegible		100%	3.2	Visual
106	Stacking bolt missing or damaged		100%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-70948 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9283963
4.3.2.11	Spacer, Foam				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Thickness		100%	3.2	Gage
102	Depth of cut (2 places)		100%	3.2	Gage
MINOR					
201	Outside diameter		100%	3.4	Gage
202	Inside diameter		100%	3.4	Gage
203	Width of small cutout		100%	3.4	Gage
204	Depth of small cutout		100%	3.4	Gage
205	Width of large cutout		100%	3.4	Gage
206	Depth of large cutout		100%	3.4	Gage
207	Evidence of poor workmanship		100%	3.4	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9331772
4.3.2.12	Filler, Aft				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length		100%	3.2	Gage
102	Largest outside diameter		100%	3.2	Gage
103	Second largest outside diameter		100%	3.2	Gage
104	Inside diameter		100%	3.2	Gage
105	Density		1/	3.2	Test/4.4.2
106	Compressive strength		1/	3.2	Test/4.4.2
107	Surface finish 2/		100%	3.2	Visual
108	Forward load angle improper		100%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES:
1/ See paragraph 4.3.3.2.
2/ The surface finish shall be smooth and hard (as molded) with no evidence of loose, crumbling particles.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

MIL-W-70948 (AR)

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.3.2.13	Filler, Nose	1 OF 1	9331774
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length		100%	3.2	Gage
102	Largest outside diameter		100%	3.2	Gage
103	Second largest outside diameter		100%	3.2	Gage
104	Inside diameter		100%	3.2	Gage
105	Width of small cutout (2 places)		100%	3.2	Gage
106	Width of large cutout (2 places)		100%	3.2	Gage
107	Depth of small cutout (2 places)		100%	3.2	Gage
108	Depth of large cutout (2 places)		100%	3.2	Gage
109	Chamfer		100%	3.2	Visual
110	Density		1/	3.2	Test/4.4.2
111	Compressive strength		1/	3.2	Test/4.4.2
MINOR					
201	Evidence of poor workmanship		100%	3.4	Visual

NOTES: 1/ See paragraph 4.3.3.2.

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

4.3.3 Testing.

4.3.3.1 Stability of bag and filler assembly (see 3.3). One (1) bag and filler assembly shall be selected from each group of twenty-five (25) or less bag and filler assemblies produced. The filler batch for each group shall be homogeneous and mixed at one time. Groups over twenty-five (25) shall be inspected by selecting one sample from each group of twenty-five (25) or portion thereof produced. If a bag and filler assembly fails to meet the applicable requirements, the filler batch represented by that assembly shall be rejected. The test shall be performed as specified in 4.4.1 using equipment in accordance with 4.3.4.

4.3.3.2 Density and compressive strength of polyurethane fillers (see Dwgs. 9331772 and 9331774). One (1) part from each lot of nose and aft fillers shall be selected for test. The density tests (non-destructive) shall be conducted on the compressive strength specimens and shall be taken from the part after removal of the filler part skin. The three 2-inch cube specimens shall be cut at 120 intervals around the part; one at the top, and one midway up the part. These tests shall be performed using equipment in accordance with 4.3.4. Any lot which fails to comply with the specified requirements shall be rejected.

4.3.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the 'Paragraph Reference/Inspection Method' column in the tables starting with paragraph 4.4.2.1 . The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See Section 6 of MIL-A-48078 and 6.3 herein.

4.4 Methods of inspection.

4.4.1 Stability of bag and filler assembly. The bag and filler assembly shall be removed from cold temperature storage and allowed to set at room temperature. After the specified time, observation shall be made for conformance with the applicable requirement. This is a destructive test. Assemblies subjected to this test shall not be returned to the lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

4.4.2 Density and compressive strength of polyurethane fillers. The density shall be conducted in accordance with ASTM D-1622 and the compressive strength tests in accordance with ASTM D-1621. Parts from which specimens are taken shall not be returned to the lot.

4.4.3 Longitudinal center of gravity. The loaded warhead shall be subjected to the longitudinal center of gravity test using approved test equipment. This is a non-destructive test. Assemblies subjected to this test shall be returned to the lot.

4.4.4 Pitch and yaw moment of inertia. The loaded warhead shall be subjected to the pitch and yaw moment of inertia test using approved test equipment. This is a non-destructive test. Assemblies subjected to this test shall be returned to the lot. (See 9266426).

4.4.5 Roll moment of inertia. The loaded warhead shall be subjected to the roll moment of inertia test using approved test equipment. This is a non-destructive test. Assemblies subjected to this test shall be returned to the lot. (See 9266382).

5. PACKAGING

5.1 Preservation and packaging.

5.1.1 Level A. The warhead section shall be preserved and packaged in accordance with Dwg. 12913897.

5.2 Packing.

5.2.1 Level A. The warhead section shall be preserved and packaged as specified in 5.1.1, shall be packed in accordance with Dwg. 12913897.

5.3 Marking. Marking shall be in accordance with Dwg. 12913897 and Code of Federal Regulations, Title 49 Parts 171-179.

5.4 Shipping. When warhead sections from more than one lot are shipped a carload, each lot shall be kept separate, and the division between lots clearly indicate to prevent mixing of the lots in transit.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a generic or explanatory nature that may be helpful, but is not manditory.)

6.1 Intended use. The XM276 LANCE practice warhead is intended to train troops on the use of the LANCE missile system.

6.2 Acquisition requirements. Procurement documents shall specify the following:

a. Title, number, and date of the specification.

b. Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced. (see 2.1)

6.3 Submission of contractor inspection equipment designs for approval. Submit two copies of designs as required to: Commander, U.S. Army AMCCOM, ATTN: SMCAR-QAR-R, Picatinny Arsenal, NJ 07806-5000. This address will be specified on the Contract Data Requirements List, DD Form 1423 in the contract.

6.4 Subject term (key word) listing.

Cellular plastics
FLSC
Dummy bombs
Roll moment of inertia
Pitch moment of inertia
Yaw moment of inertia

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1336-A623)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-W-70948 (AR)	4 DECEMBER 1991

3. DOCUMENT TITLE
WARHEAD SECTION, GM, PRACTICE XM276 LOADING, ASSEMBLING AND PACKING

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets if needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
US ARMY ARDEC STANDARDIZATION OFFICE	(1) Commercial (201) 724-6671	(2) AUTOVON 880-6671
c. ADDRESS (Include Zip Code) ATTN: SMCAR-BAC-S PICATINNY ARSENAL,NJ 07806-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:15Z
Check the source to verify that this is the current version before use.