METRIC

A-A-59794
15 November 2006

COMMERCIAL ITEM DESCRIPTION

GLOVES, FIRE FIGHTER'S, STRUCTURAL

The General Services Administration has authorized the use of this commercial item description, for all federal agencies.

1. SCOPE. This Commercial Item Description covers the requirements for a structural fire fighter's glove to be used by Navy Damage Control fire fighters.

2. SALIENT CHARACTERISTICS.

2.1 Description. The fire fighter's glove is a leather five-finger, knit wristlet style glove comprised of an outer shell, moisture barrier (liquid/fluid), and thermal liner. The system shall be permitted to be configured as a single layer or multiple layers that are permanently attached. The glove and all layers shall be available in a minimum of five sizes, (small, medium, large, xlarge, xxlarge). The glove and all layers of the glove shall be incrementally graded to comply with hand sizing dimensions as defined by National Fire Protection Association (NFPA) 1971. The glove shall have an additional insulative pad between the outer shell and moisture barrier on the back of the hand. The insulative pad covers the entire back of the glove up to the crotch of the fingers.

2.2 Materials. The contractor shall certify that the fire fighter's glove shall be constructed, tested and labeled in accordance with NFPA 1971. In addition the glove shall meet the following:

2.3 Design. Design requirements shall be in accordance with the protective glove design requirements of NFPA 1971 with the following exceptions:

a. Sample glove body shall extend circumferentially not less than 5.08 cm (2 inches) beyond the wrist crease where measured from the tip of the finger and shall be close fitting at the opening to restrict the entry of embers and other foreign particles.

b. Sample glove body and wristlet shall extend circumferentially not less than 13.97 cm (5.5 inches) beyond the wrist crease.

2.3.1 Insulative pad. The insulative pad shall be fire retardant silicone foam with an integral skin on the top and bottom surfaces. The insulative pad shall extend on the back of the glove from the end of the glove body to approximately ¼ inch below the crotch of the fingers. The insulative pad shall be secured in back of the glove in such a manner that stitched seams do not chaff or cut through the pad itself.

2.3.2 Moisture barrier. The moisture barrier shall be made out of an expanded polytetrafluoroethylene (PTFE) film either manufactured as a reinforced separate insert or be combined with one of the other layers. In either situation, the moisture barrier by itself shall be individually graded and produced in as many sizes as required glove sizes (example: small, medium, large, xlarge, xxlarge) and incrementally graded to comply with hand sizing dimensions as defined by the NFPA 1971.

2.3.3 Thermal liner. The thermal liner shall be either manufactured as a separate component or be combined with one of the other layers. In either situation the thermal liner by itself shall be individually graded and produced in as many sizes as required glove sizes (example: small, medium, large, xlarge, xxlarge) and incrementally graded to comply with hand sizing dimensions as defined by NFPA 1971.

2.3.4 Color. The body of the glove shall be dark blue with a tan thumb.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Commander, Naval Sea Systems Command, ATTN: SEA 05Q, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at www.assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:27Z
Check the source to verify that this is the current version before use.

2.4 Overall liquid integrity test. In addition to the standard Overall Liquid Integrity Test of NFPA 1971, the following modified test shall be run. The Navy required changes shall be that the convective heat conditioning procedure will be as follows:

a. The oven preheat shall be stabilized at 260 °C +6/-0 °C (500 °F, +10/-0 °F).

b. The specimen exposure time shall begin when the test thermocouple reading reaches 260 °C +6/-0 °C (500 °F, +10/-0 °F) and shall remain at that temperature for the duration of the test.

c. The specimens shall be at 260 °C +6/-0 °C (500 °F, +10/-0 °F) for a 5-minute +15/-0 seconds and then removed and subjected to required testing.

2.5 Insulative pad performance requirements. The silicone foam of the insulative pad shall meet the following performance requirements:

PROPERTY	TEST METHOD	REQUIREMENT
Tensile Strength, psi, min	ASTM D412	30
Tensile Elongation, %, min	ASTM D412	40
Compression Deflection, psi	ASTM D1056 at 25% Compression	6-14
Compression Set, %	ASTM D1056 at 50% Compression, 22 hrs at 120 °C	<5
Thermal Conductivity BTU-in/HR ft^2 °F	ASTM C518 at 80 °C	0.46
Flammability	UL 94	HF-1

2.6 Labels. A commercial label is acceptable. If procured under contract, additional permanent printed or stamped label containing the contract number and the national stock number is included.

2.7 Workmanship. Gloves shall be free from irregularities or defects which adversely affect performance, reliability, or durability.

3. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. PRODUCT CONFORMANCE PROVISIONS.

4.1 Product conformance. The products provided shall meet the salient characteristics of this Commercial Item Description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

4.2 Defects. The gloves shall be examined for the following defects: Any hole, or visible repair; material or components not in accordance with the product demonstration model; tears, pulled, loose or snagged stitches, stained, not properly sized, wrong color, missing, incorrect or illegible labels, any variance not otherwise classified herein but at variance with the product demonstration model.

5. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or order.

6. NOTES.

6.1 Source of documents.

6.1.1 ASTM International. ASTM International standards are available from ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959 or online at www.astm.org.

6.1.2 FAR. The Federal Acquisition Regulation may be obtained from the Regulatory Secretariat, 1800 F Street NW, Washington, DC 20405 or online at www.acqnet.gov.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:27Z
Check the source to verify that this is the current version before use.

6.1.3 NFPA. NFPA test methods are available from the National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471 or online at www.nfpa.org.

6.1.4 UL. UL test methods are available from COMM 2000, 1414 Brook Drive, Downers Grove, IL 60515 or online at www.ul.com.

6.2 Ordering data. The contract or order should specify the following:

a. CID document number and revision.

b. Product conformance provisions.

c. Quantity required.

6.3 Key words.

Fire fighting

Glove

MILITARY INTERESTS

Custodians:
Navy - SH
AF - 03

Review Activities:
Navy - AS, YD
AF - 84, 99
DLA - IS

CIVIL AGENCY COORDINATING ACTIVITY:
GSA - FSS

Preparing Activity:
Navy - SH
(Project 4210-0661-000)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:27Z
Check the source to verify that this is the current version before use.