MILITARY SPECIFICATION

CLOTH, OXFORD: AND CLOTH, POPLIN: COTTON, (FOR PAJAMAS)

1. SCOPE

1.1 Scope.- This specification covers the requirements for two oxford cloths and one poplin cloth to be utilized in the fabrication of pajamas (see 6.1).

1.2 Classification.- The cotton cloth shall be of the following types as specified (see 6.2):

Type I	- 5.0 ounce oxford
Type II	- 4.5-ounce oxford
Type III	- 5.5-ounce poplin

* 2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

V-T-276	-	Thread, Cotton
PPP-P-1134	-	Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD-4	-	Glossary of Fabric Imperfections
FED-STD-191	-	Textile Test Methods

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication.- The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act.

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D. C. 20580.)

3. REQUIREMENTS

3.1 Standard sample.- The cloth shall match the standard sample for shade and shall be equal to or better than the standard with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Material.-

3.2.1 Yarn.- The cotton shall be carded, combed, and spun into a single yarn for both warp and filling.

* 3.3 Color.- The cloth shall be dyed Light Blue, Shade No. 14. The use of dyes or substances containing elementary sulfur compounds capable of oxidation to sulfuric acid is prohibited. The dyestuffs shall be chosen and applied so that the dyed and finished cloth shall contain no more labile sulfur than that shown by the standard sample when tested as specified in 4.4. When a standard sample is not available, the dyed and finished cloth shall show not more than a slight trace of labile sulfur as defined in the test method when tested as specified in 4.4.

3.3.1 Matching.- The color shall match the standard sample under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin, and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

* 3.3.2 Colorfastness.- The dyed and finished cloth shall show fastness to combined laundering and bleaching, perspiration, and crocking equal to or better than the standard sample. When no standard sample is established, or is not referenced for colorfastness, the finished cloth shall show "good" fastness to combined laundering and bleaching, perspiration, and no more crocking than Munsell value 7 when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.

3.4 Physical requirements.- The finished cloth shall conform to the requirements shown in table I when tested as specified in 4.4.

TABLE I.- Physical requirements

Type	Weight per square yard (minimum)	Yarns per inch (minimum)		Breaking strength (minimum)		Weave
		Warp	Filling	Warp Pounds	Filling Pounds	
I	5.0	128	42	95	65	Oxford 1/
II	4.5	128	60	95	45	Oxford 1/
III	5.5	114	52	140	45	Poplin 2/

1/ Plain weave, with two ends weaving as one.

2/ Plain weave, one and one.

3.4.1 Width.- The width shall be as specified (see 6.2) and shall be the minimum width inclusive of selvages.

3.5 Finish.- The cloth shall be closely singed, scoured, mercerized, dyed and shall have a clear lustrous finish.

3.5.1 Nonfibrous material.- The cloth prior to dyeing, shall contain not more than 2.0 percent starch and protein content, including chloroform-soluble and water soluble material when tested as specified in 4.4.

* 3.6 pH.- The pH value of the water extract of the finished cloth shall be not less than 5.5 nor more than 8.5 when tested as specified in 4.4.

3.7 Shrinkage.- The cloth shall be preshrunk, and shall shrink not more than 2.0 percent in either the direction of the warp or the filling when tested as specified in 4.4. The preshrinking process used shall not be identified by name or trademark, either on the cloth, on the ticket, or package.

3.8 Seam efficiency.- The finished cloth shall have a seam efficiency of not less than 80 percent when tested as specified in 4.4.

* 3.9 Face identification.- The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word "Face" at each end of the piece.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.

3.10 Length and put-up.- Unless otherwise specified (see 6.2), the cloth shall be in continuous pieces of not less than 40 yards. The cloth shall be put up in folded pieces as specified in PPP-P-1134.

3.11 Fiber identification.- Each piece shall be labeled, ticketed or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.

* 3.12 Workmanship.- The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the applicable established maximum point values.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance.- Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

* 4.2 Inspection.- Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection.- In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable procurement documents.

* 4.2.2 Examination of the end item.- Examination of the end item shall be in accordance with 4.2.2.1 through 4.2.5.

* 4.2.2.1 Yard-by-yard examination.- Each piece in the sample shall be examined on the face side only. When the total yardage in the piece does not exceed 100 yards, the entire yardage in the piece shall be examined. When the total yardage in the piece exceeds 100 yards, only 100 yards shall be examined. All defects, as defined in section 1 of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.

points as listed in 4.2.2.1.1 except that only those slubs and knots which exceed the limits shown on figure 3 of FED-STD-4 shall be scored. No linear yard shall be penalized more than 4 points. The sample size shall be 20 pieces selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 30 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual pieces exceeds 45 points. If one piece exceeds 45 points per 100 square yards, a second sample of 20 pieces shall be examined only for individual piece quality examination. The lot shall be unacceptable if one or more pieces in the second sample exceeds 45 points per 100 square yards. Point computation for lot quality and individual piece quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 square yards}$$

4.2.2.1.1 Demerit points.- Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

Note: The following defects, when present, shall be scored four points for each yard in which they occur:

Width less than specified
Poor dye penetration, mottled, streaky or cloudy
Excessive neppiness
Not singed

4.2.3 Examination for length.-

4.2.3.1 Individual pieces.- During the yard-by-yard examination, each piece in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more pieces in the sample are defective in respect to length.

4.2.3.2 Total yardage in sample.- The lot shall be unacceptable if the total of the actual lengths of pieces in the sample is less than the total of the lengths marked on the tickets.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.

4.2.4 Examination for shade.- During the yard-by-yard examination, each piece in the sample shall be examined for shade. Any piece in the sample off shade, shaded side to side, side to center or end to end shall be cause for rejection of the entire lot represented by the sample.

* 4.2.5 Examination for identification of preshrinkage process, face markings, and compliance with the Rules and Regulations Under the Textile Fiber Products Identification Act.- During the yard-by-yard examination each piece in the sample shall be examined for defects listed below. The lot shall be unacceptable if two or more of the following defects are present in the sample:

Preshrinkage process identified by name or trademark on cloth or ticket.
Face stamping missing from either or both ends.
Face stamping on wrong side.
Not labeled, ticketed or invoiced in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

4.3 Examination of preparation for delivery requirements.- An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that the packaging, packing and marking comply with section 5 requirements.

* 4.4 Testing of the end item.- The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table III shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be 5 continuous yards, full width, of the finished cloth and one-fourth yard, full width, of the cloth prior to dyeing. The sample size shall be in accordance with table II. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more units fail to meet any requirements specified. All test reports shall contain the individual values utilized in expressing the final results.

TABLE II

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

* TABLE III.- Test methods

Characteristics	Requirement paragraph	Test method
Weave	3.4	Visual 1/
Weight	3.4	5041

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.

TABLE III.- Test methods (cont'd)

Characteristics	Requirement paragraph	Test method
Yarns per inch	3.4	5050
Breaking strength	3.4	5100
Labile sulfur	3.3	2020
Colorfastness to:		
Combined laundering and bleaching	3.3.2	5605
Perspiration	3.3.2	5680
Crocking	3.3.2	5651
Mercerization	3.5	Microscopic examination for swelling of cotton 2/
Nonfibrous material	3.5.1	2611
pH	3.6	2811
Shrinkage in laundering	3.7	5550
Seam efficiency	3.8	5110 3/

1/ One determination per sample unit reported as "pass" or "fail".

2/ A certificate of compliance shall be submitted and will be acceptable for the stated requirement.

3/ The thread shall conform to type IA1 of V-T-276. The needle size shall be 0.040 ± 0.001 inch, and needle thread shall be ticket No. 40, 3 ply, and the looper thread shall be ticket No. 60, 3 ply.

5. PREPARATION FOR DELIVERY

5.1 Put-up and packaging.- Put-up and packaging shall be level A, or C as specified (see 6.2).

5.1.1 Levels A, and C.- The cloth shall be put-up and packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing.- Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Levels A, B and C.- The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking.- In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of PPP-P-1134.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use.- The cloth covered by this specification is to be utilized in the fabrication of pajamas for hospital and orthopedic use.

6.2 Ordering data.- Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Type required (see 1.2).
(c) Width required (see 3.4.1).
(d) Length required if other than specified (see 3.10).
(e) Selection of applicable levels of put-up, packaging and packing required (see 5.1 and 5.2).

6.3 Standard sample.- For access to standard sample address the procuring office issuing the invitation for bids.

6.4 The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and suppliers are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL

Preparing activity:

Army - GL

Project No. 8305-0866

Review activity:

Army - MD

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:23Z
Check the source to verify that this is the current version before use.