MILITARY SPECIFICATION

FLASK SEPARATOR, 3000 PSI, K-MONEL

This amendment forms a part of Military Specification MIL-F-24032(SHIPS), 31 March 1964.

Page 2, paragraph 3.1.1: Delete and substitute:

"3.1.1 Flasks. - The material for the flasks shall be seamless K-Monel tubes having chemical composition in accordance with class A of QQ-N-286. Material from which flasks are to be made shall be in the hot finished, hot finished and annealed, or cold drawn and annealed condition. Finished flasks shall be in the annealed and age hardened condition and shall have mechanical properties specified in table I."

Page 2, table I, column 2, line 1: Delete "90,000" and substitute "85,000."

Page 2, paragraph 3.3.2: Delete and substitute:

"3.3.2 Age hardening. - Flasks shall be age hardened after annealing. Rough and finish machining may be performed before or after age hardening at the option of the manufacturer. Flasks shall be cleaned of all machining lubricants prior to age hardening."

Page 2, paragraph 3.5: Add: "The Monel (Ni-Cu) overlay (figure 2) shall be applied using electrodes conforming to type 8N10 of MIL-E-22200/3. Overlay shall be applied to the flask after annealing and prior to age hardening."

Page 4, paragraphs 4.4.3.2 and 4.4.3.2.1: Delete and substitute:

"4.4.3.2 Ultrasonic inspection. - After the hydrostatic test has been completed, each flask shall be 100 percent inspected over the cylindrical section either in a circumferential direction or longitudinal direction between the heads in accordance with one of the methods prescribed in MIL-STD-271. The equipment shall be calibrated to detect a notch equal to 3 percent of the wall thickness.

"4.4.3.2.1 Shear wave testing acceptance criteria. - Any flask having a discontinuity indication greater than that produced by the 3 percent calibration notch shall not be offered for delivery. Any flask having a discontinuity equivalent to 50 percent of that produced by the calibration notch, and over 3 inches in length, shall be rejected unless approved by the command or agency concerned. Other ultrasonic indications over 25 percent of that produced by the calibration notch, shall also be submitted to the command or agency concerned for information.

"4.4.3.2.2 Through wave testing acceptance criteria. - For the through wave testing method, a 100 percent loss of back reflection indicates a discontinuity size equal to or greater than the 3 percent calibration notch. Any flask showing such a discontinuity size shall not be offered for delivery. All flasks having discontinuities producing a loss in back reflection between 50 percent and 100 percent that are greater than 3

1/ CHANGES FROM PREVIOUS ISSUE. THE OUTSIDE MARGINS OF THIS DOCUMENT HAVE BEEN MARKED "#" TO INDICATE WHERE CHANGES (DELETIONS, ADDITIONS, ETC.) FROM THE PREVIOUS ISSUE HAVE BEEN MADE. THIS HAS BEEN DONE AS A CONVENIENCE ONLY AND THE GOVERNMENT ASSUMES NO LIABILITY WHATSOEVER FOR ANY INACCURACIES IN THESE NOTATIONS. BIDDERS AND CONTRACTORS ARE CAUTIONED TO EVALUATE THE REQUIREMENTS OF THIS DOCUMENT BASED ON THE ENTIRE CONTENT AS WRITTEN IRRESPECTIVE OF THE MARGINAL NOTATIONS AND RELATIONSHIP TO THE LAST PREVIOUS ISSUE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:46Z
Check the source to verify that this is the current version before use.

inches in length shall be reported to the command or agency concerned together with all other discontinuities producing a loss in back reflection greater than 25 percent.

"4.4.3.2.3 Ultrasonic inspection equipment shall be recalibrated periodically to insure optimum results. It shall also be recalibrated if there is any change in frequency or crystal size used.

"4.4.3.2.4 Reports. - A report shall be submitted in sketch form orientating all reportable discontinuities longitudinally or circumferentially as found, and indicating their severity and length. If the reported discontinuities are lineally disposed along the flask and the total length of all discontinuities in 12 inches of flask length is 6-inches, the flask shall not be offered for delivery."

Preparing activity:
Navy - SH
(Project 8120-N026Sh)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:46Z
Check the source to verify that this is the current version before use.