MILITARY SPECIFICATION

SILICONE FLUID, CHLORINATED PHENYL METHYL POLYSILOXANE,

NATO CODE NUMBER H-536

This amendment forms a part of Military Specification MIL-S-81087C, dated 27 April 1981, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 3

TABLE I, Viscosity @ 40°C (104°F): Change "50-60" to "48-58"

TABLE I, Flash point, min.: Change "290°C (554°F) to "288°C (550°F)"

Custodians
Army - ME
Navy - AS
AF - 20

Review Activities:
Army - AV,AT,ER,MI
AF - 68
DLA - PS

User Activities.
Army - AR
Navy - MC

Preparing Activity:
Navy - AS
(Project No. 9150-0732)

FSC 9150

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:58Z
Check the source to verify that this is the current version before use.