INCH-POUND
MIL-I-23053/8B
AMENDMENT-1
30 September 1989

MILITARY SPECIFICATION SHEET

INSULATION SLEEVING, ELECTRICAL, HEAT SHRINKABLE, POLYVINYLIDENE FLUORIDE, SEMI-RIGID, CROSSLINKED

This Amendment forms a part of MIL-I-23053/8, dated 1 May 1986, and is approved for use by all Departments and Agencies of the Department of Defense

Page 1

Under Requirements, add:

"Polymer type: The polymer shall be essentially a polymer of polyvinylidene fluoride with a crystalline melting point of at least 150°C (302°F)."

Page 2

In Table II:

a. Move "Low temperature flexibility" and its associated requirement, test procedure and conditions from the "As supplied" part of Table II to the "After unrestricted shrinkage" portion of the same table.

b. Under requirement for Secant modulus: Delete "100,000 (690)" and substitute "120,000 (828)".

c. After Concentricity, add the following:

"Crystalline Melting point °C (°F), min. 150 (302) 4/"

d. Add footnote at end of Table II: "4/ Test procedure in accordance with ASTM D 4591. Melting point calculated as specified in "Melting endotherm peak" in ASTM D 3222."

FSC 5970

AMSC N/A

DISTRIBUTION STATEMENT A, Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-19T15:20Z
Check the source to verify that this is the current version before use.

e. Delete the first two sentences of footnote 3/ and substitute:

"Specimens of size 0.187 inch (4.75mm) and smaller shall be tested as whole sections of sleeving without shrinking on conductors. Specimens of sizes larger than 0.187 inch (4.75mm) shall be a 0.250 inch (6.35mm) wide strip cut from the as supplied sleeving, then shrunk. All specimens shall be tested after unrestricted shrinkage."

Custodians:
Army - ER
Navy - AS
Air Force - 85

Review activities:
Navy - EC
Air Force - 99
DLA - IS

Preparing Activity:
Navy - AS
Project Number 5970-1052

Source: https://assist.dla.mil -- Downloaded: 202640-19T15:20Z
Check the source to verify that this is the current version before use.