MILITARY SPECIFICATION

BAG, DENTAL PROSTHESIS (Plastic)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers polyethylene plastic bags used for storage and shipment of dental prosthesis.

1.2 Classification.

1.2.1 Classes. The plastic bags covered by this specification shall be of the following classes:

Class 1 - Bag, Dental Prosthesis, Plastic, 100s
Class 2 - Bag, Dental Prosthesis, Plastic, 1000s

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specification and Standards (DoDISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

Federal

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 6520

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

L-P-378	Plastic Film (Polyethylene Thin Gage).
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-636	Boxes, Shipping Fiberboard.
PPP-B-676	Boxes, Setup.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.
MIL-STD-147	Palletized Unit Loads.
MIL-STD-794	Parts and Equipment, Procedures for Packaging of.

(Copies of specifications and standards required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Material. The plastic bags shall be made from a sheet form, type I, grade A, finish 2, conforming to L-P-378, polyethylene film material. Material shall be clean, non-colored (essentially colorless) and transparent. The film shall be manufactured by a properly controlled extrusion process to a thickness of 0.0030 inches with a tolerance of ± 10 percent.

3.2 Design and construction. The plastic bags shall be used for storage and shipment of dental prosthesis in a moisture-resistant closure to protect them from dehydration. Plastic bags shall be formed by folding one sheet and shall consist of two side seams. The edges of the side seams shall be parallel and all seams shall be parallel with the outer edges of the bag. The seams shall be sealed by normal heat sealing at a 400 to 600 degree Fahrenheit temperature range. The opening shall be on the short axis of the bag and shall be identified by the red colored stripe of permanent polyethylene extrusion located on the edge of the interlocking seal flap. The bag shall have a transparent surface which will permit ready identification of its contents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

3.2.1 Interlocking Seal. The interlocking seal on the bags shall be a single or double track zipper. The interlocking seal shall be positioned not less than 1/2 inch and not more than 3/4 inch, from the top or opening and shall be heat sealed to the plastic bag film by the same heat sealing process specified (see 3.2) for the side seams. The seal shall be straight and continuous and shall be effected by applying pressure with the fingers to the seal area. The plastic interlocking seal shall permit positive repeated opening and closing operations without any resulting impairment to the interlocking feature.

3.2.2 Dimensions. The plastic bag shall have uniform inside dimensions, exclusive of seals or seams, of four (4) inches in width and six (6) inches in length, held to tolerances of plus 1/8 inch or minus 1/16 inch.

3.3 Seam strength. Seam specimens shall withstand a static load of 3.5 pounds without peel back or slipping of seams when tested as specified in 4.4.1.

3.4 Instructions for use. Instructions for use shall be included with each unit box. The instructions shall be printed on a separate sheet of white bond or offset paper, measuring 6 $\pm$ 1/2 inches by 4 $\pm$ 1/2 inches. The printing shall show no smearing or bleeding and shall be clearly legible. The following instruction shall be printed on the paper:

"Designed to accommodate delivery of finished dentures in a moist atmosphere. Bag may be repeatedly opened and sealed by simple finger pressure. No heat sealing is required. Adequate moisture may be provided by inserting a damp cotton ball or other absorbent material, or at most, a teaspoon of water. Avoid excess water as this may cause slight leaking at the corners of the seal."

3.5 Workmanship. The bags shall be uniformly constructed and shall be free from tears, cracks, cuts, creases, blisters, wrinkles or other imperfections which may impair their usefulness or interfere with the purpose for which the bags are intended.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

4.1.1 Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.1.3 Sampling for inspection and acceptance. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot for examination and tests shall consist of all bags made by the same process from the same component material by one manufacturer and submitted for delivery at one time.

4.2 Inspection of materials. In accordance with 4.1 above, the supplier is responsible for insuring that materials used were manufactured, tested and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. An examination of the end item shall be made in accordance with the classification of defects, inspection levels, and acceptable quality levels (AQLs) set forth below. A random sample shall be drawn from each lot offered for acceptance for visual and dimensional characteristics. For purposes of determining the sample size in accordance with MIL-STD-105, the lot size for examinations under 4.3.1.1, 4.3.1.2, and 4.3.1.3 shall be expressed in units or unit packages of bags.

4.3.1.1 Examination of the end item for defects in appearance, construction, and general workmanship. The sample unit for this examination shall be one (1) bag. Examine both sides.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

Table I. Appearance, Construction, and General Workmanship Defects

Examine	Defects
Material	Bag not fabricated from material specified.
Appearance and Workmanship	Tears, cuts, or holes. Presence of scuff marks, chafed spots, sharp wrinkles or creases in body or sealed areas.
	Bags stick together to the extent that opening causes tearing or injury to any surface. Seams not uniform and in alignment; not completely sealed throughout their entire area. Seams other than specified. Not clean.
Construction	Not of uniform construction; open end not along one shorter side. Seams not straight or continuous.

4.3.1.2 Examination of the end item for dimensional defects. The sample unit for this examination shall be one (1) bag.

Table II. Dimensional Defects

Examine	Defects
Bag	Length not as specified. Width not as specified. Thickness of film not as specified.

4.3.1.3 Examination of count per unit container. The sample unit for this examination shall be one unit package (unit of issue) of bags. The average count per unit package shall be not less than the specified or indicated quantity.

4.3.1.4 Inspection levels and acceptable quality levels (AQLs) for examinations. The inspections levels for the purpose of determining the sample size and the acceptable quality levels (AQLs), expressed in defects per 100 units for Class 1, and per 1000 units for Class 2 shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

Table III. Inspection and Acceptable Quality Levels

Examination paragraph	Inspection level	AQL (Percent defective)
4.3.1.1	S-3	2.5
4.3.1.2	S-2	2.5
4.3.1.3	S-2	---

4.3.2 Testing of end item. Testing shall be performed for the characteristic as indicated in table IV on samples randomly selected from each lot of bags offered for Government acceptance. The sample unit shall be one bag. Failure to meet the AQL, as indicated, shall be cause for rejection of the lot.

Table IV. Testing of the End Item

Characteristic: Seam Strength

Basic specification requirement paragraph:	3.3
Test Method:	4.4.1
Requirement applies to:	
Individual unit	X
Lot average	-
Number of determinations per sample unit:	1
Results reported : 1/	
Pass or fail	X
Numerically to nearest	-
Inspection level	S-3
AQL in defects per 100 units	2.5

1/ If failure is indicated, report either description of failure or numerical point of failure, as applicable.

4.4 Tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

4.4.1 Seam strength. One hour after sealing, one 1-inch wide specimen shall be cut perpendicular to the line of the seam, from each seam of each sample bag. One leg of the specimen shall be so clamped that the specimen hangs freely. A load of 3-1/2 pounds shall be applied to the free end in such a manner as to avoid impact loading the seam. The load shall be allowed to act for 5 minutes, after which the seam shall be examined for slipping or peel back. The test shall be conducted at room temperature. (For reference purposes, room temperature shall be defined at 70° to 80°F). Peel back shall be defined as any separation of the seam from the inside line of contact of the sealer.

4.5 Rejection and retest. Bags which have been tested shall not be submitted for acceptance. Bags which fail to pass all requirements of this specification are classified as defective. Lots which have been rejected may be reworked or replaced to correct the defects and resubmitted for acceptance. Before resubmitting, full particulars concerning previous rejection and the action taken to correct the defect found in the original shall be furnished the inspector in writing, or his absence, forwarded to the procuring activity. Bags rejected after retest shall not be resubmitted without specific approval of the procuring activity.

4.6 Inspection of packaging. The sampling and inspection of the packing and marking for shipment and storage shall be in accordance with the quality assurances provisions of the applicable container specification and the marking requirements of MIL-STD-129.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or C as specified (see 6.1).

5.1.1 Level A.

5.1.1.1 Unit Package.

5.1.1.1.1 Class 1. One hundred bags shall be packed in a box conforming to PPP-B-566 or PPP-B-676. Closure shall be as specified in the applicable box specification.

5.1.1.1.2 Class 2. One thousand bags shall be packaged in a box conforming to PPP-B-636, type CF, class domestic. Closure shall be as specified in the applicable box specification.

5.1.2 Level C. The level C preservation for class 1 and class 2 bags shall conform to the MIL-STD-794 requirements for this level.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.1).

5.2.1 Level A.

5.2.1.1 Class 1. Ten unit packages shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-636, class weather-resistant. Closure, strapping and weatherproofing shall be as specified in the applicable box specification.

5.2.1.2 Class 2. Bags packaged to the degree of protection as specified in 5.1.1.1.2 shall require no further overpacking except the box shall conform to PPP-B-636, class weather-resistant. Closure, strapping and weatherproofing shall be specified in the applicable box specification.

5.2.2 Level B.

5.2.2.1 Class 1. Ten unit package shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-636, class domestic. Closure shall be as specified in the applicable box specification.

5.2.2.2 Class 2. Bags packed to the degree of protection as specified in 5.1.1.1.2 shall require no additional protection.

5.2.3 Level C. The level C packing for class 1 and class 2 bags shall conform to MIL-STD-794 requirements for this level.

5.2.4 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.2.5 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantities for shipment to one destination equal 40 cubic feet or more. Loads shall be unitized on pallets conforming to MIL-STD-147. Quantities less than 40 cubic feet need not be unitized. Pallet loads including the pallet shall not exceed 43 inches in height, 48 inches in width, and 40 inches in length, and shall conform to Type IV or Type V.

5.2.5.1 Levels A and B. Dental prosthesis bags packed as specified in 5.2.1 and 5.2.2 shall be unitized on pallets conforming to MIL-STD-147.

5.2.5.2 Level C. Dental prosthesis bags packed as specified in 5.2.3 shall be unitized as specified in 5.2.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 Levels A, B, and C.

5.3.1.1 Class 1. Each unit package, exterior container and unitized load shall be marked as specified in MIL-STD-129.

5.3.1.2 Class 2. When the unit package is utilized as the exterior container, each unit package shall be marked with exterior container markings as specified in MIL-STD-129. Each unitized load shall also be marked as specified in MIL-STD-129.

5.4 General.

5.4.1 Exterior container. Exterior container (see 5.2.1, 5.2.2, and 5.2.3) shall be of minimum tare and cube consistent with the protection required and shall contain equal quantities of identical stock numbered items to the greatest extent practicable.

5.4.2 Packaging inspection. The inspection of these packaging requirements shall be in accordance with 4.6.

6. NOTES

6.1 Ordering data.

6.1.1 Acquisition requirements. Acquisition documents should specify the following:

(a) Number and date of this specification.
(b) Class required (see 1.2.1).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2 National Stock Number (NSN) coverage. This specification covers the following items appearing in the Federal Supply Catalog:

Stock Number	Item Identification
6520-00-926-9041	BAG, DENTAL PROSTHESIS, Plastic, 100s.
6520-01-181-6972	BAG, DENTAL PROSTHESIS, Plastic, 1000s.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

6.3 This specification does not cover all types, classes, grades, or sizes of the commodity indicated by the title of this specification, or those which are commercially available, but is intended to cover the type which are normally procured to meet military requirements.

6.4 Subject term (key word) listing.

Bag
Dental Prosthesis
Plastic

Military Interests:

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Civil Agency Coordinating Activity
VA-OSS

06813

Preparing activity:
DoD-MB

Agent:
DLA-DM

Project No. 6520-1801

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-B-36528A	BAG, DENTAL PROSTHESIS (PLASTIC)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:45Z
Check the source to verify that this is the current version before use.