[NOT MEASUREMENT
SENSITIVE]
A-A-33A
October 17, 1997
SUPERSEDING
A-A-33
September 26, 1979

COMMERCIAL ITEM DESCRIPTION

SCALE REMOVING COMPOUND (LIQUID)

The General Services Administration has authorized the use of this Commercial Item Description (CID) for all federal agencies.

1. SCOPE. This CID covers a liquid form scale removing compound, hereinafter referred to as "compound," intended for removing scale deposits from environmental surfaces, commercial dishwashing machines, and boiler coils. This compound can be used in laboratories, food handling and processing areas, veterinary areas, and dairy plants.

2. SALIENT CHARACTERISTICS.

2.1 Materials. Unless otherwise specified herein, materials shall be in accordance with the manufacturer's material specifications. The compound shall be a uniform liquid, free of sediments and suspended particles, and shall contain a corrosion inhibiting agent and wetting agent.

2.1.1 Phosphoric acid (as P_2O_5). The compound shall have a phosphoric acid content of not less than 30.0 percent (%) and not more than 40.0% when determined in accordance with ASTM D820 Electrometric Titration Method.

2.1.2 Hydrogen-ion concentration (pH). The compound shall have a pH of not more than 2.0 when determined in accordance with ASTM E70.

2.1.3 Citric acid. The compound shall have a citric acid content of more than 6% when measured in accordance with ASTM D4608.

2.1.4 Hydrochloric acid (HCl). The compound shall contain not more than 10% HCl when determined in accordance with the manufacturer's standard practice.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any other data which may improve this document should be sent by letter to: Defense Logistic Agency, Defense Supply Center Richmond, ATTN: DSCR-VBD, Richmond, VA 23297-5610.

AMSC N/A FSC 6850

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T02:58Z
Check the source to verify that this is the current version before use.

2.1.5 Excluded ingredients. The compound shall not contain sulfuric acid or organic solvents.

2.2 Surface tension. The compound shall have a surface tension not greater than 8.08 x 10^{-3} poundals per inch (44.0 dynes per centimeter) when measured in accordance with ASTM D1331 using a sample at 77 degrees Fahrenheit (^{o}F) [25 degrees Celsius (^{o}C)] in a 1% aqueous solution.

2.3 Corrosive effect on steel. The compound shall have a corrosive effect on steel of not more than 0.15% loss of mass on 2 inch (in.) [51 millimeters (mm)] long by 2 in. wide by 0.035 in. (0.89 mm) thick coupons of hot rolled steel after a 24 hour period of immersion in the compound.

2.4 Nonvolatile matter. The compound shall have a nonvolatile matter content of not less than 30.0% at 221^{o}F (105^{o}C) when determined in accordance with ASTM D2834.

2.5 Foaming. The compound shall exhibit no foam at temperatures above 100^{o}F (38^{o}C).

2.6 Identification and markings. Identification and markings shall be permanent and legible and shall include, as a minimum, the manufacturer's identification code (CAGE) and labeling with instructions for use.

3. REGULATORY REQUIREMENTS.

3.1 Hazardous materials. The scale removing compound shall meet all applicable Federal codes and regulations concerning hazardous materials, including package marking.

4. QUALITY ASSURANCE PROVISIONS.

4.1 Product conformance. The products shall meet the salient characteristics of this CID, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial market. The Government reserves the right to require proof of such conformance.

4.2 Market acceptability. The compound shall have been sold previously to the Government or to the commercial market in order to qualify for acceptability under this CID.

5. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or order (see 6.2).

6. NOTES.

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T02:58Z
Check the source to verify that this is the current version before use.

6.1 Addresses for obtaining copies of Non-Government publications. Copies of ASTM D820 "Standard Test Methods for Chemical Analysis of Soaps Containing Synthetic Detergents," ASTM D1331 "Standard Test Methods for Surface and Interfacial Tension of Solutions of Surface-Active Agents," ASTM D2834 "Standard Test Method for Nonvolatile Matter (Total Solids) in Water-Emulsion Floor Polishes, Solvent-Based Floor Polishes, and Polymer Emulsion Floor Polishes," ASTM D4608 "Standard Test Method for Citrates in Detergents," and ASTM E70 "Standard Test Method for pH of Aqueous Solutions with Glass Electrode AASHTO T200" may be obtained from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

6.2 Ordering data. Acquisition documents must specify the following:

a. Title, number, and date of this CID.
b. Issue of the Department of Defense Index of Specifications and Standards (DoDISS) to be cited in the solicitation, and if required, the specific issue of individual documents referenced.
c. Packaging requirements.

6.3 Cross-reference data. Scale removing compound conforming to this CID is interchangeable/substitutable with scale removing compound conforming to P-S-120B, type II, dated April 8, 1977.

MILITARY INTERESTS:

Custodian:
DLA - GS

CIVIL AGENCY COORDINATING ACTIVITY:
GSA-FSS

Preparing Activity:
DLA - GS

(Project 6850-1220)

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T02:58Z
Check the source to verify that this is the current version before use.