MILITARY SPECIFICATION

EMULSION, POLYETHYLENE (FOR USE IN AMMUNITION)

This specification is approved for use by the US Army Armament Research and Development Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one type of a polyethylene emulsion used in the formulation of explosive compositions (6.3).

2. APPLICABLE DOCUMENTS

2.1 Issue of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specificaton to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification For

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-129 - Marking for Shipping and Storage
MIL-STD-1218 - ACS Chemicals

FSC: 6810

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

MIL-STD-1235 - Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement function should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

ASTM-D5	- Penetration of Bituminous Materials
ASTM-D1386	- Acid Number (Empirical) of Natural Waxes
ASTM-D1505	- Density of Plastics by Density-Gradient Technique
ASTM-D2834	- Nonvolatile Matter (Total Solids) in Water Emulsion Floor Polishes, and Polymer Emulsion Floor Polishes, Test For
ASTM-D2905	- Statement on Number of Specimens Required to Determine the Average Quality of a Textile Material
ASTM-E28	- Softening Point by Ring and Ball Apparatus
ASTM-E70	- pH of Aqueous Solutions with Glass Electrode
ASTM-E300	- Sampling Industrial Chemicals

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technicl groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Composition.

3.1.1 Polyethylene. The polyethylene used in the emulsion shall comply with the requirements in Table I:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

TABLE I. Requirements for Polyethylene (See 6.5)

Property	Requirement	Applicable Test Method
Acid Number	14-17	4.6.1.1
Penetration, mm	0.8-1.4	4.6.1.2
Viscosity @ 140°C, cps, max	200	4.6.1.3
Softening Point, °C	95-100	4.6.1.4
Density, g/cc	0.90-0.94	4.6.1.5

3.1.2 Emulsion. The emulsion shall be a uniform dispersion of the following materials, as indicated in Table II (see 6.11).

TABLE II. Emulsion Formulation

Composition	% by Weight	Notes
Polyethylene	20.38	See 6.5
Tall Oil Fatty Acid	3.57	See 6.6
Morpholine	3.57	See 6.7
Stearic Acid (See 6.10)	1.13	See 6.8
Ammonia (28%) (See 6.10)	0.50	
Water	70.85	See 6.11

3.1.3 Emulsion properties. The properties of the emulsion shall comply with the requirements in Table III.

TABLE III. Emulsion Properties

Property	Requirement	Applicable Test Method
Chemical Composition (based on total solids)		4.6.2.1
Linoleic Acid, %	6.5 ± 1.0	4.6.2.1.1
Oleic Acid, %	7.5 ± 1.0	4.6.2.1.1
Stearic Acid, %	4.5 ± 0.5	4.6.2.1.1
Polyethylene, %	81.5 ± 3.0	4.6.2.1.2.2
Penetration, mm	2.0-3.0	4.6.2.1.3.1
Viscosity @ 140°C, cps, max.	85	4.6.2.1.3.2
Softening Point, °C	94-98	4.6.2.1.3.3
pH	9-10	4.6.2.2
Transmission Value, %, min.	50	4.6.2.3
Dry Weight, %, min.	24.5	4.6.2.4

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

3.2 First article inspection. This specification contains provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection and standard quality assurance provisions. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Quality conformance inspection (see 4.4)

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisons of 4.3.2. The first article shall consist of 20 liters of the polyethylene emulsion obtained by sampling as described in 4.5.1. In addition, a one (1) kilogram sample of the polethylene used in the manufacture of the emulsion shall also be submitted. The samples shall be obtained from a production lot which has been produced by the contractor using the same production processes, procedures and equipment as will be used in fulfilling the contract. All materials, shall be obtained from the same sources of supply as will be used in regular production.

4.3.2 Inspections to be performed. The sample will be subjected by the Government to any or all of the examinations or tests specified in 4.6 of this specification.

4.3.3 Rejection. See MIL-A-48078.

4.4 Quality conformance inspection.

4.4.1 Lot formation. A lot shall consist of one or more batches of the polyethylene emulsion produced by one manufacturer, in accordance with the same specification, or same specification revision, under one continuous set of operating conditions. Each lot shall consist of that quantity of polyethylene that has been subjected to the same

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

unit chemical or physical mixing process intended to make the final product homogeneous. The product shall be submitted for inspection in accordance with MIL-STD-105.

4.4.2 Examination. Unless otherwise specified in the classification of defects and test tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II (see MIL-A-48078).

4.5 Testing.

PRECAUTION WARNING

This specification covers sampling and testing of toxic or hazardous materials. Accordingly, it is emphasized that all applicable safety rules, regulations and procedures must be followed in handling and processing these materials.

4.5.1 Sampling.

4.5.1.1 Polyethylene. Two independent representative samples shall be withdrawn from each batch or lot of polyethylene used in the formulation of the emulsion, using ASTM Procedure E300 for solids. If either of these samples fail to meet any test requirements given in Table I of 3.1.1, the polyethylene shall not be used in the emulsion formulation.

4.5.1.2 Emulsion. Approximately 2 liters of the polyethylene emulsion shall be withdrawn from each batch to be tested using ASTM Procedure E300 for liquids. Samples shall be selected for inspection in accordance with MIL-STD-1235, CSP-1 Plan, Sample Frequency Code Letter B, AQL 6.5%. If the sample fails to meet any test requirement the batch represented by the sample shall be rejected. All batches produced between the time that the last batch was tested and accepted and the batch which failed should be tested in accordance with the applicable methods given in paragraph 4.6. If any of these batches fail to meet any of the test requirements, that batch shall also be rejected. In addition, after any failure of a batch the contractor will return to 100% inspection until "i" successive batches are accepted as required by MIL-STD-1235. The samples shall be subjected to the tests listed in Table IV:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

TABLE IV. Defect classification

Inspection/Requirement (Emulsion) Table IV	Defect classification
Chemical composition	Major
pH	Major
Transmission	Major
Penetration	Major
Viscosity	Major
Softening point	Major
Dry weight	Major

4.5.3 Inspection equipment. The contractor shall use commercial inspection equipment for all of the tests and examinations specified in 4.6. The contractor shall have the required equipment available, follow proper calibration methods and perform the testing in accordance with accepted operating procedures. Government approval of all inspection equipment is required prior to its use for acceptance procedures.

4.6 Test methods and procedures. The following tests shall be performed using prescribed analytical procedures for replicate determinations given in standard analytical textbooks. ASTM Method D2905 may also be used to determine the number of replicates required. Also, unless otherwise specified herein, all chemicals and reagents shall be ACS or reagent grade in accordance with MIL-STD-1218.

4.6.1 Polyethylene prior to incorporation in emulsion.

4.6.1.1 Acid number. Determine the acid number of the polyethylene sample in accordance with the method given in ASTM-D1386.

4.6.1.2 Penetration. Determine the penetration value for the polyethylene sample in accordance with the method given in ASTM-D5.

4.6.1.3 Viscosity. Determine the viscosity of the polyethylene sample as follows:

Place an eight gram sample of the polyethylene in the viscosimeter cup of a Brookfield Thermosel Model LVT Viscosimeter. Attach the large spindle to the viscosimeter shaft being careful not to bend the thin wire used for this purpose.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

Lower the viscosimeter cup into the heating unit and turn it until the cup firmly sets itself in the heating unit keyway. Bring the heating bath temperature to 140°C and slowly lower the spindle into the cup in stages being sure the connecting wire does not bend or bow but hangs straight down.

Lower the spindle until the two support arms just touch the flat top of the heating unit and then back up 1 mm.

Set the RPM rate so that the viscosimeter pointer is on scale preferably near the 50 mark. Wait for the sample temperature to stabilize at 140°C. Record the viscosimeter pointer reading at five minute intervals over the period of thirty minutes. Average the readings and calculate the viscosity using the following formula:

$$\text{Viscosity, in centipoises} = \frac{30\text{RPM} \times B}{A}$$

Where: A is the RPM rate used for the determinations and B is the average of the viscosimeter readings.

4.6.1.4 Softening point. Determine the softening point of the polyethylene sample in accordance with the method given in ASTM E-28.

4.6.1.5 Density. Determine the density of the polyethylene sample in accordance with the method given in ASTM D1505.

4.6.2 Emulsion.

4.6.2.1 Composition.

4.6.2.1.1 Determination of stearic, oleic and linoleic acids.

Prepare the standard stock solution as follows:

Accurately weigh about 60 mg of stearic acid, 70 mg of oleic acid and 60 mg of linoleic acid into a 50.0 ml volumetric flask. Dissolve the fatty acids in chloroform and dilute to the 50.0 ml mark with chloroform. Prepare the polyethylene emulsion as follows: Pipet 10.0 ml. of polyethylene emulsion into a stared 100 ml. beaker. Weigh the beaker and emulsion to the nearest 0.001g. Determine the sample weight (W) by subtracting the beaker tare weight from the weight of the beaker and emulsion. Add 10 ml. of

Source: https://assist.dla.mil -- Downloaded: 202610-23T02:25Z
Check the source to verify that this is the currentversion before use.

distilled water, and 1 ml. of 6N HCL. Stir mixture well with glass rod and allow to stand with occasional stirring for 10 minutes. Quantitatively transfer precipitate into small (60 ml.) sintered glass funnel of coarse porosity. Using suction, wash three to four times with 25-30 ml. of distilled water until filtrate is neutral to pHydrion paper, stirring the precipitate thoroughly during each wash. Rinse once with 20 ml. of 50% methanol/water. Suction-dry precipitate on filter for 10 minutes to remove residual water. Quantitatively transfer the precipitate to glass stoppered 125 ml. Erlenmeyer flask, add 50 ml. of chloroform and place in an ultrasonic vibrator or mechanical shaker until all solids are suspended. Finally quantitatively transfer the solution to a 100.0 ml. volumetric flask and dilute to volume with chloroform. Transfer a portion of the solution to a centrifuge tube and centrifuge until the lower portion of the solution is clear. Pipet 4.0 ml. of the clear solution and transfer to a 10.0 ml. volumetric flask. Into four appropriately marked 10 ml. volumetric flasks, pipet 2.0 ml., 3.0 ml., 4.0 ml., 5.0 ml. and 6.0 ml. of Standard Stock Solution. Add 1 drop of phenolphthalein (0.1% phenolph-thalein solution in methanol) solution to each flasks, and neutralize each to a pink end point with 0.5% methanolic potassium hydroxide solution. Evaporate the solutions in the volumetric flasks to dryness in a 45-50°C water bath with the aid of a stream of dry nitrogen. Pipet 1.5 ml. of alkylating agent, prepared by dissolving 555 mg of , p-dibromoacetophenone and 53.0 mg of crown ether (1,4,7,10, 13,16-hexaoxacyclo-octadecane), in 20 ml. of benzene, into each volumetric flask and place flasks in a ultrasonic vibrator for several minutes in order to suspend any residues. (All operations involving the use of benzene must be conducted in an efficient fume hood.) Place flasks in an 80°C water bath for 20 minutes shaking frequently. Do not allow to dry out. If necessary add 0.5 ml. of benzene to each flasks. Mix well. Cool to room temperature, and make up to volume with benzene. Draw a line 1.5 cm from the lower edge of a 20 X 20 cm KC18 Reversed Phase Thin Layer Chromatographic plate (with fluorescent indicator, Whatman, Inc.) with a soft lead pencil. Mark points of application at 2 cm intervals along the line and using disposable open-end capillaries (Drummond Microcaps or equal) apply 5 lambda of each sample and standard to the plate. Run in duplicate. Allow solvent to evaporate from spots on plate and place the plates in a filter paper lined developing chamber being sure the developing solvent, acetonitrile: Chloroform (90:10), is well below the level of the spots on the plate. Allow the solvent front to ascend 12 cm from the pencil line on the plate.

Source: https://assist.dla.mil -- Downloaded: 202610-23T02:25Z
Check the source to verify that this is the currentversion before use.

Remove plates from the developing chamber and allow the solvent to evaporate from the plate at room temperature or in a 50-55°C oven for 2 or 3 minutes. Read the intensity of spots using a Schoeffel Spectrodensitometer Model SD 3000 or equal equipped with a suitable integrator. Calculate average peak areas for each standard and sample spot; R_f values for the fatty acids are: stearic acid - 0.33, oleic acid - 0.40 and linoleic acid - 0.53. Plot the average peak area for each of standard fatty acid spots versus their concentration in mg. Determine the concentration of each fatty acid in the sample by comparing the average peak area of its spots on the TLC plate with the peak area vs concentration plots obtained for the corresponding fatty acid. Calculate the percentage of each fatty acid in the emulsion precipitate sample using the following equation:

$$F = \frac{C \times 100}{W \times D \times 0.98}$$

Where:

F = percent fatty acid
C = weight of fatty acid in mg
W = weight of polyethylene emulsion sample in mg
D = decimal equivalent of the percent dry weight as determined in 4.5.5
0.98 = factor to correct the concentration of fatty acid in 100 ml. solution for presence of 2 ml. of suspended polyethylene

4.6.2.1.2 Determination of polyethylene content and properties. Prior to performing the tests given in paragraph 4.6.2.1.2.2 (Polyethylene content), 4.6.2.1.3.1 (Penetration), 4.6.2.1.3.2 Viscosity, and 4.6.2.1.3.3 (Softening point), a portion of the emulsion sample obtained in 4.6.1.2 shall be pre-treated to separate the polyethylene from the emulsion.

4.6.2.1.2.1 Preparation of polyethylene precipitate. Transfer an approximately 300g portion of the polyethylene emulsion to a liter beaker and add about 600 ml of distilled water. To the beaker and contents add approximately 16 ml of 56% acetic acid while stirring. Place beaker and contents on a steam bath and heat at 95-97°C and allow to cool to 45-50°C. Filter contents of beaker through a Buchner funnel fitted with a medium porosity filter paper. Wash the polyethylene precipitate several times with a total of 1000 ml of warm (45-50°C) distilled water. Transfer sample to a drying dish and dry in a forced draft oven and allow to cool. Reserve precipitate for tests listed in 4.6.2.1.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

4.6.2.1.2.2 Polyethylene content. Place an accurately weighed approximately one gram sample of the polyethylene precipitate obtained in 4.6.2.1.2.1 in a tared medium porosity filtering crucible. Place the crucible in a vacuum filtering apparatus and wash the precipitate with six 10cc portions of chloroform. Allow each washing to remain in contact with the precipitate for at least 30 seconds with stirring before removing by vacuum filtration. Aspirate after the final washing until the odor of chloroform is no longer noticeable, dry in a 100°C oven, and weigh. Repeat the drying and weighing procedures until two consecutive weighings agree within 1 mg.

Calculate the percent polyethylene as follows:

$$\text{Percent polyethylene} = \frac{(B-C) \quad X100}{S}$$

Where: B = weight of crucible and polyethylene in grams
C = tare weight of crucible in grams
and S = Sample weight in grams of the polyethylene precipitate

4.6.2.1.3 Polyethylene properties.

4.6.2.1.3.1 Penetration. Determine the penetration of the prepared sample obtained in 4.6.2.1.2.1 in accordance with method given in ASTM-D5.

4.6.2.1.3.2 Viscosity. Determine the viscosity of the prepared sample obtained in 4.6.2.1.2.1 in accordance with the method given in 4.5.3.

4.6.2.1.3.3 Softening point. Determine the softening point of the prepared sample obtained in 4.6.2.1.2.1 in accordance with the method given in ASTM E-28.

4.6.2.2 pH. Determine the pH of the emulsion sample, obtained in 4.5.1.2 in accordance with the method given in ASTM D-70.

4.6.2.3 Transmission. Determine the percent transmission of the emulsion sample obtained in 4.5.1.2 as follows:

Set the wavelength dial of a Bausch and Lomb Spectronic 20 or equal spectrophotometer at 500 nm and adjust the trans-

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

mission indicator to zero. Fill one of a pair of matched sample cells with distilled water, place it in the sample chamber of the spectrophotometer. Adjust the transmission indicator for 100% transmission.

Pipet 1.00 ml of the polyethylene emulsion into a 100 ml volumetric flash, dilute to the mark with distilled water and mix thoroughly. Fill the second matched sample cell with the diluted polyuethylene emulsion and place it in the sample chamber. Read and record the value on transmission dial as the percent transmission.

4.6.2.4 Dry weight. Determine the dry weight of the emulsion sample (4.5.1.2) in accordance with the method given in ASTM-D2834.

5. PREPARATION FOR DELIVERY (See 6.1).

5.1 Packing.

5.1.1 Level A and Level C. Unless otherwise specified, the polyethylene emulsion shall be packed in accordance with manufacturer's commercial practice to assure acceptance by common carrier for safe delivery. (See 6.9)

5.2 Marking. Unless otherwise specified, the shipping containers shall be marked in accordance with MIL-STD-129, and shall include the lot number.

6. NOTES

6.1 Ordering data. See MIL-A-48078 (PA).

6.2 Equivalent methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted thru the Contracting Officer to: Commander, US Army Armament Research and Development Command, ATTN: DRDAR-QAR, Dover, New Jersey 07801. This description should include but not be limited to the procedures used, the accuracy and precision of the method, test data to demonstrate the accuracy and precision and drawings of any special equipment required.

6.3 Intended use. The polyethylene emulsion described in this specification is intended to be used as an alternate, when approved, for desensitizing wax (MIL-W-20553) used in explosive compositions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

6.4 Submission of inspection equipment designs for approval. See MIL-A-48078. Submit equipment designs, as required, to Commander, US Army Armament Research and Development Command, ATTN: DRDAR-QAR, Dover, New Jersey 07801.

6.5 Polyethylene. Material meeting the requirement of this specification was previously obtained from Allied Chemical Corp., Morristown, N.J., designated A-C Polyethylene Grade 656. Use of another source of polyethylene requires prior approval of the Contracting Officer.

6.6 Tall oil fatty acid. Material used previously and found satisfactory was obtained from Arizona Chemical Corp., Wayne, New Jersey 07801. Use of another source of tall oil requires prior approval of the Contracting Officer.

6.7 Morpholine. Material used previously and found satisfactory was obtained from Jefferson Chemical Corp., Houston, Texas, having the following properties:

Appearance	Clear and substantially free of suspended matter.
Boiling range, ASTM, °C	
IBP:	126.0 min.
DP:	130.0 max.
Color, Pt-Co. scale	15 max.
Purity, wt. %	99.0 min.
Specific gravity, 20/20°C	1.001 min.
	1.004 min.
Water miscibility, 10cc in 90cc water	No turbidity

SELECT PROPERTIES

Boiling point, 760 mm., °C	128.9
Flash point (open cup), °F	100
Freezing point, °C	-4.9
Weight, lbs./gal., 20°C	8.3

Use of another source of Morpholine requires prior approval of the Contracting Officer.

6.8 Stearic acid. Material used previously and found satisfactory was Hystrene 9718 manufactured by Humko Division, Kraftco Corp., Memphis, Tennessee 38101.

6.9 Freezing. The material in shipment or storage shall be maintained at a temprature in excess of 2° °C and not more than 45° °C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

6.10 Stearic acid and ammonia. The total amount of stearic acid and ammonia shall be added as ammonium stearate solution at a temperature below 50° °C.

6.11 Water content. The water content of the polyethylene emulsion may be reduced, however, the concentrations of all components of the emulsion must remain in the same relative proportions as is given in 3.1.2.

Custodian:
Army-AR

Preparing Activity
Army-AR

Project Number: 6810-AA88

Source: https://assist.dla.mil -- Downloaded: 202610-23T02:25Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY CARD

FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Armament R & D Command
ATTN: DRDAR-QAR
Dover, New Jersey 07801

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:25Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-E-63218 Emulsion, Polyethylene

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1 ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2 REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426

EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 202610-23T02:25Z
Check the source to verify that this is the current version before use.