MILITARY SPECIFICATION

# SEALER, WELD-THROUGH FOR OVERLAPPING SURFACES

This specification is approved for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 This specification covers a single package weldable sealer for use on ferrous and nonferrous material surfaces prior to spot welding, riveting or bolting the overlapped areas.

1.2 Purpose. The purpose of this specification is to control crevice corrosion in ferrous and nonferrous assemblies. Galvanic corrosion can be controlled when mechanically attaching ferrous and nonferrous materials.

## 2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified (see 6.2), the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

| | |
|---|---|
| PPP-D-705 | - Drum, Shipping and Storage: Steel 16 and 30 Gallon Capacity. |
| PPP-D-729 | - Drums, Shipping and Storage, Steel, 55-Gallon (208 Liters). |

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Mobility Equipment Research and Development Command, ATTN: DRDME-DS, Fort Belvoir, VA 22060 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

| | |
|---|---|
| PPP-D-732 | - Drums, Metal, 55-Gallon Reconditioned (For Shipment of Noncorrosive Material) |
| PPP-P-704 | - Pails, Metal: (Shipping, Steel, 1 through 12 Gallons). |
| PPP-P-1892 | - Paint, Varnish, Lacquer, and Related Materials: Packaging and Marking of. |

STANDARDS

MILITARY

| | |
|---|---|
| MIL-STD-105 | - Sampling Procedure, Inspection by Attributes. |
| MIL-STD-129 | - Marking for Shipment and Storage. |
| MIL-STD-147 | - Palletized Unit Loads 40 inch by 40 inch Partial and "4" way pallets. |
| MIL-STD-1188 | - Commercial Packaging of Supplies and Equipment. |

(Copies of specifications, standards, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer).

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

B117 - Salt Spray Testing.
D93 - Flash Point of Pigmented Materials (Pensky Martin).
D1475 - Density of Paint Varnish and Related Products.
D1849 - Package Stability of Paint.
D2196 - Rheological Properties of Non-Newtonian Materials.
D2247 - Coated Metal Specimens at 100% Relative Humidity.
D2369 - Volatile Content of Solvent Reducible Paints.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

SOUTH COAST AIR QUALITY MANAGEMENT DISTRICT

Rule 102 - Photochemically Reactive Solvents.
Rule 1107 - Manufactured Metal Parts and Products Coatings.

(Application for copies should be addressed to South Coast Air Quality Management District, 915 East Flair Drive, El Monte, CA 91731.)



Source: https://assist.dla.mil -- Downloaded: 202640-22T21:50Z
Check the source to verify that this is the current version before use.

(Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies).

2.3 Order of precedence. In the event of a conflict between the text of this specification and the reference cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Qualification. (Type or brand approval). The sealer furnished under this specification shall be qualified through the qualified products list. Any change in the formulation of a qualified product will necessitate its requalification (see 6.4).

3.2 Material. The sealer shall be composed of non-volatile base materials dispersed in a petroleum solvent so to form a fluid formulation that will meet the requirements of this specification. The compound shall be free of grit and abrasives, and shall not be injurious to personnel applying it if reasonable procedures and safety precautions are employed.

3.3 Color. The material shall be tan to brown in color.

3.4 Composition.

3.4.1 Sealer. The sealer shall be a one package thixotropic material. The sealer shall be free of benzene and chlorinated hydrocarbons and shall meet rules No. 102 and 1107 of South Coast Air Quality Management District.

3.5 Quantitive requirements. The sealer shall conform to the quantitive requirements of table I when tested in 4.4.

TABLE I. Quantitive requirements of sealer.

| Characteristics | Minimum | Maximum |
|---|---|---|
| Viscosity-Brookfield No. LV | 24,000 (CPS) | 30,700 (CPS) |
| Specific gravity @ 15.6° C | 0.979 | --- |
| Flash point PMCC | 133° F | --- |
| Volatile content | ---- | 34% |
| Drying time: | | |
| Air drying; minutes, set to touch | 120 | |

3.5.1 Condition in container. The sealer tested as in 4.4 shall show no livering, curdling, excessive settling and shall with minimum mixing return to a smooth homogeneous state.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

3.5.2 Storage stability. When tested as in 4.4.4 the sealer shall show no livering, curdling or heavy settling. A minimum of mixing shall return the sealer to a smooth homogeneous state. No thinning of the sealer should ever be required.

3.5.3 Lot and batch control. Each lot or batch of sealer shall be tested as in 4.2 and 4.4.2.

3.5.4 Rolling properties. The sealer tested in 4.4.6.2 shall roll satisfactorily in all respects and shall produce a uniform film, free from pin holes and craters.

3.5.5 Brushing properties. The sealer tested in 4.4.6.3 shall brush satisfactorily and shall produce a uniform film, free from pin holes and craters.

3.5.6 Welding characteristics. When tested in 4.4.8 the sealer shall show satisfactory resistance to welding and the sealer shall reflow covering the heat effected zone.

3.5.7 Humidity resistance. When tested in accordance with 4.4.11, the test panel shall show no corrosion immediately after removal from the humidity chamber on overlapped area except for minor blemishes when compared with the blank.

3.5.8 Salt spray resistance. When tested as in 4.4.12 and examined immediately after removal from the salt spray test, the test panels shall show no corrosion on overlapped area except for minor blemishes when compared with the blank.

3.5.9 Sag test. There will be no migration into the masked area with the panels in a vertical position when tested as in 4.4.6.7.

3.5.10 Spraying Properties. The sealer, when sprayed in accordance with 4.4.6.1, shall flow out and cover the panel with no sags or runs.

3.5.11 Weld test results. The average nugget size shall be .160 and all spot welds shall result in nuggets.

3.5.12 Flexibility. No cracking or loss of adhesion shall be observed.

## 4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless specified in the contract or purchase order the contractor is responsible for the performance of all inspection requirements as specified therein. Except as otherwise specified, the contractor may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to the prescribed requirements.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

4.2 Sampling inspection and testing. Sampling and inspection shall be performed in accordance with Sections 1022 and 1031 of FED-STD-141.

4.3 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. Qualifications
b. Acceptance of individual lots.
c. Inspection of packaging (see 4.5).

4.3.1 Qualification test. The qualification test shall consist of testing all requirements specified in Section 3.

4.3.2 Acceptance test. Acceptance tests for acceptance of individual lots shall consist of tests specified in Section 4 with the exception of storage stability in 4.4.4 and weldable characteristics in 4.4.8.

4.4 Test methods.

4.4.1 Test conditions. The routine and referee testing conditions shall be in accordance with Section 9 of FED-STD-141, except as otherwise specified therein.

4.4.2 Test. The following test shall be conducted in accordance with FED-STD-141 or ASTM specification as hereinafter specified.

TABLE II. Test methods and requirements.

| Item | Applicable Method in FED-STD-141 | ASTM Ref. | Reference Paragraph | Requirements Paragraph |
|---|---|---|---|---|
| Viscosity | --- | D2196 | 4.4.3 | Table I |
| Specific gravity | --- | D1475 | --- | Table I |
| Flash point | --- | D93 | --- | Table I |
| Volatile content | --- | D2369 | 4.4.6.6 | Table I |
| Flexibility | 6221 | --- | 4.4.7 | 3.5.12 |
| Drying time | --- | --- | 4.4.6.4 | Table I |
| Storage stability: | | | | |
| Partially full | 3021 | --- | 4.4.4 | 3.5.2 |
| Full | --- | D1849 | 4.4.4 | 3.5.2 |
| Color | --- | --- | 4.4.6.5 | 3.3 |
| Sag Test | --- | --- | 4.4.6.7 | 3.5.9 |
| Spraying | | | | |
| Properties | --- | --- | 4.4.6.1 | 3.5.10 |
| Rolling | | | | |
| Properties | --- | --- | 4.4.6.2 | 3.5.4 |
| Brushing | | | | |
| Properties | --- | --- | 4.4.6.3 | 3.5.5 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

TABLE II. Test Methods and Requirements. (continued)

| Item | Applicable Method in FED-STD-141 | ASTM Ref. | Reference Paragraph | Requirements Paragraph |
|---|---|---|---|---|
| Welding characteristics | --- | --- | 4.4.8 | 3.5.6 |
| Humidity resistance | --- | D2247 | 4.4.11 | 3.5.7 |
| Salt spray resistance | --- | B117 | 4.4.12 | 3.5.8 |

4.4.3 Viscosity (packaged). Determine viscosity as in ASTM D2196. At the time material is shipped from manufacturer or received by user the viscosity shall check to table I. After material is stored any length of time, seven minutes of mixing should bring material to proper viscosity.

4.4.4 Storage stability.

4.4.4.1 Partially full container. Determine 48 hour skinning in accordance with 3021 of FED-STD-141. Reseal and age seven days at 60° C and observe for compliance with 3.5.2.

4.4.4.2 Full container. In accordance with ASTM D1849, allow a full standard quart can of sealer to stand undisturbed for six months and examine the contents. Evaluate in accordance with 3.5.2, but agitate the contents in the can for five minutes on a paint shaker prior to reexamining. Determine viscosity and make other applicable tests to determine compliance with table I.

4.4.5 Panel preparation. Panel shall be sprayed using airless spray equipment with a uniform film thickness of .010 inch, wet film, as in 4.4.6.1. No special pretreatment is performed to the panels prior to coating.

4.4.5.1 Procedure (ferrous material). All panels shall be clean, dry and rust free, plain SAC 1010 cold roll steel panels, 4 inches x 12 inches, .032 inch thick. Coat untreated panel with maximum .0003 inch of mil oil no. 100/100. Stand panels in a vertical position to allow any excess oil to drain off for one hour prior to applying the sealer.

4.4.5.2 Procedure (nonferrous material). All panels shall be clean, dry, corrosion free, plain 5052H32 aluminum, 4-inches x 12-inches, .030 inch thick. Do not pre-clean panels prior to applying sealer for test.

4.4.6 Application properties.

4.4.6.1 Spraying properties. Airless spray shall be used and the material shall be sprayed at the viscosity as received. The spray specification shall be:



Source: https://assist.dla.mil -- Downloaded: 202640-22T21:50Z
Check the source to verify that this is the currentversion before use.

a. Feed pump 12-1.
b. Pump pressure - 40/60 pounds.
c. Gun Orfice - .23 to .026 inch.
d. Distance of gun to work - 4 to 10 inches.
e. Material shall not require agitation during spraying operation.

A wet film thickness of .008 to .010 inch, minimum, shall be applied.

4.4.6.2 Roller properties. The sealer shall be applied with a hand roller. The sealer shall be used at the viscosity received. Wet film thickness of .004 inch to .008 inch can be obtained by using a shorter or longer nap roller.

4.4.6.3 Brushing properties. The sealer shall be applied at the viscosity as received. Films from .004 to .008 inch shall be applied.

4.4.6.4 Drying time. All test panels shall be conditioned prior to testing by allowing them to air dry for 96 hours at 77° F plus or minus 2° F in a relative humidity of 55 plus or minus 6 percent.

4.4.6.5 Color. Color shall be determined visually in the open can.

4.4.6.6 Volatile content. The percentage of volatile of the sealer shall be determined by ASTM D2369. Examine for compliance to table I.

4.4.6.7 Sag test. The sag test shall be performed by masking the lower half of 4-inch x 12-inch panels, spraying the upper half .015-inch wet film thickness, set in a vertical position for fifteen minutes, then placed in an oven at 350° F, for two minutes. Examine for conformation to 3.5.9.

4.4.7 Flexibility. Determine the flexibility in accordance with method 6221 of FED-STD-141. Test panels shall be prepared as 4.4.6. Test panels shall be conditioned prior to testing in accordance with 4.4.6.4. Bend over 1/8 inch mandrel for compliance to 3.5.12.

4.4.8 Welding characteristics.

4.4.8.1 Equipment and instrumentation. Required for spot welding ferrous and nonferrous material.

4.4.8.1.1 Spot welding - single point - ferrous material. A single point spot welder having a low inertic head shall be used. At a transformer tap setting of 4.0 to 5.0 volts, open circuit, secondary voltage, adjustments shall be made to obtain the following.

Electrode force - 400 lb.
Weld time - 8 cycles
Secondary amperes - 7,200 amps

The welding transformer shall be excited for adjustment of the welding current. Its timing accuracy (0 to 15 cycles) shall be plus or minus (0) cycles.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

Electrodes are two RWMA class 2 material spot welding cap electrodes .375 inch in diameter, having a .187 inch diameter welding face formed from a 45° truncated cone, are used for the weld test for ferrous material.

4.4.8.1.2 Instrumentation. A galvanometer-type oscillograph shall be used for recording the sine wave of the secondary current.

4.4.8.1.3 Panel preparation and test. Panels shall be prepared as in 4.4.5, 4.4.5.1 and 4.4.5.2. Panels shall be spot welded as soon as sealer is applied and 24 hours after sealer is applied.

4.4.8.1.4 Welding test procedures. When test panels are prepared as in 4.4.5 and spot welded as in 4.4.8.1.1, four spot welds shall be made on each panel no closer than .5 inch apart and .5 inch from the edge of the panels. After performing the peel test, see 4.4.9, measure each nugget in two directions. Examine for compliance to 3.5.11.

4.4.8.1.5 Spot welding - single point - nonferrous material. Spot welding equipment with a three phase frequency convertor is recommended and shall be set as follows for panels prepared as in 4.4.5 and 4.4.5.2:

Electrode - .625 with a 4.0 radius
Electrode force - 700 lb.
Weld current - 36,000 amps
Post heat - 9,000 amps
Weld cycles - 4

Electrodes are two RWMA class 1.

4.4.8.1.5.1 Panel preparation. Test panels shall be prepared as in 4.4.5, 4.4.5.1, and 4.4.5.2.

4.4.8.1.6 Welding test procedure. Test panels are prepared as indicated in 4.4.8.1.5. Four spots shall be made on each panel no closer than .875 inch to each other and to the edge of the panel. After performing the peel test, see 4.4.9, measure the nugget in two directions. Examine for compliance to 3.5.11.

4.4.9 Peel test. The peel test is a destructive test. It shall be performed by gripping one panel in a vise or holding device. The pieces are peeled apart using pinchers or other tools. This permits visual examination of the soundness of a spot weld.

4.4.10 Panel preparation for humidity and salt fog tests. Using test panels prepared in 4.4.5.1 (steel) and 4.4.5.2 (aluminum) prepare eight each of the following welded assemblies of steel and aluminum for the humidity and salt fog tests. On the long edge of the panel roll with a two-inch roller a two-inch strip sealer from bottom to top of panel to obtain a wet film thickness of .008 to .010 inches. Place a like uncoated panel over the wet sealer to cover it as closely as possible. Hold the assembly together and spot weld as in 4.4.8.1.4 (steel) or



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

4.4.8.1.6 (aluminum), except make two rows of spot welds 1/2 inch inside each overlapping edge. Start first weld one inch from top and bottom. Then repeat spot welds every 2 inch intervals. This yields seven spot welds in each row. Spray or brush sealer on back and front of welded assembly to get .008 to .010 in wet film.

4.4.11 Humidity test. Four test panels each of steel and aluminum shall be used as in 4.4.10. Panels shall then be conditioned by air drying for 96 hours as specified in 4.4.6.4 prior to putting three of each type in a humidity cabinet. Save the fourth panel as a blank. The test shall be conducted in accordance with ASTM D2247 for 2,000 hours. Remove the two sets of panels from test. Clean exposed areas of test samples and blanks of sealer. Drill out spot welds, lift panels apart. Clean the overlapped area of sealer and examine for compliance to 3.5.7.

4.4.12 Salt spray test. Four test panels of steel and aluminum are selected as in 4.4.10. Air dry 96 hours as in 4.4.6.4.. Expose three of each type (save blank) to a 5 percent salt spray for 2,000 hours ASTM B117. Examine exposed and blanks panels as in 4.4.11 for compliance to 3.5.8.

4.5 Inspection of packaging.

4.5.1 Quality conformance inspection of pack.

4.5.1.1 Unit of product. For the purpose of inspection, a completed pack prepared for shipment shall be considered a unit of product.

4.5.1.2 Sampling. Sampling for examination shall be in accordance with MIL-STD-105.

4.5.1.3 Examination. Samples selected in accordance with 4.5.1.2 shall be examined for the following defects. The acceptable quality level (AQL) shall be 2.5 percent defective.

| No. | Defect | A | Comm. |
|---|---|---|---|
| 101 | Unit container size not as specified. | 5.1 | 5.1 |
| 102 | Unit container construction not as specified. | 5.1.1 | 5.1.2 |
| 103 | Palletization not as specified (when required). | 5.1.1.4 | |
| 104. | Marking not as specified | 5.2.1 | 5.2.2 |

5. PACKAGING

5.1 Packing. Packing shall be level A or commercial (see 6.2), in the quantity specified (see 6.2), in unit containers conforming to the following:

5.1.1 Level A.

5.1.1.1 Five-gallon pail. The 5-gallon pails shall conform to PPP-P-704, type optional, class as applicable.



Source: https://assist.dla.mil -- Downloaded: 202610-22T21:50Z
Check the source to verify that this is the current version before use.

5.1.1.2 Sixteen-gallon drum. The 16-gallon drums shall conform to PPP-D-705, type as applicable.

5.1.1.3 Fifty-five gallon drum. The 55-gallon drums shall conform to PPP-D-729. Alternatively, when specified (see 6.2), the 55-gallon drums shall conform to PPP-D-732. Drum types shall be as applicable and classes shall be optional.

5.1.1.4 Palletization. When specified (see 6.2), the pails and drums shall be palletized in accordance with MIL-STD-147.

5.1.2 Commercial. The sealer shall be packed in the quantity specified (see 6.2), in unit containers conforming to the requirements of MIL-STD-1188.

5.2 Marking. Each container, in addition to the marking requirements of 5.2.1 and 5.2.2, shall be marked, as applicable, with the manufacturer's qualified product list designation.

5.2.1 Level A. Level A marking shall be in accordance with MIL-STD-129. Any additional marking (see 6.2) shall be in accordance with the special marking requirements of PPP-P-1892.

5.2.2 Commercial. Commercial marking shall be in accordance with MIL-STD-1188.

6. NOTES

6.1 Intended use. The sealer covered by this specification is intended to protect against crevice corrosion. Therefore, the sealer shall be applied to fill the joints of spot welded and joints held together by fasteners.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Date of issue of DoDISS applicable and exceptions thereto (see 2.1.1).
c. Unit container sizes required (see 5.1).
d. Degree of packing required (see 5.1).
e. When reconditioned drums are required (see 5.1.1.3).
f. When palletization is required (see 5.1.1.4).
g. Any additional markings required (see 5.2.1).

6.3 Baking or heat treating. When baking or heat treating is required as part of an assembly, the sealer may be applied and baked at temperatures up to 440° F for twenty minutes.

6.4 Qualification. With respect to products requiring qualification, awards will be made only for such products as have, prior to the time set for opening or bids, been tested and approved for inclusion in the applicable qualified products list whether or not such products have actually been so listed by that date. The



Source: https://assist.dla.mil -- Downloaded: 202610-22T21:50Z
Check the source to verify that this is the currentversion before use.

attention of the contractors is called to this requirement and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for products covered by this specification. The activity responsible for the qualified products list is: Commander, US Army Mobility Equipment Research and Development Command, Fort Belvoir, VA 22060, ATTN: DRDME-VO and information pertaining to qualification of products may be obtained from the activity.

Custodians:
Army - ME
Navy - YD

Preparing Activity:
Army - ME

Project 8010-1001

Review Activities:
Army - MR, MI
Navy - SH

User Activity:
Army - AT



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-S-53018 Sealer, Weld-Through for Overlapping Surfaces

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1426 1 OCT 76

EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

**BUSINESS REPLY CARD**

FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

COMMANDER
US ARMY MOBILITY EQUIPMENT RESEARCH
AND DEVELOPMENT COMMAND
ATTN: DRDME-DS
FORT BELVOIR, VA 22060

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:50Z
Check the source to verify that this is the current version before use.