INCH-POUND

MIL-S-21042C(MC)
2 January 1990
SUPERSEDING
MIL-S-21042B(MC)
12 April 1972

MILITARY SPECIFICATION

SLING, FLAGSTAFF: LEATHER, WHITE; WITH BRASS SOCKET

This specification is approved for use by U. S. Marine Corps, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers requirements for one type of leather sling with highly polished brass fitting and engraved with United States Marine Corps lettering as shown on the referenced drawings.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

A-A-50197	-	Thread, Linen
C-F-206	-	Felt, Sheet, Cloth, Wool, Pressed
V-T-276	-	Thread, Cotton
KK-L-271	-	Leather, Cattlehide, Strap, Vegetable-tanned

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to the Commanding General (PSE-C), Marine Corps Research, Development and Acquisition Command, Washington, D. C. 20380, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8345

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-B-17757 - Boxes, Fiber, Corrugated (Modular Sized)

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods
FED-STD-311 - Leather, Methods of Sampling and Testing
FED-STD-595 - Color
FED-STD-751 - Stitches, Seams and Stitchings

MILITARY

MIL-STD-105 - Sampling Procedure and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

DRAWINGS

MARINE CORPS

71C5040A0000 - Sling, Flagstaff; Leather; White; With Brass Socket-Assembly
71C5040A0001 - Sling, Flagstaff; Leather; White; With Brass Socket-Metal Details
71C5040A0002 - Sling, Flagstaff; Leather; White; With Brass Socket-Buckle
71C5040A0003 - Sling, Flagstaff; Leather; White; With Brass Socket-Leather Details

(Unless otherwise indicated, copies of federal and military specifications, standards and handbooks are available from the Naval Publications and Forms Center (Attn: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099).

2.1.2 Other Government documents, drawings, and publications. The following other Government documents and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

LAWS AND REGULATIONS

U. S. Postal Service Manual

(Application for copies should be addressed to the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402)

Department of Defense (DoD) Standard Color Card of
Official Standardized Shades for Sewing Threads 1968

(Application for copies should be addressed to the Color Association of the United States, Inc., 200 Madison Avenue, New York, NY 10016.)

2.2 Other publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the current version before use.

documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Association, ATTN: Order Section, 1616 P Street, N.W., Washington, D. C. 20026.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification Rules

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard sample. Standard samples, when furnished, are solely for guidance and information to the Contractor (see 6.3). Variation from this specification may appear in the sample in which case the specification shall govern.

3.2 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.3 Materials.

3.3.1 Leather.

3.3.1.1 Cowhide. The leather for the carrying straps, buckle straps, sliding keepers, and front and back covers shall be cowhide, free from cuts, damaged grain, open scratches, grub holes, brands, wrinkles or any other defect which may affect the appearance or serviceability of the finished sling.

3.3.1.1.1 Tannage. The leather shall be white mineral tanned by a suitable synthetic retannage (melamine, vinyl, or equal), exhibiting properties that meet the requirements of this specification.

3.3.1.1.2 Finish. The leather shall be full grain or full grain lightly snuffed. The flesh side shall be smooth and free from loose flesh.

3.3.1.1.3 Cracking. The leather shall not crack when tested as specified in Section 4, Table I.

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the current version before use.

3.3.1.1.4 Chemical and thermal requirements. The leather shall conform to the following chemical and thermal requirements when tested as specified in Section 4, Table I.

Characteristics	Minimum	Maximum
Chloroform extract (- percent)	6	-
Total ash (- percent)	9	-
pH	3	4.5
Shrinkage temperature (°C)	85	-

3.3.1.1.5 Thickness. The carrying straps, buckle straps, and sliding keepers shall be 6 to 8 ounces, and the front and back covers shall be 2-1/2 to 3 ounce.

3.3.1.1.6 Color. The leather shall be white on the flesh side and grain side approximating shade No. 27875 of FED-STD-595, showing good fastness to wet and dry crocking and showing no appreciable "yellowing" when tested as specified in Section 4, Table I.

3.3.1.2 Cattlehide. Reinforcement leather shall be split cattlehide, 7-1/2 to 8 ounce for the front plate and 4-1/2 to 5 ounce for the back pad, conforming to type I, II, III, or IV, class 1, of KK-L-271.

3.3.2 Metal. The plate holder shall be made from sheet copper having a minimum copper content of 99.5 percent. All other metal parts shall be a copper base alloy having a chemical composition of 64.0 to 68.5 percent copper and the remainder zinc and trace elements. The color shall be the basis of acceptability of the metal for chemical composition except in case of dispute, when an analysis shall be made. The alloy for the parts visible on the outside of the sling shall be free from pits, scale (including red oxide), dents, nicks, cracks, deep scratches, segregations, and foreign inclusions that cannot be removed in later processing.

3.3.3 Lacquer. Lacquer shall be pale, clear, synthetic lacquer.

3.3.4 Hard solder. Hard solder shall be a nonferrous alloy having a melting point of not less than 1075°F.

3.3.5 Adhesive. The adhesive used for gluing together the parts indicated in Drawing No. 71C5040A0003 shall be natural or synthetic latex, natural or synthetic rubber solvent cement, or synthetic resin cements.

3.3.6 Pad. The pad shall be 1/4 to 3/8-inch thick wool felt, conforming to type I, classification 8R5 of C-F-206.

3.3.7 Thread. Sewing thread shall be 5 ply cotton, glazed finish, ticket number 10 conforming to type III B of V-T-276, or the thread may be 5 ply linen lockstitch twist conforming to type II, class 2 of A-A-50197. The color shall be bleached white.

3.4 Design. The sling shall be the U. S. Marine Corps design shown on Drawing Nos. 71C5040A0000 through 71C5040A0003.

Source: https://assist.dla.mil -- Downloaded: 202640-19T08:35Z
Check the source to verify that this is the currenversion before use.

3.5 Construction. The slings shall be made of the materials specified herein and constructed to include the components and construction details shown on Drawing Nos. 71C5040A0000 through 71C5040A0003 and as specified herein.

3.5.1 Stitching. Stitch type 301, 5 to 6 stitches per inch, conforming to FED-STD-751, shall be used for all stitching. Thread breaks in stitching shall be backstitched not less than 1 inch at each break. Stitching shall be backstitched at the ends to prevent raveling. Thread tension shall be maintained properly so that there will be no loose stitching and the lock will be embedded in the center of the materials sewed. All thread ends shall be trimmed. The triangular stitching joining the buckle straps to the carrying straps shall be commenced and finished in any one of the three sides of the triangle but not at any of the three points formed by the angles of the triangle.

3.5.2 Leather parts. Sliding keepers and front and back covers shall be assembled with the grain side of the leather to the outside of the sling. The straps shall be assembled so that the grain side of the leather is facing up when the sling is worn.

3.5.3 Gluing. Glued joints shall be securely bonded with the adhesive specified herein. NO adhesive shall appear upon any outside finished surface.

3.5.4 Soldering. Soldered parts shall be completely joined without excess solder and all excess flux shall be removed. The joints shall be clean, smooth, and strong without burned or reduced areas. The soldered joint shall withstand the test specified in Section 4, Table I.

3.5.5 Metal parts.

3.5.5.1 Finish. All outer surfaces and edges of metal parts visible on the outside of the sling shall be highly polished to a mirror-like finish free from dents, nicks, and scratches. All other surfaces and edges shall be clean, smooth, and free from burrs, drag, step, tool marks, sharp edges and corners, and roughness. Finishing shall not be carried to the point where the edges are excessively rounded or details of design fail to meet the requirements shown on Drawing Nos. 71C5040A0001 and 71C5040A0002 and as specified herein. The highly polished surfaces and edges shall have uniform gold color free from scale and shall match the approved sample for color and finish.

3.5.5.2 Lacquering. All highly polished surfaces and edges shall be thoroughly lacquered. The dry lacquer film shall be continuous, level, adherent, and free from lint, dust, and other foreign inclusions that may affect appearance or serviceability, and shall withstand the test for tackiness specified in Section 4, Table I.

3.6 Finished measurements. The finished sling shall conform to the measurements specified in Drawing No. 71C5040A0003.

3.7 Workmanship. The finished sling shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQL) (see 6.5).

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).
c. In-process inspection (see 4.4.2).

4.3 First article inspection. When first article is required, inspection shall be made of a completely fabricated sling for all provisions of this specification (see 6.2).

4.4 Quality conformance inspection. Inspection shall be performed in accordance with MIL-STD-105, except when otherwise specified herein.

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document. In addition to testing provisions contained in subsidiary specifications, figures and standards, testing shall be performed on components listed in Table I for characteristics noted. Wherever applicable, tests shall be conducted in accordance with FED-STD-311. All test reports shall contain the individual values utilized in expressing the final results. The sample size shall be as shown below, and the lot shall be unacceptable if one or more units fail to meet any requirements specified.

Lot Size	Sample Size
800 or less	2
801 up to and including to 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.

Table I Test Methods

Component and lot	Characteristic	Rqmt Para.	Test Method	No. Determinations per sample unit	Results reported as	Sample unit
Cowhide (sides)	Material Identification	3.3.1.1	Std Com'l	1	Pass or fail	1 - 8"X8" of leather from 15 sides
	Tannage 1/	3.3.1.1.1	Std Com'l	1	Pass or fail	
	Cracking	3.3.1.1.3	4011			
	Chloroform Extract	3.3.1.1.4	6341			
	Ash, total	3.3.1.1.4	6421			
	pH	3.3.1.1.4	6621			
	Shrinkage temperature	3.3.1.1.4	7011			
	Thickness	3.3.1.1.5	1021			
	Yellowing	3.3.1.1.6	4.4.1	1	Pass or fail	
	Color	3.3.1.1.6	Visual	1	Pass or fail	
	Crocking	3.3.1.1.6	3011			
Hardware (each)	Chemical composition 1/	3.3.2	Std Com'l	2	To nearest 0.1 percent	
	Soldered joints	3.5.4	4.4.2	1	Pass or fail	
	Finish	3.5.5.1	Visual	1	Pass or fail	
	Color	3.5.5.1	Visual	1	Pass or fail	
Adhesive (pint)	Material Identification 1/	3.3.5	Std Com'l	1	Pass or fail	
Lacquer (pint)	Material Identification 1/	3.3.3	Std Com'l	1	Pass or fail	
	Tackiness	3.5.5.2	4.4.3	1	Pass or fail	
Solder (lb)	Material Identification 1/	3.3.4	Std Com'l	1	Pass or fail	

1/ Accept on certificate of compliance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.

4.4.2 In-process inspection. In-process inspection will be performed during manufacturing of the sling to determine compliance with all required operations and processes which cannot be determined in the completely fabricated sling, and to assure that good workmanship has been employed. Particular attention should be paid to the cementing of leather and felt parts and to peening, swaging and soldering of metal components. Any deviation from requirements or poor workmanship found in in-process inspection may be cause for rejection of the end item or items.

4.4.3 Examination of the end item. The end item shall be examined for the defects listed in 4.4.3.1 and 4.4.3.2. The sample unit shall be one completely fabricated sling. The inspection level shall be II. (See 6.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT	CLASSIFICATION		
		MAJOR	MINOR	
			A	B
4.4.3.1 General defects. General defects shall be classified as follows:				
Finish of leather components and thread	a. Not specified finish or color (compare with approved sample).	101		
	b. Color not uniform.		201	
Metal components (applicable to those components that are visible in the item)	a. Not specified finish or color (compare with approved sample).	102		
	b. Not polished to a mirror-like finish.	103		
	c. Any pit, scale, oxide, dent, nick, tool mark, scratch or roughness, seriously affecting appearance. seriously.	104		
	d. Any pit, scale, oxide, dent, nick, tool mark, scratch or roughness, affecting appearance but not seriously.		202	
	e. Solder on exposed metal surface.	105		
	f. Excess polishing of metal parts which results in loss of detail to a degree seriously affecting appearance.	106		
	g. Excess polishing of metal parts which results in loss of detail, affecting appearance but not seriously.		203	
	h. Any component not coated with lacquer, area of no coating, lacquer runs or sags, gritty surface or imbedded foreign matter.		204	
	i. Lacquer coating tacky (when tackiness is evident, test in accordance with 4.4.1).		205	
Cleanliness	a. Any spot, stain or foreign matter that is clearly noticeable but can be readily removed with a cleaning agent.		206	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT	CLASSIFICATION		
		MAJOR	MINOR	
			A	B
	b. Any permanent type stain or spot clearly noticeable.	107		
Design	Any characteristic not in accordance with the specified requirements and approved sample.	108		
Material (General)	Any component not fabricated of the specified material.	109		
	a. Not full grain or not full grain lightly snuffed.	110		
	b. Deeply snuffed, i.e., fiber structure damaged.	111		
	c. Any hole, cut, rupture or deep scratch.	112		
	d. Any brand mark, grub hole, scar tissue, hip mark, brittle or bony area, abraded area or otherwise defective, seriously affecting serviceability or appearance.	113		
	e. Any brand mark, grub hole, scar tissue, hip mark, brittle or bony area, abraded area, shallow scratch or otherwise defective, affecting serviceability or appearance but not seriously.		207	
	f. Flanky, spongy or stretchy leather.	114		
	g. Fat wrinkles, seriously affecting serviceability	115		
	h. Fat wrinkles, affecting serviceability but not seriously.		208	
	i. Flesh side not smooth or contains loose flesh.		209	
Construction and workmanship (general) (applicable to all components and assemblies)	Any component missing.	116		
	a. Any part fractured, ripped, torn, punctured, malformed or otherwise damaged, seriously affecting serviceability.	117		

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT	CLASSIFICATION		
		MAJOR	MINOR	
			A	B
	b. Any part defective, affecting serviceability but not seriously.		210	
	c. Any operation omitted or not properly performed, seriously affecting serviceability.	118		
	d. Any operation omitted or not properly performed, affecting serviceability but not seriously.		211	
	e. Any part misplaced or not properly joined, resulting in distortion or otherwise impairing use of end item to a degree seriously affecting serviceability.	119		
	f. Any part misplaced or not properly joined, affecting serviceability but not seriously.		212	
Metal components assembly	a. Buckle reversed on assembly.	120		
	b. Escutcheon pin missing.	121		
	c. Escutcheon pin reversed on assembly.		213	
	d. Any escutcheon pin not sufficiently peened.	122		
	e. Binding screw missing.	123		
	f. Any threaded component stripped.	124		
	g. More than one binding screw not drawn tightly to assembly.		214	
	h. Strap tip not a flush fit to leather.	125		
	i. Cup assembly will not function as intended.	126		
	j. End of ball stud not swagged, i.e., cup can be screwed off stud.	127		
	k. Any screw or rivet head cocked on assembly.		215	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT	CLASSIFICATION		
		MAJOR	MINOR	
			A	B
Seams and stitching	1. Any sharp metal edge, burr or sliver.	128		
	a. Not specified seam or stitch type.	129		
	b. Any row of stitching missing.	130		
	c. Loose stitch tension, resulting in a loosely secured seam, or locks exposed on surface of leather.	131		
	d. Tight stitch tension, i.e., stitches rupture leather or may break in use of the end item.	132		
	e. Thread ends not trimmed throughout assembly.		216	
	f. End of any stitched row of thread break not backstitched.	133		
	g. Thread break in any row of stitching backstitched less than 1 inch.		217	
	h. Triangular stitching starts at any intersecting points of the triangle (see 3.5.1).		218	
	i. Two or more stitches per inch less than the minimum specified.	134		
	j. One stitch per inch less than the minimum specified.		219	
	k. Excessive number of stitches per inch, damaging leather.	135		
	l. More than the maximum number of stitches per inch, but not damaging leather.		220	
	m. Gage of stitching not within the specified tolerance or is irregular.		221	
	n. Any open seam.	136		

NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken, or two or more consecutive skipped stitches or run-offs occur.

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT	CLASSIFICATION		
		MAJOR	MINOR	
			A	B
Assembly	a. Front or back cover or strap not assembled so that the grain side of leather is up or on exterior side when sling is in the use position.	137		
	b. Strap keeper is not assembled with grain side of leather on exterior.		222	
	c. Any buckle tongue hole omitted on strap.		223	
	d. Strap keeper not formed with a lap joint.		224	
	e. Strap keeper is fixed on strap, i.e., not free to slide on strap.	138		
	f. Leather not smoothly formed over socket assembly, e.g., puckered loose, etc.	139		
	g. Contour of parts or formation of assembly not in accordance with drawing details, seriously affecting serviceability or appearance.	140		
	h. Contour of parts or formation of assembly not in accordance with drawing details, affecting serviceability or appearance but not seriously.		225	
Marking	Engraved inscription not in accordance with details evidenced in the approved sample.	141		

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the current version before use.

4.4.3.2 Dimensional examination. The sling shall be examined for defects in dimensions. Dimensional determination shall be performed to ascertain that all dimensions are in accordance with criteria specified in Drawing Nos. 71C5040A0000 through 71C5040A0003. Any dimension found that exceeds the applicable tolerance shall constitute a defect. The inspection level shall be S-3 (see 6.5).

4.4.4 Examination of packaging. An examination shall be made to determine compliance with packaging, packing, and marking requirements of Section 5 of this specification. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared with the exception that it not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the inspection lot. The inspection level shall be S-2 (see 6.5).

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing or not as specified. Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as incomplete wrapping and inadequate securing of tape, incomplete closure of container flaps, improper taping, loose strapping or inadequate stapling.
	Bulged or distorted container.
Content	Number of packages is more or less than required.
Weight	Net weight exceeds requirement.

4.4 Tests.

4.4.1 Test for "yellowing" of white leather. The leather shall be tested in accordance with Method 5660 of FED-STD-191.

4.4.2 Test for soldered joints. Samples to be tested shall be placed in an oven maintained at 1075°F ± 10°F for not less than 15 minutes. While at the specified temperature, the samples shall be lifted by the female binding screw without the soldered parts separating.

4.4.3 Test for tackiness. At room temperature (60° to 80°F) press a piece of tissue paper against the lacquered surface of the specimen for 30 seconds, using any pressure capable of being exerted by the thumb and two fingers. The tissue paper shall not adhere to the lacquered surface, but shall fall free when pressure is released.

Source: https://assist.dla.mil -- Downloaded: 20260-19T08:35Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. Packaging shall be level A or commercial as specified (see 6.2).

5.1.1 Level A. Slings shall be properly folded and well wrapped individually in kraft paper secured with gummed kraft paper tape. A gummed paper label shall be attached to each wrapped sling listing the stock number, contract number and name of contractor.

5.1.2 Commercial. Slings shall be packaged in accordance with manufacturer's commercial practice.

5.2 Packing. Packing shall be level B or commercial as specified (see 6.2).

5.2.1 Level B. Ten (10) slings, packaged as specified in 5.1.1, shall be packed in a fiberboard shipping container with liner conforming to CF, class domestic, variety SW, size 2A of MIL-B-17757 and assembled, closed and reinforced as specified in the box specification. The fiberboard used in fabricating the box and liner shall be grade 275 and 200 respectively. Each container shall have the contents completely covered on the top and bottom with a sheet of commercial grade kraft paper.

5.2.2 Commercial. Slings packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination. Containers shall be in accordance with Uniform Freight Classification Rules, or regulations of other carriers applicable to the mode of transportation.

5.3 Marking. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with the requirements of MIL-STD-129.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.

6.1 Intended use. The slings covered by this specification are intended for carrying a flagstaff.

6.2 Acquisition requirements. Acquisition documents should specify the following:

(a) Title, number and date of this specification.
(b) Whether first article is required (see 3.2).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(d) Acceptance criteria required (see 6.5).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209 and the requirements of this specification. The sample(s) presented for inspection may be first articles, preproduction samples, first production of sample(s) taken from the first lot depending on the contractors history and will be as directed by the Contracting

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the currentversion before use.

Officer. The Contractor Officer should include specific instructions in all acquisitions instructions regarding arrangements for selection, inspection, and approval of the first article.

6.4 Standard sample and shade sample. For information regarding the availability of standard samples and standard shade specified, address inquiry to acquiring activity issuing the invitation for bids.

6.5 Acceptance criteria. The acceptance criteria below are recommended for use. The acceptance criteria as specified in the contractor or purchase order shall be binding. Unless otherwise specified, the following acceptance criteria are in accordance with MIL-STD-105.

6.5.1 For end item visual examination. An acceptance quality level (AQL), expressed in terms of defects per hundred units, of 2.5 for major defects and 6.5 for total (major and minor) combined defects is recommended.

6.5.2 For end item dimensional examination. An AQL, expressed in terms of defects per hundred units, of 2.5 is recommended.

6.6 Subject term (key word) listing.

Flag
Marine Corps

6.7 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Preparing activity:
Navy - MC
Project No. 8345-N179

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-21042C(MC)	SLING, FLAGSTAFF: LEATHER, WHITE; WITH BRASS SOCKET

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
3b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	8. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
7b. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	9. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426

PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 202610-19T08:35Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commanding General
Marine Corps Research, Development
and Acquisition Command, Code PSE-C
Washington, D.C. 20380-0001

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:35Z
Check the source to verify that this is the current version before use.