MIL-B-36341A (DSA-DM)
27 May 1975
SUPERSEDING
MIL-B-36341 (DM)
4 December 1964

MILITARY SPECIFICATION

BURET, GAS, 100 ml.

This limited coordination Military specification has been prepared by the Defense Personnel Support Center based upon currently available technical information, but it has not been approved for promulgation as a coordinated revision of Military Specification MIL-B-36341 (DM) It is subject to modification However, pending its promulgation as a coordinated Military specification, it may be used in procurement

1. SCOPE

1.1 This specification covers one type of straight gas buret.

2. APPLICABLE DOCUMENTS

2.1 Specifications, standards and drawing. The following documents, of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

DD-G-541	Glass (Laboratory).
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner
PPP-B-636	Box, Shipping, Fiberboard.

Military

MIL-L-10547	Liners, Case and Sheet, Overwrap; Water-Vaporproof, or Waterproof, Flexible.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage

FSC 6630

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:26Z
Check the source to verify that this is the current version before use.

DRAWING

Defense Personnel Support Center

DPSC Drawing No. 20723	Buret, Straight

(Copies of specifications, standards and drawings required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer)

2 2 Other publications The following documents form a part of this specification to the extent specified herein Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM Designation C148	Tentative Methods of Polariscopic Examination of Glass Containers.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

U.S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

Commercial Standard CS21	Interchangeable Taper--Ground Joints, Stopcocks, Stoppers and Spherical-Ground Joints.
NBS Circular 602	Testing of Glass Volumetric Apparatus.

(Application for copies, accompanied by money order, coupon or check, should be addressed to the Superintendent of Documents, U S Government Printing Office, Washington, DC 20402 Price may be obtained from the Superintendent of Documents

3 REQUIREMENTS

3 1 Material Buret shall be borosilicate glass conforming to DD-G-541 Type I, class A or B

3 2 Construction Buret shall be constructed in accordance with Drawing No. 20723. Any cross section of the graduated portion of the inlet and outlet tubes taken in a plane perpendicular to their longitudinal axes shall be circular Thickness of walls of the graduated portion and inlet and outlet tubes shall be as specified on the drawing, where not specified, thickness shall be 1 6 $\pm$ 0 4 millimeters

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:26Z
Check the source to verify that this is the currentversion before use.

(mm.) Dimensions, shape and markings of stopcock shall be in accordance with Commercial Standard CS21, stopcock designation 2, double oblique bore

3.3 Marking. Markings shall be permanent and shall be engraved, etched and filled with pigment, or stained and fired in The appearance of filled, etched and stained markings shall not change when tested as specified in 4 4 1 Engraved markings need not be tested

3 3 1 Graduation markings Graduation markings shall be sharply defined lines of uniform width (maximum 0 3 mm) Graduation markings shall be perpendicular to the vertical axis of the buret and parallel to each other Graduations shall be legibly numbered, as shown on the drawing.

3.3 2 Identification marking. Burets shall be legibly and permanently marked with the manufacturer's name or registered trademark.

3.4 Annealing. Annealing of buret shall be such that there is no severe strain. When tested as specified in 4.4 2, ring strain shall not exceed a temper No. 1, and any longitudinal strain shall be faint and diffused.

* 3.5 Capacity accuracy. The accuracy of the buret shall comply with the following subparagraphs for total volume and partial volume.

* 3.5.1 Total volume. The buret shall deliver 100 milliliters (ml) ± 5 ml., when tested as specified in 4.4.3

* 3.5.2 Partial volume. The accuracy of each graduation, as a percentage of the total volume, shall be within the following tolerances when tested as specified in 4.4.3:

Graduations	Tolerances (%)
0-2	0 025
2-10	0 25
10-91	2 50
91-99	0 25
99-100	0 025

3 6 Leakage Stopcock shall not leak when tested as specified in 4 4 4

3 7 Workmanship Workmanship shall be first class throughout Burets shall be free from defects which detract from their appearance or may impair their serviceability

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:26Z
Check the source to verify that this is the current version before use.

4 QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Records Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate

* 4 1 2 Inspection Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item

* 4 1.3 Certificate of quality Certificate of quality, supplied by the manufacturer of the glass, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the Item Identification, the name of the material, the lot number, the lot size the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and Table I. The unit of product shall be one buret

* Table I Sampling for examination

	Inspection level	AQL (percent defective)
For visual examination		
Major defects	II	2 5
Minor defects	II	4 0
For dimensional examination	S-1	2 5

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:26Z
Check the source to verify that this is the current version before use.

4.2.2 For tests Sampling for tests shall be conducted in accordance with MIL-STD-105 and Table II. The unit of product shall be one buret Acceptance number shall be zero

Table II Sampling for tests

Characteristic	Requirement	Test procedure	Inspection level
Permanency of marking	3 3	4 4.1	S-2 *
Strain	3 4	4 4 2	S-4
Capacity	3.5	4 4 3	S-1
Leakage	3 6	4 4 4	S-2

* Sample shall be divided by three for separate performance of tests described in 4.4 1 1, 4 4 1.2 1 and 4 4 1 2 2

4 3 Examination. The burets shall be examined to determine compliance with all requirements contained in this specification. Examination shall be conducted in accordance with but not limited to the defects listed in Table III:

Table III Classification of defects

Category	Defects
Major	
101	Component part missing
102	Buret not free of sharp edges.
103	Buret not free of cracks
104	Buret not free of chips.
105	Buret not free of protrusions
106	Graduation, capacity, calibration or taper size markings not complete, correct or legible.
107	Lubricated stopcock does not turn in barrel without binding
Minor	
201	Buret not free of bubbles
202	Buret not free of scratches
203	Manufacturer's name or registered trademark not complete, correct or legible

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:26Z
Check the source to verify that this is the currentversion before use.

4.3.1 Dimensional examination. The burets shall be examined for defects in dimensions (see 3.2). Any dimension not within the tolerance specified herein shall be classified as a defect.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Permanency of marking.

4.4.1.1 Resistance to alkali. The buret, with stopcock removed, shall be completely immersed in 1N sodium hydroxide solution at room temperature, covered, boiled for 1/2 hour, and allowed to stand in the alkali for an additional 1 hour. The buret shall then be removed, thoroughly rinsed with distilled water and dried by rubbing vigorously with a cloth.

4.4.1.2 Resistance to acid.

4.4.1.2.1 Hydrochloric acid. The buret shall be completely immersed in concentrated hydrochloric acid (specific gravity 1.18) at room temperature, covered boiled for 1/2 hour, and allowed to stand in the acid for an additional 1 hour. The buret shall then be removed, thoroughly rinsed with distilled water, and dried by rubbing vigorously with a cloth.

4.4.1.2.2 Sulfuric acid. The buret shall be completely immersed in concentrated sulfuric acid (specific gravity 1.84) at room temperature and allowed to stand 1 hour. The buret shall then be removed, thoroughly rinsed with distilled water, and dried by rubbing vigorously with a cloth.

4.4.2 Strain. Buret shall be tested for strain in accordance with ASTM Designation C148, method A or B.

4.4.3 Capacity accuracy. Determination of capacity accuracy shall be made in accordance with the techniques and procedures of NBS Circular 602 for 20° Centigrade (°C.). After cleaning (paragraph 3.3 of NBS Circular 602), a buret stopcock shall be connected to the bottom of the buret by means of rubber tubing. The tubing shall be as short as possible to minimize the movement of the stopcock. The size of the tip of the stopcock shall restrict the rate of outflow of the buret for the graduated length to not more than 3 minutes or less than 70 seconds. Testing of the graduations shall be performed in accordance with 3.5 of NBS Circular 602. The first measurement shall be the total volume from the 100 mark to the "0" mark. Subsequent determinations shall measure the following capacities:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:26Z
Check the source to verify that this is the current version before use.

99 5 to 0
95 0 to 0
50 0 to 0
6 0 to 0
1.0 to 0

The volume at each determination shall be calculated as a percentage of the total volume (the first measurement) and compared with tolerances specified in 3 5

4 4.4 Leakage Leakage through the stopcock shall be tested with no lubricant on the barrel and plug. Plug shall be wetted with water and inserted in the barrel in the open position and turned 90° to a firm set. A vacuum of 25 inches of mercury shall be applied across the stopcock for a period of 1 minute. Evidence of leakage shall be the movement of liquid, possibly accompanied by the appearance of dry areas on the ground surfaces.

* 4.5 Examination for preparation for delivery. An examination shall be made to determine whether the packaging, packing and marking comply with the requirements of Section 5. Defects shall be scored as specified in Table IV. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2, and the acceptable quality level shall be 4.0 (defects per hundred units)

* Table IV Examination for preparation for delivery

Examination	Defects
Containers	Not as specified
Quantity	Quantity in interior packages and shipping containers not as specified
Packaging and packing quantities	Any component missing or damaged
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, tape improperly applied, or containers distorted
Markings	Omitted, incorrect, illegible, improper size, location, sequence or method of application.

* 5 PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be Level A or C as specified (see 6.1).

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:26Z
Check the source to verify that this is the current version before use.

5.1 1 Level A.

5 1.1.1 Unit package. Each buret shall be packaged in a box of appropriate size constructed in accordance with PPP-B-636, class domestic, style optional. Box design shall include diecut or molded polystyrene or polyurethane fittings so designed as to prevent movement and to support the buret equally on all surfaces. Closure of box shall be adequate to prevent accidental opening

5 1 2 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose

5 2 Packing. Packing shall be Level A, B or C as specified (see 6 1)

5 2 1 Level A Two burets shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-601, overseas type, PPP-B-621, class 2, or PPP-B-636, class weather-resistant, grade V3c Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.1.1 Case liners. Each Level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto Case liner shall not be required for fiberboard boxes. Fiberboard box shall be waterproof in accordance with the appendix of PPP-B-636

5.2.2 Level B. Two burets shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-601, domestic type; PPP-B-621, class 1, or PPP-B-636, type CF, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5 2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size and kind commonly used for the purpose, constructed so as to insure acceptance and safe delivery called for in the box specification.

5.3 Marking.

5 3 1 Unit package and exterior container Each unit package and exterior container shall be marked in accordance with MIL-STD-129 Marking shall include the legend: "GLASS--HANDLE WITH CARE "

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:26Z
Check the source to verify that this is the current version before use.

6 NOTES

6 1 Ordering data Procurement documents should specify the following

a. Title, number and date of this specification
b Applicable National Stock Number (NSN)
c Applicable levels of packaging and packing (see 5.1 and 5.2).

6.2 This specification covers the following item as listed in the Federal Supply Catalog

National Stock No.	Item Identification
6630-00-490-1731	BURET, GAS, 100 ml

6.3 The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue

Custodians
Army - MD
Navy - MS
Air Force - 03

Preparing activity
Defense Supply Agency - DM

Project No 6630-0242
1S

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No 22-R255

INSTRUCTIONS The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay or will otherwise enhance use of the document DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government Fold on lines on reverse side, staple in corner, and send to preparing activity Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements Attach any pertinent data which may be of use in improving this document If there are additional papers, attach to form and place both in an envelope addressed to preparing activity

DOCUMENT IDENTIFIER AND TITLE

MIL-B-36341A (DSA-DM)

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1 HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A GIVE PARAGRAPH NUMBER AND WORDING

B RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2 COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3 IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4 REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

GPO 1974 - 603 680 6126 2 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:26Z
Check the source to verify that this is the current version before use.

FOLD

Defense Personnel Support Center
2800 South 20th Street
Philadelphia, PA 19101

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD 304



Commander
Defense Personnel Support Center
ATTN DPSC-ATT
2800 South 20th Street
Philadelphia, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:26Z
Check the source to verify that this is the current version before use.