MIL-C-36332B
25 February 1977
SUPERSEDING
MIL-C-36332A
20 April 1972 and
MIL-C-36332
19 November 1964

MILITARY SPECIFICATION

CASE, SPECTACLE, ENVELOPE TYPE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers an envelope type spectacle case, suitable for carrying standard plastic frame spectacles and aircrew glasses.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of the specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-676 - Boxes, Set-Up.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Hq, Defense Personnel Support Center, ATTN: Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6540

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:25Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-E-5272 - Environmental Testing, Aeronautical and Associated Equipment, General Specification for.
MIL-L-10547 - Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.
MIL-G-25948 - Glasses, Sun, HGU-4/P (With Case).
MIL-S-36497 - Spectacle, Fronts and Temples, Cellulose Acetate.

STANDARDS

FEDERAL

FED-STD-406 - Plastics: Methods of Testing.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for shipment and storage.

DRAWING

Defense Personnel Support Center (DPSC)

20881 - Case, Spectacle, Envelope Type.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

Designations

D 618 - Conditioning Plastics and Electrical Insulating Materials for Testing.
D 638 - Method of Test for Tensile Properties of Plastics (Tentative).
D 651 - Method of Test for Tensile Strength of Molded Electrical Insulating Materials.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:25Z
Check the source to verify that this is the current version before use.

D 792 - Methods of Test for Specific Gravity and Density of Plastics (Tenative).
D 882 - Tensile Properties of Thin Plastic Sheeting (Tentative).
D 1203 - Loss of Plasticizer from Plastics (Activated Carbon Methods) (Tenative).
D 1204 - Measuring Changes in Linear Dimensions of Nonrigid Thermoplastic Sheeting or Film.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Materials. Except as specified herein, materials shall conform to the applicable portions of the specifications, standards, and drawing listed in section 2, and be subjected to the tests and meet the requirements specified therein. When materials to be used are not specifically designated, those used shall be of the highest commercial quality, and entirely suitable for the purpose intended.

3.1.1 Plastic case covering. The plastic sheeting for the carrying case shall be flexible polyvinyl chloride plastic. It shall be 100 percent virgin material. Reprocessed material shall not be used. The color of the plastic shall be black. The outer surface of the case shall have a simulated natural grain leather finish.

3.1.1.1 Thickness. The thickness of the plastic sheeting shall be 0.032 inch thick $\pm$ 10 percent. The thickness shall be measured as specified in 4.4.1.1.1.

3.1.1.2 Fungus resistance. The plastic sheeting shall be fungus resistant when tested as specified in 4.4.1.2.

3.1.1.3 Tensile strength and ultimate elongation. The plastic sheeting shall have a minimum tensile strength of 2300 pounds per square inch (psi) when tested as specified in 4.4.1.3. The minimum ultimate elongation shall be 200 percent in any direction when tested as specified in 4.4.1.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:25Z
Check the source to verify that this is the current version before use.

3.1.1.4 Tear resistance. The minimum tear resistance (Graves) of the plastic sheeting shall be 400 pounds per inch thickness when tested in accordance with the method specified in 4.4.1.4.

3.1.1.5 Plasticizer volatility. The maximum loss in weight based on the initial weight shall be not more than 3 percent when tested at a temperature of 70° ± 2° Centigrade (C.) for 24 hours as specified in 4.4.1.5.

3.1.1.6 Cold crack. The plastic sheeting shall show no evidence of cracking when tested at a temperature of 0° ± 3.6° Fahrenheit (F.) as specified in 4.4.1.6.

3.1.1.7 Identification of case covering. The plastic sheeting used for the case covering shall ignite with difficulty; shall burn, but extinguish itself upon removal from the flame, shall have an acrid odor, and shall burn with green spurts, when tested as specified in 4.4.1.7.

3.1.1.8 Dimensional stability (shrinkage). The plastic sheeting shall not have more than 5 percent shrinkage when tested in accordance with the method specified in 4.4.1.8.

3.1.2 Snap fastener. The case shall be secured by a snap fastener which shall have a 16 line (0.40) inch cap, solid stud, with flanged underpart of suitable width for the purpose intended. The snap fastener shall be brass or steel, nickel-plated. The cap shall be painted with an enamel of a color to match the color of the plastic for the case.

3.1.3 Plastic case insert. The plastic case insert shall be molded of medium impact styrene plastic material entirely suitable for the purpose intended, with the following properties:

Tensile strength	4,800 - 5,800 psi
Specific gravity	1.05 - 1.07

The material shall be tested in accordance with the method specified in 4.4.2.

3.1.4 Identification card. The identification card shall be heavy white paper, suitable for the purpose intended.

3.2 Construction.

3.2.1 Case covering. Construction of the case covering shall be of the material specified and shall conform to Defense Personnel Support Center (DPSC) Drawing No. 20881. The edge that forms the pocket for the case insert shall be properly heat-sealed. The top edge shall extend slightly above the insert so that the front of the insert is not visible from the open case front. The case shall be of the envelope type with closed ends and shall be secured by a snap fastener. When snap fastener is closed, the end of the flap shall not project beyond the bottom of the case.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:25Z
Check the source to verify that this is the current version before use.

3.2.2 Case insert. The case insert shall be of the overall dimensions as shown on the drawing and shall be capable of holding the aircrew sun glasses, HGU-4/P, as specified in MIL-G-25948, as well as the assembled plastic fronts and temples as specified in MIL-S-36497. The center reinforcements of the plastic insert case shall have single or double reinforcements. The insert may have ribs on the back surface provided the requirements specified above are met.

3.2.3 Identification card. The identification card shall conform to the drawing for marking and dimensions. The size of the marking shall be entirely suitable for the purpose intended and shall be permanent and legible.

3.2.4 Assembly. The front surface of the insert shall be bonded to the inside of the pocket of the covering case. The identification card shall be placed in the case behind the insert.

3.3 Workmanship. Workmanship shall be first class throughout. Cases shall be well made. Snap fasteners shall be properly set. The finished cases shall be uniform in color, texture, and finish. The cases shall be free from dirt, perforations, pits, cracks, holes, blisters, cuts, tears, oil, foreign matter, bubbles, or other defects which detract from their appearance or may impair their serviceability. The occurrence of defects shall not exceed the limits set by the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:25Z
Check the source to verify that this is the current version before use.

4.1.2 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.3 Certificate of quality. Certificates of quality supplied by the manufacturer of the components or materials may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the National Stock Number (NSN), the name of the component material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and specification requirements.

4.2 Sampling.

* 4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and as indicated in table I. The unit of product shall be one case.

TABLE I. Sampling criteria for examination.

Type of defect	Inspection level	AQL (percent defective)
Major A	S-3	1.0
Major B	II	1.0
Minor	II	2.5
Dimensional	S-3	2.5

* 4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and as indicated in table II. Where possible, the same sample unit shall be used for the determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:25Z
Check the source to verify that this is the currentversion before use.

TABLE II. *Sampling criteria for tests.*

Characteristics	Requirement	Test procedure	Sample unit	Inspection level	AQL (percent defective)
Plastic case covering:					
Identification	3.1.1.7	4.4.1.7	Yard	S-1	2.5
Thickness	3.1.1.1	4.4.1.1.1	Yard	S-1	2.5
Fungus resistance	3.1.1.2	4.4.1.2	Yard	S-1	2.5
Tensile strength	3.1.1.3	4.4.1.3	Yard	S-1	2.5
Ultimate elongation	3.1.1.3	4.4.1.3	Yard	S-1	2.5
Tear resistance	3.1.1.4	4.4.1.4	Yard	S-1	2.5
Plasticizer volatility	3.1.1.5	4.4.1.5	Yard	S-1	2.5
Cold crack	3.1.1.6	4.4.1.6	Yard	S-1	2.5
Color	3.1.1	Visual	Yard	S-1	2.5
Dimensional stability (shrinkage)	3.1.1.8	4.4.1.8	10 inch square	S-1	2.5
Plastic case insert:					
Tensile strength	3.1.3	4.4.2.1	Test specimen	S-1	2.5
Specific gravity	3.1.3	4.4.2.2	Test specimen	S-1	2.5

4.3 Examination. The spectacle cases shall be examined to determine compliance with all requirements contained in this specification.

4.3.1 Examination for defects in dimensions. Any dimension not within the specified tolerance shall be classified as a defect.

4.3.2 Classification of defects. Examination shall be conducted in accordance with, but not restricted to, the following classification of defects. Additional defects shall be classified in accordance with MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:25Z
Check the source to verify that this is the current version before use.

TABLE III. Classification of defects.

Categories	Defects
Major A	
101	Case is not the style and design specified.
Major B	
151	Heat seal that forms the case pocket is not continuous along the edge.
152	Case is not free of cuts, cracks, blisters, tears, and holes.
153	Case is not free of dirt, oil, and other foreign matter.
154	Snap fastener is loosely set.
155	Male and female elements of snap fastener are improperly aligned.
156	Snap fastener does not open and close satisfactorily.
157	Case insert not bonded to the front inside surface of the carrying case pocket.
Minor	
201	Heat seal is uneven with ragged edges.
202	Enamel finish of snap fastener does not match the color of the plastic case.
203	Enamel finish of snap fastener is not free of peeled and blistered areas.
204	Finish of plastic sheeting not as specified.
205	Identification card missing.

* 4.3.3 Packaging inspection. The inspection of the intermediate package, packing and marking for shipment and storage shall be in accordance with quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Tests for plastic sheeting.

4.4.1.1 Standard conditioning. Unless otherwise specified, samples for test shall be conditioned at a temparature of 73.5 $\pm$ 2° F., and a relative humidity of 50 $\pm$ 4 percent for a period of not less than 16 hours.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:25Z
Check the source to verify that this is the currentversion before use.

4.4.1.1.1 Thickness. The thickness shall be determined from five uniformly spaced readings taken across the width of the sheet. The gage used for the measurement of thickness shall be a dead-weight type equipped with a dial graduated to read directly to 0.0001 inch. The presser foot shall be circular with a diameter of 0.25 ± 0.01 inch. The presser foot and moving parts connected therewith shall be weighted so as to apply a total load of 3 ± 0.1 ounce to the specimen. The presser foot and anvil surface shall be plane to within 0.0001 inch and parallel to each other within 0.001 inch. The referee test method for thickness shall be the method specified in 4.4.1.1.2.

4.4.1.1.2 Average thickness (weight method).

4.4.1.1.2.1 Apparatus.

(a) Analytical balance, equipped with pan straddle or other stationary support, sensitive to 0.0005 gram (gm).
(b) Class S. weights.
(c) Beaker, 250 milliliters.
(d) Five nonabsorbant thread or wire.
(e) Thermometer, 0° to 100°C., graduated in 1° divisions.
(f) Die or template, for cutting test specimens, 10 centimeter (cm) by 10 cm, with a dimensional tolerance of ± 0.01 cm per side.
(g) Sharp knife or razor.

4.4.1.1.2.2 Test specimens. Five 10 cm by 10 cm specimens taken uniformly across the width of the sheet shall be tested.

4.4.1.1.2.3 Test conditions. The specimens shall be conditioned and tested in accordance with procedure A of ASTM Designation D 618.

4.4.1.1.2.4 Procedure. By means of the die or template and the sharp knife or razor, cut five specimens from the sample of material. Weigh each specimen to the nearest 0.5 milligram (mg) on the analytical balance. Record the weight as W. Following the procedure of ASTM Designation D 792, method A, determine the specific gravity of each specimen and record as D. Use of a wetting agent is recommended.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:25Z
Check the source to verify that this is the currentversion before use.

4.4.1.1.2.5 Calculations. Calculate the average thickness of each test specimen, using the following formula, and average the five values:

$$T = \frac{394\ W}{100\ D} = 3.94\ \frac{W}{D}$$

T = average thickness of test specimen in mils.
W = weight of test specimen in gm.
D = Density of test specimen in gm/cc/specific gravity = density in metric units.
394 = Conversion factor, cm to mils.
100 = area of specimen in sq sm.

4.4.1.2 Fungus resistance. The plastic sheeting shall be tested in accordance with procedure I of the fungus-resistance tests as specified in MIL-E-5272.

4.4.1.3 Tensile strength and ultimate elongation. Tensile strength and ultimate elongation shall be determined as specified in method B of ASTM Designation D 882. No autographic stress-strain curve is needed. The test specimens shall be 1 inch wide.

4.4.1.4 Tear-resistance Graves. The tesr-resistance (Graves) shall be determined in accordance with method 1121 of FED-STD-406.

4.4.1.5 Plasticizer volatility. The plasticizer volatility shall be determined in accordance with ASTM Designation D 1203.

4.4.1.6 Cold crack.

4.4.1.6.1 Apparatus. Apparatus shall consist of a cold chamber capable of maintaining the required temperature within 2°C. (3.6°F.) for the required time; a steel roller, approximately 5-1/2 inches in diameter, approximately 2 inches wide, with a suitable hand guide (the total weight of roller and guide shall be 10 pounds), and a pair of gloves.

4.4.1.6.2 Test specimen. The specimen shall be a square of plastic not less than 8 by 8 inches. Three specimens shall be taken for test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:25Z
Check the source to verify that this is the current version before use.

4.4.1.6.3 Procedure. The specimen shall be exposed at a temperature of $0^{\circ} \pm 3.6^{\circ}$F. for 1 hour. Without being removed from the specified temperature conditions, the specimen shall be creased 180° in the center of the machine and transverse directions, respectively, by folding slightly while lying on a flat smooth surface and running the center of the steel roller over the fold a single time. The specimen shall be opened between the two creasing operations. The pressure on the specimen shall be the weight of the roller. The temperature of the roller shall be the same as that of the specimen. The specimen shall be handled with gloves and care taken that its temperature remains uniform throughout the test. After the test, the sample shall be examined visually at room temperature. The plastic material shall show no evidence of cracking.

4.4.1.7 Identification.

4.4.1.7.1 Materials required to perform the identification test are as follows:

(a) Bunsen flame.
(b) Tongs.
(c) Sample of plastic sheeting (3 inches or more long).
(d) Piece of copper wire.

4.4.1.7.2 Procedure. Heat the copper wire in a Bunsen flame until it no longer imparts a green tinge to the flame. Hold the sample of plastic sheeting together with the copper wire at the edge of flame until sheeting ignites. Observe for characteristics described in 3.1.1.7.

4.4.1.8 Dimensional stability (shrinkage). The change in linear dimensions of the plastic sheeting shall be determined in accordance with ASTM Designation D 1204.

4.4.2 Tests on plastic case insert.

4.4.2.1 Tensile strength. The case insert shall be tested for tensile strength in conformance with ASTM Designation D 638 and D 651.

4.4.2.2 Specific gravity. The case insert shall be tested for specific gravity in conformance with ASTM Designation D 792.

* 5. PACKAGING

5.1 Packaging. Packaging shall be level A or C, as specified (See 6.2)

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:25Z
Check the source to verify that this is the current version before use.

5.1.1 Unit of issue. One (1) case, as specified, constitutes one unit of issue.

5.1.2 Level A.

5.1.2.1 Unit package. Each case shall be inserted in a snug fitting, clear-plastic bag or a kraft bag. Closure of the bag shall be adequate to prevent spilling of contents under normal handling.

5.1.2.2 Intermediate package. Intermediate package shall be a box of appropriate size constructed in accordance with PPP-B-676 or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.1.3 Level C. Cases shall be clean, dry and individually packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C, as specified (See 6.2).

5.2.1 Level A. Twenty four intermediate packages (576 units) shall be packaged in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP PPP-B-621, class 2; or PPP-B-636, class weather-resistant. Closure and strapping shall be as specified in the appendix of the applicable box specifications.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Each fiberboard box shall be waterproofed as specified in the appendix of the box specification.

5.2.2 Level B. Twenty four intermediate packages (576 units) shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; pr PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. The packaged cases shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:25Z
Check the source to verify that this is the current version before use.

5.3 Marking. Each unit, intermediate and exterior container shall be marked as specified in MIL-STD-129. When plastic bags are used for the unit package, marking may be printed on a label and inserted in the bag in such a manner so as to permit ready identification.

5.3.3 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) National Stock Number.
(c) Selection of applicable levels of packaging and packing (See 5.1 and 5.2).

6.2 National Stock Number coverage. The spectacle case covered by this specification is listed in the Federal Supply Catalog under the following stock number:

National Stock Number	Item Identification
6540-00-735-5157	CASE, SPECTACLE, ENVELOPE TYPE

* 6.3 Changes. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the previous issue.

Custodians:
Army - MD
Navy - DM
Air Force - 03

Preparing activity:
Defense Logistics Agency-DM

Project No. 6540-1051

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:25Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD - 304

U.S. MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:25Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL-C-36332B CASE, SPECTACLE, ENVELOPE TYPE

NAME OF ORGANIZATION AND ADDRESS	CONTRACT NUMBER
	MATERIAL PROCURED UNDER A ☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*	TELEPHONE NO.
	DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:25Z
Check the source to verify that this is the current version before use.