MILITARY SPECIFICATION

CASE, SPECTACLE, ENVELOPE TYPE; SOFT FABRIC LINING

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers an envelope type spectacle case with soft nylon cloth or rayon flocked lining.

1.2 Classification. Cases covered by this specification shall be of one type and class.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposals form a part of the specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

L-P-394	- Plastic Molding Material, Polypropylene, Injection and Extrusion.
V-T-295	- Thread, Nylon.
PPP-B-566	- Boxes, Folding, Paperboard.
PPP-B-585	- Boxes, Wood, Wirebound.
PPP-B-601	- Boxes, Wood, Cleated-Plywood.
PPP-B-621	- Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-B-676	- Boxes, Set-Up, Paperboard.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Headquarters, Defense Personnel Support Center, ATTN: Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-E-5272 - Environmental Testing, Aeronautical and Associated Equipment, General Specification for.
MIL-L-10547 - Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.
MIL-G-25948 - Sunglasses, HGU-4/P (With Case).
MIL-S-36497 - Spectacle, Fronts and Temples.

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods.
FED-STD-406 - Plastics: Methods of Testing.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

DRAWING

Defense Personnel Support Center (DPSC).

23244 CASE, SPECTACLE, ENVELOPE TYPE, SOFT LINING.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 618 - Conditioning Plastics and Electrical Insulating Materials for Testing.
D 638 - Method of Test for Tensile Properties of Plastics (Tentative).
D 651 - Methods of Test for Tensile Strength of Molded Electrical Insulating Materials.
D 792 - Methods of Test for Specific Gravity and Density of Plastics (Tentative).
D 882 - Tensile Properties of Thin Plastic Sheeting (Tentative).

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

D 1203 - Loss of Plasticizer from Plastics (Activated Carbon Methods) (Tentative).
D 1204 - Measuring Changes in Linear Dimensions of Nonrigid Thermoplastic Sheeting or Film.
D 1564 - Standard Methods of Testing Slab Flexible Urethane Foam.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Materials. Except as specified herein, materials shall conform to the applicable portions of the specifications, standards, and drawing listed in section 2, and be subject to the tests and meet the requirements specified therein. When materials to be used are not specifically designated, those used shall be of the highest commercial quality, and entirely suitable for the purpose intended.

3.1.1 Plastic case exterior. The plastic sheeting for the carrying case shall be flexible polyvinyl chloride plastic. It shall be 100 percent virgin material. Reprocessed material shall not be used. The color of the plastic shall be black. The outer surface of the case shall have a simulated natural grain leather finish.

3.1.1.1 Thickness. The thickness of the plastic sheeting shall be 0.018 ± .002 inch. The thickness shall be measured as specified in 4.4.1.1.1.

3.1.1.2 Fungus resistance. The plastic sheeting shall be fungus resistant when tested as specified in 4.4.1.2.

3.1.1.3 Tensile strength and ultimate elongation. The plastic sheeting shall have a minimum tensile strength of 2300 pounds per square inch (psi) when tested as specified in 4.4.1.3. The minimum ultimate elongation shall be 200 percent in any direction when tested as specified in 4.4.1.3.

3.1.1.4 Tear resistance. The minimum tear resistance (Graves) of the plastic sheeting shall be 400 pounds per inch thickness when tested in accordance with the method specified in 4.4.1.4.

3.1.1.5 Plasticizer volatility. The maximum loss in weight based on the initial weight shall be not more than 3 percent when tested at a temperature of $70^{\circ} \pm 2^{\circ}$ Centigrade ($^{\circ}C$) for 24 hours as specified in 4.4.1.5.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

3.1.1.6 Cold crack. The plastic sheeting shall show no evidence of cracking when tested at a temperature of $0^{\circ} \pm 3.6^{\circ}$ Fahrenheit ($^{\circ}F$) as specified in 4.4.1.6.

3.1.1.7 Identification of case covering. The plastic sheeting used for the case shall be ignited; shall burn, but extinguish itself upon removal from the flame, shall have an acrid odor, and shall burn with green spurts, when tested as specified in 4.4.1.7.

* 3.1.1.8 Dimensional stability (shrinkage). The plastic sheeting shall not have more than 5 percent shrinkage when tested in accordance with the method specified in 4.4.1.8.

3.1.2 Snap fastener. The case shall be secured by a snap fastener consisting of a male and a female half. The male fastener shall be a solid stud, nickel plated brass with flanged or flared underpart to hold stud in place. The female component shall be a cap and socket. The cap shall be 16 line size (0.40 inch) and painted black enamel to match the case color. The socket shall permit firm engagement of the stud and still allow disengagement with reasonable force.

3.1.3 Plastic case insert. The plastic case insert shall be molded of medium or high impact polystyrene or of polypropylene plastic. The polystyrene shall conform to the following properties, when tested as specified in 4.4.2:

Tensile strength, psi, minimum	1500
Specific gravity at 23° C	1.05 to 1.07

Polypropylene shall conform to L-P-394, Type I. Color of the insert shall be natural or black.

3.1.4 Foam. The foam for the padding shall be open pore polyurethane, polyester type, conforming to the following characteristics:

Color	charcoal
Density	1.5 to 1.9 pounds/cu. ft.
Tensile strength, psi, minimum	20
Tear strength, pounds/inch, minimum	3.0
Compression set, percent, maximum	7

3.1.5 Lining. The lining for the case shall be either a soft finish nylon tricot knit or a soft high pile rayon flocking. The lining shall not produce scratches on plastic lenses carried in the spectacle case, even after prolonged usage. The lining shall be fluoride free.

* 3.1.5.1 Nylon cloth. The nylon cloth used for the lining shall be 100 percent nylon, 40 denier. The finished product shall have a gloss or semi-gloss finish. The total of loops and strands (wales and courses) on the finished product shall be a minimum of 70, with a minimum of 38 wales and 32 courses or vice versa (38-32 or 32-38).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:24Z
Check the source to verify that this is the current version before use.

3.1.5.2 Flocking. The material used for the flocking shall be rayon fiber, 5.5 denier.

3.1.5.3 Color. The color of the lining shall be black.

3.1.6 Thread. Thread shall be black nylon, Type II or III of V-T-295.

3.1.7 Identification card. The identification card shall be stiff white paper, suitable for use as described herein.

3.2 Construction. Construction of the case shall be as shown on DPSC Drawing No. 23244. The patterns for the case shall be cut from a sandwich or laminate of the vinyl sheet, foam, and lining. The foam shall be adhered to the vinyl sheet by the flame method and the nylon shall be adhered by heat or adhesive. Flocking shall be by beater bar. The pattern shall be sewn to form a pocket for the case insert. The top edge of the pocket shall be sufficiently high to cover the top front edge of the insert. The case shall be of the envelope type and shall be secured by a snap fastener. When the snap fastener is closed, the end of the flap shall not project beyond the bottom of the case. Edges shall be bound and stitched as shown on the drawing.

3.2.1 Case insert. The case insert shall conform to the overall dimensions shown on the drawing. It shall be one-piece rigid construction with integrally molded bridge section. The back of the insert shall have cut-outs on both sides of the center to assure lens contact with the soft fabric lining instead of the insert. The insert shall be capable of holding the air crew sun glasses, HGU-4/P, as specified in MIL-G-25948 as well as the assembled plastic fronts and temples as specified in MIL-S-36497.

3.2.2 Identification card. The identification card shall conform to the drawing for marking and dimensions. The size of the marking shall be entirely suitable for the purpose intended and shall be permanent and legible.

3.2.3 Assembly. The surface of the insert shall be bonded to the inside of the pocket of the covering case or attached to the snap fastener stud at the front. The identification card shall be placed in the case behind the insert.

3.3 Workmanship. Workmanship shall be first class throughout. Snap fasteners shall be properly set. The finished cases shall be uniform in color, texture, and finish. The cases shall be free from dirt, perforations, pits, cracks, holes, blisters, cuts, tears, oil, foreign matter, bubbles, or other defects which detract from their appearance or impair their serviceability. The occurence of defects shall not exceed the limits set by the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual and auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality supplied by the manufacturers of the components may be furnished in lieu of actual performan of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the National Stock Number (NSN), the item identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, the individual test results, and the specification requirements.

* 4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as indicated in table I. Unit of product for examination shall be one case.

TABLE I. Sampling criteria for examination.

Defect category	Inspection level	AQL (percent defective)
Major A	S-3	1.0
Major B	II	1.0
Minor	II	2.5

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIl-STD-105 and as indicated in table II. The acceptance quality level for each test shall be 1.5. Where feasible, the same sample shall be used for the determination of two or more characteristics. For each test, the requirement is applicable to the individual unit of product.

4.2.2.1 Subsidiary specifications. Sampling for testing under referenced subsidiary specifications shall be as specified therein.

TABLE II. Sampling criteria for tests.

Characteristic	Require-ment	Test procedure	Sample unit	Inspection level	Minimum sample size
Plastic case covering:					
Identification	3.1.1.7	4.4.1.7	Yard	S-1	3
Thickness	3.1.1.1	4.4.1.1.1	Yard	S-1	3
Fungus resistance	3.1.1.2	4.4.1.2	Yard	S-1	3
Tensile strength	3.1.1.3	4.4.1.3	Yard	S-1	3
Ultimate elongation	3.1.1.3	4.4.1.3	Yard	S-1	3
Tear resistance	3.1.1.4	4.4.1.4	Yard	S-1	3
Plasticizer volatility	3.1.1.5	4.4.1.5	Yard	S-1	3
Cold crack	3.1.1.6	4.4.1.6	Yard	S-1	3
Color	3.1.1	Visual	Yard	S-1	3
Dimensional stability (shrinkage)	3.1.1.8	4.4.1.8	10 inch	S-1	3
Plastic case insert:					
Tensile strength	3.1.3	4.4.2.1	Test specimen	S-1	3
Specific gravity	3.1.3	4.4.2.2	Test specimen	S-1	3
Plastic foam:					
Color	3.1.4	Visual	Test specimen	S-1	3
Density	3.1.4	4.4.3	Test specimen	S-1	3
Tensile strength	3.1.4	4.4.3	Test specimen	S-1	3
Tear strength	3.1.4	4.4.3	Test specimen	S-1	3
Compression set	3.1.4	4.4.3	Test specimen	S-1	3

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

TABLE II. Sampling criteria for tests. - Continued

Characteristic	Requirement	Test procedure	Sample unit	Inspection level	Minimum sample size
Nylon cloth:					
Identification	3.1.5.1		1/		
Denier	3.1.5.1		1/		
Wales and courses	3.1.5.1	4.4.4	Test specimen	S-1	5
Flocking:					
Identification	3.1.5.2		1/		
Denier	3.1.5.2		1/		

1/ The supplier shall submit a certificate of compliance for these characteristics.

4.3 Examination. The spectacle cases shall be examined to determine compliance with all requirements contained in this specification. Examination shall be conducted in accordance with but not limited to the defects in table III. Additional defects shall be classified in accordance with MIL-STD-105.

TABLE III. Classification of defects.

Categories	Defects
Major A	
101	Lining not soft or non abrasive to lens.
102	Case is not style or design specified.
103	Dimensions not within specified tolerance.
Major B	
151	Binding for the case is not continuous around the edges.
152	Case is not free of cuts, cracks, blisters, tears, or holes.
153	Case is not free of dirt, oil, or other foreign matter.
154	Snap fastener is loosely set.
155	Male and female elements of snap fastener are improperly aligned.
156	Snap fastener does not permit firm engagement.
157	Snap fastener easily disengaged.
158	Case insert not bonded to the front inside surface of the carrying case pocket, or not held in place by the fastener stud.
159	Foam incompletely adhered to vinyl.
160	Lining not uniformly adhered to foam.
Minor	
201	Binding is uneven with ragged edges.
202	Enamel finish of snap fastener does not match the color of the plastic case.
203	Enamel finish of snap fastener is not free of peeled or blistered areas.
204	Finish of plastic sheeting not as specified.
205	Identification card missing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:24Z
Check the source to verify that this is the current version before use.

4.3.1 Packaging inspection. The inspection of the unit packaging, packing and marking for shipment and storage shall be in accordance with quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Plastic sheeting.

4.4.1.1 Standard conditioning. Unless otherwise specified, samples for test shall be conditioned at a temperature of $23^{\circ} \pm 1.1^{\circ}$ C ($73.5^{\circ} \pm 2^{\circ}$ F), and a relative humidity of 50 ± 4 percent for a period of not less than 16 hours.

4.4.1.1.1 Thickness. The thickness shall be determined from five uniformly spaced readings taken across the width of the sheet. The gage used for the measurement of thickness shall be a dead-weight type equipped with a dial graduated to read directly to 0.0001 inch. The presser foot shall be circular with a diameter of 0.25 ± 0.01 inch. The presser foot and moving parts connected therewith shall be weighted so as to apply a total load of 3 ± 0.1 ounce to the specimen. The presser foot and anvil surface shall be plane to within 0.0001 inch. The referee test method for thickness shall be the method specified in 4.4.1.1.2.

4.4.1.1.2 Average thickness (weight method).

4.4.1.1.2.1 Apparatus:

(a) Analytical balance, equipped with pan straddle or other stationary support, sensitive to 0.0005 gram (gm).
(b) Class S. weights.
(c) Beaker, 250 milliliters (ml).
(d) Five nonabsorbent threads or wires.
(e) Thermometer, 0° to 100° C, graduated in 1° C divisions.
(f) Die or template, for cutting test specimens, 10 centimeter (cm) by 10 cm, with a dimensional tolerance of ± 0.01 cm per side.
(g) Sharp knife or razor.

4.4.1.1.2.2 Test specimens. Five 10 cm by 10 cm specimens taken uniformly across the width of the sheet shall be tested.

4.4.1.1.2.3 Test conditions. The specimens shall be conditioned and tested in accordance with procedure A of ASTM D 618.

4.4.1.1.2.4 Procedure. By means of the die or template and the sharp knife or razor, cut five specimens from the sample of material. Weigh each specimen to the nearest 0.5 milligram (mg) on the analytical balance. Record the weight as W. Following the procedure of ASTM D 792, method A, determine the specific gravity of each specimen and record as D. Use of a wetting agent is recommended.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:24Z
Check the source to verify that this is the current version before use.

4.4.1.1.2.4.1 Calculations. Calculate the average thickness of each test specimen, using the following formula, and average the five values:

$$T = \frac{394}{100}\frac{W}{D} = 3.94\frac{W}{D}$$

T = Average thickness of test specimen in mils.
W = Weight of test specimen in gm.
D = Density of test specimen in gm/cc.
394 = Conversion factor, cm to mils.
100 = Area of specimen in sq. cm.

4.4.1.2 Fungus resistance. The plastic sheeting shall be tested in accordance with procedure I of the fungus-resistance tests as specified in MIL-E-5272.

4.4.1.3 Tensile strength and ultimate elongation. Tensile strength and ultimate elongation shall be determined as specified in method B of ASTM Standard D 882. No autographic stress-strain curve is needed. The test specimens shall be 1 inch wide.

4.4.1.4 Tear-resistance (Graves). The tear-resistance (Graves) shall be determined in accordance with method 1121 of FED-STD-406.

4.4.1.5 Plasticizer volatility. The plasticizer volatility shall be determined in accordance with ASTM D 1203.

4.4.1.6 Cold crack.

4.4.1.6.1 Apparatus.

4.4.1.6.1.1 Cold chamber. The cold chamber shall be capable of maintaining the required temperature within 2° C (3.6^{o} F) for the required time.

4.4.1.6.1.2 Steel roller. The steel roller shall be approximately 5-1/2 inches in diameter, approximately 2 inches wide, with a suitable hand guide. The total weight shall be 10 pounds.

4.4.1.6.1.3 Pair of gloves.

4.4.1.6.2 Test specimen. The specimen shall be a square of plastic not less than 8 by 8 inches. Three specimens shall be taken for test.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

4.4.1.6.3 Procedure. The specimen shall be exposed at a temperature of $0^{\circ} \pm 3.6^{\circ}$ F for 1 hour. Without being removed from the specified temperature conditions, the specimen shall be creased 180° in the center of the machine and transverse directions, respectively, by folding slightly while lying on a flat smooth surface and running the center of the steel roller over the fold a single time. The specimen shall be opened between the two creasing operations. The pressure on the specimen shall be the weight of the roller. The temperature of the roller shall be the same as that of the specimen. The specimen shall be handled with gloves and care taken that its temperature remains uniform throughout the test. After the test, the sample shall be examined visually at room temperature. The plastic material shall show no evidence of cracking.

4.4.1.7 Identification.

4.4.1.7.1 Materials. Materials required to perform the identification test are as follows:

Bunsen flame.
Tongs.
Sample of plastic sheeting (3 inches or more long).
Piece of copper wire.

4.4.1.7.2 Procedure. Heat the copper wire in a Bunsen flame until it no longer imparts a green tinge to the flame. Hold sample of plastic sheeting together with the copper wire to the edge of the flame until the sheeting ignites.

4.4.1.8 Dimensional stability (shrinkage). The change in linear dimensions of the plastic sheeting shall be determined in accordance with ASTM D 1204.

4.4.2 Plastic case insert.

4.4.2.1 Tensile strength. The case insert shall be tested for tensile strength in conformance with ASTM D 638 and D 651.

4.4.2.2 Specific gravity. The case insert shall be tested for specific gravity in conformance with ASTM D 792.

4.4.3 Plastic foam. Tests required for the polyurethane foam shall be conducted in accordance with the methods in ASTM D 1564.

4.4.4 Nylon cloth. The number of wales and courses in the nylon tricot cloth shall be determined in accordance with method 5070 of FED-STD-191.

5. PACKAGING

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Unit of issue. One spectacle case constitutes one unit of issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:24Z
Check the source to verify that this is the current version before use.

5.1.2 Level A.

5.1.2.1 Unit package. Each case shall be packaged in a plastic or kraft paper bag or wrapped in kraft paper or other suitable material. Wraps or bags shall be secured with tape or by other suitable means.

5.1.2.2 Intermediate package. Twenty-four unit packages shall be packaged in a box conforming to PPP-B-566 or PPP-B-676. Closure shall be as specified in the appendix of the applicable box specification.

5.1.3 Level C. Spectacle cases shall be clean, dry and packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A. Twenty-four intermediate packages (576 units) shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant. Closure and strapping shall be as specified in the appendix of the box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall be as specified in the appendix of MIL-L-10547. Fiberboard boxes shall be waterproofed as specified in the appendix of PPP-B-636.

5.2.2 Level B. Twenty-four intermediate packages (576 units) shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-585, class 3, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. The packaged spectacle cases shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

5.3 Marking. Interior packages and exterior containers shall be marked as specified in MIL-STD-129.

6. NOTES

6.1 Intended use. The spectacle case covered by this specification is intended to be used for carrying spectacles with plastic lenses.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) NSN.
(c) Selection of applicable levels of packing and packaging (see 5.1 and 5.2).

6.3 NSN coverage. The spectacle case covered by this specification, is listed in the Federal Supply Catalog as follows:

National Stock Number	Item Identification
6540-00-042-8752	CASE, SPECTACLE, Envelope Type, Soft Fabric Lining

* 6.4 Specification changes. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the previous issue.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activity:
DOD - MB

Preparing activity:
Defense Logistics Agency - DM

Project No. 6540-1052

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

POSTAGE AND FEES PAID



OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:24Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE
MIL-C-36828A CASE, SPECTACLE, ENVELOPE TYPE; SOFT FABRIC LINING

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1426 1 OCT 76

EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:24Z
Check the source to verify that this is the current version before use.