INCH-POUND

MIL-C-44307B
15 January 1991
SUPERSEDING
MIL-C-44307(GL)
28 January 1988

MILITARY SPECIFICATION

COVER, BIVY, EXTREME AND INTERMEDIATE COLD WEATHER SLEEPING SYSTEMS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type and size of moisture vapor permeable, bivy cover for attachment to the sleeping bag component of the extreme and intermediate cold weather sleeping systems.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issue of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5019 by using the Standardization Documents Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8465

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

A-A-50083	-	Bag, Plastic, Folded Garment
DDD-L-20	-	Label: For Clothing, Equipage and Tentage, (General Use)
PPP-B-26	-	Bag, Plastic, (General Purpose)
PPP-B-636	-	Boxes, Shipping, Fiberboard

MILITARY

MIL-L-35078	-	Loads, Unit; Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For

STANDARDS

FEDERAL

FED-STD-191	-	Textile, Test Methods
FED-STD-751	-	Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-147	-	Palletized Unit Loads
MIL-STD-731	-	Quality of Wood Members for Containers and Pallets

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

2-2-444 - Cover, Extreme Cold Weather Sleeping System (ECWSS)

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-EMSS, Natick, MA 01760-5014.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

COLOR ASSOCIATION OF THE UNITED STATES, INC.

Department of Defense Standards Shades for Sewing Threads 1968

(Application for copies should be addressed to the Color Association of the United States, Inc., 24 East 34th Street, New York, NY 10016.)

(Non-Government standards and other publications are normally available from organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Guide sample. Samples, when furnished, are solely for guidance and information to the contractor (see 6.4). Variation from this specification may appear in the sample, in which case this specification shall govern.

3.3 Materials. The materials shall be as specified herein and on Drawing 2-2-444 and all subsidiary drawings and parts lists pertaining thereto. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.3.1 Labels. Each cover shall have a class 15 combination identification and instruction label conforming to type VI of DDD-L-20. The label color shall be Medium Green, C.A. 70034, 70130, or 70151 and shall show fastness to laundering. The label shall read as follows:

COVER, BIVY EXTREME AND INTERMEDIATE COLD WEATHER SLEEPING SYSTEM

a. Field Laundry: The cover should be laundered utilizing "Formula II" of TM 10-280. NOTE: DO NOT STARCH, BLEACH, OR DRY CLEAN.

Drying: The cover should be finished in a tumbledryer, loaded not more than 2/3 of rated capacity at low heat cycle (do not exceed 100°F). NOTE: DO NOT PRESS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

b. Machine/Hand Laundering. Use wash/wear/permanent press fabric cycle or by hand, using warm water (90° to 110°F) and mild laundry detergent. Rinse thoroughly in clean warm water. NOTE: DO NOT USE CHLORINE BLEACH OR STARCH.

Drying: Tumble dry at low temperature (100°F) and remove immediately from dryer. Avoid over-drying. To drip dry, remove from water and place on rust-proof hanger. NOTE: DO NOT PRESS.

3.3.2 Seam sealing tape. The tape for covering and sealing all designated seams and stitching shall be 1 ± 1/16 inch wide strips cut from Olive Green 106, laminated cloth fabricated in layers as follows:

a. Nylon 6.6 tricot weighing 1.5 ± 0.3 ounces per square yard.
b. The middle layer shall consist of microporous expanded polytetrafluoroethylene film weighing 0.6 + 0.2, -0.1 ounces per square yard.
c. Adhesive, thermoplastic not less than 5.4 mils thick.

3.4 Design and construction. The design and construction of the cover shall be as specified herein and as shown on Drawing 2-2-444 and all subsidiary drawings and parts lists pertaining thereto.

3.4.1 Stitches, seams, and stitching. All stitches, seams, and stitching shall conform to FED-STD-751. The type of seam, stitching, and stitches per inch shall be as shown on Drawing 2-2-444 and subsidiary drawings. Seam allowances shall be maintained with seams so that no raw edges, run-offs, twists, pleats, puckers, or open seams occur.

3.4.2 Setting snap fasteners. A hole shall be prepunched through the materials before inserting the male and female part of the snap fastener or eyelets. The prepunched hole shall be smaller than the outside diameter of the fastener barrel so that the barrel must be forced through the hole. The fasteners shall be securely clinched without cutting the adjacent material and no more than three splits shall occur in the button or eyelet barrels.

3.4.3 Use of automated apparel equipment. Automated apparel equipment may be used to perform any of the operations specified in Drawing 2-2-444 and all subsidiary drawings providing that the seam and stitch type are as specified and the finished component conforms to the required dimensions and configurations.

3.4.4 Thread ends. All thread ends shall be trimmed to a length of not more than 1/4 inch unless otherwise specified.

3.5 Heat sealing. Seams and stitching as indicated on Drawing 2-2-444 and all subsidiary drawings shall be sealed with heat sealing tape on the inner side of the cover. The entire width of the seam tape shall be hot air sealed over the seam or stitching. The tape shall be applied by high temperature air blown on the thermoplastic adhesive face of the sealing tape, which is then driven through pressurized rollers, attaching the tape and sealing the seam or

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

shall be arranged in unit loads in accordance with MIL-STD-2073 for the type

stitching. The machine shall operate on 1200 to 3600 watts, with a 115 to 220 VAC air heater with slotted pneumatically activated driven rollers which press the tape onto the seam or stitching being sealed at a maximum of 20 feet per minute. All seam tape shall be applied without tension and shall be applied so that a minimum of 3/16 inch overlap is on both sides of the sewn seam. Every effort shall be made to avoid tape end joints where the tape passes over taped seams on the cover. All seam tapes shall overlap a minimum of 3/4 inch at joining points. Sealed seams and stitchings shall show no leakage when tested as specified in 4.4.4.

3.5.1 Heat sealing machine. The tape shall be applied on a seam sealing machine capable of controlling and maintaining hot air nozzle temperature, pressure, direction, feed roller speed, compression, and seam seal tape positioning. For optium results, the seam seal tape manufacturers recommendations for pressure, temperature, and speed shall be utilized.

3.6 Repairs. Repairing the cover by mending, patching, or darning is not allowed. However, heat sealing tape may be used for repairing sewn seams and for repair of missing yarns in the tricot knit on the inside of the cover up to 15 inches long. Up to three repairs totaling 15 inches in length shall be allowed. Seam tape may also be used to repair areas where the original tape does not overlap sewn seams by the minimum 3/16 inch on both sides. The same dimensions as above shall apply.

3.7 Finished measurements. The cover shall conform to the following finished measurements.

Area to be measured	Measurement inches	Tolerance inches
Height 1/	83	± 1-1/2
Widest width 2/	35	± 1
Narrowest width 3/	13-1/2	± 1/2

1/ With the drawstring totally loosened and the cover snapped closed, butt the hood drawcord tunnel with the collar drawcord tunnel to form a straight horizontal line. With the cover in this position measure length in a straight line from the top of the hood fold line to the foot piece seam.

2/ With the cover positioned as indicated in footnote 1/, measure across the width of the cover at its widest point from outside fold to outside fold.

3/ With the cover positioned as indicated in footnotes 1/ and 2/, measure horizontally in the center of the foot piece from the right side seam to the left side seam.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

3.8 Workmanship. The finished cover shall conform to the quality of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality level.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities sutiable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not releive the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to ensure compliance with all dimensional requirements.

4.1.3 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.2 and 4.4.3 and tested for the characteristic specified in 4.4.4. The presence of any defect or failure of the test shall be cause for rejection of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.1.1 Certification. The contractor shall furnish a certificate of compliance for the requirements specified in 3.3.2 for seam sealing tape and Drawing 2-2-444 for barrel locks and snap fasteners.

4.4.2 End item visual examination. The end items shall be examined for the defects listed in table I. The lot size shall be expressed in units of covers. The sample unit shall be one cover. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major defects and 15.0 for total (major and minor combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor
Material defects and damages	Any smash, multiple float, or loose slub	101	
	Cut, tear, mend, burn, needle chew, or hole	102	
Cleanliness	Any spot, streak, or stain of permanent nature on any portion of cover which would be visible when in use		201
	Removable spot, streak, or stain on outside of cover		202
	Thread ends not trimmed throughout cover		203
	Any holding or basting threads visible on the outside of the finished cover		204
Component and assembly	Any defective component 1/	103	205
	Any component part omitted	104	
	Any required operation omitted or improperly performed 1/	105	206
Drawcord	Any drawcord caught in stitching restricting use of drawcord	106	
	Any end not heat sealed		207
	Any drawcord omitted	107	
	Any end not knotted or not having a barrel lock		208
	Any drawcord insufficient in length	108	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Snap fasteners, general	Not specified style	109	
	Finish omitted or not as specified		209
	One or more omitted, broken or malformed failing to serve intended purpose; burrs; or sharp edges	110	
	Insecurely clinched to a degree that one or more fasteners may be detached from flap or tape; one or more excessively clinched cutting adjacent material		210
	Four or more splits in button or eyelet barrel		211
Labels	Missing, illegible, or incorrect	111	
	Incorrectly placed or attached		212
Accuracy of seaming	Seam badly twisted, pleated, or puckered 1/	112	213
	Part of cover caught in any unrelated operation or stitching 1/	113	214
	Thread break secured by stitching back of the break less than 1/2 inch		215
	Ends of all seams and stitchings when not caught in other seams or stitching, backtacked less than 1/2 inch		216
	Color of thread not as specified		217
	Gage of seam tape less than 3/16 inch from seam allowance	114	
Seam tape adhesion	Seam tape lifting off fabric	115	
	Visible scorching (heat degradation of the fabric on the laminate) in excess of 3/16 inch in width or 1/2 inch in length at any location along a taped seam	116	
Open seams	More than 1/8 inch up to 1/4 inch		218
	More than 1/4 inch	117	
	NOTE: One or more broken or two or more continuous skipped or run-off stitches constitute an open seam. On double		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Open seams (cont'd)	stitched seams, a seam is considered open when one or both sides of the seam is open. Raw edge not securely caught in stitching shall be classified as an open seam.		
Seam and stitch types	Not specified seam or stitch type	118	
Stitch tension	Loose tension in any area: - more than 1 inch but not more than 2 inches		219
	- more than 2 inches	119	
	Tight tension (stitches break when normal strain is applied to the seam or stitching)	120	
Stitches per inch to be scored only when the condition exists on major portion of the seam	Less than minimum specified: - one stitch		220
	- two or more stitches	121	
	More than maximum specified		221

1/ This defect shall be scored as major when seriously affecting serviceability or appearance, and as minor when affecting serviceability or appearance but not seriously.

4.4.3 End item dimensional examination. The end items shall be examined for the finished dimensions specified in 3.7. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of covers. The sample unit shall be one cover. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

4.4.4 End item testing. The end items shall be tested as specified in 4.5.1 for conformance to the leakage requirement in 3.5. The lot size shall be expressed in units of covers. The sample unit shall be one cover. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 6.5 for test failures.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and unit pack)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete closure of container flap, loose strapping, improper taping, or inadequate stapling Bulged or distorted container
Content	Number of covers per container more or less than specified 1/

1/ For this defect, one shipping container in the sample shall be examined.

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirements
Palletization	Pallet pattern not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.5 Methods of inspection.

4.5.1 Hydrostatic resistance test. The hydrostatic resistance of sealed seam areas of the cover shall be tested in accordance with Method 5516 of FED-STD-191, except for the following: The seam area of the fabricated cover sample unit, shall be tested without cutting or otherwise damaging the cover. The test may be performed on any device which tests the same specimen area at

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

the equivalent pressure. The hydrostatic head shall be 50 cm pressure for 3 minutes. The cover shall be tested at three different locations as follows: top, mid-way, foot. Evidence of leakage in one or more seam locations shall be considered a test failure.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each cover shall be folded to the approximate dimensions of 16 inches in length, 11 inches in width, and 2-1/2 inches in depth. The cover shall then be placed in a clear polyethylene bag conforming to type I or II, style 1 or 2 of PPP-B-26 or a plastic bag conforming to A-A-50083. Style 1 bags shall have a 1/4 inch hole located near the bottom corner to allow air to escape.

5.1.2 Commercial. The covers shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing. Twelve covers, preserved as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each box shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Inside dimensions of each container shall be approximately 22 inches in length, 16 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced in accordance with the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Twelve covers, preserved as specified in 5.1, shall be packed in a shipping container. The shipping container shall be a fiberboard box conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each box shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636 except that the inspection shall be in accordance with 4.4.5. Inside dimensions of each container shall be approximately 22 inches in length, 16 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall be closed in accordance with method II as specified in PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

documents shall be those listed in the issue of the Department of Defense

5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the fiberboard shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.4.5.

5.2.3 Commercial packing. Covers, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), covers, packed as specified in 5.2.2 or 5.2.3 shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C and D or film bonding means F or G. Pallet pattern shall be number 3 in accordance with the appendix of MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The sleeping bag cover is intended for use by personnel of the Department of Defense as a component of the Extreme and Intermediate Cold Weather Sleeping Systems.

6.2 Acquisition documents. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. When a first article is required (see 3.1, 4.3 and 6.3).
d. Levels of preservation and packing (see 5.1 and 5.2).
e. Type and class of unit load required (see 5.2.1).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
g. When palletization is required (see 5.3).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

6.4 Samples. For access to samples, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Subject term (key word) listing.

Dry cold
Moisture vapor permeable
Sleeping bag
Wet cold

6.6 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Air Force - 99

Review activities:

Army - MD
Navy - MC
Air Force - 82
DLA - CT

User activity:

Air Force - 45

Preparing activity:

Army - GL

(Project 8465-0071)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-C-44307B	1991 January 15

3. DOCUMENT TITLE
COVER, BIVY, EXTREME AND INTERMEDIATE COLD WEATHER SLEEPING SYSTEMS

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
U.S. Army Natick RD&E Center	(1) Commercial 508-651-4532	(2) AUTOVON 256-4532
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-IRT Natick, MA 01760-5019	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 NATICK OP, APR 90 *Previous editions are obsolete.* 198/290

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:20Z
Check the source to verify that this is the current version before use.