MIL-P-44305
13 June 1988

MILITARY SPECIFICATION

PLASTIC FILM, FLEXIBLE, POLYAMIDE AND POLYETHYLENE

This specification is approved for use by all Department and Agencies of the Department of Defense

1. SCOPE

1.1 Scope. This document is for one type of flexible, polyamide and polyethylene plastic film. It is to be used for making an identification pocket, window and lamination layer for the chemical protective patient wrap (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issue of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

A-A-203 - Paper, Kraft, Untreated

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 9330

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

PPP-B-591 - Boxes, Shipping, Fiberboard, Wood-Cleated
PPP-B-601 - Boxes, Wood, Cleated Plywood
PPP-B-636 - Boxes, Shipping, Fiberboard
PPP-D-723 - Drum, Fiber
PPP-T-45 - Tape, Gummed, Paper Reinforced and Plain, for Sealing and Securing
PPP-T-60 - Tape, Packaging, Waterproof
PPP-T-76 - Tape, Pressure Sensitive Adhesive, Packaging/Paper (For Carton Sealing)

MILITARY

MIL-L-10547 - Liner, Case and Sheet, Overwrap, Water Vaporproof or Waterproof, Flexible

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads
MIL-STD-282 - Filter Units, Protective Clothing Gas Mask Components and Related Products, Performance Test Methods

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 882 - Standard Test Methods for Tensile Properties of Thin Plastic Sheeting
D 2582 - Test Method for Puncture-Propagation Tear
D 3951 - Standard Practice for Commercial Packaging

(Copies should be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Laboratory report approval. Unless otherwise specified (see 6.2), at the time of submission of a bid the contractor shall submit to the contracting officer a certified copy of a recent laboratory report certifying that the film was manufactured in a plant where the manufacturing will be performed if a contract is awarded. The laboratory report shall also contain test data that demonstrates the finished product proposed by the contractor has been tested in accordance with and found to comply with the requirements of this document. All tests involving toxicological agents shall be conducted by the U.S. Army Armament Munitions and Chemical Command. A 7-yard sample shall be submitted to the U.S. Army Armament Munitions and Chemical Command (Edgewood Area), Chemical Test Branch, Building E5100, Aberdeen Proving Ground, MD 21010-5423, and a minimum of 30 days shall be allowed for receipt of test results. Any of the following types of reports will be satisfactory for all other test requirements.

a. An independent or commercial laboratory report.
b. The prospective contractor's own laboratory report.
c. A governmental laboratory report from a contract within one year of date of submission of bid.

The purpose of the above requirements is to assist the Government in determining capability of bidders to manufacture a film meeting all the requirement of this document. The submission of an acceptable report under this requirement shall not be construed as relieving a contractor from subsequently meeting all requirements of the document on all deliveries.

3.2 First article. When specified in the contract or purchase order, a sample shall be submitted to first article inspection (see 4.3, 6.2, and 6.4).

3.3 Materials. The flexible plastic film shall be composed of two types of plastic materials.

3.3.1 Polyethylene film or coating. The polyethylene material shall be natural color (essentially colorless) and transparent.

3.3.2 Polyamide film. The polyamide film shall be a 0.0006 inch nominal thickness film of the poly-epsilon-caprolactum type polymer. The film shall be natural color (essentially colorless) and transparent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

3.4 Plastic film. The polyethylene film or coating specified in 3.3.1 shall be coated or laminated to one side of the polyamide film specified in 3.3.2. The polyamide film side shall be the face side of the finished coated or laminated film.

3.5 Physical characteristics. The finished coated or laminated film shall conform to the physical properties specified in table I when tested as specified in 4.4.4.

TABLE I. Physical properties

Characteristic	Requirement	
	Min.	Max.
Thickness, inch	0.0030	0.0033
Tensile strength at break, psi:		
Machine direction	2500	--
Transverse direction	2000	--
Elongation at break, percent:		
Machine direction	175	--
Transverse direction	225	--
Yield stress, psi:		
Machine direction	1900	--
Transverse direction	1800	--
Resistance to puncture propagation, kilograms:		
Machine direction	4.8	--
Transverse direction	4.8	--
Heat seal strength as percent of film strength:		
Machine direction	60	--
Transverse direction	60	--
Toxicological agent resistance, hours:		
Mustard (HD)	5	--
Thickened GD	5	--

3.6 Length and width. The length of the rolls of film shall be as specified (see 6.2). The width of the film shall be 40 inches minimum. Each roll shall contain not more than three pieces and no piece shall be less than 10 feet in length.

3.7 Put-up and marking. The finished coated or laminated plastic film shall be put-up on rolls wound with the polyethylene (back) side of the film toward the outside of the roll. Each roll shall be marked or labeled on the end of the paperboard tube to indicate that the polyethylene side of the film has been wound toward the outside of the roll.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner.

3.8 Workmanship. The plastic film shall be smooth and uniform to the touch and in appearance. The coating shall be uniformly coated or laminated. The plastic film shall be free from foreign matter, holes, tears, wrinkles, creases and folds.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein,unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for defects listed in table II and shall be tested for the characteristics specified in table III. The presence of any defect or failure to pass any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents, unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

4.4.2 End item examination. The end items shall be examined for the defects listed in table II. The lot size shall be expressed in units of linear yards of film. The sample unit shall be one linear yard of film. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5.

TABLE II. End item visual defects

Examine	Defects
Workmanship	Texture and finish not uniform. Hole, tear, crack or blister. More than fifteen gels, fish eyes, unmelted material or foreign matter per square yard. Edge contains nick or cut.
Put-up	Polyethylene side of film not toward outside of roll.
Marking	Incorrect, omitted, illegible, or improper location.

4.4.3 End item dimensional examination. The end items shall be examined for the defects listed below. The lot size shall be expressed in units of rolls. The sample unit shall be one roll. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defects
Width	Less than minimum specified.
Length	Any roll less than 95 percent of specified length. Overall average length of two or more rolls less than 99 percent of specified length. Shortest piece of film in roll less than 10 feet.

4.4.4 End item testing. The end items shall be tested for the characteristics listed in table III. The lot size shall be expressed in units of rolls. The sample unit shall be 3 linear yards. Each sample unit shall be taken from a different roll. The lot shall be unacceptable if any sample unit fails to meet any specified requirement. All test reports shall contain the individual values used in expressing the final results.

Lot size	Sample size (sample units)
0 - 50	2
51 - 500	3
501 - 35000	5
35001 and over	8

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

TABLE III. End item tests

Characteristic	Requirement paragraph	Test method
Thickness	3.5	ASTM D 882
Tensile strength at break	3.5	ASTM D 882 1/
Elongation at break	3.5	ASTM D 882 1/
Yield stress	3.5	ASTM D 882 1/
Resistance to puncture propagation	3.5	ASTM D 2582
Heat seal strength	3.5	4.5.1
Toxicological agent resistance:		
Mustard (HD)	3.5	4.5.2.1
Thickened GD	3.5	4.5.2.2

1/ The width of the specimen shall be 1.0 inch.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior interior)	Omitted; incorrect; illegible; or improper location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping, or inadquate stapling. Bulged or distorted container.
Contents	Number per container is more or less than specified.

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

4.5 Methods of inspection.

4.5.1 Heat seal strength.

4.5.1.1 Apparatus. The apparatus shall consist of the appropriate heat sealing equipment with accurate controls for temperature, pressure and time, and the tensile testing equipment specified in ASTM D 882.

4.5.1.2 Specimens. From each sample unit, a sufficient number of representative 6 by 12 inch pieces of the material shall be cut. Half of the specimens shall have the 12-inch dimension parallel to the machine direction and half, parallel to the transverse direction. Each specimen shall be folded in the middle with polyethylene side to the inside of the fold, its two 6-inch ends accurately aligned and sealed together by conditions shall be adjusted, using the film manufacturer's recommendations as a guide, to make a seal having the best appearance and the highest seal strength. When the optimum setting has been found, all other specimens shall be sealed under the same conditions. The specimens whose seals show evidence of poor workmanship shall not be tested. Seal strength values obtained during adjustment of the sealing apparatus shall not be used in computing the average heat strength value. From the flattened tubes formed cut 1-inch wide bands perpendicular to the seam, discarding the end strips. The bands shall be permitted to cool for a minimum of 1 hour in standard atmosphere. They shall then be cut along the fold line to form 1-inch wide specimens with the heat sealed seams extending across the specimens at their midlengths, which shall then be tested.

4.5.1.3 Procedure. Each specimen shall be tested in accordance with ASTM D 882, except that the heat sealed seam shall be in the middle of the test length.

4.5.1.4 Report. Calculate the average heat seal breaking strength in pounds for each sample unit. Divide each average by the lot average film breaking strength, for the appropriate direction, obtained using ASTM D 882 with 1 inch wide specimens, and multiply by 100 to obtain the sample unit average heat seal breaking strength as percent of film strength.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

4.5.2 Toxicological agent resistance. Each sample unit of the finished coated or laminated film shall have a sample of 3 continuous yards, full width, removed and forwarded to the U.S. Army Armament Munitions and Chemical Command for testing in accordance with table IV (see 6.3).

TABLE IV. End item toxicological agent resistance

Characteristic	Requirement paragraph	Test method
Resistance to mustard (HD)	Table I	4.5.2.1
Resistance to thickened GD	Table I	4.5.2.2

4.5.2.1 Resistance to mustard (HD) test. Resistance to permeation by mustard (HD) shall be determined as specified in Method T 209 of MIL-STD-282, except that the chemmical agent challenge shall be 5 grams per square meter applied in droplets on the film surface. Test specimens shall be obtained by quartering a 3-yard piece of the film and selecting from each quarter, with one determination made on the face side of each specimen. No test specimen shall be taken within 2 inches of the edge. All specimens shall meet the requirements listed in table I. In the event that three of the four tested specimens meet the requirements but one does not, then two additional specimens from each quarter shall be tested with one determination made on each specimen. If seven of the eight specimens tested meet the requirements in table I and the eighth specimen is not less than 270 minutes, the sample unit shall be considered acceptable.

4.5.2.2 Resistance to thickened GD test. Resistance to permeation by thickened GD shall be determined as specified in Method T 208 of MIL-STD-282, except that the chemical agent challenge shall be 5 grams per square meter applied in droplets and that the cumulative amount of agent in the effluent shall be 108 per square centimeter. Test specimens shall be obtained by quartering a 3-yard piece of the film and selecting two samples, at random, from each quarter, with eight determinations made on the face side of the film. No test specimen shall be taken within 2 inches of the edge. All samples shall meet the requirements listed in table I. In the event that seven of the tested specimens meet the requirements but one does not, four additional test specimens from each quarter shall be tested. If all sixteen specimens meet the requirements, the sample unit shall be considered acceptable.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

5.1.1 Level A. Plastic film shall be uniformly rolled on a convolute or spiral wound paperboard tube with an inside diameter of not less than 2 inches nor more than 6-1/4 inches. Each roll shall be restrained from unwinding and then wrapped with at least one thickness of 30 pound minimum basis weight kraft paper conforming to A-A-203. The wrap shall be lapped approximately 6 inches and secured the entire length of the roll with 2-inch minimum width pressure sensitive tape conforming to PPP-T-60 or PPP-T-76; or gummed paper tape conforming to type III, grade B of PPP-T-45. The width of the wrapper shall be such that the wrapper can be folded over the ends of the roll. The folded ends of the wrapper shall be fastened either by tucking into the tube and placing a restraining device into the tube or by gluing a circular piece of paper over the folded wrapper ends.

5.1.2 Commercial. The plastic film shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing. Plastic film, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636, except that the dimensional limitation shall not apply; class II, style A of PPP-B-591; overseas type, style A or I, grade A or B of PPP-B-601; or type III, grade D of PPP-D-723. Each fiberboard container shall be waterproofed in accordance with the appendix of PPP-B-636. Each fiber drum shall be closed in accordance with PPP-D-723 with pressure-sensitive tape conforming to PPP-T-60. Each PPP-B-591 and PPP-B-601 container shall be provided with a type I or II, grade C sealed liner conforming to MIL-L-10547. Each shipping container shall be closed and reinforced in accordance with the applicable container specification. The weight of the contents of each PPP-B-636 container shall not exceed 65 pounds or 150 pounds for each of the other shipping containers.

5.2.2 Level B packing. Plastic film, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety DW) or SF, class domestic, grade 275 pf PPP-B-636, except that the dimensional limitations shall not apply; class I, style A of PPP-B-591; domestic type, style A or I, grade B of PPP-B-601; or type I, grade D of PPP-D-723. Each shipping container shall be closed in accordance with the applicable container specification. The weight of the contents of each PPP-B-636 container shall not exceed 65 pounds or 150 pounds for each of the other shipping containers.

5.2.2.1 Weather-resistant containers. When specified (see 6.2), the PPP-B-636 shipping containers specified in 5.2.2 shall be grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the container specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

5.2.3 Commercial packing. Plastic film, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. Unless otherwise specified (see 6.2), plastic film packed as specified in 5.2 shall be palletized in accordance with load type I or XIII (as applicable) of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. The load type I pallet pattern shall be in accordance with the appendix of MIL-STD-147. Interlocking of load type I containers shall be effected by reversing the pattern of each course. If the load type I container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer. The load type XIII containers shall be stacked vertically in a single course with a wood cap over and under the load. A strap shall be positioned girthwise around the load type XIII containers outside of and at the vertical center of the fiber drums and shall be the first strap applied to the load.

5.4 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

5.4.1 Precautionary marking. The following precaution marking shall appear in letters not less than 3/4 inches in height on at least one side and wherever practical on two sides of each shipping container.

STAND ON END

KEEP COOL AND DRY

6. NOTES

6.1 Intended use. The laminated film is intended for use as the transparent window in the pocket and as a barrier film laminated to the ground sheet component of chemical warfare agent resistant patient wrap.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. First article (see 3.2, 4.3, and 6.4).
c. When laboratory report approval is not required (see 3.1).
d. Length and width required (see 3.6).
e. Selection of applicable levels of preservation, and packing (see 5.1 and 5.2).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
g. When palletization is required (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

6.3 Toxicological tests. Because of the extreme dangers involved in handling toxicological warfare agents, and the special equipment required in connection with their use, all document tests involving toxicological agents will be Government acceptance testing performed by the U.S. Army Armament Munitions and Chemical Command (Edgewood Area), Chemical Test Branch, Building E 5100, Aberdeen Proving Ground, MD 21010-5423.

6.4 First article. When a first article sample is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.5 Subject term (key word) listing.

Film, Plastic
Flexible
Polyamide
Polyethylene

Custodians:

Army - GL
Navy - SH
Air Force - 99

Review activity:

Army - MR

Preparing activity:

Army - GL

Project No. 9330-1029

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

U.S. ARMY NATICK RESEARCH, DEVELOPMENT
and ENGINEERING CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
U.S. Army Natick Research, Development
and Engineering Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-P-44305	Plastic Film, Flexible, Polyamide and Polyethylene

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:19Z
Check the source to verify that this is the current version before use.