INCH–POUND

MIL–T–25524D(USAF)
8 April 1994

SUPERSEDING
MIL–T–25524C(USAF)
30 January 1981

MILITARY SPECIFICATION

TURBINE FUEL, AVIATION, THERMALLY STABLE

This specification is approved for use by the Department of the Air Force and is available for use by all Departments and Agencies of the Department of Defense

1. SCOPE

1.1 Scope. This specification covers one grade of turbine fuel designated as JPTS (see 6.1)

2. APPLICABLE DOCUMENTS

2.1 Government documents

2.1.1 Specifications, standards, handbooks, and regulations. The following specifications, standards, handbooks, and regulations form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2)

SPECIFICATIONS

MILITARY

MIL–I–25017	Inhibitor, Corrosion/Lubricity Improver, Fuel Soluble (Metric)
MIL–I–85470	Inhibitor, Icing, Fuel System, High Flash, NATO Code Number S–1745

STANDARDS

FEDERAL

FED–STD–313	The Preparation and Submission of Material Safety Data Sheets
FED–STD–791	Lubricants, Liquid Fuels, and Related Products, Methods of Testing

MILITARY

MIL–STD–290	Packaging of Petroleum and Related Products

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: ASC/ENOSD, Bldg 125, 2335 Seventh Street, Suite 6, Wright–Patterson AFB OH 45433–7809, by using the self–addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter

AMSC N/A

FSC 9130

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

QUALIFIED PRODUCTS LIST

QPL–25017	Inhibitor, Corrosion/Lubricity Improver, Fuel Soluble

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Defense Printing Service Detachment Office, Building 4, Section D, 700 Robbins Avenue, Philadelphia PA 19111–5094)

2.2 Non–Government publications. The following documents form a part of this document to the extent specified herein Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DoDISS cited in the solicitation Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6 2)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D56	Standard Test Method for Flash Point by Tag Closed Tester
ASTM D86	Standard Test Method for Distillation of Petroleum Products
ASTM D93	Standard Test Methods for Flash Point by Pensky–Martens Closed Tester
ASTM D129	Standard Test Method for Sulfur in Petroleum Products (General Bomb Method)
ASTM D130	Standard Test Method for Detection of Copper Corrosion from Petroleum Products by the Copper Strip Tarnish Test
ASTM D156	Standard Test Method for Saybolt Color of Petroleum Products (Saybolt Chromometer Method)
ASTM D240	Standard Test Method for Heat of Combustion of Liquid Hydrocarbon Fuels by Bomb Calorimeter
ASTM D381	Standard Test Method for Existent Gum in Fuels by Jet Evaporation
ASTM D445	Standard Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)
ASTM D1094	Standard Test Method for Water Reaction of Aviation Fuels (DoD adopted)
ASTM D1250	Standard Guide for Petroleum Measurement Tables
ASTM D1266	Standard Test Method for Sulfur in Petroleum Products (Lamp Method)
ASTM D1298	Standard Practice for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method (DoD adopted)
ASTM D1319	Standard Test Method for Hydrocarbon Types in Liquid Petroleum Products by Fluorescent Indicator Adsorption
ASTM D1322	Standard Test Method for Smoke Point of Aviation Turbine Fuels
ASTM D2276	Standard Test Method for Particulate Contaminant in Aviation Fuel by Line Sampling (DoD adopted)
ASTM D2386	Standard Test Method for Freezing Point of Aviation Fuels
ASTM D2622	Standard Test Method for Sulfur in Petroleum Products by X–Ray Spectrometry
ASTM D2887	Standard Test Method for Boiling Range Distribution of Petroleum Fractions by Gas Chromatography (DoD adopted)
ASTM D3120	Standard Test Method for Trace Quantities of Sulfur in Light Liquid Petroleum Hydrocarbons by Oxidative Microcoulometry (DoD adopted)
ASTM D3227	Standard Test Method for Mercaptan Sulfur in Gasoline, Kerosine, Aviation Turbine, and Distillate Fuels (Potentiometric Method)
ASTM D3241	Standard Test Method for Thermal Oxidation Stability of Aviation Turbine Fuels (JFTOT Procedure)
ASTM D3242	Standard Test Method for Acidity in Aviation Turbine Fuel (DoD adopted)
ASTM D3338	Standard Test Method for Estimation of Net Heat of Combustion of Aviation Fuels

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

ASTM D3343	Standard Test Method for Estimation of Hydrogen Content of Aviation Fuels (DoD adopted)
ASTM D3701	Standard Test Method for Hydrogen Content of Aviation Turbine Fuels by Low Resolution Nuclear Magnetic Resonance Spectrometry
ASTM D3828	Standard Test Methods for Flash Point by Setaflash Closed Tester (DoD adopted)
ASTM D3948	Standard Test Methods for Determining Water Separation Characteristics of Aviation Turbine Fuels by Portable Separometer (DoD adopted)
ASTM D4052	Standard Test Method for Density and Relative Density of Liquids by Digital Density Meter (DoD adopted)
ASTM D4057	Standard Practice for Manual Sampling of Petroleum and Petroleum Products
ASTM D4177	Standard Practice for Automatic Sampling of Petroleum and Petroleum Products (DoD adopted)
ASTM D4294	Standard Test Method for Sulfur in Petroleum Products by Energy– Dispersive X–Ray Fluorescence Spectroscopy (DoD adopted)
ASTM D4306	Standard Practice for Aviation Fuel Sample Containers for Tests Affected by Trace Contamination
ASTM D4809	Standard Test Method for Heat of Combustion of Liquid Hydrocarbon Fuels by Bomb Calorimeter (Intermediate Precision Method) (DoD adopted)
ASTM D4952	Standard Test Method for Qualitative Analysis for Active Sulfur Species in Fuels and Solvents (Doctor Test)
ASTM D5006	Standard Test Method for Measurement of Fuel System Icing Inhibitors (Ether Type) in Aviation Fuels
ASTM E29	Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
ASTM E380	Standard for Use of International System of Units (SI)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia PA 19013–1187)

2.3 Transportation. The following rules, regulations, and instructions shall govern the movement of the fuel in domestic and foreign transportation

DEPARTMENT OF TRANSPORTATION (DOT)

Title 49 Code of Federal Regulations (CFR) Parts 106 – 180

(Application for copies should be addressed to the Superintendent of Documents, Government Printing Office (GPO), Washington DC 20402)

JOINT MILITARY REGULATION

AFR 71–4, TM 38–250 NAVSUP PUB 505, MCO P4030 19E DLAM 4145 3, amendments to and reissues thereof, Packaging and Material Handling Preparing Hazardous Materials for Military Air Shipments"

(Application for copies should be addressed to local Installation or Base Document Control Unit)

INTERNATIONAL MARITIME ORGANIZATION (IMO)

International Maritime Dangerous Goods Code (IMDG), Publication 200 89 10 E, Vols I – IV amendments to and reissues thereof

(Application for copies should be addressed to the International Maritime Organization, 4 Albert Embankment, London SEI 7SR England)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

INTERNATIONAL AIR TRANSPORT ASSOCIATION (IATA)

"Dangerous Goods Regulations", amendments to and reissues thereof

(Application for copies should be addressed to the Publications Assistant, International Air Transport Association, 2000 Peel Street, Montreal, Quebec, Canada H3A 2R4)

INTERNATIONAL CIVIL AVIATION ORGANIZATION (ICAO)

"Technical Instructions for the Safe Transport of Dangerous Goods by Air", DOC 9284–AN/905, amendments to and reissues thereof

(Application for copies should be addressed to the Document Sales Unit, International Civil Aviation Organization, 1000 Sherbrooke Street West, Suite 400, Montreal, Quebec, Canada H3A 2R2)

(Non–Government standards and other publications are normally available from the organizations which prepare or distribute the documents These documents also may be available in or though libraries or other informational services)

2.4 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained

3. REQUIREMENTS

3.1 Preproduction. This specification makes provisions for preproduction testing

3.2 Materials. Except as otherwise specified herein, the fuel shall consist completely of hydrocarbon compounds Virgin, recycled, or reclaimed petroleum products may be used

3.3 Chemical and physical requirements. The chemical and physical requirements of the finished fuel (hydrocarbon blend plus all additives listed herein) shall conform to the requirements listed in section 3 and table I Requirements contained herein are not subject to correction for test tolerances

3.3.1 Storage stability. The finished fuel shall remain stable and conform to the requirements in table I for at least 1 year when tested in accordance with 4 6 3

3.4 Additives. The type and amount of each additive used shall be reported (see 6 2e)

3.4.1 Antioxidants. Immediately after processing and before the fuel is exposed to the atmosphere, an approved antioxidant shall be added to prevent the formation of gums and peroxides after manufacture The concentration of antioxidant to be added shall be as follows

a Not less than 17 mg nor more than 24 mg of active ingredient per liter of fuel (6 0 to 8 4 pounds of active ingredient per 1,000 barrels of fuel) to all JPTS fuel that contains blending stocks which have been hydrogen treated

b At the option of the supplier, not more that 24 mg of active ingredient per liter of fuel (8 4 pounds of active ingredient per 1,000 barrels of fuel) may be added to the JPTS fuel that does not contain hydrogen treated blending stocks

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

3.4.1.1 Approved antioxidants. The following antioxidant formulations are approved

a 2,6–ditertiary butyl–4–methylphenol

b 2,4–dimethyl–6–tertiary butylphenol

c 2,6–ditertiary butylphenol

d 75 percent minimum 2,6–ditertiary butylphenol
25 percent maximum tertiary and tritertiary bytylphenols

e 72 percent minimum 2,4–dimethyl–6–tertiary butylphenol
28 percent maximum monomethyl and dimethyl tertiary butylphenol

3.4.2 Metal deactivator. A metal deactivator, N,N'–disalicylidene–1,2–propanediamine or N,N'–disalicylidene–1,2–cyclohexanediamine, may be blended into the fuel in an amount not to exceed 5 7 mg of active ingredient per liter of fuel (2 pounds of active ingredient per 1,000 barrels of fuel) Metal deactivator additive shall not be used in JPTS unless the supplier has obtained written consent from the Procuring Activity

3.4.3 Fuel system icing inhibitor. The use of a fuel system icing inhibitor shall be mandatory The icing inhibitor shall be in accordance with *MIL–I–85470* The point of injection of the additive and the type of the additive shall be determined by agreement between the purchase authority and the supplier

3.4.4 Special additive. The fuel shall contain from 8 6 to 11 4 mg/L of fuel (3 to 4 pounds/1,000 barrels of fuel) of DuPont JFA–5[®] additive

3.4.5 Corrosion inhibitor/lubricity improver additive. A corrosion inhibitor/lubricity improver additive qualified for JPTS and conforming to *MIL–I–25017* shall be blended into the fuel by the supplier The amount added shall be equal to or greater than the minimum effective concentration and shall not exceed the maximum allowable concentration listed in the latest revision of *QPL–25017* The supplier or transporting agency, or both, shall maintain and upon request make available to the Government evidence the corrosion inhibitor/lubricity improver additive used is equal in every respect to the qualified products listed on *QPL–25017*

3.4.5.1 Approved corrosion inhibitor/lubricity improver additives. The following corrosion inhibitor/lubricity improver additives qualified for JPTS on *QPL–25017* are

a HITEC 580®

b NALCO 5403®

c MOBILAD F800®

d IPC 4410®

e IPC 4445®

f TOLAD 3220®

g PETROLITE NC–351®

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical and physical requirements and test methods.

Requirements	Minimum	Maximum	ASTM Standards Test Methods
Color, Saybolt	+24		D156
Total acid number, mg KOH/g		0 015	D3242
Aromatics, volume percent	5 0	20 0	D1319
Olefins, volume percent		3 0	D1319
Sulfur, Mercaptan, mass percent OR		0 001	D3227
Doctor Test		negative	D4952
Sulfur, total, mass percent		0 3	D129, D1266, D2622, D3120, or [1]D4294
Distillation temperature, °C (D2887 limits in parentheses)			[1]D86 or D2887
Initial boiling point	157 (105)		
10 percent recovered		193 (174)	
50 percent recovered		204 (207)	
90 percent recovered		238 (250)	
End point		260 (288)	
Residue, volume percent (D86)		1 5	
Loss, volume percent (D86)		1 5	
Flash point, °C (°F)	43 (110)		D56, [1]D93, or [2]D3828
Density, kg/L (API) at 15°C	0 767 (53 0)	0 797 (46 0)	D1298 or [1]D4052
Freezing point, °C (°F)		–53 (–64)	D2386
Viscosity, centistokes, at –40°C		12 0	D445
Net heat of combustion, MJ/kg (BTU/lb)	42 8 (18,400)		[1]D240, D3338, or [3]D4809
Hydrogen content, mass percent OR	14 00		D3343 or [1 and 4]D3701
Smoke point, mm	25 0		D1322
Copper strip corrosion, 2 hr at 100°C		lb	D130
Thermal stability (JFTOT)			
JFTOT TDR, max		12	[5]D3241
JFTOT mm Hg pres diff , max		25	[5]D3241

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical and physical requirements and test methods – Continued.

Requirements	Minimum	Maximum	ASTM Standards Test Methods
Existent gum, mg/100 mL		5 0	[6]D381
Particulate matter, mg/L			[7]D2276
Origin		0 3	
Destination		0 5	
Water reaction			D1094
Interface rating		lb	
Water separation characteristics	Report		D3948
Additives			
JFA–5, mg/L	8 6	11 4	
Metal deactivator	Report conc and Type		
Antioxidant, ppm by weight	Report conc and Type		
Fuel system icing inhibitor, vol percent	0 10	0 15	[8]D5006
Corrosion inhibitor/lubricity improver	[9]	[9]	

[1] Referee Test Method

[2] *ASTM D56* may give results up to 1°C (2°F) below the *ASTM D93* results *ASTM D3828* may give results up to 2 7°C (3°F) below the *ASTM D93* results

[3] For calculating the net heat of combustion using *ASTM D3338*, the average distillation temperature shall be calculated as follows, when the distillation is performed using *ASTM D2887*

$$V = \frac{10\% + 50\% + 90\%}{3}$$

[4] For calculating the hydrogen content using *ASTM D3343*, the average distillation temperature shall be calculated as follows when the distillation is performed using *ASTM D2887*

$$V = \frac{10\% + 50\% + 90\%}{3}$$

[5] See 4 6 2 1 for the JFTOT procedures and rating procedures

[6] If air is used instead of steam while performing *ASTM D381*, it must be reported In case of a failure with air, the sample must be retested using steam

[7] A minimum sample size of 3 785 liters (1 gallon) shall be filtered

[8] Test shall be performed in accordance with *ASTM D5006* or method 5327, 5340, or 5342 of *FED–STD–791* Use the appropriate scale of the refractometer

[9] See 3 4 5

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

3.4.6 Premixing of additives. Additives shall not be premixed with other additives before injection into the fuel so as to prevent possible reactions among the concentrated forms of different additives

3.5 Workmanship. At the time of Government acceptance, the finished fuel shall be clear, bright, and visually free from undissolved water, sediment, or suspended matter In case of dispute, the fuel shall be clear and bright at 21°C (70°F) If the finished fuel is not visually free from sediment or suspended matter but meets the table I particulate matter requirement, the fuel shall be considered to have met this workmanship requirement

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements

4.1.1 Responsibility for compliance All items shall meet all requirements of sections 3 and 5 The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility to ensure all products or supplies submitted to the Government for acceptance comply with all requirements of the contract Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements However, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material

4.2 Classification of inspections. The inspection requirements specified herein are classified as follow

a Preproduction inspection (see 4 4)

b Quality conformance inspection (see 4 5)

4.3 Inspection conditions. Requirements contained in table I are absolute, as defined in *ASTM E29*, and shall not be subject to correction for test tolerances If multiple determinations are made, results falling within any specified repeatability and reproducibility tolerances may be averaged For rounding off of significant figures, *ASTM E29*, Absolute Method, shall apply to all tests required by this specification

4.4 Preproduction tests. Test requirements of 3 3 1 shall be complied with prior to bid on any product required under this specification This test shall be conducted in accordance with 4 6 3

4.4.1 Preproduction samples. One, 208–liter (55–gallon) drum of fuel from the first batch that represents the product offered to the Government under any contract shall be forwarded to WL/POSF, Bldg 490, 1790 Loop Road N, Wright–Patterson AFB OH 45433–7103 The 208–liter (55–gallon) sample forwarded under each contract shall be accompanied by test data that illustrate the test results required by section 4 5 performed on products produced or blended in an identical manner to the batch sample The Government will perform tests as necessary to confirm or validate the contractor's test results Failure of the storage stability test will render the contractor ineligible for further contract award, pending assurance by the supplier to the satisfaction of the Wright Laboratory's Fuels Branch (WL/POSF) that any future product will meet the storage stability requirement The storage stability test must then be repeated on the improved product to prove the product is totally acceptable

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

4.5 Quality conformance inspection. Test for the acceptance of individual lots shall consist of tests for all requirements specified in section 3, except storage stability Quality conformance inspection shall include the test requirement herein

4.5.1 Inspection lot. For acceptance purposes, individual lots shall be examined as specified herein and subjected to tests for all requirements cited in section 3

4.5.1.1 Bulk lot. A bulk lot shall consist of an indefinite quantity of a homogeneous mixture of material offered for acceptance in a single, isolated container or manufactured in a single plant run (not to exceed 24 hours) through the same processing equipment, with no change in ingredient material

4.5.1.2 Packaged lot. A packaged lot shall consist of an indefinite number of 208–liter (55–gallon) drums or smaller unit packages of identical size and type, offered for acceptance, and filled from the isolated tank containing a homogeneous mixture of material or filled with a homogeneous mixture of material manufactured in a single plant run (not to exceed 24 hours) through the same processing equipment, with no change in ingredient material

4.5.2 Sampling plans

4.5.2.1 Sampling for verification of product quality. Each bulk or packaged lot of material shall be sampled for verification of product quality in accordance with *ASTM D4057* and/or *ASTM D4177*, except where individual test procedures contain specific sampling instructions

4.5.2.1.1 A number of jet fuel properties are very sensitive to trace contamination which can originate from sample containers Refer to *ASTM D4306* for recommended sample containers

4.5.2.2 Sampling for examination of filled containers for delivery. A random sample of filled containers shall be selected from each lot The samples shall be examined in accordance with 4 6 1 3

4.5.3 Inspection. Inspection shall be performed in accordance with method 9601 of *FED–STD–791*

4.5.4 Batch sample. WL/POSF reserves the right to have an 18 9–liter (5–gallon) sample of each batch of fuel produced under any contract forwarded to WL/POSF, Bldg 490, 1790 Loop Road N, Wright–Patterson AFB OH 45433–7103 This sample will be stored at Wright–Patterson AFB and will represent a retained sample from each batch of fuel produced All specification tests may be performed any time within 12 months from date of manufacture Failure of any test will render the contractor ineligible for further contract award, pending verification of the quality of the product to the satisfaction of Wright Laboratory's Fuel Branch (WL/POSF) The Contracting Officer and contractor will be promptly advised of any failures

4.6 Inspection methods

4.6.1 Examination of product

4.6.1.1 Visual inspection. Samples selected in accordance with 4 5 1 shall be visually examined for compliance with 3 5

4.6.1.2 Examination of empty containers. Prior to filling, each empty unit container shall be visually inspected for cleanliness and suitability in accordance with *ASTM D4057*

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

4.6.1.3 Examination of filled containers. Samples taken as specified in 4 5 2 shall be examined for conformance to *MIL–STD–290* with regard to fill, closure, sealing, leakage, packaging, packing, and markings Any container having one or more defects under the required fill shall be rejected

4.6.2 Chemical and physical tests. Tests to determine conformance to chemical and physical requirements (see 3 3) shall be conducted in accordance with the applicable test methods listed in table I and those specified herein

4.6.2.1 Thermal stability. The thermal stability test shall be conducted using *ASTM D3241* (JFTOT) The heater tube shall be rated using the Alcor Mark 8A or Alcor Mark 9 Tube Deposit Rater (TDR) (see 4 6 2 1 2a)

4 6.2 1.1 Stability test conditions

a Heater tube temperature at maximum point 335°C (635°F)

b Fuel system pressure 3 43 MPa (500 pounds/square inch of gravity)

c Fuel flow rate 3 0 milliliter/minute

d Test duration 150 minutes

4.6.2.1.2 Stability test results. The fuel sample is acceptable, if all the following criteria are met

a The maximum differential between the post–test and the pre–test Alcor Mark 8A or Mark 9 TDR rating does not exceed 12 TDR units Both before and after the JFTOT test, the heater tube shall be rated at 1 millimeter (mm) increments over the length of the heater tube that can be rated using the Alcor Mark 8A or Mark 9 TDR The maximum increase in the TDR ratings (i e , the maximum difference seen between the post–test and the pre–test TDR rating) shall be reported If the maximum increase in TDR rating does not exceed 12 TDR units, the results are satisfactory

b The maximum differential pressure across the test filter does not exceed 25 mm of mercury

4.6.2.2 Reported data. The following data shall be reported

a Tube deposit TDR ratings

b Differential pressure across the test filter

4.6.3 Storage stability. The storage stability test on the finished fuel shall be conducted by placing 200 ± 3 8 liters (53 ± 1 gallons) in a 208–liter (55–gallon), 18–gauge DOT 17E uncoated steel drum The filled drum shall be stored at 54 4°C (130°F) for 1 year (12 months) At 3–month intervals, samples shall be withdrawn and subjected to the thermal stability test (see 4 6 2 1) At the conclusion of the 12–month storage stability test, the fuel will be subjected to all test requirements of table I If the fuel fails any of the 3–month thermal stability tests, the fuel shall be resampled and retested to insure the initial sample was valid Failure of the thermal stability test at any of the 3–month intervals or failure of any of the table I test requirements at the conclusion of the 12–month storage stability test constitutes a failure of the storage stability test (see 4 4 1) The Air Force Wright Laboratory Fuel Branch (WL/POSF), Bldg 490, 1790 Loop Road N, Wright–Patterson AFB OH 45433–7103, will conduct this test

4.7 Test report. Test data required by 4 6 2 shall be reported in the same order as listed in table I, unless directed otherwise by the Procuring Activity

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging, packing, and markings. Packaging, packing, and markings shall be in accordance with *MIL–STD–290* All fuel containers shall be marked with the flashpoint obtained in 4 6 2 in both degrees Centigrade and degrees Fahrenheit of the fuel contained therein

5.2 Transportation of fuels. The transportation of JPTS fuel shall be in accordance with the Domestic and International Rules and Regulations listed in 2 3

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory)

6 1 Intended use. The fuel covered by this specification is intended for use in aircraft turbine engines (see 1 1)

6.2 Acquisition requirements. Acquisition documents must specify the following.

a Title, number, and date of this specification

b Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2 1 and 2 2)

c Quantity required and size containers desired

d Level of packaging and packing required (see 5 1)

e Location, injection method, and type of metal deactivator additive, fuel system icing inhibitor additive, and corrosion inhibitor/lubricity improver additive, as required

6 3 Conversion of metric units. Units of measure have been converted to the International System of Units (Metric) in accordance with ASTM E380 If test results are obtained in units other than Metric or there is a requirement to report dual units, ASTM E380 or ASTM D1250, Volume XI/XII, should be used to convert the units

6.4 Material Safety Data Sheets. Contracting Officers will identify those activities which require copies of completed Material Safety Data Sheets prepared in accordance with FED–STD–313 The pertinent Government mailing addresses for submission of data are listed in FED–STD–313

6 5 Subject term (key word) listing

additive
antioxidant
corrosion inhibitor
deactivator
flash point
fuel system icing inhibitor
jet fuel
lubricity improver

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes

Custodian
Air Force – 11

Preparing activity
Air Force – 11

Review activity
Air Force – 68

(Project 9130–1046)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1 The preparing activity must complete blocks 1, 2, 3, and 8 In block 1, both the document number and revision letter should be given

2 The submitter of this form must complete blocks 4, 5, 6, and 7

3 The preparing activity must provide a reply within 30 days from receipt of the form

NOTE This form may not be used to request copies of documents, not to request waivers, or clarification of requirements on current contracts Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractural requirements

I RECOMMEND A CHANGE:	1 DOCUMENT NUMBER **MIL-T-25524D**	2 DOCUMENT DATE *(YYMMDD)* **94-04-08**

3 DOCUMENT TITLE

TURBINE FUEL, AVIATION, THERMALLY STABLE

4 NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible Attach extra sheets as needed)*

5 REASON FOR RECOMMENDATION

6 SUBMITTER

a NAME *(Last, First, Middle Initial)*	b ORGANIZATION	
c ADDRESS *(Include Zip Code)*	d TELEPHONE *(Include Area Code)* (1) Commercial (2) DSN *(If applicable)*	7 DATE SUBMITTED *(YYMMDD)*

8 PREPARING ACTIVITY

A NAME ASC/ENOSD AF CODE 11	B TELEPHONE *(Include Area Code)* (1) Commercial (513) 255-6281 (2) DSN *(If applicable)* 785-6281
C ADDRESS *(Include Zip Code)* 2335 SEVENTH STREET, SUITE 6 WRIGHT-PATTERSON AFB OH 45433-7809	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church VA 22041-3466 Telephone (703) 756-2340 DSN 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T06:37Z
Check the source to verify that this is the current version before use.