MIL-P-25515C
4 Dec 1968

SUPERSEDING
MIL-P-25515B(ASG)
1 July 1963, and
MIL-P-16040A(ORD)
10 April 1961

MILITARY SPECIFICATION

PLASTIC MATERIALS, PHENOLIC RESIN, GLASS-FIBER BASE, LAMINATED

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope - This specification covers the requirements for fiberglass reinforced phenolic resin laminate sheets and parts, for use in structural and other applications.

1.2 Classification - The fiber glass reinforced phenolic resin laminates shall be classified by the fabric and mat number listed in Table I and shall be of the following grades, as specified.

Grade A - Normal Mechanical Properties

Grade B - Improved Mechanical Properties

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids, form a part of this specification:

SPECIFICATIONS

Federal

PPP-B-585	Box, Wood, Wirebound

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 20260-20T05:36Z
Check the source to verify that this is the current version before use.

Federal (Continued)

PPP-B-601	Box, Wood, Cleated-Plywood
PPP-B-[illegible]	Box, Wood, Nailed and Lock-Corner
PPP-B-636	Box, Fiberboard

Military

MIL-P-116	Preservation, Methods of
MIL-C-9084	Cloth, Glass, Finished, For Polyester Resin Laminates
MIL-R-9299	Resin, Phenolic, Low-Pressure Laminating
MIL-P-9400	Plastic Laminate Materials and Sandwich Construction, Glass Fiber Base, Low-Pressure Aircraft Structural, Process Specification Requirements

STANDARDS

Federal

Federal Test Method Std. No. 406	Plastics: Methods of Testing

Military

MIL-STD-129	Marking for Shipment and Storage

(Copies of specifications, standards and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Preproduction samples. Prior to the beginning of quantity production, the prime contractor (see 6.3) shall furnish preproduction samples which shall be subjected to testing for conformance with the requirements of this specification (see 4.3 and 6.2).

3.2 Materials. Materials shall be as specified herein. When materials not specifically designated are used, such materials shall be subject to the approval of the procuring activity.

Source: https://assist.dla.mil -- Downloaded: 20260-20T05:36Z
Check the source to verify that this is the current version before use.

3.2.1 Fabric - The fabric shall be of the continuous-filament type glass fabric and shall conform to MIL-C-9084, except the finish shall be the applicable finish used in the resin under MIL-R-9299.

3.2.2 Mat - Mats, when required, shall be of the construction and composition, and shall have the properties, specified (see Table I and pars. 6.2 and 6.4). When the mat is not otherwise specified, it shall be as described in the process specification (see 3.3).

3.2.3 Resin - The resin used to impregnate the glass reinforcing agent shall conform to MIL-R-9299. The resin manufacturer's curing instructions shall be followed in the use of catalysts, curing, and post cure cycles except where the fabricator has determined more suitable catalytic systems and curing cycles for a particular application. These systems and cycles shall be fully described in the fabricator's process specification and substantiated by the accompanying data required under 4.6.

3.3 Process specification - A detailed description of the manufacturing and fabricating process and methods of control of manufacturing variables in the form of a titled, numbered, and dated process specification shall be prepared by the prime contractor, or obtained from a subcontractor (see 6.3), and approved by the prime contractor. The process specification shall comply with the requirements of MIL-P-9400, and follow its format as closely as possible. The process specification shall be made available by the prime contractor at the commencement of the production of material to which it applies and, thereafter, during the course of production for use of authorized Government and industry inspectors in the facilities of the prime contractor, his subcontractors, or his vendors. It shall also be made available, on request, for review by engineers of the procuring activity. The prime contractor shall represent that compliance with such process specification will produce a material meeting all the contract requirements.

3.4 Foreign materials - No metal, paper, or other foreign material shall be present in the finished plastic materials unless allowed by the drawing for the part.

3.4.1 Mat laminates - Finely divided, inert, inorganic fillers may be used in mat laminates only, provided other specification requirements are met by the laminates.

3.5 Gap and laps - Unless specifically approved by the procuring activity, there shall be no gaps between pieces of glass fabric in any lamination. When laps are necessary, they shall be with a lap width of at least 1/2 inch. No two laps shall be superimposed upon each other in the plastic material.

3.6 Physical properties - The minimum and maximum values of specific gravity and resin content, and the minimum Barcol hardness value for the finished sheet or part shall be as specified in the approved contractor's process specification.

Source: https://assist.dla.mil -- Downloaded: 202610-20T05:36Z
Check the source to verify that this is the current version before use.

3.7 Mechanical properties - The mechanical properties in the longitudinal direction, of a 12 ply parallel laminated flat panel impregnated with the specific resin being employed and fabricated in accordance with the contractor's approved process specification, shall conform to the requirements of Tables I and II.

3.8 Dimensions and makeup of laminates -

3.8.1 Laminated plastic sheets

3.8.1.1 Thickness - Unless otherwise specified, laminated sheets shall conform with the thickness and tolerance requirements listed in Table III.

3.8.1.2 Length and width - Unless otherwise specified, manufacturer's standard sheet sizes between 36 and 96 inches in length and between 36 and 48 inches in width will be acceptable. The length and widths of the sheets shall be as specified within a tolerance of ±1.0 inch.

3.8.1.3 Warp or twist - The warp or twist of the laminate shall not exceed that shown in Table IV. Percentage of warp is given in terms of length and width, and percentage of twist is given in terms of dimensions from one corner to the opposite corner.

3.8.2 Laminated plastic parts - The thickness, dimensions, makeup of the laminate, comprising the number of plies of the various fabrics or mat, their position and direction, and other specific information for laminated plastic materials shall be as specified in drawings, specifications, or contracts for the parts.

3.9 Overlays - Unless specifically approved by the procuring activity, glass-fiber-base phenolic-resin laminated plastic material shall not be made with a gel resin overlay, integrally molded or otherwise, or with any other such thick resin surface or surfacing material.

3.10 Workmanship

3.10.1 Plastic materials, in those areas which are critical structurally or aerodynamically, shall be uniform, smooth and free from unbonded or uncured areas, gaps, cracks, holes, blisters, resin pockets, areas lacking resin, tackiness, excess surface resin, laps, wrinkles, delaminations, patches, porosity, and other similar defects. The critical structural and aerodynamic areas shall be as specified in drawings, specifications, or contracts for the parts.

3.10.2 Allowable defects - Allowable defects are those which do not affect serviceability, are fully described in the contractor's approved process specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T05:36Z
Check the source to verify that this is the current version before use.

TABLE I

LONGITUDINAL MECHANICAL PROPERITES OF GRADES A AND B (12 PLY) LOW-PRESSURE LAMINATED GLASS-FIBER-BASE PHENOLIC-RESIN PLASTIC MATERIAL AT STANDARD CONDITIONS 1/

Fabric number	Tensile strength thousands of psi Method 1011 2/		Compressive strength thousands of psi Method 1021 2/		Flexural strength thousands of psi Method 1031 2/		Flexural modulus of elasticity (initial) millions of psi Method 1031 2/	
	Standard Conditions	Wet Conditions	Standard Conditions	Wet Conditions	Standard Conditions	Wet Conditions	Standard Conditions	Wet Conditions
Grade A								
112	48	46	40	36	60	54	3.5	3.0
116	48	46	36	32	54	48	3.5	3.0
128	48	46	28	25	54	47	3.5	3.0
162	48	46	19	18	42	36	2.9	2.5
164	40	36	26	24	42	36	2.9	2.5
120	48	46	40	36	60	54	3.5	3.0
181	40	38	35	30	50	42	3.0	2.5
182	52	48	38	35	60	54	3.5	3.0
183	52	48	36	32	54	48	3.5	3.0
184	52	48	31	28	54	48	3.5	3.0
143	96	90	58	54	108	97	6.2	5.4
Mat	24	22	24	22	29	26	1.9	1.4
Grade B								
181	46	44	58	53	75	70	3.5	3.0

1/ Properties listed are for parallel laminated panels except for mat.

2/ Tests are to be performed in accordance with 4.5. All values are minimum for the average of five specimens. Method numbers refer to Fed. Test Method Std. No. 406.

Source: https://assist.dla.mil -- Downloaded: 2026/10-20T05:36Z
Check the source to verify that this is the current version before use.

TABLE II

LONGITUDINAL MECHANICAL PROPERTIES OF GRADES A AND B LAMINATED (12 PLY) GLASS-FIBER-BASE PHENOLIC-RESIN PLASTIC MATERIAL AT ELEVATED TEMPARATURE 1

Fabric number	Tensile strength thousands of psi Method 1011 2	Compressive strength thousands of psi Method 1021 2	Flexural strength thousands of psi Method 1031 2	Flexural modulus of elasticity (initial) millions of psi Method 1031 2	Flexural strength thousands of psi Method 1031 2	Flexural modulus of elasticity (initial) millions of psi Method 1031 2
	At 500° F after 1/2 hour at 500° F				At 500° F after 100 hours at 500° F	
Grade A						
112	36	24	48	3.5	24	2.9
116	36	34	43	3.5	22	2.9
128	36	24	42	3.5	22	2.9
162	36	17	34	2.9	17	2.4
164	30	23	34	2.9	17	2.4
120	36	24	48	3.5	24	2.9
181	30	20	40	3.0	20	2.5
182	38	32	48	3.5	24	2.9
183	38	34	43	3.5	22	2.9
184	38	26	43	3.5	22	2.9
143	72	49	86	6.2	37	5.2
Mat	18	29	23	1.9	12	1.6
Grade B						
181	39	32	52	3.1	45	2.9

1 Properties listed are for parallel laminated panels except for mat.

2 Tests are to be performed in accordance with 4.5. All values are minimum for the average of five specimens. Method numbers refer to Fed. Test Method Std. No. 406.

Source: https://assist.dla.mil -- Downloaded: 2026/10-20T05:36Z
Check the source to verify that this is the current version before use.

TABLE III

THICKNESS TOLERANCE OF LAMINATE 1

Nominal thickness 2		Permissible variations in inch (±)
Inch	Decimal equivalent in inch	
1/32	.031	.0065
3/64	.047	.0075
1/16	.0625	.0075
3/32	.094	.009
1/8	.125	.012
5/32	.156	.015
3/16	.1875	.019
7/32	.219	.021
1/4	.250	.022

1 On sheets of nominal thickness not listed in this table, the permissible variations shall be the same as for the next greater thickness.

2 The tolerance shall apply to each of at least 5 thickness readings taken at equally spaced intervals across the width of the sheet.

TABLE IV
WARP OR TWIST OF LAMINATE

Thickness	Permissible variation, on basis of 36-inch dimension 1
Inch	Maximum percent
1/32 to under 1/16	3.00
1/16 to under 1/8	2.50
1/8 to 1/4, inclusive	1.00
Over 1/4, up to and including 1/2	0.50

1/ These values do not apply to cut pieces but only to sheet sizes as manufactured. For any standard sheet size other than 36 inches, use the following formula:

$$\frac{D_X}{D\,36} = \frac{L_X^2}{(36)^2}$$

Where: D_X = Permissible deviation from straight edge in inches for the given length.

D 36 = Permissible deviation in inches for 36 inch length.

L_X = The given length in inches.

Source: https://assist.dla.mil -- Downloaded: 20260-20T05:36Z
Check the source to verify that this is the current version before use.

3.10.3 Reparable defects are those which can be repaired without affecting serviceability and are fully described in the contractor's approved process specification.

3.10.4 Allowable or reparable defects in excess of those listed in the approved process may be cause for rejection. Where requirements for these defects are more severe, orders, contracts, drawings, or specifications for specific material shall govern acceptability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection - Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Materials and components - In accordance with 4.1, the supplier shall be responsible for assuring that all materials and components used have been inspected and found to conform with all applicable requirements of this specification, and, to the extent specified herein, of referenced specifications and standards. In case of conflict, this specification shall govern.

4.2 Classification of tests - The inspection and testing of the laminated plastic materials shall be classified as follows:

(a) Preproduction tests (see 4.3)

(b) Quality conformance tests (see 4.4)

4.3 Preproduction tests -

4.3.1 Preproduction tests - Prior to production under contract, sample flat sheets, 12 ply, shall be parallel laminated for each grade of resin, and fabric numbers or mat to be employed in production of parts and for each type of process (including catalysts and curing cycles) as specified in the process specification. Separate samples shall be included for each producer, if two or more producers use the same type of resins, fabric numbers, mats, or processes. Sample sheets made as indicated, shall be tested in the longitudinal direction regardless of the continuity of fabric or mat and type of lay-up of specific parts. Sample sheets shall be subjected to the preproduction tests specified in 4.3.3. Cuttings of at least five specimens (machined to size and suitable for testing) from each sample flat sheet for each test required by Tables I and II and one 2- by 2- foot panel shall be furnished by the prime contractor to the procuring activity within 10 days after receipt of a specific request therefor from the procuring activity anytime prior to the completion of the prime contract in which this specification is incorporated. The above is at the option of the procuring activity in the event that the government check tests may be required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T05:36Z
Check the source to verify that this is the current version before use.

4.3.2 Exceptions - The preproduction samples, tests, and reports required herein need not be duplicated for new orders or different parts, provided the materials and processes have not been changed and a certified statement to that effect is furnished the procuring activity with a report of the tests made. However, the procuring activity shall have the right to require the performance of any of the tests at any time when it is deemed necessary to determine the conformance of the material to the requirements of this specification.

4.3.3 Preproduction tests - Preproduction tests shall consist of all tests described under 4.6.

4.4 Quality conformance tests - The quality conformance tests shall consist of all tests described under 4.4.2.

4.4.1 Sampling - From each lot of sheets or parts, at least one part or sample flat sheet, 12 ply, shall be parallel laminated in accordance with the approved process specification. Unless otherwise specified herein, five specimens for each test shall be taken from each sample part or sheet.

4.4.1.1 Lot - A lot shall be defined as all sheets or parts made from the same material and same design of part under the approved process specification.

4.4.2 Quality conformance tests - The quality conformance tests shall consist of the following:

(a) Specific Gravity (4.6.1.1)

(b) Resin Content (4.6.1.2)

(c) Barcol Hardness (4.6.1.3)

(d) Ultimate Flexural Strength (4.6.2.3)

(1) Dry Conditions (standard) (4.5.1)

(2) Wet Conditions (4.5.2)

(3) Short and long time aging at 500° F (4.5.3)

4.4.3 Rejection and retest - In case of failure of the sample to meet the specified tests, an additional sample representative of the same lot shall be tested. If this sample fails the specified tests, the lot shall be rejected and the material shall not be used in the production of sheets or parts.

4.4.4 Sheets and parts - Each sheet or part molded of the plastic material shall be inspected to determine conformance with the requirements of the approved

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T05:36Z
Check the source to verify that this is the current version before use.

process specification and MIL-P-9400. The inspection shall be made before any coating or finish of any kind is applied to the molded part.

4.5 Test conditions -

4.5.1 Standard conditions - Standard conditions shall be 73.4 ± 2° F and 50 ± 4 percent relative humidity. Specimens shall be tested after being exposed for 4 days to this temperature and humidity. Specimens may be tested without the 4 day exposure, except where there is a doubt that the materials will conform to the requirement when the standard condition is specified.

4.5.2 Wet conditions - Specimens shall be immersed for 2 hours in boiling distilled water, cooled in water to 73.4 ± 2° F, and tested immediately upon removal from the water without drying the specimens. For referee testing, specimens shall be immersed in distilled water for 30 days, and tested without drying upon removal from the water.

4.5.3 Exposure at 500° F - Specimens shall be placed in a test chamber maintained at 500 ± 5° F for 1/2 hour and tested immediately at the same temperature. For long term aging tests, specimens may be conditioned for 100 hours in a circulating air oven maintained at 500 ± 5° F, then transferred to a 500 ± 5° F test chamber for 1/2 hour and tested at this temperature.

4.6 Test methods -

4.6.1 Physical properties -

4.6.1.1 Specific Gravity - Specific gravity shall be determined in accordance with method 5011 or 5012 of Fed. Test Method Std. No. 406.

4.6.1.2 Resin content - Resin content shall be determined in accordance with Method 7061 of Fed. Test Method Std. No. 406.

4.6.1.3 Barcol hardness - Barcol hardness shall be obtained by direct reading of the Barcol Impressor.

4.6.2 Mechanical properties -

4.6.2.1 Ultimate tensile strength - The tensile tests shall be conducted in accordance with Method 1011 of Fed. Test Method Std. No. 406 using Type II specimens.

4.6.2.2 Compression (edgewise) - Twelve ply specimens shall be supported in a jig and tested edgewise in accordance with Method 1021 of Fed. Test Method Std. No. 406.

Source: https://assist.dla.mil -- Downloaded: 202610-20T05:36Z
Check the source to verify that this is the current version before use.

... should be a preproduction sample.

4.6.2.3 Flexural properties, ultimate strength, and modulus of elasticity - The flexural properties test shall be conducted in accordance with Method 1031 of Fed. Test Method Std. No. 406.

4.6.3 Warp or twist - Sheet specimens shall be tested in accordance with Method 6051 of Fed. Test Method Std. No. 406.

4.7 Packaging, packing, and marking - Preparation for delivery shall be examined for conformance to Section 5.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packaging -

5.1.1 Level A -

5.1.1.1 Unit packaging - Sheets shall be packaged in quantities specified, in accordance with Method III of MIL-P-116. The exterior container shall be the unit container. The preservation and packaging for parts shall be as specified in the specifications, drawings, or contracts for the parts fabricated from the plastic material.

5.1.2 Level C - Unit and intermediate packaging shall be in accordance with manufacturer's best commercial practice.

5.2 Packing -

5.2.1 Level A - Sheets shall be packed in quantities specified in wirebound wood boxes conforming to PPP-B-585 class 3, wood cleated plywood boxes conforming to PPP-B-601 overseas type, nailed wood boxes conforming to PPP-B-621 class 2, or fiber boxes conforming to PPP-B-636, class 2. The gross weight of the fiber boxes shall be as specified in PPP-B-636 and gross weight for the other boxes shall not exceed 200 pounds. Containers shall be closed and strapped in accordance with the applicable container specification or appendix thereto. The packing for parts shall be as specified in the specifications, drawings, or contracts for the parts fabricated from the plastic material.

5.2.2 Level B - Sheets shall be packed in quantities specified in domestic type shipping containers conforming to the requirements of PPP-B-601, PPP-B-621, or PPP-B-636. As far as practical, containers shall be of uniform shape and size, of minimum cube and tare consistent with the protection required, and contain identical quantities. The gross weight of a pack conforming to PPP-B-636 shall be as specified in PPP-B-636 and gross weight for packs conforming to the other specifications shall not exceed 200 pounds. Containers shall be closed and strapped in accordance with applicable container specifications or appendix thereto.

Source: https://assist.dla.mil -- Downloaded: 202640-20T05:36Z
Check the source to verify that this is the current version before use.

5.2.3 Level C - Packing shall be in accordance with commercial practice adequate to ensure acceptance and safe delivery by the carrier for the mode of transportation employed.

5.3 Marking - Interior and exterior containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use - The Grade A laminated plastic materials covered by this specification are intended for use in moderately stressed applications such as wing tips, fairings, etc., and for use in other structural applications requiring heat resistances up to temperatures of 260 C (500 F). The Grade B laminated plastic material is intended for higher stressed applications such as primary airframe structures.

6.1.1 The mechanical properties specified in this specification are for parallel laminated materials. When the materials are used cross-laminated or in other lay-up, or in combination of lay-ups of materials, the mechanical properties will vary, and for design use may be calculated in accordance with available procedures approved by the procuring activity, or determined empirically. Mechanical properties may also vary with the direction of loading, and may also be calculated with other procedures approved by the procuring activity or determined empirically (see MIL-HDBK-17, Plastics for Flight Vehicles, Reinforced Plastics, 5 Nov. 1959 edition). However, inspection tests are still to be carried out in accordance with the requirements of this specification.

6.2 Ordering data - Procurement documents should specify the following:

(a) Title, number, and date of this specification.

(b) Thickness of material.

(c) Make-up of this thickness as to number of plies and lay-up, and identification of the plies as to fabric number and finish used under this specification.

(d) Grade of material under this specification.

(e) Where the preproduction test samples should be sent, the activity responsible for testing, and instructions concerning the submittal of test reports.

(f) If preproduction test report is required on contracts or orders subsequent to the initial order.

Source: https://assist.dla.mil -- Downloaded: 202610-20T05:36Z
Check the source to verify that this is the current version before use.

(g) Applicable levels of packaging and packing required (see 5.1 and 5.2).

(h) Construction and properties of mat, if required (see Table I and 6.4).

6.3 Definitions -

6.3.1 Prime contractor - A prime contractor is a contractor fabricating components under direct contract with the Government or subcontracting the fabrication of part or all of such components; or a fabricator supplying parts directly to the Government.

6.3.2 Subcontractor - A subcontractor is a fabricator supplying components to a prime contractor.

6.4 Mat - It is recommended that the construction and properties of the mat, when required, be described using terminology and inspection methods of MIL-M-43248.

6.5 Grade A material of this specification replaces both Types and Classes of MIL-P-25515B(ASG). Grade B covers a new material with improved properties.

Custodians:
Army - MR
Navy - AS
Air Force - 11

Preparing activity:
Navy - AS
Project No. 9330-0213

Review activites:
Army - AV, MI, MR, MU
Navy - AS
Air Force - 84, 85

Review user information is current as of the date of this document. For future coordination of changes to this document, draft circulatinn should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Source: https://assist.dla.mil -- Downloaded: 202610-20T05:36Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION MIL-P-25515C — PLASTIC MATERIALS, PHENOLIC RESIN, GLASS-FIBER BASE, LAMINATED

ORGANIZATION *(Of submitter)* | CITY AND STATE

CONTRACT NO. | QUANTITY OF ITEMS PROCURED | DOLLAR AMOUNT

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE

☐ YES ☐ NO IF "YES," IN WHAT WAY

4. REMARKS *(Use as pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

5. SUBMITTED *(Activity, typed name and activity)* | DATE

DD FORM NO. 64 1426 REPLACES NAVSHIPS FORM 4863 WHICH IS OBSOLETE C-8279

Source: https://assist.dla.mil -- Downloaded: 202610-20T05:36Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF THE NAVY
Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

Weapons Engineering Standardization Office (Code X)
Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T05:36Z
Check the source to verify that this is the current version before use.