MILITARY SPECIFICATION SHEET

* INSULATION SLEEVING, ELECTRICAL, FLEXIBLE, COATED,
CLASS 200, TYPE C, CATEGORY c

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the insulation sleeving described herein shall consist of this document and the latest issue of MIL-I-3190.

The sleeving shall be of the following classification:

* Class 200, type C, category c.

REQUIREMENTS:
The insulation sleeving shall be in accordance with tables I, II, and III.

TABLE I. Performance requirements.

Property	Conditioning prior to test	Test	Unit	Value required
Dielectric breakdown:				
* Straight	96/23/50	4.7.2.2	Volts (minimum average)	8,000
* Straight	96/23/50	4.7.2.2	Volts (minimum individual)	6,000
* Straight	96/23/96	4.7.2.2	Percent of average value obtained on test after condition 96/23/50 (minimum)	80
Straight	At temperature of 200°C 2/200	4.7.2.2	Volts (minimum average)	5,000
90 degree bend		4.7.2.3	Volts (minimum average)	5,500

AMSC N/A
FSC 5970
DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:18Z
Check the source to verify that this is the current version before use.

The sleeving shall be directed vertically downward. The sleeving. The ...

TABLE I. Performance requirements. - Continued

Property	Conditioning prior to test	Test	Unit	Value required
Flammability	96/23/50	4.7.5.2 method B	Seconds to burn 1 inch 1/ for each individual specimen	45
Transformer oil	48 hours	4.7.6.3	Observation	No disintegration or swelling
Thermal endurance	See 4.7.9	4.7.9	Temperature index (°C) at 15000 hours (minimum)	200
Thermal stability	96/250	4.7.10	Volts (minimum average)	4,500
* Hydrolytic stability	336 hours over water at 70°C	4.7.7	Volts: (Minimum average) Observation	5,500 volts No disintegration, reversion or tackiness

1/ Specimens which burn less than 1 inch meet flame resistance requirements.

TABLE II. Qualification inspection requirements.

Examination or test	Requirement	Test	Minimum number of tests for each size and for each condition as specified in table I
Visual examination	3.3, 3.6	4.6	10
Dimensions	3.4	4.7.1	10
Dielectric breakdown: Straight - 96/23/50, 96/23/96 and at temperature	Table I	4.7.2.2	10
90 degree bend	Table I	4.7.2.3	5
Flammability	Table I	4.7.5.2 method B	5
Transformer oil	Table I	4.7.6.3	3
Thermal endurance	Table I	4.7.9	See 4.7.9
* Hydrolytic stability	Table I	4.7.7	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:18Z
Check the source to verify that this is the current version before use.

TABLE III. Quality conformance inspection requirements.

Examination or test	Requirement	Test	Conditioning prior to test	Minimum number of tests per sample unit
Visual examination	3.3, 3.6	4.6	96/23/50	As required per sampling
Dimensions	3.4	4.7	96/23/50	As required per sampling
Dielectric breakdown:				
Straight	Table I	4.7.2.2	96/23/50 96/23/96	10 10
Flammability	Table I	4.7.5.2 method B	96/23/50	5
Transformer oil resistance	Table I	4.7.6.3	96/23/50	3
Thermal stability	Table I	4.7.10	96/200	5

Intended use. The temperature index for this class of sleeving is 200°C. This material is intended for applications in electrical equipment requiring primary insulation having high heat and radiation resistance and providing adequate mechanical protection. The sleeving may be used where additional protection against environmental conditions or protection in localized areas is desired.

Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - ER
Navy - SH
Air Force - 20

Review activities:
Army - AR, AV, EA, MI
Navy - EC
Air Force - 85, 99, 80
DLA - GS

User activities:
Army - ME
Navy - MC, OS

Preparing activity:
Navy - SH
(Project 5970-1009-03)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:18Z
Check the source to verify that this is the current version before use.