MIL-G-13210(CmlC)
14 January 1954
SUPERSEDING
Army 20-40C
4 December 1940

MILITARY SPECIFICATION

GASKETS, RUBBER

1. SCOPE

1.1 Scope.- This specification covers one type of rubber gasket intended for use in making gas-tight connections in the assembly of gas mask canisters.

1.2 Size.- Unless otherwise specified gaskets shall be furnished in the following sizes (see 6.1):

Size 1 - Drawing A5-2-607
Size 2 - Drawing A5-2-600
Size 3 - Drawing A5-64-50

2. APPLICABLE DOCUMENTS

2.1 The following specifications, standards, and drawings, of the issue in effect on date of invitation for bids, form a part of this specification:

SPECIFICATIONS

MILITARY

JAN-P-120 - Packaging and Packing for Overseas Shipment - Cartons, Folding, Paperboard.
MIL-R-3065 - Rubber and Synthetic Rubber Compounds, General Purpose (Except Tires, Inner Tubes, Sponge Rubber, and Hard Rubber).
MIL-P-10577 - Packaging of Components and Subassemblies, Domestic Shipment to Assembly Plants.
MIL-P-10717 - Packaging of Spare Parts and Accessories for Gas Masks.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

Source: https://assist.dla.mil -- Downloaded: 202610-18T00:12Z
Check the source to verify that this is the current version before use.

MIL-STD-129 - Marking of Shipments.

DRAWINGS

CHEMICAL CORPS

A5-2-607 - Gasket.
A5-2-800 - Gasket.
A5-64-50 - Gasket, Canister.

(Copies of specifications, standards, drawings, and publications, required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Rubber compound.

3.1.1 Material.- The gasket shall be made from natural or synthetic rubber conforming to type RN 50y ABF or RS 50y ABF of Specification MIL-R-3065.

3.1.2 Physical requirements.- The physical requirements shall conform to those of the applicable type as specified in Specification MIL-R-3065 when tested as specified therein.

3.2 Size.- The size shall be as specified (see 1.2 and 6.1).

3.3 Workmanship.- Workmanship shall be in accordance with good commerical practice. The gaskets shall be free from defects affecting appearance and serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Lot.- A lot shall consist of the gaskets of one size produced by one manufacturer from the same rubber formulation under essentially the same manufacturing conditions in not more than 1 work week. A sub-lot shall consist of the gaskets produced in not more than one 8-hour production period. The inspection lot for nondestructive inspection, within the above limitations, shall be designated by the inspector.

4.2 Sampling.

4.2.1 For nondestructive inspection.- Sampling for nondestructive inspection shall be conducted in accordance with the classification of defects (see 4.3.3) and Standard MIL-STD-105.

4.2.2 For physical properties tests.- The manufacturer shall submit with each sublot a sufficient number of test slabs and test blocks to furnish 10 specimens for each test specified in Specification MIL-R-3065.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:12Z
Check the source to verify that this is the current version before use.

4.3 Inspection.

4.3.1 Materials.- The inspector shall ascertain that all materials of the gasket, covered by separate specifications, are in accordance with the applicable specifications, prior to final acceptance of the gasket.

4.3.2 Packaging, packing, and marking.- The inspector shall inspect the packaging, packing, and marking for compliance with section 5.

4.3.3 Classification of defects.- Inspection of the gasket shall be conducted as follows:

4.3.3.1 Gasket.- (Dwg. A5-2-807, Dwg. A5-2-800, or Dwg. A5-64-50)

Categories and defects		Gage or other method of inspection
Major	AQL 0.65 percent	
1.	Inside diameter incorrect	Scale
2.	Outside diameter incorrect	Scale
3.	Damage	Visual
4.	Contamination (grease or oil)	Visual
Minor	AQL 1.5 percent	
51.	Porosity, blisters, cracks, foreign matter	Visual
52.	Thickness incorrect	E24-1-1103
53.	Improper trim	Visual
54.	Contamination (other than grease or oil)	Visual
Incidental		
	None	

4.4 Tests.

4.4.1 Methods.- Tests on the rubber compound shall be conducted in accordance with the applicable method of Specification MIL-R-3065.

4.5 Retest and rejection.- If more than one specimen fails to meet its applicable requirement, the sublot represented shall be rejected. If one specimen fails, the sublot shall be retested using the same number of specimens as used for test. If more than one specimen fails in test and retest combined, the sublot represented shall be rejected.

5. PREPARATION FOR DELIVERY

5.1 Packaging (see 6.1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:12Z
Check the source to verify that this is the current version before use.

5.1.1 For shipment to assembly plants.- The gaskets shall be packaged in accordance with Specification MIL-P-10577. Prior to packaging, the gaskets shall be dusted with zinc stearate, talc, or other suitable material to prevent sticking. The container for the gaskets shall be a paperboard carton conforming to Specification JAN-P-120. The gaskets shall be stacked in the carton with a uniform number of gaskets in each stack. The stacks shall be separated by interlocking, half-slotted paperboard partitions.

5.1.2 For shipment as spare parts.- The gaskets shall be packaged in accordance with Specification MIL-P-10717.

5.2 Packing (see 6.1).

5.2.1 For shipment to assembly plants.- The gaskets packaged as specified in 5.1.1, shall be packed in accordance with Specification MIL-P-10577.

5.2.2 For shipment as spare parts.- The gaskets shall be packed in accordance with Specification MIL-P-10717.

5.3 Marking.- In addition to any special marking required by the contract or order, all shipping containers shall be marked in accordance with Standard MIL-STD-129. Marking shall include the following:

Federal Stock Number _____
Chemical Corps Stock Number _____
GASKET, RUBBER

6. NOTES

6.1 Ordering data.- Procurement documents should specify:

a. Title, number, and date of this specification.
b. The size of gasket required.
c. The type of packaging and packing required.

Patent notice.- When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Custodian:
Army - Chemical Corps

Other interest:
Army - MO

Source: https://assist.dla.mil -- Downloaded: 20260-18T00:12Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity (as indicated on reverse hereof).

SPECIFICATION

ORGANIZATION (Of submitter) | CITY AND STATE

CONTRACT NO. | QUANTITY OF ITEMS PROCURED | DOLLAR AMOUNT $

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS (Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)

SUBMITTED BY (Printed or typed name and activity) | DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE PLATE 15419

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:12Z
Check the source to verify that this is the current version before use.