MILITARY SPECIFICATION

CARTRIDGE, DELAY CCU-4/A

This amendment forms a part of MIL-C-81789 (AS) dated 6 August 1970, and is approved by the Naval Air Systems Command, Department of the Navy

Page 2

Under DRAWINGS, delete "2838226 Primer (Source Control Drawing)" and substitute "838AS102 Powder, Smokeless."

Delete "2838229 Holder and Primer Assembly" and substitute "2518447 Holder and Primer Assembly."

Page 4

3.3, line 2, delete "2838226" and substitute "8799925."

3.4, line 3, delete "with the exception that primer mixture weight and material shall be as specified on Drawing 2838226." and substitute "loaded with primer mixture 5086 as specified on Drawing 2518447."

3.7.3, line 2, delete the first sentence and substitute "The smokeless powder utilized shall meet the requirements of 838AS102 and shall exhibit no evidence of decomposition."

Page 9

4.7.7.1, delete and substitute:

"4.7.7.1 The number of cartridges selected from each production lot for the ballistic test shall be in accordance with the requirements of MIL-STD-105, Inspection Level II, for an AQL of 0.15, single sampling plan for normal inspection. The sample shall be randomly divided into three equal groups. If the sample does not divide evenly, the odd cartridges shall be placed in the third group. Samples in Group I inserted in the sleeve (Drawing

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:10Z
Check the source to verify that this is the current version before use.

2838190), of the test set (Drawing 2838183), shall be conditioned at -65° ± 5° F for not less than six nor more than twenty-four hours and fired in the test set within two minutes after removal from conditioning. Samples in Group 2 inserted in the sleeve (Drawing 2838190), of the test set (Drawing 2838183), shall be conditioned at 200° ± 5° F for not less than six nor more than twenty-four hours and fired in the test set within two minutes after removal from conditioning. Samples in Group 3 inserted in the sleeve (Drawing 2838190), of the test set (Drawing 2838183), shall be conditioned at 70° ± 5° F for a minimum of six hours and fired in the test set within two minutes after removal from conditioning. In addition to the sample of cartridges for the above tests, ten additional cartridges shall be furnished from the production lot for investigative purposes."

Preparing activity:
Navy (AS)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:10Z
Check the source to verify that this is the current version before use.