MIL-K-81786/3A(AS)
21 MAY 1986
SUPERSEDING
MIL-K-81786/3(AS)
20 April 1972

MILITARY SPECIFICATION

KIT TUBING, PLASTIC, HEAT SHRINKABLE (LOW RECOVERY TEMPERATURE), ELECTRICALLY INSULATING, FLEXIBLE, FLAME RETARDED, IRRADIATED POLYOLEFIN: SHRINK RATIO 2 TO 1

The complete requirements for procuring the plastic tubing described herein shall consist of this document and the issue in effect of MIL-K-81786(AS).

REQUIREMENTS: The tubing shall meet the requirements of AMS 3587.

Sizes - See table I
Type - tubular
Material - Polyolefin
Color - See table I
Length - See table I

TABLE I. Dimensions.

Part No.	Color	Dimensions (inch)				Length
		As Supplied I.D. min	After Unrestricted Shrinkage			
			I.D. max	Nominal Wall Thickness	Wall Thickness Tolerance	(ft)
M81786/3-1	Red	.046	.023	.016	± .003	16
M81786/3-2	Blue	.063	.031	.017	± .003	16
M81786/3-3	Yellow	.093	.046	.020	± .003	16
M81786/3-4	Black	.125	.062	.020	± .003	16
M81786/3-5	Black	.187	.093	.023	± .003	8
M81786/3-6	Black	.250	.125	.028	± .003	8
M81786/3-7	Black	.375	.187	.028	± .003	8
M81786/3-8	Black	.500	.250	.028	± .003	8
M81786/3-9	Black	.750	.375	.033	± .004	8
M81786/3-10	Black	1.000	.500	.035	± .005	8

Preparing Activity:
Navy - AS
(Project No. 4940-N511)

AMSC N/A

FSC 4940

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil - Downloaded: 2026-10-23T06:09Z
Check the source to verify that this is the current version before use.