# MILITARY SPECIFICATION

## TUBE, MOTOR, FOR 2.75 INCH ROCKET, MARK 66

This specification is approved for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification establishes the requirements for the manufacture and inspection of one type of motor tube for the 2.75 inch rocket, Mark 66.

## 2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and handbooks. Unless otherwise specified, the following specifications, standards and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specifiation to the extent specified herein.

SPECIFICATIONS

MILITARY

| | |
|---|---|
| MIL-A-2550 | Ammunition, General Specification For |
| MIL-C-5541 | Chemical Conversion Coatings on Aluminum and Aluminum Alloys |

STANDARDS

FEDERAL

| | |
|---|---|
| FED-STD-151 | Metals: Test Methods |

Beneficial comments, (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to the Naval Air Engineering Center, Engineering Specifications and Standards Department (Code 93), Lakehurst, NJ 08733, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

STANDARDS - Continued

MILITARY

| | |
|---|---|
| MIL-STD-105 | Sampling Procedures and Tables for Inspection by Attributes |
| MIL-STD-1167 | Ammunition Data Card |
| MIL-STD-1168 | Ammunition Lot Numbering |
| MIL-STD-1169 | Packaging, Packing and Marking for Shipment of Inert Ammunition Components |
| MIL-STD-1235 | Single and Multi-Level Continuous Sampling Procedures and Table for Inspection by Attributes |

2.1.2 Other Government documents, drawings and publications. The following other Government documents, drawings nd publications form a part of this specification to the extent specified herein.

DRAWINGS

NAVAL AIR SYSTEMS COMMAND

| | |
|---|---|
| 233AS107 | Tube, Motor |

(Copies of specifications, standards, handbooks, drawings and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Other publications. The following document(s) forms a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

| | |
|---|---|
| ASTM B117 | Salt Spray (Fog) Testing, Method of |

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 First article. When specified, a sample shall be subjected to first article inspection (see 4.4 and 6.3).

3.2 Material. Unless otherwise specified in the contract or purchase order, material utilized in the fabrication of the motor tube shall conform to the specifications and requirements on drawing 233AS107 or as specified herein.

3.2.1 Recycled, virgin and reclaimed materials. There is no exclusion to the use of recycled or reclaimed materials and no mandate for the use of virgin materials provided it meets the requirements of this specification.

3.3 Design and construction. The motor tubes shall be of the design, construction and physical dimensions specified in 233AS107 or as specified herein. The provisions of MIL-A-2550 shall apply.

3.4 Performance.

3.4.1 Hydrostatic. The motor tube shall be capable of withstanding an internal hydrostatic pressure of 2,650 +100 -0 psi for a minimum period of 15 seconds when tested as specified in 4.6.1 without leakage or pressure drop or permanent deformation. Acceptable motor tubes shall be marked with the letter H indent stamped with 3/32 character, located as shown on 233AS107. There shall be no deformation due to marking.

3.4.2 Air. The motor tube shall be capable of withstanding a minimum air pressure of 15 psi for 10 seconds when tested as specified in 4.6.2 without emitting bubbles if the water submergence test is used, or without exceeding a leak rate of $10^{-4}$ cc/sec if the dry test is used.

3.4.3 Bearing surface. The bearing surface of the motor tube shall not be reduced greater than that allowed on drawing 233AS107 when tested as specified in 4.6.3

3.4.4 Section. The motor tube thickness in the transition area shall not be less than that specified on drawing 233AS107 when tested as specified in 4.6.4.

3.4.5 Permanent deformation. There shall be no deformation in excess of the requirement specified on drawing 233AS107 when the motor tube is tested as specified in 4.6.5.

3.4.6 Salt spray. The painted motor tube, prepared in accordance with drawing 233AS107, and the test panel, prepared in accordance with MIL-C-5541, after subjection to the salt spray test specified in 4.6.6 and 4.6.7 respectively, shall show no more than five spots or pits, none larger than 1/32 inch in diameter on the exterior surfaces, or in the case of the panel, the bottom side of the panel exposed to salt spray, except in areas within 1/16 inch of sharp edges and in the lockwire groove. There shall be no more than three spots or pits, none larger than 1/32 inch in diameter, in the lockwire groove. The total of powdery areas or loose films covering more than ten percent of the total surface shall also be cause for rejection.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

3.5 Surface and internal defects. All motor tubes shall be free of surface imperfections on the interior and exterior surfaces which are indication of discontinuities internal to the metal (included are cracks, lube bursts, laminations, segregations, porosity, flakes, inclusions and other internal defects). Surface imperfections which do not intrude into the metal shall be considered workmanship defects (see 3.8).

3.6 Finish. Motor tubes shall be treated and painted as specified on drawing 233AS107.

3.7 Identification marking. Motor tubes shall be marked as specified on drawing 233AS107.

3.8 Workmanship. All motor tubes shall be fabricated and finished in a thorough, workmanlike manner. They shall be free of surface imperfections including pits, seams, scale, blisters, shallow lube bursts, and other discontinuities which do not intrude into the metal. All parts shall be free of burrs, chips, sharp edges, unblended radii, metal shavings, dirt, grease, rust corrosion and other foreign matter. The cleaning methods used shall not be injurious to any part nor shall any part be contaminated by the cleaning agents employed. Exterior surface coatings shall be continuous except for light scratches not exposing bare material. All required markings shall be neat and sharply defined.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspections. The inspections herein are classified as follows:

a. First article inspection (see 4.4).

b. Quality conformance inspection (see 4.5).

4.3 Test report. A test report shall be submitted along with a certificate (see 6.2.2) attesting that the information is correct and applicable to the product being submitted. Information shall include the following:

a. The product complies with all of the quality assurance provisions of this specification.

b. Drawing and specification number and date, together with identification and date of changes thereto.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

c. Certificates of conformance for material are on file and available for review when the material is controlled by the acquiring activity or commercial specifications referenced in any contractual document.

d. Number of items.

e. Date submitted.

4.4 First article inspection. Unless otherwise specified in the contract or purchase order, first article inspection shall consist of the tests and examinations listed in table I. A test report and certificate shall be submitted along with certificates of conformance of material (see 4.3 and 6.2.2).

4.4.1 Sample. First article sample shall consist of:

a. Ten motor tubes before painting
b. Thirty motor tubes after painting
c. One chemical film treated test panel (for use in salt spray test)

Failure to pass any one of the inspections listed in table I shall be cause for rejection of the motor tube and discontinuing further tests.

4.5 Quality conformance inspection. Quality conformance inspection shall consist of the following inspections:

a. Individual inspections (see 4.5.1)
b. Sampling inspection (see 4.5.2)

A test report and certificate shall be submitted along with certificates of conformance of material (see 4.3 and 6.2.2).

4.5.1 Individual inspections. Individual inspections are those inspections conducted on each motor tube. Individual inspections for the motor tubes are shown in table II. Failure to pass any of these inspections shall be cause for rejection of the motor tube.

4.5.2 Sampling inspection. The sampling inspection shall consist of the tests and examinations listed in table III.

4.5.3 Inspection lot. The inspection lot definition, formation and size shall be in accordance with MIL-STD-105. Each inspection lot shall bear a unique lot number. Ammunition data cards shall be prepared for each lot in accordance with MIL-STD-1167.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

4.5.4 Sampling plan. Sampling plans for major and minor defects shall be in accordance with MIL-STD-105 inspection level I except that continuous sampling plans in accordance with MIL-STD-1235 may be used if approved by the acquiring activity. Instead of applying the Acceptance Quality Level (AQL) designated in table III to the groups of major and minor defects listed, the contractor may elect to apply the AQL to individual defects using an AQL of .40 percent for each major defect and on AQL of .65 percent for each minor defect. When this method is elected, it shall be applied to all of the major and minor defects listed in table III except for major defects 103, 105, 106, 125, 127, 128 and 129. The sampling plan for major defects 106, 125, 127 and 129 shall be as follows:

a. Bearing surface (major defect M106): A sample consisting of one motor tube shall be taken from a maximum of each four hours production. Each defective motor tube shall be cause for rejection of the units produced since the last acceptable tube was inspected.

b. Section (major defect M125): Five motor tubes shall be randomly selected from each inspection lot. Any defective motor tube shall be cause for rejection of the lot represented.

c. Permanent deformation (major defect M127): A sample consisting of a minimum of one motor tube shall be taken per hour of production. If one or more motor tubes are rejected, all motor tubes processed since the last successful test shall be rejected and held for engineering evaluation and disposition.

d. Salt spray (major defect M129): A sample shall consist of one painted motor tube, randomly selected during production of each lot, and one test panel, prepared in accordance with MIL-C-5541. Failure shall be cause for rejection of the motor tubes.

4.5.5 Classification of defects. Defects shall be classified as shown in table II for critical defects and in table III for major and minor defects.

4.6 Methods of inspection.

4.6.1 Hydrostatic. The hydrostatic test shall be run on the integral bulkhead motor tube after machining, prior to painting and prior to dimensional checkout. Each motor tube shall be subjected to an internal hydrostatic pressure of 2,650 +100 -0 psi for 15 seconds minimum, applied to the 2.606 inch diameter. Observation shall be made for pressure drop. Pressure drop shall be noted after pressurization (pumping action or supply of fluid) is terminated. The tube aft of the bulkhead shall be tested as a true pressure vessel and shall be free to expand in all directions during the pressure test. Hydrotesting of that portion of the motor tube which is forward of the bulkhead is not required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

4.6.2 Air. The air test shall be run non-destructively on the integral bulkhead motor tube, prior to painting. A minimum pressure of 15 psi air pressure shall be applied to the 2.606 inch diameter for 10 seconds. Observation shall be made for bubbles if the tube is submerged in water or observation shall be made for a leak rate in excess of the requirement if the dry method is utilized. Air testing of that portion of the motor tube which is forward of the bulkhead is not required.

4.6.3 Bearing surface. An impression of the bearing surface of the unpainted motor tube shall be made by pouring four small plaster or non-shrinking molding plastic casts about a 310 degree periphery. The casts shall be measured to determine reduction in the bearing surface.

4.6.4 Section. Each motor tube in the sample, prior to painting, shall be sectioned through the centerline of the longitudinal axis of the aft chamber. The longitudinal section shall be deburred to facilitate accurate measurement. The thinnest portion of the transition area shall be measured.

4.6.5 Permanent deformation. The selected motor tube prior to painting, shall be tested for integral bulkhead position before and after the hydrostatic test. Failure to meet the requirement of 3.4.5 shall be cause for rejection.

4.6.6 Salt spray (motor tube). An accelerated corrosion test shall be performed utilizing the equipment and procedures prescribed by FED-STD-151, Method ASTM B117 on a painted motor tube. The tube shall be placed in a vertical position in the test chamber with the interior surfaces down to preclude accumulation of solution. A 20 percent concentration of sodium chloride solution shall be used and the duration of test shall be 144 hours. The tube shall be air dried for a minimum of 96 hours before testing. The tube shall then be exposed to the 20 percent salt spray as specified in FED-STD-151, Method ASTM B117. Defectives are motor tubes failing to meet the requirements of 3.4.6.

4.6.7 Salt spray (test panel). An accelerated corrosion test, using a 20 percent concentration of sodium chloride solution, shall be performed on the test panel utilizing the equipment prescribed by FED-STD-151 and the procedures as specified in MIL-C-5541. The duration of the test shall be 144 hours. The test panel shall be air dried for a minimum of 96 hours before testing. Defectives are those failing to meet the requirements of 3.4.6.

4.6.8 Examination. Motor tubes shall be inspected for conformance to the requirements of this specification and drawing 233AS107 with respect to material, design, construction, surface and internal defects, finish, marking and workmanship (see 3.2, 3.3, 3.5, 3.6, 3.7 and 3.8).

4.7 Inspection of packaging. The sampling and inspection of the preservation-packaging, packing and container marking shall conform to this specification (see section 5).



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation-packaging. Preservation-packaging shall be level B in accordance with MIL-STD-1169 (see 6.2.1).

5.2 Packing. Packing shall be level B in accordance with MIL-STD-1169 as specified (see 6.2.1).

5.3 Marking. In addition to any special or other identification marking required by the contract (see 6.2.1), shipping containers shall be marked in accordance with level B of MIL-STD-1169.

5.3.1 Ammunition lot number. Ammunition lot numbering shall appear on shipping containers and shall be in accordance with MIL-STD-1168.

6. NOTES

6.1 Intended use. The motor tube is intended for use with a 2.75 inch rocket, Mark 66.

6.2 Ordering data.

6.2.1 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.
b. Part number.
c. Quantity required.
d. Level of preservation-packaging, packing and marking.
e. Whether first article is required.
f. First article sample acceptance, if other than specified in Section 4 of this specification.
g. Production lot acceptance, if other than specified in Section 4 of this specification.
h. Sampling inspection selection.
i. Name and location of government representative responsible for random selection of inspection samples.
j. Where first article samples (see 4.4.1), random selected inspection samples (see 4.5.4), test reports and certificates (see 4.3), data items, certification letters of materials and ammunition data cards are to be forwarded.
k. Name and location of Government approved test laboratory.

6.2.2 Data requirements. When this specification is used in an acquisition which incorporates a DD Form 1423, Contract Data Requirements List (CDRL), the data requirements identified below shall be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance ith the approved CDRL incorporated into the contract. When the provisions of DAR 7-104.9(n)(2) are invoked and the DD Form 1423 is not used, the data specified below shall be delivered by the contractor in accordance with the contract or purchase order requirements. Deliverable data required by this specification is cited in the following paragraphs:



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

| Paragraph No. | Data Requirement Title | Applicable DID No. | Option |
|---|---|---|---|
| 4.3 | Certification Data/ Report | UDI-A-23264 | 10.2.4 |

(Data item description related to this specification, and identified in section 6 will be approved and listed as such in DoD 5000.19L., Vol. II, AMSDL. Copies of data item descriptions required by the contractors in connection with specific acquisition functions should be obtained from the Naval Publications and Forms Center or as directed by the contracting officer.)

6.3 First article. When a first article is required, the item will be tested and should be a first article sample. A sample containing known defects should not be submitted unless specifically authorized by the acquiring activity. A first article sample, or portion thereof, as directed by the contracting officer, should be submitted whenever there is a lapse in production for a period in excess of 90 days or whenever a change occurs in manufacturing, material used, drawing or specification such as to signficantly affect product uniformity as determined by the acquiring activity. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations and test approval of the documents and disposition of first article.

6.4 Quality assurance definitions. Definitions for quality assurance terms are in accordance with MIL-STD-109.

Custodians:
Navy - AS
Army - MI

Review activity:
Navy - OS

Preparing activity:
Navy - AS
(Project No. 1340-0659)



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

TABLE I. First article inspection.

| Examination or test | Requirement paragraph | Method paragraph |
|---|---|---|
| Visual and mechanical inspection (external and internal) | 3.2, 3.3, 3.5, 3.6, 3.7, 3.8 | 4.6.8 |
| Hydrostatic and presence of hydrostatic stamp | 3.4.1 | 4.6.1 |
| Air | 3.4.2 | 4.6.2 |
| Bearing surface | 3.4.3 | 4.6.3 |
| Section | 3.4.4 | 4.6.4 |
| Permanent deformation | 3.4.5 | 4.6.5 |
| Salt spray 1/ | 3.4.6 | 4.6.6, 4.6.7 |

1/ The salt spray test shall be accomplished on thirty painted motor tubes and one chemical film treated test panel.

TABLE II. Individual inspections.

| Classification of defect | Examination or test (after painting) | Requirement paragraph | Method paragraph |
|---|---|---|---|
| Critical | | | |
| 1 | Evidence of corrosion, surface and internal defects | 3.2, 3.3 and 3.5 | 4.6.8 |
| 2 | Hydrostatic test and presence of hydrostatic stamp | 3.4.1 | 4.6.1 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

TABLE III. Sampling inspections.

| Classification of defect | Examination or test (before painting) | AQL percent defective | Requirement paragraph | Method paragraph |
|---|---|---|---|---|
| Major | | 4.0 | | |
| 101/102 | Surface finish improper or not free of imperfections from aft end to 1" from aft end... | .40 | 3.3, 3.5 | 4.6.8 |
| 103 | Inside diameter of motor tube for aft 2.00" | .25 | 3.3 | 4.6.8 |
| | Inside diameter for length of motor tube in the aft chamber | .40 | 3.3 | 4.6.8 |
| 104 | Motor tube wall thickness in the aft chamber, min | .40 | 3.3 | 4.6.8 |
| 105 | Depth of lockwire groove | .25 | 3.3 | 4.6.8 |
| 106 | Bearing surface | see 4.5.4a | 3.4.3 | 4.6.3 |
| 107 | Depth of thread, min (based on configuration) | .40 | 3.3 | 4.6.8 |
| 108 | Outside diameters runout for straightness | .40 | 3.3 | 4.6.8 |
| 110 | Runout of load bearing surface of lockwire groove excessive | .40 | 3.3 | 4.6.8 |
| 111 | Circular runout of forward outside diameter of motor tube with aft outside diameter | .40 | 3.3 | 4.6.8 |
| 112 | Chamfer missing or improper at forward end of cavity adjacent to thread | .40 | 3.3 | 4.6.8 |
| 113 | Inside diameter of the lockwire groove | .40 | 3.3 | 4.6.8 |
| 114 | Wall thickness in lockwire groove | .40 | 3.3 | 4.6.8 |
| 115 | True position of inside diameter forward of bulkhead section with thread | .40 | 3.3 | 4.6.8 |
| 116 | Inside diameter forward of bulkhead section | .40 | 3.3 | 4.6.8 |
| 117 | Length of motor tube | .40 | 3.3 | 4.6.8 |
| 118 | Distance from forward edge of lockwire slot to forward edge of lockwire groove, min | .40 | 3.3 | 4.6.8 |
| 119 | Distance from aft edge of lockwire slot to aft edge of lockwire groove, min | .40 | 3.3 | 4.6.8 |
| 120 | Runout of forward warhead mounting face excessive | .40 | 3.3 | 4.6.8 |
| 121 | Circular runout of thread with the aft outside diameter of tube | .40 | 3.3 | 4.6.8 |



Source: https://assist.dla.mil Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

TABLE III. Sampling inspections - Continued.

| Classification of defect | Examination or test | AQL percent defective | Requirement paragraph | Method paragraph |
|---|---|---|---|---|
| Major | (before painting) | 4.0 | | |
| 122 | Depth from forward end to bulkhead, min | .40 | 3.3 | 4.6.8 |
| 123 | Distance from aft end to lockwire groove | .40 | 3.3 | 4.6.8 |
| 124 | Width of lockwire slot | .40 | 3.3 | 4.6.8 |
| 125 | Surface discontinuities in transition area (section) | see 4.5.b | 3.4.4 | 4.6.4 |
| 126 | Width of lockwire groove | .40 | 3.3 | 4.6.8 |
| 127 | Deformation of integral bulkhead after hydrostatic test | see 4.5.4c | 3.4.5 | 4.6.5 |
| 128 | Leakage (air) | .25 | 3.4.2 | 4.6.2 |
| Minor | (before painting) | 2.5 | | |
| 201 | Outside diameter of forward end of motor tube, min | .65 | 3.3 | 4.6.8 |
| 202 | Thickness of bulkhead | .65 | 3.3 | 4.6.8 |
| 203 | Thickness at aft end incorrect | .65 | 3.3 | 4.6.8 |
| 204 | Length of lockwire slot, min | .65 | 3.3 | 4.6.8 |
| 205 | Inside diameter of tube adjacent to thread | .65 | 3.3 | 4.6.8 |
| Major | (after painting) | 4.0 | | |
| 109 | Paint missing or inadequate | .40 | 3.6 | 4.6.8 |
| 129 | Accelerated corrosion (salt spray) | see 4.5.4d | 3.4.6 | 4.6.6 and 4.6.7 |
| Minor | (after painting) | 2.5 | | |
| 206 | Evidence of poor workmanship | .65 | 3.8 | 4.6.8 |
| 207 | Identification missing, incorrect or inadequate | .65 | 3.7 | 4.6.8 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS:** In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE* This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

---

(Fold along this line)

---

(Fold along this line)

DEPARTMENT OF THE NAVY
Commanding Officer
Naval Air Engineering Center
Engineering Specifications and Standards Department
(ESSD), Code 93
Lakehurst, NJ 08733

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

**BUSINESS REPLY MAIL**
FIRST CLASS PERMIT NO 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commanding Officer
Naval Air Engineering Center
Engineering Specifications and Standards Dept.
(ESSD), Code 93
Lakehurst, NJ 08733

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| MIL-T-85630 | Tube, Motor, For 2.75 Inch Rocket, Mark 66 |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR |
| | ☐ USER |
| b. ADDRESS *(Street, City, State, ZIP Code)* | ☐ MANUFACTURER |
| | ☐ OTHER *(Specify)*: _____ |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |

*(TO DETACH THIS FORM, CUT ALONG THIS LINE.)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.