INCH-POUND

MIL-G-63343 (AR)
AMENDMENT 3
4 January 1994
SUPERSEDING
AMENDMENT 2
29 December 1981

MILITARY SPECIFICATION

GRENADE, XM74, HEMISPHERES FOR

This amendment forms a part of Military Specification MIL-G-63343 (AR), dated 11 July 1980, and is approved for use by the US Army Armament, Munitions and Chemical Command, and is available for use by all Department and Agencies of the Department of Defense.

Change item designation from "XM74" to "M74" in title and wherever it appears in this specification.

PAGE 1

2.1 Delete "MIL-I-6866" and substitute "MIL-STD-6866".

Delete "FSC 1375" and substitute "FSC 1330".

PAGE 3

* 3.2.1.1 Microstructure. Delete paragraph in its entirety and substitute the following:

"3.2.1.1 Microstructure. The microstructure shall exhibit a uniform distribution of tungsten and binder material, and matrix depletion (porosity) shall not exceed 0.15% (volume) when viewed at 200 magnifications and tested as specified in 4.5.3".

PAGE 7

* 4.4.2.1 Delete Minors 201 and 202 in their entirety.

Minor 209: Delete in its entirety.

Minor 211, Add the following: "Straightness incorrect (2 places), 0.65%, 3.2, Gage".

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:41Z
Check the source to verify that this is the current version before use.

* 4.5.3 Microstructure: Delete paragraph in its entirety and substitute the following:

4.5.3 Microstructure. The test shall be performed on a test blank from a disc using any method satisfactory to the procuring agency. (The measurement techniques outlined in Metals Handbook, 9th Edition, Vol. 9, A.S.M., are approved and recommended.) Only the following will be counted for the purpose of porosity value measurement:

a. all areas of binder depletion.
b. sub-surface blisters.
c. porosity caused by inclusions with a dimension greater than 10 microns.
d. shrinkage breaks in the binder or gamma phase having a length greater than 10 microns.

If number of failures exceed the requirements of 4.4.2, the lot shall be rejected".

* 4.5.4 Mechanical properties. Delete paragraph in its entirety and substitute the following:

"4.5.4 Mechnical properties. Tensile test blanks conforming to ASTM E8 (Rectangular Tension Test Specimens), shall be prepared from completed discs. These samples shall be free of scoring when subjected to testing at a strain rate no greater than .10 inch per inch per minute as specified in ASTM E8. If any test specimen fails to meet ultimate tensile strength and elongation requirements, it shall be classified defective. If the number of failures exceeds the requirements of 4.4.2, the lot shall be rejected".

* 4.5.5 Penetrant inspection, First sentence. Delete "MIL-I-6866, Table I" and substitute "MIL-STD-6866".

* 6.3 Submission of inspection equipment for design approval. Delete last sentence in its entirety and substitute: "Submit designs as required to "Commander, US Army Armament, Research, Development and Engineering Center, ATTN: SMCAR-QAT-I, Picatinny Arsenal, NJ 07806-5000".

* 6.4 Informational tests. Delete paragraph in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:41Z
Check the source to verify that this is the current version before use.

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1330-A380)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:41Z
Check the source to verify that this is the current version before use.