FEDERAL SPECIFICATION

BUCKRAM, COTTON

This amendment, which forms a part of Federal Specification CCC–B–751, dated 7 February 1949, was approved on the above date by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

Page 2, table **I,** footnote 1: Delete reference "4.4" and substitute "4.3.2".

Page 2, paragraph **3.4.2.2,** line 5: Delete "4.4" and substitute "4.3.2".

Page 2, paragraph **3.5:** Delete and substitute paragraphs **3.5** through **3.5.6** as follows:

3.5 Type III, for clothing, double texture.

3.5.1 *Construction.*—Type III buckram shall be made of two plies of type II, class 3 buckram and shall be joined by laminating the two fabrics together.

3.5.2 *Laminating materials.*—The sizing and laminating materials used shall be of synthetic resin type, unaffected by standard dry cleaning solvents and standard launderings. There shall be no objectionable odor caused by these materials, and they shall in no way tender the buckram either at the time of manufacture or in storage.

3.5.3 *Weight.*—The weight of the buckram shall be not less than 32 ounces nor more than 34 ounces per square yard.

3.5.4 *Breaking strength.*—The minimum breaking strength of the combined buckram shall not be less than that required in table II for a single ply of the component fabric. The laminating material shall not tender the fabric at time of manufacturing.

3.5.5 *Resistance to dry cleaning.*—The combined buckram shall show no appreciable stiffening or embrittlement and no evidence of delamination when subjected to three cycles of the test prescribed in **4.3.3.**

3.5.6 *Resistance to laundering.*—The combined buckram shall show no appreciable stiffening or embrittlement and no evidence of delamination when subjected to six cycles of the test prescribed in **4.3.4.**

Page 4, section **4** (continued): At end of section, add new paragraphs **4.3.3** and **4.3.4** as follows:

4.3.3 *Resistance to dry cleaning.*—Test for resistance of dry cleaning shall be made in accordance with section VI, paragraph 5a (2) of Supplement to Federal Specification CCC–T–191.

4.3.4 *Resistance to laundering.*—Test for resistance to laundering shall be made in accordance with section XIV, paragraphs 1 and 2, of Federal Specification CCC–T–191.

Page 5, section **7:** End of section, add new paragraphs **7.4** through **7.4.2** as follows:

7.4 Air Force.

7.4.1 *Applicable specification.*

Military Specification:

MIL–P–6065—Packaging, Packing, and Marking of Cloth and Fabric.

7.4.2 *Packaging, packing, and marking* for the Air Force shall be in accordance with Specification MIL–P–6065.

(Copies of specifications required for Air Force purchases may be obtained from the Commanding General, Air Matériel Command, Wright-Patterson Air Force Base, Dayton 1, Ohio. Both the title and identifying symbol or number should be stipulated when requesting copies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.