MILITARY SPECIFICATION

BAR, METAL & WIRE (NONELECTRICAL), CARBON AND ALLOY STEEL, COLD DRAWN FOR AP BULLET CORES AND SHOT

This amendment forms a part of MIL-B-12504E(MR) dated 10 February 1987 and is approved for use by the Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 4

3.7: Delete and substitute:

"3.7 Crack or seam inspection. One of the following methods shall be used to inspect bars for the presence and depth of cracks or seams.

Method 1 - Magnetic particle inspection. Bars inspected by magnetic particle shall conform to table IV for depth of cracks and seams.

Method 2 - Magnetic inspection. The bars shall conform to table IV for depth of cracks and seams when inspected electromagnetically, using pre-established comparison standards specified by the procuring activity (see 6.2).

TABLE IV. Magnetic requirements.

Nominal diameter, inch	Depth of crack or seam, inch, maximum
17/64	0.010
29/64	.010
27/32 - 29/32	.020"

Change paragraph 3.10.1:

From: "...the tolerances shown in table IV."
To: "...the tolerances shown in table V."

From: "TABLE IV. Permissible variations in diameter"
To: "TABLE V. Permissible variations in diameter."

PAGE 8

6.2: Add the following subparagraph:

"(n) where magnetic inspection comparison standards may be obtained (see 3.7)."

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T22:53Z
Check the source to verify that this is the current version before use.