MILITARY SPECIFICATION

CROSSARMS, WOOD

This amendment forms a part of Military Specification MIL-C-12436C dated 8 April 1971.

Page 1

1.1, delete and substitute: "1.1 Scope. This specification covers treated and untreated crossarms."

Page 3

3.3, line 3, delete "spacing shall be selected from table I." and substitute "spacing shall be in accordance with table I as specified."

Page 5

3.7.1, delete and substitute: "3.7.1 Retention. Unless otherwise specified (see 6.2), the lower minimum net retention for each solution and species as shown in table II shall be required."

3.7.2, delete "4.4.2.3" and substitute "4.4.2.4."

Page 6

3.12 through 3.12.2, delete and substitute:

"3.12 Penetration.

3.12.1 Sap-wood penetration. Depth of penetration of preservative in sap-wood shall be not less than 100 percent.

3.12.2 Heartwood penetration.

3.12.2.1 Longitudinal penetration. Douglas-fir crossarms shall have a minimum penetration of the heartwood longitudinally from the pin holes, boltholes , and ends of 2-1/2 inches and 3 inches for 6 pounds and 8 pounds of creosote, respectively, and 2-1/2 inches and 3 inches for 0.30 pounds and 0.40 pounds of pentachlorophenol, respectively. Southern Pine crossarms shall have a minimum penetration of the heartwood longitudinally from the pin holes, boltholes , and ends of 1-1/2 inches.

Source: https://assist.dla.mil -- Downloaded: 20261O-17T22:49Z
Check the source to verify that this is the current version before use.

3.12.2.2 Depth penetration. When Douglas-fir crossarms are incised, the incised faces shall be penetrated by preservative a minimum of 3/16 inch deep (see 3.6)."

Page 7

4.3.4.1, line 2, delete "4.3.3.2" and substitute "4.3.3.1".

4.3.5.2.1, line 2, at end of paragraph add: "AQL shall be 4.0 percent defective."

4.3.5.2.3, line 3, at end of paragraph add: "AQL shall be 4.0 percent defective."

Page 8

4.4.2.1, lines 5, 6, and 7, delete last sentence and substitute: "Failure of the charge to conform to the moisture content specified in 3.11 shall constitute failure of this test."

Page 9

4.4.2.3, delete and substitute:

"4.4.2.3 Penetration. Penetration shall be determined in accordance with AWPA Standard M2. Nonconformance to 3.12 shall constitute failure of this test."

Page 10

6.2 (l), delete .

After 6.2(m), add:

"(n) Length, boring details, pin hole arrangement, and brace bolthole spacing required (see 3.3)."

Custodians:

Army - ME
Navy - YD
Air Force - 84

Review activities:

Army - EL

User activities:

Army - CE
Navy - MC

Preparing activity:

Army - ME

Project No. 5510-0138

Source: https://assist.dla.mil -- Downloaded: 202610-17T22:49Z
Check the source to verify that this is the current version before use.