MIL-C-21109B(AS)
10 August 1966
SUPERSEDING
MIL-C-21109A(Wep)
16 April 1962

MILITARY SPECIFICATION

Cloth, Coated, Nylon, Raft Bottom

This specification has been approved by the Naval Air Systems Command, Department of the Navy.

1. SCOPE

1.1 Scope - This specification covers requirements for procurement of nylon base natural or synthetic natural rubber coated cloth intended for use in life raft bottom construction. (See 6.1)

1.2 Classification - The raft bottom coated cloth shall be of the following types as specified (see 6.2):

Type I - 7 oz.
Type II - 14 oz.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

CCC-T-191	Textile Test Methods
PPP-P-51	Packaging, Packing, and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks and Synthetics)

Military

MIL-C-21108	Cloth, Nylon, Raft Bottom

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

STANDARDS

Federal

FED.TEST METHOD STD.NO. 141	Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing
FED-STD-595	Colors
FED-STD-601	Rubber, Sampling and Testing

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes

(When requesting any of the applicable documents, refer to both title and number. All requests should be made via the cognizant Government inspector. Copies of this specification and other unclassified specifications and drawings required by contractors in connection with specific procurement functions should be obtained upon application to the Commanding Officer, Naval Supply Depot (Code 1051), 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120. All other documents should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Preproduction - The raft bottom coated cloth furnished under this specification shall be a product, sample of which has been inspected and has passed the preproduction inspection specified in Section 4.

3.2 Materials - The coated cloth shall consist of nylon base cloth uniformly coated with a natural rubber or synthetic natural rubber base compound and construction in accordance with 3.3.

3.2.1 Base cloth - The base cloth shall conform to the requirements of MIL-C-21108, Type I or II as required in 3.3.

3.2.2 Coating - The compound used in coating the base cloths shall contain not less than 80 percent by volume of new plantation natural rubber or synthetic natural rubber. The compound shall also contain softeners, curing agents, antioxidants and reinforcing materials. The compound used in the outer coatings shall be pigmented during the compounding process so that the cured coating shall have a uniform

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

and permanent color as specified in 3.5. The pigment shall be of such fineness that 100 percent of the pigment shall pass through a standard 325 mesh screen. The foundation coating and rubber coating compounds shall not be injurious to the base cloth and shall contain no compounding ingredients which would bloom to the surface or which would adversely affect the specified properties of the finished coated cloth. The compounding ingredients shall be prepared in such proportions as to cure properly and provide proofing films which shall be insoluble in water to the extent that the coating compound water extractable matter shall amount to no more than 1 percent by weight (see 4.5.6). The coating compound, cured in sheet form to the same degree of cure and in the same manner as the finished product, shall conform to the physical requirements specified in Table I.

TABLE I

Physical Properties of Cured Coating Compound

Characteristic	Requirement	Method No. of FED-STD-601
Tensile strength Original, psi After heat aging for 168 hours at 212±2°F (100±1.1°C), percent loss	2300 min 30 max	4111 -- 7221
Elongation Original, percent After heat aging for 168 hours at 212±2°F (100±1.1°C), percent loss	450 min 15 max	4111 -- 7221
Shore hardness Original After heat aging for 168 hours at 212±2°F (100±1.1°C), change	50±10 ±5	3021

3.2.2.1 Coating adhesion - The coating adhesion test specimens described in 4.3.1.1 shall have a coating adhesion of not less than 7.0 pounds per inch of width when tested as specified in 4.5.6.2.

3.3 Construction and weight distribution - The construction and weight distribution of components of the finished cloth shall be as specified in Table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

3.3.1 Manufacture - A foundation coating, which shall be compatible with the base cloth and the remainder of the coating compound, shall be applied to the base cloth in order to achieve the required adhesion; and the coating compound shall then be applied to the base cloth by means of a spread coating operation. The rubber coating compound shall be applied in a sequence of operations so that both sides of cloth shall be coated and built up to the construction shown in Table II. The pigment shall be incorporated in the outermost coatings. The coated cloth shall be cured to meet the requirements of this specification. The cured coated cloth may be lightly dusted with talc or zinc stearate.

TABLE II

Construction and Weight Distribution, Ounces Per Sq. Yd.

Coated Cloth	Rubber Coating Compound	Nylon Cloth MIL-C-21108		Rubber Coating Compound	Total Weight
		Type I	Type II		
Type I	2±0.2	2.7 max	-------	2±0.2	6.3 to 7.0
Type II	4.2±0.2	-------	6.0 max	4.2±0.2	13.3 to 14.5

3.4 Age - Material offered for acceptance under this specification shall be from current production, and not more than 90 days old prior to release for shipment by the cognizant Government quality assurance representative. The date of completion of the coating operations shall be stamped at the end of each roll and on the identification tags. The ink used for stamping this date of manufacture on the roll shall be free of manganese and copper (see 4.5.4 and Table VI).

3.5 Color - Unless otherwise specified, the uniform permanent color of the finished coated cloth shall be an approximate match to color chip 12197, International orange of FED-STD-595 (see 4.5.8).

3.6 Properties of coated cloth - The coated cloth properties shall conform to the requirements specified in Table III and in the following paragraphs when tested as indicated therein.

3.6.1 Resistance to heat aging - In addition to exhibiting the above properties, after heat aging for 168 hours at 200±2°F(93±1.1°C), the coated cloth shall not have become stiff and brittle nor soft and tacky (see 4.5.9).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

TABLE III

Properties of Coated Cloth

Characteristic	CCC-T-191 Method No.	Requirement	
		Type I	Type II
Breaking strength, grab method, As received, pounds, min (see 4.5.9)	5100		
Warp		150	300
Filling		140	300
After heat aging for 168 hours at 200±2°F (93±1.1°C) breaking strength loss, percent, max	5850	10	10
Hydrostatic resistance, pounds per sq. in., min (see 4.5.9)	5512		
As received		50	100
After heat aging for 168 hours at 200±2°F (93±1.1°C)	5850	50	100
Blocking at 200±2°F (93±1.1°C), rating, max (see 4.5.11)	5872	2	2

3.6.2 Resistance to low temperature exposure - After low temperature exposure for 4 hours at -65±2°F(-54±1.1°C) and the folding procedure specified in 4.5.10 the coated cloth shall show no signs of cracking.

3.7 Dimensions - Unless otherwise specified, for direct Government purchases, the coated cloth shall be furnished in rolls with a minimum length of 250 yards and a maximum length of 350 yards. The minimum length of pieces shall be 50 yards (see 4.5.4). Width shall be as specified by the procuring activity (see 6.2).

3.8 Workmanship - The finished coated cloth shall be made from clean, evenly woven base cloth evenly coated and uniformly processed to produce the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection - Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection records of the examinations and tests shall be kept complete and available to the Government as specified in the contract or order.

4.2 Classification of inspection - The examination and testing of the raft bottom coated cloth shall be classified as follows:

(a) Preproduction inspection - Preproduction inspection consists of examinations and tests performed on samples which are representative of the production item after award of a contract to determine that the production item meets the requirements of this specification.

(b) Quality conformance inspection - Quality conformance inspection consists of examinations and tests performed on individual lots to determine conformance of the lots with the requirements set forth in this specification.

4.3 Preproduction inspection - The preproduction inspection of the raft bottom coated cloth shall consist of examinations and tests for all of the requirements of this specification. (See 4.5)

4.3.1 Preproduction samples - Unless otherwise specified, as soon as practicable after the award of the contract or order, the manufacturer shall furnish preproduction samples of each type of cloth for inspection to determine conformance with this specification. The preproduction inspection sample shall consist of required specimens of coated cloth, base cloth, a coating adhesion test specimen prepared as described in 4.3.1.1, and sheets of cured coating compound. The size and quantities of components of the preproduction sample shall be specified by the procuring activity. Quantity production shall be withheld until the preproduction sample has been pronounced satisfactory by the Government.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

When a contractor is in continuous production of this item from contract to contract, submission of further preproduction samples on the new contract may be waived at the discretion of the procuring activity. Approval of the preproduction samples or the waiving of preproduction inspection does not preclude the requirements of performing the quality conformance inspection. The preproduction sample shall be forwarded to the Supply Officer, Naval Air Engineering Center, Philadelphia, Pennsylvania 19112, Attention, Director, Aeronautical Materials Laboratory. The preproduction samples shall be plainly identified by securely attached durable tags or labels marked with the following information:

> Samples submitted by (name) (date) for preproduction inspection in accordance with the requirements of MIL-C-21109B(AS) under Contract No.

4.3.1.1 Coating adhesion test specimen - The coating adhesion test specimen shall be prepared by the manufacturer (coater). Each of 2 pieces of base cloth (see 3.2.1) measuring 12 by 12 inches shall be coated with the uncured coating compound described in 3.2.2. The specimen shall be constructed so that adhesion will be measured in the warp direction. The 2 pieces shall be placed together, coating to coating, except for a 1 inch wide separation along one edge allowed by insertion of paper. The specimen shall be cured in the same manner and degree of cure as the finished product. Specimens shall be made to represent the construction and weight distribution as shown in Table II.

4.3.2 Upon completion of the preproduction inspection, all the applicable inspection reports and, when applicable, recommendations and comments pertinent for use in monitoring production shall be forwarded to the Government quality assurance representative.

4.4 Quality conformance inspection - The Quality conformance inspection shall consist of an examination for acceptability of quality control methods used by the manufacturer, an examination for conformance to the packaging, packing, and marking requirements, and examining and testing the acceptance samples for all the requirements of this specification except Coating adhesion, Resistance to heat aging, and Resistance to low temperature exposure. If a component material covered by a Government specification has previously been inspected and approved by a Government quality assurance representative for acceptance under contract, such inspection need not be repeated for the purposes of this specification, and acceptance may be based on the contractor's certification of compliance. All the sampling and inspection levels shall conform to MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

4.4.1 Quality conformance inspection samples -

4.4.1.1 Inspection lot - A lot of coated cloth shall consist of a quantity of the product manufactured from 10 batches of coating compound or fraction thereof, manufactured under essentially the same conditions, and offered for delivery at one time. The lot size shall be expressed in units of 1 yard each, unless otherwise specified.

4.4.1.2 Sample for yard-by-yard examination - A sample for the Yard-by-yard examination shall be selected in accordance with MIL-STD-105, Inspection Level II. The acceptable quality level shall be 2.5 percent for major, and 10.0 percent defects (major and minor combined) per 100 units (yards). Sufficient rolls shall be selected at random from the lot so that the required sample yardage shall be obtained by examining approximately 25 consecutive yards out of each sample roll (see 4.5.2). The sample for Yard-by-yard examination of the base cloth shall be selected in accordance with MIL-C-21108.

4.4.1.3 Sample for overall, dimension, and age examinations - A sample for the Overall examination (see 4.5.3) and the Dimensions and age examinations (see 4.5.4) shall be selected at random in accordance with Tabel IV. The unit of product for these examinations shall be one piece.

TABLE IV

Lot Size in Yards	Sample Size in Pieces	Max Number of Defects Acceptable in Sample
Up to 1300 1/	3	0
1301 to 3200	5	0
3201 to 8000	7	0
8001 to 22,000	10	0
22,001 to 110,000	15	1
110,001 and over	25	1

1/ If a lot contains fewer than three (3) pieces, each piece in the lot shall be examined.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

4.4.1.4 Sample for tests - The sample unit for purposes of Quality conformance inspection tests shall be 2 yards. The number of sample units to be tested shall be in accordance with Inspection Level S-1 of MIL-STD-105, considering the lot size in units of 2 yards. The acceptable quality level shall be 4.0 percent defective. Random sampling shall be accomplished so that each 2-yard sample shall be taken from different rolls. Each sample shall be suitably tagged to identify it with the roll sampled. The test samples shall include four 6 by 6 by 0.07 to 0.08 inch sheets of cured coating compound from each batch and the coating compound samples shall be identified with the lot number. The test samples of coating compound and coated cloth shall have been cured to the same degree of cure. The sample for tests of the base cloths shall be selected in accordance with MIL-C-21108.

4.4.1.5 Sample for packaging, packing, and marking examination - The sample unit shall be one shipping container fully prepared for delivery. The lot size shall be the number of containers in the inspection lot. The sample size shall be determined in accordance with MIL-STD-105, Inspection Level S-2; and the acceptable quality level shall be 4.0 percent defective (see 4.5.1).

4.5 Inspection methods - Unless otherwise specified, inspection shall be in accordance with the provisions of MIL-STD-105 and testing shall be in accordance with the conditions and methods of CCC-T-191. Unless otherwise specified, the physical and chemical values specified in Section 3 apply to the average of the determinations made on the unit of product.

4.5.1 Packaging, packing, and marking examination - Each sample shipping container fully prepared for delivery shall be examined to determine compliance with the packaging, packing, and marking requirements of this specification. Examination shall be made for the following defects:

Markings, exterior and interior	Missing; incorrect; illegible; of improper size, location, or method of application
Materials	Component materials non-conforming, missing, damaged, or otherwise defective affecting serviceability
Workmanship	Inadequate application of components such as incomplete closure of case liners, container flaps, loose strapping, etc. Bulging or distortion of containers.
Weight	Gross weight exceeds requirement

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

4.5.2 Yard-by-yard examination - The required yardage of each piece of cloth in the sample (see 4.4.1.2) shall be examined over a bank of lights for defects as listed and classified in MIL-C-21108 for the base cloth and as listed and classified in Table V for the coated cloth. The Government reserves the right to require examination for any defects not included herein and to classify such defects in accordance with the definitions contained in MIL-STD-105. All defects found shall be counted regardless of their proximity one to another, except where 2 or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs.

4.5.3 Overall examination - The required number of pieces of coated cloth in the sample (see 4.4.1.3) shall be examined for defects as listed in Table VI. Each defect shall be counted no more than once in each piece examined.

4.5.4 Dimension and age examinations - Each piece of coated cloth in each roll in the sample (see 4.4.1.3) shall be counted and measured, and the age of each roll shall be determined. Width and length shall be measured as specified in Methods 5020 and 5010 of CCC-T-191. Any gross length or width of a roll found to be less than the minimum dimension specified in the contract, any roll found to have more than the maximum number of pieces per roll specified in the contract, any gross length of a piece found to be less than the minimum length of the shortest piece in a roll as specified in the contract, or any gross length found to be less than the gross length marked on the piece ticket by 2 yards or more shall be considered a defect. The maximum number of defects allowable is shown in Table IV. The lot shall be unacceptable if the total of the actual gross lengths of pieces in the sample is less than the total of the gross lengths marked on piece tickets. The lot shall be unacceptable if the age of any sample roll exceeds the limit specified in 3.4. The lot shall be unacceptable if the width of the material is not within tolerances specified in the contract (see 6.2). The absence of manganese and copper in the ink used for stamping the date of manufacture on the roll shall be verified (see 3.4).

4.5.5 Base cloths - The base cloths shall be examined and tested to determine conformance to MIL-C-21108 and the requirements of this specification (see 3.2.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

TABLE V

Classification of Defects for Coated Cloth

Defects	Classification	
	Major	Minor
Blisters or lumps		
1/4 square inch or less in combined directions, clearly visible 1/		X
Over 1/4 square inch in combined directions, clearly visible 1/	X	
Coating faults		
Blooming	X	
Creases	X	
Folds - winding on tubes		X
Uneven coating		X
Heavily coated areas, clearly visible 1/		X
Thin areas where coating compound is insufficient	X	
Coating missing	X	
Cuts	X	
Foreign matter incorporated in coating	X	
Pinholes	X	
Selvage defects affecting coating adhesion and resulting in uncoated area	X	
Splice mark clearly visible on coated side 1/		
If coating is not removed		X
If coating is missing	X	
Stains in coating surface		
Any spot or stain (compound, oil, dirt) over 1 inch in length in any direction, clearly visible 1/		X
Streaks		
Shade streaks in coating, clearly visible 1/	X	
Tears	X	

1/ At normal examination distance (approximately 3 feet).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

TABLE VI

Overall Defects

Selvage curled, folded, rolled or slack continuously or intermittently throughout the piece.
Overall uncleanness or objectionable odor.
Uneven coating throughout the piece.
Off-shade, shaded end to end, side to side, side to center or throughout the piece
Mottled, cloudy or streaky throughout the piece.
Date of coating application missing from end of roll or identification tag.

4.5.6 Coating - Conformance to the coating compound ingredient requirements shall be determined by appropriate examination and testing in accordance with 3.2.2 and by acceptance of a contractor's certification of compliance. Solubility in water shall be determined in accordance with Method 6631 of FED-STD-601. Shore durometer hardness (after 15 seconds) shall be determined in accordance with Method 3021 of FED-STD-601.

4.5.6.1 Tensile strength and elongation - The tensile strength and elongation of cured coating compound samples shall be determined after exposure to heat aging as well as on the original samples. The determinations of tensile strength and elongation shall be made in accordance with Method 4111 of FED-STD-601. The Type III die shall be used to prepare specimens. The specimens to be heat aged shall be exposed for 168 hours in an oven maintained at a temperature of 212±2°F (100±1.1°C) in accordance with Method 7221 of FED-STD-601 (see Table I).

4.5.6.2 Coating adhesion - The Coating adhesion test specimens described in 4.3.1.1 shall be subjected to the Adhesion test in accordance with Method 8011 of FED-STD-601. Adhesion shall be measured in the warp direction (see 3.2.2.1).

4.5.7. Construction, weight distribution, and manufacture-- Conformance to the construction and weight distribution requirements of Table II and manufacture requirements of 3.3.1 shall be determined by appropriate examination in accordance with Method 5041 of CCC-T-191.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

4.5.8 Color - The color of the coated cloth shall be compared with the standard color chip specified in 3.5 and 6.2 in accordance with Method 4250 of FED-STD-141.

4.5.9 Resistance to heat aging - Resistance to heat aging of the coated cloth shall be determined in accordance with Method 5850 of CCC-T-191. The test specimens shall be heated in the oven for 168 hours at a temperature of 200±2°F (93±1.°C). After the heat aging, the specimens shall be examined for stiffness, brittleness, softness, and tackiness (see 3.6.1). Heat aged specimens shall be cooled and conditioned under standard atmospheric conditions for 4 hours, and then separate specimens shall be tested as indicated in Table III for breaking strength by the grab method in accordance with Method 5100 of CCC-T-191, and hydrostatic resistance in accordance with Method 5512 of CCC-T-191. These properties of the exposed cloth shall be compared with those of the cloth in the as received condition.

4.5.10 Resistance to low temperature exposure - Specimens of coated cloth shall be separately folded into quarters, the folds being made along the warp and filling directions of the base cloth (see Table II). The folds shall be sharply creased and each folded specimen shall be placed on a polished metal plate and completely covered with another metal plate. A weight shall be centrally placed on each covering plate. The covering plate and weight shall weigh a total of 5 pounds. These assemblies shall be subjected to a temperature of -65±2°F (-54±1.1°C) for a total of 4 hours. After 3-1/2 hours of exposure to this temperature, the specimens shall be unfolded carefully and refolded so that the folds are reversed. The unfolding and refolding shall be performed in the cold box at the specified low temperature. After refolding, and with the covering plate and weight replaced, the assembly shall remain in the cold box at the specified low temperature, for the remainder of the 4-hour period. The specimens shall then be removed, conditioned under standard atmospheric conditions for 2 hours, and examined for evidence of cracking (see 3.6.2).

4.5.11 Blocking - The blocking test rating of the coated cloth shall be determined in accordance with Method 5872 of CCC-T-191 except the exposure temperature shall be 200±2°F (93±1.1°C) (see Table III).

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing, and marking - Cloth shall be packaged, packed, and marked in accordance with PPP-P-51, except that, prior to rolling, the coated face of the fabric shall be dusted with a suitable talc to prevent tackiness. The levels of packaging and packing shall be as specified by the procuring activity (see 6.2). In addition to the markings required, each tag shall be marked with the following information: "Date of Application of Coating". In addition, the following precautionary marking shall appear on all containers: "STORE IN A COOL DRY PLACE". (See 4.5.1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use - The coated cloths covered by this specification are intended for use in the manufacture of life raft bottoms. Type I is for one-man rafts, cylinder carriers, oral inflation valve pockets, sea anchor mooring patches, and accessory patches used in the manufacture of pararafts and packet rafts. Type II is for the multi-place life raft bottoms.

6.2 Ordering date - Procurement documents should specify the following:

(a) Title, number, and date of this specification

(b) Type required (see 1.2)

(c) Color required if other than as specified in 3.5

(d) Width and width tolerance required

(e) Dimensions and roll put-up requirements, if other than as specified in 3.7

(f) Quantity required

(g) Selection of applicable levels of packaging and packing (see 5.1)

6.2.1 In the preparation of contracts or orders, it must be noted that various options, choices and alternatives, as indicated in PPP-P-51, may be exercised in the preparation for delivery of the commodity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

MIL-C-21109B(AS) CLOTH, COATED, RAFT BOTTOM

ORGANIZATION *(Of submitter)*	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE C-8279

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

Weapons Engineering Standardization Office (Code X)
Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T08:55Z
Check the source to verify that this is the current version before use.