MILITARY SPECIFICATION

CLEANING COMPOUNDS, ELECTRICAL AND ELECTRONIC COMPONENTS

This specification is approved for use within the Naval Air Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for two types and two compositions of a cleaning compound formulated for removing solder flux residue and other contaminants from electrical and electronic components.

1.2 Classification. The cleaning compounds covered by this specification shall be of the following types and compositions, as specified (see 6.2.1):

Type I - Aerosol
Type II - General use

Composition A - Trichlorotrifluoroethane blend
Composition B - 1,1,1 - Trichloroethane blend

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Systems Engineering and Standardization Department (Code 93), Naval Air Engineering Center, Lakehurst, NJ 08733-5100, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

O-E-760	-	Ethyl Alcohol (Ethanol), Denatured Alcohol, Proprietary Solvents and Special Industrial Solvents.
BB-C-101	-	Carbon Dioxide (CO_2), Technical and USP.
TT-B-848	-	Butyl Alcohol, Secondary. (For use in Organic Coatings).
PPP-B-636	-	Boxes, Shipping, Fiberboard.
PPP-C-96	-	Can, Metal, 28 Gage and Lighter.
PPP-D-729	-	Drums, Shipping and Storage, Steel, 55-Gallon (208 Liters).
PPP-P-704	-	Pails, Metal: (Shipping, Steel, 1 through 12-Gallons).

MILITARY

MIL-C-81302	-	Cleaning Compound, Solvent, Trichlorotrifluoroethane.
MIL-T-81533	-	1,1,1 Trichloroethane (Methyl Chloroform) Inhibited, Vapor Degreasing.

STANDARDS

FEDERAL

FED-STD-313	-	Material Safety Data Sheets, Preparation and the Submission of.
FED-STD-791	-	Lubricant, Liquid Fuel and Related Products, Methods of Testing.

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.

2.1.2 Other Government documents (publications). The following other Government documents (publications) form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

PUBLICATIONS

DEPARTMENT OF TRANSPORTATION

CODE OF FEDERAL REGULATIONS

49 CFR - Transportation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

(Application for copies of the Department of Transportation Code of Federal Regulations (CFR) should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

(Copies of specifications, standards, and other Government documents (publications) required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 270	-	Petroleum and Petroleum Products, Sampling.
ASTM D 1078	-	Distillation Range of Volatile Organic Liquids.
ASTM D 2109	-	Nonvolatile Matter in Halogenated Organic Solvents and Their Admixtures.
ASTM D 2111	-	Specific Gravity of Halogenated Organic Solvents and Their Admixtures.
ASTM D 2942	-	Total Acid Acceptance of Halogenated Organic Solvents (Nonreflux Method).
ASTM D 3401	-	Water in Halogenated Organic Solvents and Their Admixtures.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Materials. The materials used in composition A and B shall conform to Table I when tested as specified in 4.5.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

TABLE I. Compositional characteristics.

Ingredient	Requirement (percent by weight)
Composition A:	
Trichlorotrifluoroethane (MIL-C-81302, Type II)	95.2 ± 0.35
Ethanol (O-E-760, Grade III)	3.8 ± 0.25
Nitromethane	1.0 ± 0.10
Composition B:	
1,1,1 Trichloroethane (MIL-T-81533)	91.5 minimum
Butanol (TT-B-848)	2.5 ± 0.2

3.2 Chemical and physical properties. The chemical and physical properties of the cleaning compound shall conform to the requirements specified in Table II when tested as specified in 4.4.

TABLE II. Chemical and physical properties.

Property	Requirement	Test Para.
Moisture content, ppm, max	200	4.4.2
Nonvolatile residue, ppm, max		4.4.3
Type I	25	
Type II	10	
Halide ion	Negative	4.4.4
Specific Gravity 25/25° C		4.4.5
Composition A	1.290 - 1.330	
Composition B	1.270 - 1.300	
Distillation range (Composition B, only)		4.4.6
Initial, min	67° C (153° F)	
Dry, max	88° C (190° F)	
Leakage Type I only	3.3.1	4.4.7
Weight Type I only	3.3.2	4.4.8
Content Type I only	3.3.3	4.4.9

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

3.3 Type I.

3.3.1 Leakage. When tested as specified in 4.4.7, the pressurized container shall not leak nor become distorted.

3.3.2 Weight. When tested as specified in 4.4.8, the content of the pressurized container for composition A shall weigh not less than 16.0 ounces, and not less than 14.0 ounces for composition B.

3.3.3 Content. The filled pressurized can, when tested as specified in 4.4.9, shall contain not less than 15.0 ounces of composition A cleaning compound and not less than 13.75 ounces of composition B cleaning compound. The remainder shall be carbon dioxide (propellant) conforming to BB-C-101, Grade B.

3.4 Toxicity. The material shall have no adverse effect on the health of personnel when used for its intended purpose in accordance with the manufacturer's instructions. Questions pertaining to the toxic effect shall be referred by the contracting activity to the appropriate departmental medical service who will act as an advisor to the contracting agency (see 4.3 and 6.4).

3.5 Workmanship. The cleaning compound furnished under this specification shall be a homogeneous and uniform product free of suspended matter, sediment, grit or other foreign matter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractors overall inspection system or quality program for the life of the contract. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspection. The inspection requirements specified herein shall be classified as quality conformance inspection (see 4.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

4.2.1 Inspection conditions. Unless otherwise authorized by the contracting officer, all inspections shall be performed in an atmosphere of 50 ± 4 percent relative humidity and at a temperature of 23° ± 1° C (73.4° ± 2° F).

4.3 Quality conformance inspection. Quality conformance inspection shall consist of the tests specified in Tables I and II and the examinations specified in 4.3.2.1, 4.3.2.2, and 4.3.3. The contractor shall make available an applicable test report with each inspection lot. The test report shall be certified and show test results for the requirements specified in 3.1 through 3.3.3. Material safety data sheet shall be prepared in accordance with FED-STD-313 and shall accompany the test report.

4.3.1 Lot formation. A lot shall consist of all the cleaning compound produced by one manufacturer, at one plant, from the same materials and under essentially the same manufacturing conditions, provided the operation is continuous and does not exceed 24 hours. In the event the process is a batch operation, each batch shall constitute a lot (see 6.3).

4.3.2 Sampling. A random sample of filled containers shall be selected from each lot for the examinations and tests specified in 4.3.2.1 and 4.3.2.2.

4.3.2.1 Examination of end items. The content of each Type II container shall be examined for the defects listed in Table III and for amount of content. The sample size shall be in accordance with Table IV. The sample unit for this examination shall be one filled container. The lot shall be rejected if there is any evidence of nonconformance in appearance.

TABLE III. Examination of end item.

Examine	Defect
Material	Not as specified
Appearance	Presence of foreign matter

TABLE IV. Sample size for content.

Number of containers	
Lot size	Sample size
Up to 50	5
51 - 500	7
501 - 35,000	8
35,001 and over	11

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

4.3.2.2 Inspection of filled containers. The sample unit for this examination shall be one filled container. The sample size shall be as specified in Table IV. The lot shall be unacceptable if the average net content per container for all units examined is less than specified.

4.3.3 Packaging inspection. An examination shall be made to determine if the preservation, packing and marking comply with the requirements of Section 5. The sample unit shall be one shipping container fully prepared for delivery except for closure. Each sample unit shall be examined for the defects listed in Table V. The lot size shall be the number of shipping containers in the lot. The examination shall be in accordance with MIL-STD-105, Inspection Level S-2 and Acceptable Quality Level (AQL) of 2.5 defects per hundred units. Sealed shipping containers, containing the end item, shall also be examined for compliance with Section 5.

TABLE V. List of defects for packaging.

Item	Defects
Exterior and interior markings	Missing, incorrect, incomplete, illegible, of improper size, location, sequence, or method of application; markings not the same on the interior and exterior containers.
Packaging and packing materials	Any nonconforming component; any component missing, damaged or otherwise defective.
Workmanship	Inadequate application of the components such as, incomplete closure of the unit package, intermediate package, caseliners, containers flaps, loose strappings, etc.; bulging or distortion of the containers.

4.3.4 Sampling for tests.

4.3.4.1 Type I. Twenty filled pressurized containers shall be selected at random from each lot for the tests specified in 4.4. The tests specified in 4.4.7 through 4.4.9 shall be conducted in triplicate. The remaining tests shall be conducted on a composite sample consisting of the cleaning compound portion of the remaining containers. The lot shall be rejected if the material fails one or more tests.

4.3.4.2 Type II. A 1-gallon sample of the cleaning compound shall be selected in accordance with ASTM D 270 for all the tests specified in 4.4 except 4.4.7 through 4.4.9. Any failure shall result in the rejection of the lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

4.4 Test methods.

4.4.1 Composition. Weight percent of components in Table I shall be determined using a gas chromatograph with adequate sensitivity. The instrument shall be suitably programmed to effect separation of the various components within a reasonable period of time (12 to 14 minutes). Any of the accepted methods of calculating weight percent may be employed. The supplier shall specify the instrument, test parameters and method of calculating weight percent when reporting test results.

4.4.2 Moisture content. The moisture content of the cleaning compound shall be determined in accordance with ASTM D 3401 by titration with Karl Fischer reagent using an aquameter. The Karl Fischer reagent shall have a moisture equivalent of approximately 0.4 milligram (mg) of water per milliliter (ml) of reagent, as standardized using ACS grade sodium tartrate dihydrate. The titration flask and all reagents shall be protected at all times from atmospheric moisture by utilizing tightly sealed joints and suitable desiccants in all air vents. Add 30 - 40 ml of ACS grade absolute methanol to a dry titration flask. Adjust stirrer speed and titrate the methanol in accordance with directions supplied with the aquameter. Then, under the driest conditions possible, add 100 ml of the sample to the same flask and immediately titrate to the endpoint. The moisture content in parts per million shall be calculated as follows:

$$\text{Ppm moisture} = \frac{A \times B \times 10^3}{W}$$

Where:

A = ml of Karl Fischer reagent used to titrate the sample.

B = mg of water equivalent to one ml of Karl Fischer reagent.

W = weight of sample in grams (volume times specific gravity).

4.4.3 Residue. The total residue shall be determined in accordance with ASTM D 2109 or as follows: Transfer 500 ml of cleaning compound to a clean 800 ml beaker. Boil the 500 ml gently on a hot plate until the volume has been reduced so that a second 500 ml of sample may be added. (Add a clean glass stirring rod to the 800 ml beaker to prevent bumping during boiling.) After the second addition (500 ml) has been reduced to a low volume (50 to 100 ml), add another 490 ml, boil and this time reduce the contents of the beaker to approximately 20 ml. Transfer the approximately 20 ml to a weighed 35 ml vial (containing one glass bead) and rinse the 800 ml beaker with the final 10 ml portion of the sample. The 10 ml rinse shall also be transferred to the 35 ml vial. Boil the contents of the 35 ml vial very gently until the volume has been reduced to approximately 5 to 10 ml. Transfer the vial to an oven at 100° ± 2° C (212° ± 3.6° F), evaporate to dryness, and dry for one hour. After one hour, remove the vial from the oven, cool in a desiccator, and reweigh to the nearest 0.1 mg. Calculate the total residue as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

$$\text{Ppm residue} = \frac{(A - B) \times 10^6}{W}$$

Where:

A = weight of vial and residue in grams.

B = weight of vial in grams.

W = sample weight in grams (volume times specific gravity).

NOTE: All glassware shall be cleaned as specified in method 3009 of FED-STD-791, except that an additional and final rinse shall be accomplished by using a portion of the test sample filtered in accordance with method 3009 of FED-STD-791.

4.4.4 Halide ion content. Place 5 ml of absolute methyl alcohol in a test tube, add 3 to 4 drops of a saturated solution of $AgNO_3$ in absolute methyl alcohol, shake and add 5 ml of the sample being tested. The resulting solution should remain clear. The formation of any turbidity indicates the presence of halide ion in the sample.

4.4.5 Specific gravity. Specific gravity shall be determined in accordance with ASTM D 2111.

4.4.6 Distillation range (Composition B only). The distillation range of Composition B cleaning compound shall be determined in accordance with ASTM D 1078.

4.4.7 Leakage (Type I only). Using a filled pressurized can, spray for three seconds and pause for two seconds. Repeat this cycle five times. The can shall then be submerged completely in water maintained at 54° ± 1.1° C (130° ± 2° F) for five minutes. The emission of bubbles indicates leakage. At the end of five minutes, remove the can from the water and examine it for distortion.

4.4.8 Weight. Weigh the filled pressurized can to the nearest 0.1-oz. Spray the content for 3 minutes and pause for 1 minute. Again, spray for three minutes and pause for one minute. Repeat the cycle until there is no further evidence of spray formation. Puncture a hole in the can and empty it completely. Weigh the empty can to the nearest 0.1-oz. Calculate the weight of the content by subtracting the weight of the empty can from the weight of the full can.

4.4.9 Content. Accurately weigh the filled can to the nearest 0.01 gram. Place the can for a minimum of 24 hours in a cold box maintained at -23° ± 1.1° C (-10° ± 2° F). Remove the sample and puncture a small hole in the top of the can. Allow the temperature of the sample to rise gradually until it reaches room temperature. Weigh the remainder (can plus solvent) to the nearest 0.01 gram. The can shall then be emptied and weighed to the nearest 0.01 gram. Calculate the weight of the propellent and the solvent as follows:

Source: https://assist.dla.mil - Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

Weight of propellent = $W_1 - W_2$

Weight of solvent = $W_2 - W_3$

W_1 = Initial weight (can plus total content)

W_2 = Weight of can and solvent after propellent has been expelled

W_3 = Weight of empty can.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or C, as specified (see 6.2.1).

5.1.1 Level A.

5.1.1.1 Type I. Unless otherwise specified in the contract or order, Type I cleaning compound shall be packaged in 16-oz pressurized containers conforming to Type IX, Class 5 of PPP-C-96. All internal surfaces of the container shall be lined with a material that will not affect nor be affected by the content of the container. The valve shall be a Newman Green No. B14-10-123 or equivalent in performance. The sprayhead shall be a Newman Green No. 102-20-18 or equivalent in performance. Each container shall have a snug fitting metal or plastic protective cap. A 5-inch plastic extension designed to fit the sprayhead shall be attached to the outside of the can. All containers shall be new and free from contaminants. The pressurized containers shall conform to applicable requirement of the Code of Federal Regulations (CRF) Title 49.

5.1.1.2 Type II. The Type II cleaning compound shall be furnished in 1-gallon, 5-gallon or 55-gallon containers, as specified (see 6.2.1). Unless otherwise specified in the contact or order, the 1-gallon and 5-gallon containers shall conform to Type I, Class 3 of PPP-P-704. The 55-gallon container shall conform to Type I of PPP-D-729. All internal surfaces of the container shall be lined with a material that will not affect nor be affected by the cleaning compound.

5.1.1.3 Intermediate packs (Type I only). Twelve containers, preserved as specified in 5.1.1.1, shall be packaged in a fiberboard box conforming to PPP-B-636, Type CF, Class Domestic, Style RSC, Grade 200. The 12 cans, arranged 3 in width and 4 in length, shall fit snugly in the fiberboard box, and each unit shall be nested in a snug fitting, full-height, half-slotted style partition. The box and the partition shall be made of the same material. The box closure shall be in accordance with the appendix to PPP-B-636.

5.1.2 Level C. The cleaning compound shall be preserved in specified quantities in a manner that shall afford adequate protection to prevent damage or deterioration during shipment under all environmental conditions. The containers shall conform to the requirements of CFR Title 49.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

5.2.1 Level A. Two Type I intermediate packs, preserved as specified in 5.1.1.3, shall be packed in a snug fitting fiberboard box conforming to PPP-B-636, Type CF, Variety SW, Class Weather Resistant, Grade V3c and taped in accordance with the appendix to PPP-B-636. Four Type II 1-gallon containers, preserved as specified in 5.1.1.2, shall be packed in a fiberboard box conforming to PPP-B-636, Type CF, Variety SW, Class Weather Resistant, Grade V3c and taped in accordance with the appendix to PPP-B-636. The four 1-gallon containers, arranged 2 by 2, shall fit snugly in the fiberboard box, and each unit shall be nested in a snug fitting, full height, half slotted style partition. The partition and the box shall be made of the same material. The Type II cleaning compound, when preserved in 5-gallon or 55-gallon containers, as specified in 5.1.1.2, shall require no overpacking. Standard 4-way entry pallets are required for handling by mechanical equipment.

5.2.2 Level B. Two Type I intermediate packs, preserved as specified in 5.1.1.3, shall be packed in a snug fitting fiberboard box conforming to PPP-B-636, Type CF, Variety SW, Class Domestic, Grade 275 and tape sealed in accordance with the appendix to PPP-B-636. Four Type II 1-gallon containers, preserved as specified in 5.1.1.2, shall be packed in a fiberboard box conforming to PPP-B-636, Type CF, Variety SW, Class Domestic, Grade 275 and tape sealed in accordance with the appendix to PPP-B-636. The four 1-gallon containers, arranged 2 by 2, shall fit snugly in the fiberboard box and each unit shall be nested in a snug fitting, full height, half slotted style partition. The partition and the box shall be made of the same material. The Type II cleaning compound, preserved in 5-gallon or 55-gallon containers, as specified in 5.1.1.2, shall require no overpacking. Standard 4-way entry pallets are required for handling by mechanical equipment.

5.2.3 Level C. The preserved cleaning compound shall be packed in shipping containers in a manner that will afford adequate protection, at the lowest rate, against damage during direct shipment from the supply source to the first receiving activity. The containers used shall conform to the rules and regulations of the mode of transportation utilized.

5.3 Marking.

5.3.1 Standard Marking. In addition to any special or other identification marking required by the contract (see 6.2.1), each unit, intermediate and shipping container shall be marked in accordance with MIL-STD-129. The complete military or contractor's type or part number, as applicable (including FSCM), shall be marked on all unit and intermediate packs in accordance with the identification marking provisions of MIL-STD-129.

5.3.2 Special marking. In addition to the marking requirements of 5.3.1, the Type I pressurized containers shall contain the following markings:

CAUTION

Content under pressure.
Do not puncture or incinerate.
Use with adequate ventilation 1/.
Do not store above 49° C (120° F).
Avoid prolonged or repeated breathing of vapors 1/.

1/ Shall also be added to the markings of Type II containers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

5.3.2.1 Instructions. Each Type I pressurized container shall also contain the following instructions:

Use in cleaning electrical and electronic components and equipment. Spray into and on equipment until the surface is wet. This will remove moisture, condensation, oil, grease and dirt.

5.3.2.2 Method of marking. Each Type I pressurized container shall be marked by the lithograph or other suitable process in accordance with normal commercial practice.

6. NOTES

6.1 Intended use. The cleaning compounds covered by this specification are intended for cleaning electrical and electronic components and are particularly effective in removing solder flux residue.

6.2 Ordering data.

6.2.1 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.

b. Type and composition required (see 1.2).

c. Quantity required by container.

d. Level of preservation and packing required (see 5.1 and 5.2).

e. Size of Type II container (see 5.1.1.2).

f. Additional marking, if required (see 5.3 through 5.3.2.2).

6.3 Batch. A batch is defined as that quantity of material which has been manufactured by some unit chemical process or subjected to some physical mixing operation intended to make the final product substantially uniform.

6.4 Material safety data sheets. Contracting officers will identify those activities requiring copies of completed material safety data sheets prepared in accordance with FED-STD-313. The pertinent Government Mailing addresses for submission of data are listed in Appendix B of FED-STD-313.

6.5 Subject term (key word) listing.

Cleaning compounds

Electrical components

Electronic components

Solder flux residue

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

6.6 Cross-reference. The cross reference between MIL-C-85447 and MIL-C-85447A is as follows:

MIL-C-85447	MIL-C-85447A
Type I	Type I, Composition A
Type II	Type II, Composition A
Not included	Type I, Composition B
Not included	Type II, Composition B

6.7 Changes from previous issue. Asterisks or (vertical lines) are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Preparing activity:
Navy - AS

(Project Number 6850-N810)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-85447A(AS)	CLEANING COMPOUNDS, ELECTRICAL AND ELECTRONIC, COMPONENTS

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*:
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:52Z
Check the source to verify that this is the current version before use.