MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), INSULATING COMPOUND, TYPE IJ-H-LOW TEMPERATURE, HEAT AND WEATHER RESISTANT, INSULATING AND JACKETING, ETHYLENE-PROPYLENE RUBBER (EPM) OR ETHYLENE-PROPYLENE-DIENE RUBBER (EPDM)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Insulating Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

UNAGED:		
Tensile strength, minimum psi	=	1200
Elongation, minimum percent	=	300
Set, maximum, inch	=	.500
Tensile stress at 200 percent elongation, minimum psi	=	250
AFTER 168 ± 1 HOUR OXYGEN BOMB AGING AT 80°C:		
Tensile strength, minimum percent of original	=	90
Elongation, minimum percent of original	=	80
AFTER 20 ± 1/2 HOUR AIR PRESSURE AGING AT 127°C:		
Tensile strength, minimum percent of original	=	90
Elongation, minimum percent of original	=	80
OVEN AGING AT 121°C:		
Tensile strength, minimum percent of original	=	85
Elongation, minimum percent of original	=	80
OZONE RESISTANCE (AFTER AIR OVEN CONDITIONING AND 168 ± 1 HOUR IN OZONE):		
At 120°F	=	No visible cracks

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:24Z
Check the source to verify that this is the current version before use.

BRITTLENESS TEMPERATURE, MAXIMUM ^{o}C:	
Unaged	= -55
Oven aged	= -55
TORSIONAL STIFFNESS RATIO, MAXIMUM:	
AT -55°C	= 5
TORSIONAL MODULUS, MAXIMUM PSI:	
AT -55°C	= 1000
COLD TENSION RECOVERY, MINIMUM PERCENT:	
AT -55°C	= 10

Custodians:
Army - CR
Air Force - 85

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

Preparing activity:
Army - CR

(Project 5970-0560-10)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:24Z
Check the source to verify that this is the current version before use.