MILITARY SPECIFICATION SHEET

# INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), INSULATING COMPOUND, TYPE IE-POLYETHYLENE IN ACCORDANCE WITH L-P-390, TYPE II, CLASS L, GRADE 3 OR 4, CATEGORY 5

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Insulating Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

## PHYSICAL PROPERTY REQUIREMENTS

| | |
|---|---|
| UNAGED: | |
| Tensile strength, minimum psi | = 1400 |
| Elongation, minimum percent | = 400 |
| AFTER 48 ± 1/2 HOUR AIR OVEN AGING AT 99 ± 1°C: | |
| Tensile strength, minimum percent of original | = 75 |
| Elongation, minimum percent of original | = 75 |
| AFTER 24 ± 1/2 HOUR AIR OVEN AGING AT 99 ± 1°C: | |
| Insulation shrinkback | = No splitting or cracking |
| Maximum inch | = .063 |
| BRITTLENESS TEMPERATURE (MAXIMUM °C) | |
| Unaged | = -55 |
| Oven aging | = -55 |

Custodians:
Army - CR
Air Force - 85

Preparing activity:
Army - CR

(Project 5970-0560-11)

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

FSC 5

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimite



Source: https://assist.dla.mil -- Downloaded: 202610-16T22:24Z
Check the source to verify that this is the current version before use.