MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), INSULATING AND JACKETING COMPOUND, TYPE TPE-S-LOW TEMPERATURE, HEAT AND OZONE RESISTANT, STYRENIC THERMOPLASTIC ELASTOMER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

UNAGED:		
Tensile strength, minimum psi	=	1300
Elongation, minimum percent	=	400
Tear strength, minimum lb in	=	160
Tensile strength at 200 percent modulus, minimum psi	=	250
Tensile strength at 400 percent modulus, minimum psi	=	500

Custodians:
Army - CR
Air Force - 85

Preparing activity:
Army - CR

(Project 5970-0560-12)

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:24Z
Check the source to verify that this is the current version before use.

Standard No. 228, except that for type IR [illegible] Method 4211 of Federal Test Metho