MILITARY SPECIFICATION SHEET

# INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), INSULATING AND JACKETING COMPOUND, TYPE TPE-O-LOW TEMPERATURE, WEATHER RESISTANT, OLEFINIC THERMAPLASTIC ELASTOMER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

## PHYSICAL PROPERTY REQUIREMENTS

| UNAGED: | | |
|---|---|---|
| Tensile strength, minimum psi | = | 1140 |
| Elongation, minimum percent | = | 700 |
| Set, maximum inch | = | .250 |
| Tensile strength at 100 percent modulus, minimum psi | = | 640 |
| Tensile strength at 300 percent modulus, minimum psi | = | 870 |
| Tear strength lb in | = | 195.5 |

Custodians:
Army - CR
Air Force - 85

Preparing activity:
Army - CR

(Project 5970-0560-13)

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.



Source: https://assist.dla.mil -- Downloaded: 202610-16T22:24Z
Check the source to verify that this is the current version before use.