MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), JACKETING COMPOUND, TYPE JR-LOW TEMPERATURE, NATURAL RUBBER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Jacketing Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

UNAGED:		
Tensile strength, minimum psi	=	2000
Elongation, minimum percent	=	350
Set, maximum, inch	=	.250
AFTER 95 ± 1/2 HOUR OXYGEN BOMB AGING AT 70°C:		
Tensile strength, minimum percent of original	=	65
Elongation, minimum percent of original	=	65
OZONE RESISTANCE (AFTER AIR-OVEN CONDITIONING AND 168 ± 1 HOUR IN OZONE):		
AT 100°F (37.7°C)	=	No Visible Cracks
BRITTLENESS TEMPERATURE:		
UNAGED:		
MAX C°	=	-55
AGED:		
MAX C°	=	-55

Custodians:
Army - CR
Air Force - 85

Preparing activity:
Army - CR

(Project 5970-0560-17)

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:25Z
Check the source to verify that this is the current version before use.