MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), JACKETING COMPOUND, TYPE JN-L-LOW TEMPERATURE, CHLOROPRENE RUBBER (CR)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Jacketing Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

UNAGED:		
Tensile strength, minimum psi	=	1500
Elongation, minimum percent	=	300
Set, maximum, inch	=	.375
Tensile stress, (200 percent elongation, minimum psi)	=	500
Tear resistance, minimum lb in	=	20
AFTER 95 ± 1/2 HOUR OXYGEN BOMB AGING AT 70°C:		
Tensile strength, minimum percent of original	=	75
Elongation, minimum percent of original	=	75
AFTER 168 ± 1 HOUR AIR OVEN AGING AT 70°C:		
Tensile strength, minimum percent of original	=	80
Elongation, minimum percent of original	=	80
OZONE RESISTANCE (AFTER AIR-OVEN CONDITIONING AND 168 ± 1 HOUR IN OZONE):		
AT 120°F (50°C)	=	No Visible Cracks
BRITTENESS TEMPERATURE:		
UNAGED:		
MAX C°	=	-55
AGED:		
MAX C°	=	-55
TORSIONAL STIFFNESS RATIO, MAX:	=	30
AFTER OIL IMMERSION:		
Tensile strength, minimum percent of original	=	60
Elongation, minimum percent of original	=	60

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2022-10-16T22:25Z
Check the source to verify that this is the current version before use.

Custodians:
Army - CR
Air Force - 85

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

Preparing activity:
Army - CR

(Project 5970-0560-19)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:25Z
Check the source to verify that this is the current version before use.