MILITARY SPECIFICATION SHEET

# INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES) INSULATING COMPOUND, TYPE IP-MEDIUM-LOW TEMPERATURE, POLYVINYLCHLORIDE (PVC) AND POLYVINYLCHLORIDE ACETATE (PVCA)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Insulating Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

## PHYSICAL PROPERTY REQUIREMENTS

| | |
|---|---|
| UNAGED: | |
| Tensile strength, minimum psi | = 1800 |
| Elongation, minimum percent | = 80 |
| Set, maximum, inch | = --- |
| AFTER 95 ± 1/2 HOUR AIR OVEN: | |
| Elongation, minimum percent of original | = 80 |
| BRITTLENESS TEMPERATURE (MAXIMUM °C): | |
| Unaged | = -40 |
| Ovenaged | = -40 |

Custodians:
Army - CR
Air Force - 85

Preparing activity:
Army - CR

(Project 5970-0560-01)

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:23Z
Check the source to verify that this is the current version before use.