MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), JACKETING COMPOUND, TYPE JH-LOW TEMPERATURE, HEAT AND WEATHER RESISTANT, ETHYLENE-PROPYLENE (EPM), OR ETHYLENE-PROPYLENE-DIENE RUBBER (EPDM)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Jacketing Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

UNAGED:		
Tensile strength, minimum psi	=	1600
Elongation, minimum percent	=	400
Set, maximum, inch	=	.375
Tensile stress, (200 percent elongation, minimum psi)	=	300
Tear resistance, minimum lb in	=	25
AFTER 168 ± 1 HOUR AIR OVEN AGING AT 121°C:		
Tensile strength, minimum percent of original	=	85
Elongation, minimum percent of original	=	80
AFTER 168 ± 1 HOUR OXYGEN BOMB AGING AT 80°C:		
Tensile strength, minimum percent of original	=	85
Elongation, minimum percent of original	=	70
AFTER 20 ± 1 HOUR AIR PRESSURE AGING AT 127°C:		
Tensile strength, minimum percent of original	=	85
Elongation, minimum percent of original	=	80
OZONE RESISTANCE (AFTER AIR-OVEN CONDITIONING AND 168 ± 1 HOUR IN OZONE):		
AT 120°F (50°C)	=	No Visible Cracks
BRITTLENESS TEMPERATURE:		
UNAGED:		
MAX C°	=	-55
AGED:		
MAX C°	=	-55
TORSIONAL STIFFNESS RATIO, MAX:	=	10

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:25Z
Check the source to verify that this is the current version before use.

COLD TENSION RECOVERY, MINIMUM: AT -55°C	=	10
TORSIONAL MODULUS: AT -55°C maximum psi	=	2,000

Custodians:
Army - CR
Air Force - 85

Review Activities:
Army - AR, ME, MI

Agent:
DLA-IS

Preparing activity:
Army - CR

(Project 5970-0560-20)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:25Z
Check the source to verify that this is the current version before use.