MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), JACKETING COMPOUND, TYPE JU-LOW TEMPERATURE, HEAT AND WEATHER RESISTANT, POLYURETHANE THERMOPLASTIC ELASTOMER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Jacketing Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

UNAGED:		
Tensile strength, minimum psi	=	3500
Elongation, minimum percent	=	550
Set, maximum, inch	=	.250
Tensile stress, (100 percent elongation, minimum psi)	=	550
Tensile stress, (300 percent elongation, maximum psi)	=	1000
Tear resistance, minimum lb in	=	90
Durometer, "A" maximum points	=	82
AFTER 20 ± 1 HOUR AIR PRESSURE AGING AT 127°C:		
Tensile strength, minimum percent of original	=	50
Elongation, minimum percent of original	=	50
OZONE RESISTANCE (AFTER AIR-OVEN CONDITIONING AND 168 ± 1 HOUR IN OZONE): AT 120°F (50°C)	=	No Visible Cracks
BRITTLENESS TEMPERATURE:		
UNAGED: MAX C°	=	-55
AGED: MAX C°	=	-55
TORSIONAL STIFFNESS RATIO, MAX:	=	35
TORSIONAL MODULUS AT -55°C, MAXIMUM PSI:	=	20,000
HYDROLYTIC STABILITY:		
Tensile strength, minimum percent of original	=	50
Elongation, minimum percent of original	=	70
Durometer "A", maximum points change	=	8

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:26Z
Check the source to verify that this is the current version before use.

Custodians:
Army - CR
Air Force - 85

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

Preparing activity:
Army - CR

(Project 5970-0560-21)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:26Z
Check the source to verify that this is the current version before use.